Smithsonian
Scholarly Press

SMITHSONIAN CONTRIBUTIONS TO MUSEUM CONSERVATION • NUMBER 10

The Mechanics of Art Materials and Its Future in Heritage Science

Edited by

*Dawn V. Rogala, Paula T. DePriest,
A. Elena Charola, and Robert J. Koestler*

SERIES PUBLICATIONS OF THE SMITHSONIAN INSTITUTION

Emphasis upon publication as a means of “diffusing knowledge” was expressed by the first Secretary of the Smithsonian. In his formal plan for the Institution, Joseph Henry outlined a program that included the following statement: “It is proposed to publish a series of reports, giving an account of the new discoveries in science, and of the changes made from year to year in all branches of knowledge.” This theme of basic research has been adhered to through the years in thousands of titles issued in series publications under the Smithsonian imprint, commencing with Smithsonian Contributions to Knowledge in 1848 and continuing with the following active series:

Smithsonian Contributions to Anthropology
Smithsonian Contributions to Botany
Smithsonian Contributions to History and Technology
Smithsonian Contributions to the Marine Sciences
Smithsonian Contributions to Museum Conservation
Smithsonian Contributions to Paleobiology
Smithsonian Contributions to Zoology

In these series, the Smithsonian Institution Scholarly Press (SISP) publishes small papers and full-scale monographs that report on research and collections of the Institution’s museums and research centers. The Smithsonian Contributions Series are distributed via exchange mailing lists to libraries, universities, and similar institutions throughout the world.

Manuscripts intended for publication in the Contributions Series undergo substantive peer review and evaluation by SISP’s Editorial Board, as well as evaluation by SISP for compliance with manuscript preparation guidelines (available at <https://scholarlypress.si.edu>). For fully searchable PDFs of all open access series and publications of the Smithsonian Institution Scholarly Press, visit <https://smithsonian.figshare.com/ScholarlyPress>.

The Mechanics of Art Materials and Its Future in Heritage Science

Edited by
Dawn V. Rogala, Paula T. DePriest,
A. Elena Charola, and Robert J. Koestler

Smithsonian
Scholarly Press

WASHINGTON, D.C.

2019

ABSTRACT

Rogala, Dawn V., Paula T. DePriest, A. Elena Charola, and Robert J. Koestler. The Mechanics of Art Materials and Its Future in Heritage Science, *Smithsonian Contributions to Museum Conservation*, number 10, vi + 135 pages, 139 figures, 2019. — In late 2016, “The Mechanics of Art Materials and Its Future in Heritage Science: A Seminar and Symposium” was held at the Smithsonian Institution’s historic Arts and Industries Building. Organized by the Smithsonian’s Museum Conservation Institute (MCI) and the Royal Danish Academy of Fine Arts, Schools of Architecture, Design and Conservation, the two-day event brought experts in mechanics research from across the globe to discuss current and future trends in the study and preservation of cultural heritage. Speakers represented a continuum of innovative mechanics research in the cultural heritage sector, from its origins at the Smithsonian to current professionals working to shape the field and train future generations of scholars. The event began with the popular paint mechanics workshop created and taught by MCI senior research scientist emeritus Marion Mecklenburg, condensed into a single-day seminar of lectures and discussion. The second day featured an international group of speakers and case studies on the state of mechanics research around the globe, with an afternoon program focused on emerging U.S.-based speakers and their thoughts on the future of the field. This volume reflects a collaborative view of cultural heritage research in mechanics; beginning with a review of mechanics research at the Smithsonian Institution and followed by the nine papers presented by the symposium speakers, this publication incorporates the work of 15 national and international research centers. The Appendix includes a bibliography of Dr. Mecklenburg’s publications and his previously unpublished 1982 report on the mechanical behavior of painting materials.

Cover images, from left to right: The packing crate of an ancient wooden saddle transported from the Tokyo National Museum to the Arthur M. Sackler Gallery in Washington, D.C. (Kamba, Fig. 1). A working tensile test-jig from the Mecklenburg Materials Archive at the Smithsonian’s Museum Conservation Institute (Rogala, Fig. 3, upper left). A theoretical model of a one-year course of relative humidity at a low-energy, self-buffering collections storage site (Larsen and Ryhl-Svendsen, Fig. 5).

Published by SMITHSONIAN INSTITUTION SCHOLARLY PRESS

P.O. Box 37012, MRC 957, Washington, D.C. 20013-7012

<https://scholarlypress.si.edu>

Compilation copyright © 2019 Smithsonian Institution

Text of Carver-Kubik and Reilly (pp. 75–86) and Appendix 1 are in the public domain. The rights to all other text and images in this publication, including cover and interior designs, are owned either by the Smithsonian Institution, by contributing authors, or by third parties. Fair use of materials is permitted for personal, educational, or noncommercial purposes. Users must cite author and source of content, must not alter or modify copyrighted content, and must comply with all other terms or restrictions that may be applicable. Users are responsible for securing permission from a rights holder for any other use.

Library of Congress Control Number: 2019945271

ISSN: 1949-2367 (online); 1949-2359 (print)

Publication date (online): 9 December 2019

⊗ The paper used in this publication meets the minimum requirements of the American National Standard for Permanence of Paper for Printed Library Materials Z39.48–1992.

Contents

PREFACE	v
<i>Dawn V. Rogala, Paula T. DePriest, A. Elena Charola, and Robert J. Koestler</i>	
Material Mechanics Research at the Smithsonian Institution	1
<i>Dawn V. Rogala</i>	
Insight into Canvas Paintings' Stability and the Influence of Structural Conservation Treatments	13
<i>Cecil Krarup Andersen and Laura Fuster-López</i>	
HERIE: A Decision-Supporting Tool Based on Quantitative Assessment of Damage Risk	21
<i>Roman Kozłowski, Arkadiusz Kupczak, Artur Działo, Łukasz Bratasz, and Michał Łukomski</i>	
Museum Study of the Climate4Wood Research Project	31
<i>Stina Ekelund, Paul van Duin, Bart Ankersmit, and André Jorissen</i>	
Microclimate and Vibration Environment of a Custom Shipping Crate	41
<i>Nobuyuki Kamba</i>	
Low-Energy Museum Storage	57
<i>Poul Klenz Larsen and Morten Ryhl-Svendsen</i>	
The Role of Micromechanics in the Epidemiology of Climate-Induced Damage	65
<i>Michał Łukomski, James Druzik, Vincent Beltran, Ashley Freeman, Foekje Boersma, and Joel Taylor</i>	
The Mechanical Behavior of Library and Archive Materials	75
<i>A. Carver-Kubik and James Reilly</i>	
Future Trends in Studies of the Mechanics of Artists' Paints	87
<i>Kenneth R. Shull</i>	
Future Trends in Mechanical Research Applied to Heritage Science	93
<i>Łukasz Bratasz, Liu Liu, Cynthia Schwarz, and Anne Gunnison</i>	

APPENDIX 1: Thoughts on “Some Aspects of the Mechanical Behavior of Fabric Supported Paintings” <i>Marion F. Mecklenburg</i>	103
APPENDIX 2: Some Aspects of the Mechanical Behavior of Fabric Supported Paintings <i>Marion F. Mecklenburg</i>	107
APPENDIX 3: Bibliography of Publications by Marion F. Mecklenburg, Chronological Listing from 1977 to 2017	131

Preface

In late October 2016, more than 250 people gathered at the Smithsonian's historic Arts and Industries Building for "The Mechanics of Art Materials and Its Future in Heritage Science: A Seminar and Symposium." The special two-day event was organized by the Smithsonian's Museum Conservation Institute (MCI) and the Royal Danish Academy of Fine Arts, Schools of Architecture, Design and Conservation. The program brought experts in mechanics research from across the globe to discuss current and future trends in the study and preservation of cultural heritage. Speakers represented a continuum of this research, from its origins at the Smithsonian to current professionals working to shape the field and train future generations of scholars. The event was funded and supported by MCI; the Danish Agency for Science, Technology and Innovation; Smithsonian Facilities; the Smithsonian Office of the Provost and Under Secretary for Museums, Education, and Research; and the International Association of Museum Facility Administrators.

The intensive program was designed to honor previous research while encouraging forward thinking through opportunities to meet and hear from scholars at the forefront of innovative mechanics research in the cultural heritage sector. Speakers addressed a diverse audience of conservators, collection managers, registrars, curators, scientists, engineers, facility managers, students, and policy makers. The event began with the popular paint mechanics workshop created and taught by MCI Senior Research Scientist Emeritus Marion Mecklenburg, condensed into a single-day seminar of lectures and discussion. The second day featured a morning program of international speakers presenting case studies on the state of mechanics research from around the globe, with an afternoon program focused on emerging U.S.-based speakers and their thoughts on the future of the field. The symposium concluded with a panel discussion on encouraging stakeholder participation in mechanics research and application that featured staff from departments and museums across the Smithsonian.

This volume reflects a collaborative view of cultural heritage research in mechanics; beginning with a review of early mechanics research at the Smithsonian Institution and followed by the nine case studies and vision papers presented by the symposium speakers, this publication incorporates the work of 15 national and international research centers. The articles in this volume represent the work of the next generation of researchers—an international group of conservators and scientists undertaking innovative studies of cultural heritage materials and environments.

The case studies highlight international collaborations and research taking place outside the United States. In the first paper, Cecil Krarup Andersen (Royal Danish

Academy of Fine Arts) and Laura Fuster-López (Polytechnic University of Valencia) build on Dr. Mecklenburg's research by examining the mechanical properties of damaged, treated, repaired, and otherwise modified artwork with stress responses that diverge from the behaviors of ideal and undamaged materials. The second paper introduces the web-based assessment tool HERIe designed by Roman Kozłowski and a team from the Polish Academy of Sciences and the National Museum in Krakow to help quantify climate-induced risk to cultural heritage materials. The paper outlines the ongoing development of the web program intended to employ simplified climate and stress calculations to project long-term mechanical behaviors. The influence of environment is also examined in the third paper, an update on the first phases of the Climate4Wood project, a collaborative effort by Dutch museums, universities, and research centers to analyze the effects of climate fluctuations on delicate collections materials through observation, modeling, and experimentation. The paper reviews the empirical data collection phase of the project in which Stina Ekelund studied a group of more than 300 decorated wooden objects in the collections of the Rijksmuseum. This information will be utilized in conjunction with facilities and engineering data to help direct future preservation strategies. The fourth paper presents a data collection project undertaken at the Tokyo National Museum by Nobuyuki Kamba, who tracked the physical and environmental stresses encountered by collections materials during each phase of transit as a means to better understand and address the risks posed by the transportation of cultural heritage objects. The fifth and final paper in this section details the low-energy collections storage project underway at the National Museum of Denmark. Authors Poul Klens Larsen (National Museum of Denmark) and Morten Ryhl-Svendsen (Royal Danish Academy of Fine Arts) discuss the self-buffering collections storage buildings being introduced in northern Europe and the possible application of these designs to differing geographic and climate conditions.

The papers from emerging researchers focus on the work of U.S.-based projects and research collaborations. The first paper in this section outlines environmental standards work underway at the Getty Conservation Institute (GCI) and elsewhere. Michał Łukomski reviews the GCI team's use of documentation and analytical procedures borrowed from epidemiology to help codify and streamline the environmental standards used in the display and storage of cultural heritage collections, including the application of micromechanical methods to further evaluate the properties of paints, binding media, and coatings. The second paper, by A. Carver-Kubik and James Reilly from the Rochester Institute of Technology's Image Permanence Institute, investigates digital image correlation as a possible tool to assess the moisture response and equilibrating behaviors of library and archive materials. The third paper, by Kenneth Shull (Northwestern University), highlights the trends in material mechanics studies that build upon the spirit and practice of established researchers, including collaboration with related research fields and the embrace of new experimental methods and computational methodology. The fourth and final paper reports on work underway by Łukasz Bratasz and a team of scientists and conservators at the Institute for the Preservation of Cultural Heritage at Yale University seeking to identify knowledge gaps and other barriers to the development of risk assessment for heritage collections. This work lies at the crossroads of chemical and mechanical behaviors, an interdisciplinary worldview that the group supports as a model for future generations of researchers.

The Appendix to this volume includes a commentary by Marion Mecklenburg on his entry into the field of mechanics research, along with the first publication of the 1982 report that laid the groundwork for the mechanics research presented throughout this volume. It concludes with a bibliography of Dr. Mecklenburg's publications. We would like to thank the speakers, attendees, and sponsors for their support of this special program.

Material Mechanics Research at the Smithsonian Institution

*Dawn V. Rogala**

ABSTRACT. The Smithsonian Institution has a long history of research focused on the mechanical properties of collection and cultural heritage objects. This paper traces the trajectory of materials mechanics research at the Smithsonian, beginning with an influential 1982 report by conservator Marion Mecklenburg on the behavior of fabric-supported paintings. The report's holistic approach to collections care would later become a key principle of the emerging field of preventive conservation. Topics introduced in that paper and expanded in subsequent Smithsonian research include the use of predictive modeling to envision temperature- and relative humidity-induced failures within a composite artwork and the role of relative humidity in collections care—research that led the Smithsonian to propose and implement systemic changes in guidelines regulating collections storage and exhibition environments. Additional research topics include the mechanical testing of paper and archive materials and modern paint formulations, the mechanical properties of materials following conservation treatment, and the effects of shock and vibration—studies that led to improved guidelines for the packing and transport of collection items. The history of material mechanics studies at the Smithsonian is the story of scientific research engaged in the proactive care of cultural heritage around the world.

INTRODUCTION

The Smithsonian Institution has a long history of research focused on the physical characteristics, aging patterns, and anticipated behaviors of collection and cultural heritage objects. On 15 October 1966, ratification of Public Law 89-674 (also known as the National Museum Act) authorized funding for the National Museum of the Smithsonian Institution “to insure that museum resources for preserving and interpreting the Nation’s heritage may be more fully utilized.”¹ Existing conservation research at the Smithsonian largely focused on technical studies in support of curatorial inquiry, first at the Freer Museum’s Laboratory for Technical Studies in Oriental Art and Archaeology (Tech Lab), founded by Rutherford J. Gettens in 1952,² and next at the Conservation Research Laboratory, founded in 1963 as an independent scientific laboratory designed to support the conservation of collections throughout the entire institution.³ Increasing U.S. congressional appropriations for the National Museum Act throughout the 1970s and 1980s encouraged the institution to seek out projects of a larger scope that would contribute to “upgrading of the quality and standards of the [museum] profession” (U.S. Senate, 1983).

One of the early projects undertaken by the Smithsonian with funding from the National Museum Act took a holistic approach to collections care that would later become a key principle of the emerging field of preventive conservation. In the late 1970s, the Smithsonian Institution contracted a material mechanics study from Marion F. Mecklenburg, a conservator in private practice in the Washington, D.C.,

Museum Conservation Institute, Smithsonian Institution, 4210 Silver Hill Road, Suitland, Maryland 20746, USA.

* Correspondence: RogalaD@si.edu

Manuscript received 2 June 2018; accepted 7 May 2019.

area. The final 1982 report, entitled “Some Aspects of the Mechanical Behavior of Fabric Supported Paintings,” was one of first papers to systematically apply engineering principles to the study of collections materials⁴ and signaled the beginning of the Smithsonian’s research focused on the material mechanics of cultural heritage collections. The report was never formally published (until this volume; see the Appendix), but excerpts were widely circulated and frequently cited, and the stress-strain modeling for art materials that first appeared in this report became a familiar part of the conservation research canon. Dr. Mecklenburg⁵ examined stress development in materials (a broad engineering rubric known as “mechanics”) using canvas-supported paintings as exemplars. This research was relevant to preservation concerns: the mechanical properties of individual art materials and the analysis of the composite structures formed by these materials. In this new approach, the behavior of any individual material could affect the behavior of adjacent materials and of the overall composite structure, from the differing dimensional changes in warp and weft canvas threads to the plastic recovery of restrained versus unrestrained paintings (see Figure 1).

This early study of individual materials made clear the influence of relative humidity on the stress response of artwork and connected the expansion-contraction behavior of adjacent materials to aging and material failure patterns seen in composite objects. Protein-based glues were found to be especially responsive materials, performing as the stiffest and most stress bearing component of a fabric-supported painting at low relative humidity and the laxest and most responsive materials at high relative humidity, with the rate and magnitude of this response depending upon the thickness of their application. The 1982 report concludes with the suggestion that some materials buffer moisture response in artwork, allowing exposure to small fluctuations in the surrounding environment without dimensional responses. Further investigation into the moisture response rate for various materials was deemed necessary to better determine practical relative humidity levels and exposure limits for the preservation of fabric-supported paintings. Dr. Mecklenburg also posited that an improved understanding of short- and long-term mechanical responses to changing environmental and physical stresses could be used to design guidelines for more effective packing and transport of artwork. Relaxed environmental standards might also be designed, he theorized, maintaining realistic and cost-effective operation of storage and display spaces while ensuring the safety of collections.

MECHANICAL PROPERTIES RESEARCH AT THE SMITHSONIAN

Dr. Mecklenburg joined the Conservation Analytical Laboratory (CAL) at the Smithsonian Institution in 1987. There, in collaboration with colleagues, he expanded upon his earlier research with studies examining the effects of

environmental exposure on the mechanical properties of composite structures such as glued joins (Mecklenburg, 1988), tensioned textiles (Collins et al., 1990), and primed panels (Mecklenburg, 1991b); the impact of treatment on the properties of individual materials (van der Reyden et al., 1988); and the use of empirical data and nondestructive analysis to assess structural condition and predict structural behavior (Murray et al., 1991a, 1991b; see Figure 2).

As part of this research, Dr. Mecklenburg and his colleagues designed and constructed a test jig for quantifying the stress response of various cultural heritage materials (Organ and Mecklenburg, 1989). The apparatus was designed to measure the forces that developed in strips of flexible material (paper, skin, and films of paint or adhesive) under controlled environmental conditions during the incremental application of tension (see Figure 3 upper left, upper center, and upper right). Tests were conducted on commercial and custom-made art supplies, including conservation materials identified on collection items and an extensive collection of limited-component paint formulations that Dr. Mecklenburg used to expand his collection of naturally aged art materials (see Figure 3 lower left, lower center, and lower right).

As research data were compiled and examined, patterns began to emerge in the relationship between materials and their behaviors under the different environmental conditions imposed by storage, exhibition, and transport. This early research was presented in 1991 at the International Conference on the Packing and Transportation of Paintings, a conference hosted by London’s Tate Gallery and jointly organized with the Canadian Conservation Institute,⁶ the Smithsonian Institution, and the National Gallery of Art, Washington, D.C., in response to growing interest in the impact of exhibition travel on the physical condition of paintings in their collections.⁷ In his editor’s notes to the conference volume, Dr. Mecklenburg lauds the event, not only for its application of engineering mechanics to the study of shock and vibration but also for the recognition of mechanics research as a tool for studying the relationship between environmental factors, such as temperature and humidity, and collections care (Mecklenburg, 1991a:12). Contributions to the conference by Smithsonian researchers included a review of the engineering formulas utilized in mechanical properties research and the application of established engineering modeling methods (also used in Mecklenburg, 1982; see Figure 4 top left, top right)⁸ to predict the behavior of composite material structures (Mecklenburg and Tumosa, 1991a). A second paper by Mecklenburg and Tumosa (1991b) used these modeling methods to predict how temperature- and relative humidity-induced failures within a composite artwork, such as a painting, would appear as cracks across its surface (see Figure 4 bottom left, bottom right). The paper also highlights other factors that impact formation of cracks, including the relative behaviors of adjoining materials, the restrained structure of some paintings, and the presence of previously compromised materials,

FIGURE 1. The stress development in materials of fabric-supported paintings. (upper left) Unrestrained dimensional change in linen fabric (warp and weft threads) versus relative humidity at 70°F. (upper right) Effect of relative humidity (RH) on the stress-strain properties of flake white pigment in linseed oil, 36 months old, at 70°F. (lower left) Restrained specimen force development versus relative humidity at 71°F for linen in the warp direction (Ulster #8800), with a length of 7 inches and width of 0.5 inch (17.78 cm × 1.27 cm) (16 yarns). (lower right) Restrained specimen force development versus relative humidity at 71°F for warp direction sample from painting by Duncan Smith, dated 1912. Illustrations are from Mecklenburg (1982), figs. 5, 6a, 12, and 16, respectively.

FIGURE 2. Material mechanics research at the Smithsonian's Conservation Analytical Laboratory (now the Museum Conservation Institute) in the late 1990s. (top) Analytical Services Group Leader Charles Tumosa and Assistant Director for Conservation Research Marion Mecklenburg in the laboratory, early 1990s. Photo by Harold E. Dougherty for the Smithsonian. (middle) Research Organic Chemist David Erhardt, Charles Tumosa, Photographic Scientist Mark McCormick-Goodhart, and Marion Mecklenburg with tensile testing apparatus, photographed for an article on museum environments. Photo by David Harp/*Smithsonian*, March 1996. (bottom) Marion Mecklenburg and Senior Paper Conservator Dianne van der Reyden, examining scanning electron micrographs of transparent papers following conservation treatment, 1991. Photo by Harold E. Dougherty for the Smithsonian.

but focuses primarily on the significant role of relative humidity in mechanical behavior of collections materials. Aside from the hazards of temperature extremes, Mecklenburg and Tumosa conclude that extreme shifts in relative humidity are of greater concern for storage and display environments because of the strong response to humidity that is observed in the most stress bearing materials in a composite painting.⁹ A handbook published after the conference (Richard et al., 1991) sought to balance the research and theoretical contributions of the conference with practical advice on the assessment and mitigation of risks to art materials imposed by various means of transport, including relative humidity, temperature, vibration, and shock.

The mechanical properties of collection materials continued to be measured and modeled by Smithsonian researchers following the 1991 conference. Methodologies for calculating individual stresses and modeling projected stress and crack patterns in composite structures were examined in detail in presentations to the Materials Research Society (Mecklenburg et al., 1992, 1995), the American Chemical Society (Mecklenburg and Tumosa, 1993), and the Pittsburgh Conference on Analytical Chemistry and Applied Spectroscopy (Tumosa and Mecklenburg, 1999) and in a paper in the *Journal of the American Institute for Conservation* (Mecklenburg et al., 1994a). Subsequent modeling studies addressed the stress responses of paintings on wooden supports (Hagan et al., 2005). Over this period the Smithsonian's study set of mechanical testing materials expanded to include, for example, paper and archive materials (van der Reyden et al., 1992; Tumosa and Mecklenburg, 1997), modern paint formulations (Mecklenburg et al., 1994b), and a range of naturally aged support materials (Erhardt et al., 1996, 1999, 2001).

The years following the 1991 conference (colloquially known as Art in Transit, after the names of its related publications) saw more detailed studies of the

FIGURE 3. Upper row: Designs for a tensile test-jig for quantifying the stress response of cultural heritage materials. (upper left) A materials list for the test-jig. (upper center and upper right) Two technical drawings of the test-jig. From Organ and Mecklenburg (1989). Lower row: Items housed in the Mecklenburg Materials Archive at the Smithsonian's Museum Conservation Institute. (lower left) A working tensile test-jig. (lower center) A selection of custom paints. (lower right) A selection of naturally aged paint film drawdowns. Photos by Smithsonian staff.

chemical and physical degradation of painting materials (Tumosa and Mecklenburg, 2003a, 2003b, 2005; Mecklenburg et al., 2005) and of the mechanical properties of collections materials that had undergone conservation treatment (Grisom et al., 1999; Tumosa et al., 1999; Mecklenburg and Tumosa, 2001). The impact of treatment on material mechanics was also studied in conjunction with academic research programs in the United States and abroad (e.g., Mecklenburg et al., 2006; Fuster-López et al., 2007, 2008, 2011), culminating in the international Cleaning 2010 conference organized by the Smithsonian Institution in collaboration with the Polytechnic University of Valencia (Mecklenburg et al., 2013a). Issues addressed in the conference papers included the effect of solvent treatment on oil-based and synthetic paint films (Tumosa and Mecklenburg, 2013; Doménech-Carbó et al.,

2013) and the potential for migration of metal ions among paint layers (Mecklenburg et al., 2013b), topics that continued to be studied through the Smithsonian's collaborative partnerships (Mecklenburg et al., 2012; Fuster-López and Mecklenburg, 2017; see Figure 5).

PROPOSING NEW ENVIRONMENTAL GUIDELINES FOR COLLECTIONS CARE

The study of the mechanical properties and dimensional change of individual materials and the resulting insight into the role of relative humidity in collections care prompted Smithsonian researchers to take a closer look at the origins and implementation of guidelines regulating environments

FIGURE 4. (top left) Residual stress distribution and crack formation resulting from desiccation of the entire painting; vectors show directions and relative magnitudes of residual stress in the central zone of painting. (top right) Residual stress distribution and crack formation at the corner of a painting resulting from desiccation of glue size and ground and paint layers accompanied by stretcher shrinkage. The illustrations in top row are from Mecklenburg (1982), figs. 25 and 24, respectively. (bottom left) The in-plane principal stress distribution as shown on stress contours resulting from a 30 G edge impact on the 76 × 102 cm model painting; the maximum stresses are extremely low, only 0.11 MPa, less than 3% of the breaking strength of the white lead paint at 50% RH, 23°C. (bottom right) The principal stress vectors resulting from a 30 G edge impact on a 76 × 102 cm model painting; the theoretical crack pattern is superimposed over the vectors, which intersect the cracks at 90°. The illustrations in bottom row are from Mecklenburg and Tumosa (1991b), figs. 8 and 9, respectively.

for collections storage and exhibition. Their studies of cold storage for acrylic paints (Erlebacher et al., 1992a, 1992b, 1992c) and photographic materials (McCormick-Goodhart and Mecklenburg, 1993) led to related work on the impact of storage conditions on composite collections made up of mixed or layered materials with disparate environmental needs and the risk of subsequent material failures within or between those materials (Mecklenburg and Tumosa, 1993). In a 1994 presentation at the American Institute for

Conservation annual meeting entitled "Relative Humidity Re-examined," Erhardt and Mecklenburg examined the relative humidity response observed in general collections and special collections materials in active and archival storage (Erhardt and Mecklenburg, 1994; see Figure 6a) and renewed Dr. Mecklenburg's earlier suggestion that it should be possible to identify ranges of relative humidity suitable for many mixed collections (Mecklenburg, 1982:26). No single relative humidity was posited in the 1994 paper as

FIGURE 5. Material mechanics research at the Smithsonian's Museum Conservation Institute (MCI): (top) 2007 visiting scholar Silvia Ottolini (Parma, Italy) studying the characterization of natural and synthetic adhesives. Photo by MCI staff. (middle) 2008 visiting scholars Cristiana Sburlino (Padua, Italy) and Debora Minotti (Florence, Italy) studying the diffusion of materials used for painting consolidation. Photo by MCI staff. (bottom) Dr. Mecklenburg with staff from the National Museum of Natural History, Department of Anthropology, consulting on the environmental response of stretched skin objects in preparation for the museum's 2010 Anchorage Loan Conservation Project: from left to right, Project Intern Dawn Planas, Project Conservator Michele Austin-Dennehy, Project Intern William Shelley, Mecklenburg, and Project Conservator Landis Smith. Photo by Project Conservator Kim Cullen Cobb.

FIGURE 6. Relative humidity stability zones from (left) Erhardt and Mecklenburg (1994:37) and (right) Erhardt et al. (1995:20). The ranges of relative humidity are suggested for various materials and situations. According to Erhardt and Mecklenburg (1994), “no one RH is ideal, and any value chosen must be a compromise.”

being appropriate for all materials, uses, and housing conditions. “The ‘optimal’ relative humidity is not a specific value upon which all considerations converge,” Erhardt and Mecklenburg (1994:32) emphasized, “but a range chosen as a compromise in an attempt to minimize the total effect of numerous reactions and processes.” Although some objects would always require restricted ranges of relative humidity, the research suggested that an expanded range of relative humidity values would be acceptable for the preservation and display of the wide array of materials found in most cultural heritage collections.

The following year, the Smithsonian team of Mecklenburg, Erhardt, McCormick-Goodhart, and Tumosa authored the report “Guidelines for the Museum Climate” for an international task force on museum air quality that charted degradation processes common to collections materials across a range of relative humidity (Erhardt et al., 1995; see Figure 6b). The report outlined the chemical and mechanical responses of various collections materials to extremes in temperature and

relative humidity and suggested expanded environmental parameters could lessen the impact of cyclical, seasonal changes. The report also noted that the expanded parameters could reduce the high installation and operating costs of equipment and facilities designed to maintain unnecessarily narrow environmental set points. The authors again emphasized that environmental parameters should be collections specific, the result of considered research and a “thorough knowledge of the materials in a collection, the ability to determine which objects and materials must be treated differently, and an understanding of the costs and problems involved in maintaining specific environments” (Erhardt et al., 1995:8).

The Smithsonian team continued to study the predicted and observed impact of temperature and relative humidity on museum objects (Erhardt et al., 1997; Mecklenburg and Tumosa, 1999; Tumosa and Mecklenburg, 1999) and worked closely with facilities and operations staff throughout the Smithsonian Institution to better understand the complex network of environmental conditioning systems in

the many collections storage, research, and exhibition buildings.¹⁰ In 2004, Smithsonian Facilities (then the Office of Facilities Engineering and Operations) implemented the team's recommendations for general collections storage and exhibit of $45\% \pm 8\%$ relative humidity (RH) and $70^{\circ}\text{F} \pm 4^{\circ}\text{F}$ (Mecklenburg et al, 2004). Subsequent publications related to this change included an overview of the retrofitting required to optimize environmental control at some of the Smithsonian's oldest buildings (Mecklenburg et al., 2004) and a refining of the methodology used to report the impact of the new guidelines on the Smithsonian's equipment operations and energy costs (Erhardt et al., 2007).¹¹ The latter included an examination of the history and development of recommendations for museum climates. During this same period, the Smithsonian team examined the use of microclimates to control storage and transport conditions (Tumosa et al., 1998, 2000; Mecklenburg, 2007) and began to analyze the impact of museum building and exhibition designs with higher levels of natural light and the impact of these light levels on exhibited collections (Mecklenburg and Del Hoyo-Melendez, 2012).

Beginning in 2010, a series of workshops, meetings, and conferences focused on museum environments and the opportunity for relaxed guidelines, such as those previously proposed by Mecklenburg and his colleagues and implemented throughout the Smithsonian. The Museum of Fine Arts, Boston, and the Getty Conservation Institute organized a meeting on "Rethinking the Museum Climate," and the American Institute for Conservation of Historic and Artistic Works (AIC) and the International Institute for Conservation of Historic and Artistic Works (IIC) held a roundtable discussion on "The Way Forward in Environmental Guidelines" with recommendations presented to the Association of Art Museum Directors (AAMD; IIC, 2010). The British Standards Institution (2012) passed revised guidelines for managing environmental conditions for cultural heritage (PAS 198), and the AIC guidelines (revised) were endorsed by the AAMD in 2013. In 2013, the Smithsonian Institution held a Summit on the Museum Preservation Environment at which its "Declaration on the Collections Preservation Environment" was presented and affirmed.¹² Presentations at the summit examined museum climate guidelines and implementation, with an emphasis on collaborative management and sustainable practices, for collections and research institutions across the globe (Stauderman and Tompkins, 2016). The declaration was a set of common values and a shared vision of environmental guidelines indebted to the innovative work of researchers, including Dr. Mecklenburg and his team.¹³ In October 2016, the Smithsonian Institution hosted *The Mechanics of Art Materials and Its Future in Heritage Science: A Seminar and Symposium*, organized in collaboration with the Royal Danish Academy of Fine Arts. The event represented the continuum of inquiry in mechanics research, from the foundational work that took place at the Smithsonian to the subsequent

projects and teams bringing new energy and methodologies to the study and preservation of collections.

The history of material mechanics research at the Smithsonian represents an important development in the field of conservation science. Following an early focus on technical studies in the service of responsive treatment for individual objects, contemporary conservation research from multiple scientific disciplines is engaged in the proactive care of entire collections. These evidence-based studies of the impact of museum environments (relative humidity, temperature, vibration and shock, and light) on the behavior and degradation of collection materials have stimulated the rise of preventive conservation as an integral part of collections care. The careful interpretation of research results accumulated over decades has allowed for the safe and practical modification of exhibition, storage, and transit conditions that simultaneously addresses the physical needs of collections and modern-day fiscal and environmental responsibilities. Today's material mechanics research requires international and interdisciplinary collaboration as preservation concerns and the collections care mandate become global. Mecklenburg's 1982 study of individual materials seemed limited, but over the past 35 years the impact of that research has improved the future of cultural heritage around the world.

NOTES

1. Sporadic appropriations for maintenance of the National Museum were approved by Congress as early as 1858 (Smithsonian Institution Archives, SIA RU000190); the National Museum Act (20 U.S.C. § 65a, 1966, <https://www.gpo.gov/fdsys/pkg/STATUTE-80/pdf/STATUTE-80-Pg953.pdf>, accessed 8 October 2016) formalized annual appropriations for the museum and provided greater latitude for the use of those funds.
2. The only conservation research laboratory at the Smithsonian Institution that predates the Conservation Research Laboratory (now the Museum Conservation Institute) is the Technical Laboratory at the Smithsonian's Freer Gallery (now the Department of Conservation and Scientific Research at the Freer Gallery of Art and Arthur M. Sackler Gallery), established in 1952 by Fogg Art Museum chemist Rutherford J. Gettens.
3. The Conservation Research Laboratory was established at the Smithsonian Institution in 1963 as an independent unit reporting to the director of the United States National Museum (the administrator for all Smithsonian museums and paninstitutional programs). In 1964 the laboratory moved into the Museum of History and Technology building (now the National Museum of American History) and in 1966 was renamed the Conservation Analytical Laboratory (CAL). In 1983, the Smithsonian Institution opened the Museum Support Center complex in Suitland, Maryland, and CAL moved into the new facility. In 1998 CAL increased its educational programming and changed its name to the Smithsonian Center for Materials Research and Education (SCMRE). In 2006, a refocusing on the care and research of collections led to another name change, as SCMRE became the Museum Conservation Institute. Materials research has remained a priority for the unit and for the Smithsonian Institution throughout this timeline (https://www.si.edu/mci/english/about_mci/history.html, accessed 18 April 2018).
4. A preliminary report by Colville and Mecklenburg was submitted in 1978.
5. M. F. Mecklenburg, *The Role of Water on the Strength of Polymers and Adhesives*, Ph.D. diss., University of Maryland, College Park, 1984.
6. The Canadian Conservation Institute was then the Canadian Conservation Institute of Communications Canada.
7. Some of the conference organizers had participated in the International Council of Museums—Committee for Conservation's 8th Triennial Meeting in

- 1987, which included presentations from working group members interested in exhibition lighting and climate control research.
8. Stress vector and distribution illustrations appearing throughout Dr. Mecklenburg's work employ the finite element analysis (FEA) method used for stress mapping in engineering. The research presented at the 1991 conference and in the subsequent postprints (entitled *Art in Transit: Studies in the Transport of Paintings*) also employs the FEA method.
 9. Desiccation of painting support materials at high temperatures and extreme brittleness of acrylic paint films at low temperatures are recognized hazards. At the moderate temperatures found in most collections storage and display spaces some of the stiffest materials that bear the most stress in paintings, such as glue size, are also the most responsive to changes in relative humidity.
 10. At that time, the Smithsonian Institution's 16 museum complexes included 434 buildings with a footprint of more the 740,000 square meters (Mecklenburg et al., 2004:518).
 11. In 2008, ways to lower energy costs in relation to museum environments were discussed in the United Kingdom at the National Museum Directors' Conference (NMDC, now the National Museum Directors' Council) and a meeting of the International Group of Exhibition Organizers from the European Bizot Group of museum directors. New guidelines were developed by NMDC and Bizot in 2009. Guidelines for museum climates recommended by the American Society of Heating, Refrigerating and Air-Conditioning Engineers (ASHRAE) generally reflect contemporary museum practice; the regulations are revised every 4 years. The current ASHRAE guidelines for mixed collections exhibition space in temperate environments (classes AA and A) are 35%–65% RH and 48°F–82°F, with different parameters established for specialty collections and acceptable fluctuations of $\pm 5\%$ – 10% RH and $\pm 4^\circ\text{F}$ (2°C) depending on seasonal adjustment and system set point (ASHRAE, 2015; Michalski, 2016:16).
 12. In 2014, the Australian Institute for the Conservation of Cultural Materials presented new temperature and relative humidity guidelines for general collection materials, IIC and the International Council of Museums—Committee for Conservation released a declaration on environmental guidelines, and the Getty Conservation Institute announced its Managing Collection Environments Initiative.
 13. In 2015, the Smithsonian Institution and the U.K. Arts and Humanities Research Council convened a meeting to discuss “Managing Cultural Heritage in a Climate Change(d) Future” and the possible related changes in collections care needs and resources.
- ## REFERENCES
- American Society of Heating, Refrigerating and Air-Conditioning Engineers (ASHRAE). 2015. “Museums, Galleries, Archives, and Libraries.” In *ASHRAE Handbook—HVAC Applications*, pp. 23.1–23.22. Atlanta, Ga.: American Society of Heating, Refrigerating and Air-Conditioning Engineers.
- British Standards Institution. 2012. Specification for Managing Environmental Conditions for Cultural Collections. PAS 198:2012. London: British Standards Institution.
- Collins, S., M. W. Ballard, and M. F. Mecklenburg. 1990. “Fabric Selection and Its Relationship to Dimensional Changes in Support Systems for Constrained Fabric Mounting Devices.” In *Textiles and Costumes on Parade: Exhibition Successes and Disasters*, pp. 10–20. Harpers Ferry, W. Va.: Harpers Ferry Regional Textile Group.
- Colville, J., and M. F. Mecklenburg. 1978. Report on the Deterioration of Fabric Supported Paint Films; Phase I - Research Report. Washington, D.C.: Smithsonian Institution.
- Doménech-Carbó, M. T., M. F. Silva, E. Aura-Castro, A. Doménech-Carbó, L. Fuster-López, J. V. Gimeno-Adelantado, S. U. Kröner, M. L. Martínez-Bazán, X. Más-Barberá, M. F. Mecklenburg, L. Osete-Cortina, and D. J. Yusá-Marco. 2013. “Multitechnique Approach to Evaluate Cleaning Treatments for Acrylic and Polyvinyl Acetate Paints.” In *New Insights into the Cleaning of Paintings: Proceedings from the Cleaning 2010 International Conference*, ed. M. F. Mecklenburg, A. E. Charola, and R. J. Koestler, pp. 125–134. Smithsonian Contributions to Museum Conservation, No. 3. Washington, D.C.: Smithsonian Institution Scholarly Press.
- Erhardt, W. D., and M. F. Mecklenburg. 1994. “Relative Humidity Re-examined.” In *Preventive Conservation: Practice, Theory and Research, Preprints of the Contributions to the Ottawa Congress*, ed. A. Roy and P. Smith, pp. 32–38. London: International Institute for Conservation.
- Erhardt, W. D., M. F. Mecklenburg, C. S. Tumosa, and M. H. McCormick-Goodhart. 1995. Guidelines for the Museum Climate: Report to the Task Force on Indoor Air Quality in Museums. Herndon, Va.: International Society of Indoor Air Quality and Climate.
- Erhardt, D., M. F. Mecklenburg, C. S. Tumosa, and M. H. McCormick-Goodhart. 1997. “The Determination of Appropriate Museum Environments.” In *The Interface between Science and Conservation*, ed. S. Bradley, pp. 153–163. British Museum Occasional Papers, No. 116. London: British Museum.
- Erhardt, W. D., M. F. Mecklenburg, C. S. Tumosa, and T. M. Olstad. 1996. “New vs Old Wood: Differences and Similarities in Physical, Mechanical, and Chemical Properties.” In *ICOM Committee for Conservation, 11th Triennial Meeting, Edinburgh, Scotland, 1–6 September 1996: Preprints*, Volume 2, ed. J. Bridgland, pp. 903–910. London: James and James.
- Erhardt, D., C. S. Tumosa, and M. F. Mecklenburg. 1999. “Material Consequences of the Aging of Paper.” In *ICOM Committee for Conservation, 12th Triennial Meeting, Lyon, 29 August–3 September 1999: Preprints*, Volume 2, ed. J. Bridgland and J. Brown, pp. 501–506. London: James and James.
- Erhardt, D., C. S. Tumosa, and M. F. Mecklenburg. 2001. “Chemical and Physical Changes in Naturally and Accelerated Aged Cellulose.” In *Historic Textiles, Papers and Polymers in Museums*, ed. J. M. Cardamone and M. Baker, pp. 23–37. ACS Symposium Series, No. 779. Washington, D.C.: American Chemical Society.
- Erhardt, D., C. S. Tumosa, and M. F. Mecklenburg. 2007. “Applying Science to the Question of Museum Climate.” In *Museum Microclimates: Contributions to the Copenhagen Conference*, eds. T. Padfield and K. Borchersen, pp. 11–18. Copenhagen, Denmark: The National Museum of Denmark. <http://www.conservationsphysics.org/mm/musmic/musmic150.pdf> (accessed 18 April 2018).
- Erlebacher, J. D., E. Brown, M. F. Mecklenburg, and C. S. Tumosa. 1992a. “The Effects of Temperature and Relative Humidity on the Mechanical Properties of Modern Painting Materials.” In *Materials Issues in Art and Archaeology III*, ed. P. B. Vandiver, J. R. Druzik, G. S. Wheeler, and I. C. Freestone, pp. 359–370. MRS Symposium Proceedings, No. 267. Pittsburgh: Materials Research Society.
- Erlebacher, J. D., M. F. Mecklenburg, and C. S. Tumosa. 1992b. The Mechanical Behavior of Artist's Acrylic Paints with Changing Temperature and Relative Humidity. *Polymer Preprints*, 33(2):646–647.
- Erlebacher, J. D., M. F. Mecklenburg, and C. S. Tumosa. 1992c. “The Mechanical Behavior of Artists' Acrylic Paints with Changing Temperature and Relative Humidity.” In *AIC Paintings Specialty Group Postprints: Papers Presented at the Twentieth Annual Meeting*, pp. 35–40. Washington, D.C.: American Institute for Conservation of Historic and Artistic Works.
- Fuster-López, L., and M. F. Mecklenburg. 2017. “A Look into Some Factors Influencing the Film Forming Properties of Oil Paint Films in Copper Paintings and the Effects of Environment in their Structural Behaviour.” In *Paintings on Copper and Other Metal Plates. Production, Degradation and Conservation Issues*, ed. L. Fuster-López, I. Chulia Blanco, M. F. Sarrió Martín, M. L. Vázquez de Ágredos Pascual, L. Carlyle, and I. Wadum, pp. 95–102. Valencia, Spain: Universidad Politécnica de Valencia.
- Fuster-López, L., M. F. Mecklenburg, D. J. Y. Marco, S. V. Palomino, and A. F. B. Dos Santos. 2007. Effects of Mordants on the Mechanical Behaviour of Dyed Silk Fabrics: Preliminary Tests on Cochineal Dyestuffs. *Arché: Publicación del Instituto Universitario de Restauración del Patrimonio de la UPV*, No. 2:115–120.
- Fuster-López, L., M. F. Mecklenburg, M. Castell, and V. Guerola. 2008. “Filling Materials for Easel Paintings: When the Ground Reintegration Becomes a Structural Concern.” In *Preparation for Painting: The Artist's Choice and Its Consequences*, ed. J. H. Townsend, T. Doherty, G. Heydenreich, and J. Ridge, pp. 180–186. London: Archetype Books.
- Fuster-López, L., A. Murray, M. F. Mecklenburg, D. Yusa-Marco, G. Mirderikvand, and M. Doutre. 2011. “Filling Materials for Easel Paintings: Current Formulations, Traditional Concerns.” In *ICOM-CC, 16th Triennial Conference, Lisbon, Portugal, 19–23 September 2011: Preprints*. Paris: ICOM-CC. <https://www.icom-cc-publications-online.org/PublicationDetail.aspx?cid=9e310b8c-92e9-4769-8a67-e061bde4647d> (accessed 18 April 2018).
- Grissom, C. A., A. E. Charola, A. Boulton, and M. F. Mecklenburg. 1999. Evaluation over Time of an Ethyl Silicate Consolidant Applied to Ancient Lime Plaster. *Studies in Conservation*, 44(2):113–120.
- Hagan, E., E. Quasney, and M. F. Mecklenburg. 2005. “A Parametric Analysis of Relative Humidity Effects on Traditional Panel Paintings.” In *Materials Issues in Art and Archaeology VII: Materials Research Society Symposium, Held November 30–December 3, 2004, Boston, Mass.*, ed. P. B. Vandiver,

- J. L. Mass, and A. Murray, pp. 3–11. MRS Symposium Proceedings, No. 852. Warrendale, Pa.: Materials Research Society.
- International Institute for Conservation of Historic and Artistic Works (IIC). 2010. The Plus/Minus Dilemma: A Way Forward in Environmental Guidelines. Transcript of the meeting held on 13 May 2010 in Milwaukee, Wis., in collaboration with the American Institute for Conservation and its annual meeting. London: International Institute for Conservation of Historic and Artistic Works.
- McCormick-Goodhart, M. H., and M. F. Mecklenburg. 1993. "Cold Storage Environments for Photographic Materials." In *Final Program and Advance Printing of Paper Summaries, IS&T's 46th Annual Conference*, pp. 277–280. Springfield, Va.: Society for Imaging Science and Technology.
- Mecklenburg, M. F. 1982. Some Aspects of the Mechanical Behavior of Fabric Supported Paintings. Washington, D.C.: Smithsonian Institution.
- Mecklenburg, M. F. 1984. The Role of Water on the Strength of Polymers and Adhesives. Ph.D. diss., University of Maryland, College Park.
- Mecklenburg, M. F. 1988. "The Effects of Atmospheric Moisture on the Mechanical Properties of Collagen under Equilibrium Conditions." In *Preprints of 16th Annual Meeting of the American Institute for Conservation of Historic and Artistic Works*, ed. S. Z. Rosenberg, pp. 231–244. Washington, D.C.: American Institute for Conservation of Historic and Artistic Works.
- Mecklenburg, M. F., ed. 1991a. *Art in Transit: Studies in the Transport of Paintings*. Washington, D.C.: National Gallery of Art.
- Mecklenburg, M. F. 1991b. "Some Mechanical and Physical Properties of Gilded Gesso." In *Gilded Wood Conservation and History*, ed. D. Bigelow, E. Cornu, G. J. Landrey, and C. Van Horne, pp. 163–170. Madison, Conn.: Sound View Press.
- Mecklenburg, M. F. 2007. "Micro Climates and Moisture Induced Damage to Paintings." In *Museum Microclimates: Contributions to the Copenhagen Conference*, eds. T. Padfield and K. Borchers, pp. 19–25. Copenhagen, Denmark: The National Museum of Denmark. <http://www.conservationphysics.org/mm/musmic/musmic150.pdf> (accessed 18 April 2018).
- Mecklenburg, M. F., A. E. Charola, and R. J. Koestler, ed. 2013a. *New Insights into the Cleaning of Paintings: Proceedings from the Cleaning 2010 International Conference, Universidad Politécnica de Valencia and Museum Conservation Institute*. Smithsonian Contributions to Museum Conservation, No. 3. Washington, D.C.: Smithsonian Institution Scholarly Press.
- Mecklenburg, M. F., J. M. Del Hoyo-Melendez. 2012. Development and Application of a Mathematical Model to Explain Fading Rate Inconsistencies Observed in Light-sensitive Materials. *Coloration Technology*, 128(2):139–146.
- Mecklenburg, M. F., L. Fuster-López, and S. Ottolini. 2012. "A Look at the Structural Requirements of Consolidation Adhesives for Easel Paintings." In *Adhesives and Consolidants in Painting Conservation*, ed. A. Barros D'Sa, L. Bone, A. Gent, and R. Ciarricoates, pp. 7–23. London: Archetype.
- Mecklenburg, M. F., M. H. McCormick-Goodhart, and C. S. Tumosa. 1994a. Investigation into the Deterioration of Paintings and Photographs Using Computerized Modeling of Stress Development. *Journal of the American Institute for Conservation*, 33(2):153–170.
- Mecklenburg, M. F., M. Rossi, and L. Fuster López. 2006. "Failure Mechanisms in Canvas Supported Paintings: Approaches for Developing Consolidation Protocols." In *The Care of Painted Surfaces: Materials and Methods for Consolidation, and Scientific Methods to Evaluate Their Effectiveness; Proceedings of the Conference, Milan, November 10–11, 2006*, pp. 49–58. Saonara, Italy: Il Prato.
- Mecklenburg, M. F., and C. S. Tumosa. 1991a. "An Introduction into the Mechanical Behavior of Paintings under Rapid Loading Conditions." In *Art in Transit: Studies in the Transport of Paintings*, ed. M. F. Mecklenburg, pp. 137–171. Washington, D.C.: National Gallery of Art.
- Mecklenburg, M. F., and C. S. Tumosa. 1991b. "Mechanical Behavior of Paintings Subjected to Changes in Temperature and Relative Humidity." In *Art in Transit: Studies in the Transport of Paintings*, ed. M. F. Mecklenburg, pp. 173–216. Washington, D.C.: National Gallery of Art.
- Mecklenburg, M. F., and C. S. Tumosa. 1993. Computer Modeling of the Effects of Temperature and Relative Humidity on Stresses in the Layers of Cultural Materials. *Polymeric Materials, Science and Engineering: Proceedings of the ACS Division of Polymeric Materials Science and Engineering*, 68:226–228.
- Mecklenburg, M. F., and C. S. Tumosa. 1999. Temperature and Relative Humidity Effects on the Mechanical and Chemical Stability of Collections. *ASHRAE Journal*, 41(4):69–74.
- Mecklenburg, M. F., and C. S. Tumosa. 2001. Traditional Oil Paints: The Effects of Long-Term Chemical and Mechanical Properties on Restoration Efforts. *MRS Bulletin*, 26(1):51–55.
- Mecklenburg, M. F., C. S. Tumosa, and D. Erhardt. 2004. New Environmental Guidelines at the Smithsonian Institution. *Papyrus*, 5(3) 16–17.
- Mecklenburg, M. F., C. S. Tumosa, and D. Erhardt. 2005. "The Changing Mechanical Properties of Aging Oil Paints." In *Materials Issues in Art and Archaeology VII: Materials Research Society Symposium, held November 30–December 3, 2004, Boston, Mass.*, ed. P. B. Vandiver, J. L. Mass, and A. Murray, pp. 13–24. MRS Symposium Proceedings, No. 852. Warrendale, Pa.: Materials Research Society.
- Mecklenburg, M. F., C. S. Tumosa, and J. D. Erlebacher. 1994b. Mechanical Behavior of Artist's Acrylic Paints under Equilibrium Conditions. *Polymer Preprints*, 35:297–298.
- Mecklenburg, M. F., C. S. Tumosa, and M. H. McCormick-Goodhart. 1992. "A General Method for Determining the Mechanical Properties Needed for the Computer Analysis of Polymeric Structures Subjected to Changes in Temperature and Relative Humidity." In *Materials Issues in Art and Archaeology III*, ed. P. B. Vandiver, J. R. Druzik, G. S. Wheeler, and I. C. Freestone, pp. 337–358. MRS Symposium Proceedings, No. 267. Pittsburgh: Materials Research Society.
- Mecklenburg, M. F., C. S. Tumosa, and M. H. McCormick-Goodhart. 1995. "A General Model Relating Externally Applied Forces to Environmentally Induced Stresses in Materials." In *Materials Issues in Art and Archaeology IV*, ed. P. B. Vandiver, J. R. Druzik, J. L. G. Madrid, I. C. Freestone, and G. S. Wheeler, pp. 285–292. MRS Symposium Proceedings, No. 352. Pittsburgh: Materials Research Society.
- Mecklenburg, M. F., C. S. Tumosa, and A. Pride. 2004. Preserving Legacy Buildings. In "HVAC Retrofit." Supplement, *ASHRAE Journal*, 46(6):S18–S23.
- Mecklenburg, M. F., C. S. Tumosa, and E. P. Vicenzi. 2013b. "The Influence of Pigments and Ion Migration on the Durability of Drying Oil and Alkyd Paints." In *New Insights into the Cleaning of Paintings: Proceedings from the Cleaning 2010 International Conference*, ed. M. F. Mecklenburg, A. E. Charola, and R. J. Koestler, pp. 59–67. Smithsonian Contributions to Museum Conservation, No. 3. Washington, D.C.: Smithsonian Institution Scholarly Press.
- Mecklenburg, M. F., and J. M. Del Hoyo-Melendez. 2012. Development and Application of a Mathematical Model to Explain Fading Rate Inconsistencies Observed in Light-sensitive Materials. *Coloration Technology*, 128(2):139–146.
- Michalski, S. 2016. "Climate Guidelines for Heritage Collections: Where We Are in 2014 and How We Got Here." In *Proceedings of the Smithsonian Institution Summit on the Museum Preservation Environment*, ed. S. Stauderman and W. G. Tompkins, pp. 7–32. Washington, D.C.: Smithsonian Institution Scholarly Press.
- Murray, A., R. E. Green, M. F. Mecklenburg, and C. M. Fortunko. 1991a. "NDE Applied to the Conservation of Wooden Panel Painting." In *Nondestructive Characterization of Materials IV*, ed. C. O. Ruud, pp. 73–80. New York: Plenum Press.
- Murray, A., R. E. Green, M. F. Mecklenburg, and C. M. Fortunko. 1991b. "Non-destructive Evaluation of Works of Art." In *Art in Transit: Studies in the Transport of Paintings*, ed. M. F. Mecklenburg, pp. 249–260. Washington D.C.: National Gallery of Art.
- Organ, R. M., and M. F. Mecklenburg. 1989. Notes on the Test-Jig Made and Used by Marion F. Mecklenburg. Internal Report. Washington, D.C.: Conservation Analytical Laboratory, Smithsonian Institution.
- Richard, M., M. F. Mecklenburg, and R. M. Merrill, eds. 1991. *Art in Transit: Handbook for Packing and Transporting Paintings*. Washington, D.C.: National Gallery of Art.
- Smithsonian Institution Archives. SIA RU000190, United States National Museum Office of the Director, Records, circa 1921–1973. Smithsonian Institution, Washington, D.C.
- Stauderman, S., and W. G. Tompkins, eds. 2016. *Proceedings of the Smithsonian Institution Summit on the Museum Preservation Environment*. Washington, D.C.: Smithsonian Institution Scholarly Press.
- Tumosa, C. S., McCormick-Goodhart, M. H., Mecklenburg, M. F. 1998. The Physical Properties of Photographic Film Polymers Subjected to Cold Storage Environments. *Polymer Preprints* 39:1245–1246. New York, NY: American Chemical Society.
- Tumosa, C. S., McCormick-Goodhart, M. H., Mecklenburg, M. F. 2001. "The Physical Properties of Photographic Film Polymers Subjected to Cold Storage Environments." In *Historic Textiles, Papers and Polymers in Museums*, Symposium 779, eds. J. M. Cardamone and M. Baker, pp. 136–144. Washington, D.C.: American Chemical Society.
- Tumosa, C. S., and M. F. Mecklenburg. 1997. Some Mechanical Properties of Skin. *Mid-Atlantic Association of Forensic Scientists Newsletter*, 25(1):18–22.

- Tumosa, C. S., and M. F. Mecklenburg. 1999. "Materials Characterization and the Computer Modeling of Works of Art." In *Abstracts Pittcon 99*, Abstract 858. Pittsburgh: Pittsburgh Conference and Exposition.
- Tumosa, C. S., and M. F. Mecklenburg. 2003a. Weight Changes in Acrylic Emulsion Paints and the Implications for Accelerated Ageing. *WAAC Newsletter*, 25(3):12–14.
- Tumosa, C. S., and M. F. Mecklenburg. 2003b. Weight Changes on Oxidation of Drying and Semi-drying Oils. *Collection Forum*, 18(1–2):116–123.
- Tumosa, C. S., and M. F. Mecklenburg. 2005. The Influence of Lead Ions on the Drying of Oils. *Reviews in Conservation*, 6:39–47.
- Tumosa, C. S., and M. F. Mecklenburg. 2013. "Oil Paints: The Chemistry of Drying Oils and the Potential for Solvent Disruption." In *New Insights into the Cleaning of Paintings: Proceedings from the Cleaning 2010 International Conference*, ed. M. F. Mecklenburg, A. E. Charola, and R. J. Koestler, pp. 51–58. Smithsonian Contributions to Museum Conservation, No. 3. Washington, D.C.: Smithsonian Institution Scholarly Press.
- Tumosa, C. S., J. Millard, D. Erhardt, and M. F. Mecklenburg. 1999. Effects of Solvents on the Physical Properties of Paint Films. In *ICOM Committee for Conservation, 12th Triennial Meeting, Lyon, 29 August–3 September 1999: Preprints*, ed. J. Bridgland and J. Brown, Volume 1, pp. 347–352. London: James and James.
- U.S. Senate. 1983. Report No. 98-95, Amending the Act of October 15, 1966 (80 STAT. 953; 20 U.S.C. 65a), Relating to the National Museum of the Smithsonian Institution, so as to Authorize Additional Appropriations to the Smithsonian Institution for Carrying Out the Purposes of Said Act, Relating to the Smithsonian Institution. <https://repository.si.edu/handle/10088/28950> (accessed 8 October 2016).
- van der Reyden, D. L., C. Hofmann, M. T. Baker, and M. Mecklenburg. 1992. "Modern Transparent Papers: Materials, Degradation, and the Effects of Some Conservation Treatments." In *Materials Issues in Art and Archaeology III*, ed. P. B. Vandiver, J. R. Druzik, G. S. Wheeler, and I. C. Freestone, pp. 379–395. MRS Symposium Proceedings, No. 267. Pittsburgh: Materials Research Society.
- van der Reyden, D. L., M. F. Mecklenburg, M. T. Baker, and M. Hamill. 1988. Update on Current Research into Aqueous Light Bleaching at the Conservation Analytical Laboratory. *Book and Paper Group Annual*, 7:73–106.

Insight into Canvas Paintings' Stability and the Influence of Structural Conservation Treatments

Cecil Krarup Andersen^{1} and Laura Fuster-López²*

ABSTRACT. Materials science has proven useful when designing conservation solutions since it provides a broader understanding of the properties and behavior of single materials (artists' and conservation materials) as well as their interaction with each other in a composite painted structure. Early on, it was recognized that this approach would be useful for research in conservation methods and materials. Adding or removing materials through conservation intervention inevitably changes the structure and properties of an object and thereby changes the way it responds to external stimuli. Studies have shown that some of the treatments applied by paintings conservators will change the way that objects perform in time, especially the way they respond to changes in temperature and/or relative humidity. Use of adhesives (i.e., consolidation of paint, mending cracks, etc.), a more substantial addition of materials (i.e., lining, filling lacunae, etc.), or simply replacing a varnish can lead to significant change in the painting structure and properties and, consequently, the way the new composite ages in different climates. Understanding the structural behavior of painting materials is therefore crucial to the design of conservation strategies that support long-term preservation. This paper presents insights into the current knowledge on the changes induced by selected conservation treatments and the consequences of adding or removing material. The aim is to reflect on options for designing conservation treatments that are both interventive and preventive, rendering the painting equally or more able to tolerate climate fluctuations than before treatment.

INTRODUCTION

Treatments performed by conservators in day-to-day practice often change the structure of the treated object, thus affecting its response to changes in temperature or relative humidity (RH) as well as its performance over time. With best intentions, conservators have traditionally added materials like wax, glues, and resins or removed materials from previous interventions. Materials were, in many cases, restrained or tensioned, resulting in increased stress levels to the original material. It is therefore important to have a better sense of the specific consequences that conservation treatments may have on the objects in both the near and the far future.

In order to select treatments that consider the long-term effects, it is important to know the relevant ambient climate, moisture and temperature swelling coefficients of original and added materials, and to be aware of the changes in structure and mechanical properties that each treatment causes. The study of the mechanical and dimensional properties of objects and conservation materials provides a

¹ Royal Danish Academy of Fine Arts, Schools of Architecture, Design and Conservation, Philip de Langes Allé 10, 1435 Copenhagen K, Denmark.

² Universitat Politècnica de València, Instituto Universitario de Restauración del Patrimonio. Camino de Vera, s/n, 46022 Valencia, Spain.

* Corresponding author cka@kadk.dk

Manuscript received 2 June 2018; accepted 7 May 2019.

tangible way to understand the behavior and the structural consequences of conservation choices.

This paper will discuss results obtained by research into structural and mechanical behavior of treated paintings and the impact that treatment has on the stability of paintings. This paper furthermore proposes a three-step approach to structural conservation that will integrate consideration for structural changes into the conservation decision-making process. The focus is on paintings, but the materials science approach can be used widely for other objects and represents a fundamental method to comprehend the challenges that conservators face (Fuster-López and Andersen, 2014).

THE MATERIALS SCIENCE APPROACH IN CONSERVATION

Conservation can change an object. In order to understand this change one must understand the object from a materials science point of view. The discipline of materials science was defined as a function of four essential components by the American engineer William D. Callister: processing, structure, properties, and function (Callister, 2007:4).

In terms of materials' performance, these components are a good starting point for cultural heritage as well. The question is, What happens once degradation sets in and is followed by a conservation treatment where structure, properties, and performance can be changed in various ways? The local climate surrounding the object may also affect structure, properties, and performance significantly (Figure 1).

Early steps of using an engineering approach to paintings were taken in the beginning of the twentieth century,

as described in a report from the Courtauld Institute (MacIntyre et al., 1934). This report pointed out the different responses to relative humidity of the substrate and the paint layer in a canvas painting that will “either tend to loosen the paint film from the canvas or produce cracks” (MacIntyre et al., 1934:14). This report and an article that same year from the same group of researchers (Plenderleith and Cursiter, 1934) show early examples of systematic testing of structural conservation methods through so-called endurance tests of, for example, tinfoil covering of panel paintings and a wax-resin lining of canvas paintings. These tests included rather extreme conditions like immersion of a painting in a water tank.

A typical article on conservation in the 1960s, 1970s, and 1980s aimed at demonstrating the usefulness or drawbacks of a certain material, method, or approach (Hacke, 1963; Berger, 1970; Mehra, 1975; Ketnath, 1976; Mecklenburg and Webster, 1977; Hedley and Villers, 1982; Fieux, 1984). Research into the effect of structural conservation thus had the nature of exchanging ideas or reviewing consequences of conservation methods based on criteria like stiffness, hygroscopicity, and reversibility. However, there was no consensus as to the optimal demands for conservation treatments like lining or consolidation. Structural all-in-one treatments like wax-resin and glue-paste linings were questioned while new methods and a consensus on long-term strategies for structural treatments were sought. With the introduction of preventive conservation approaches and the emerging field of conservation science, more research now is concerned with methods of documenting behavior in paintings rather than investigating the effect that conservation methods have. This line of approach has led to advances in our ability to predict how materials will behave in certain ambient climates, but not many advances have been made when it comes to new treatment options. Meanwhile, large structural treatments are still performed, and we are still not able to understand the full consequences of the impact that previous treatments have on paintings in our collections. The desire to keep paintings in their original historic settings—sometimes avoiding nonoriginal glazing or major structural treatments—can result in smaller interventions in which cracks are filled or paintings are retensioned without sufficient support.

New advances linked to the environmental discussion have recently been made in the investigation of deformation (Groves et al., 2007, 2008; Malowany et al., 2014; Klausmeyer et al., 2016) and moisture sorption (Hendrickx et al., 2016a, 2016b). Neither sorption nor deformation, however, is the direct cause of failure in materials. Stress is the direct cause of failure, and it would therefore be useful if the above-mentioned research was complemented with research into the stress development and failure in materials at different ambient conditions. The consequences of structural conservation can then be assessed method by method.

FIGURE 1. Model inspired by Callister (2007) for the interrelated concepts affecting the structure, properties, and performance of objects. After production of an object degradation process, structural conservation and ambient climate can change all three concepts and thus change the way the object looks and performs and/or degrades.

THE STRUCTURAL IMPLICATIONS OF SOME CONSERVATION DECISIONS

Reinforcing a paneled structure, providing an additional stretchable support (i.e., lining, strip lining, etc.), mending torn fabrics, filling missing paint layers, and simply providing cohesion to powdery or flaking paint have been common practices in paintings conservation throughout history. In all these cases adhesives have been used to a greater or lesser extent and can be considered the common thread when following the history of the conservation-restoration profession. Describing the development of conservation materials and methods depends on the geographical location and climate, as well as criteria trends in this constantly evolving field.

ADHESIVES IN THE CONSERVATION OF PAINTINGS

With the early developments of the chemical industry after World War II, synthetic resins came on the market. The

use of natural adhesives (glues, gums, resins, etc.) coexisted with these new technical developments (see Figure 2). The fine arts soon became flooded with synthetic paints and adhesives, and this has been a growing tendency to date. The use of suction tables and hot tables (Ruhemann, 1953; Hacke 1963; Mehra, 1975), humidification systems, and all kinds of devices were soon associated with the potential use of synthetic resins to treat powdery and flaking paint, relax stiff fabrics, and line paintings. The apparent advantages offered by the new synthetic adhesives over the natural ones favored their popularity and increased use in the field during the 1990s.

The use of adhesives has significant structural implications in painting stability since they change paintings irreversibly. It is widely known that each adhesive presents different adhesive and cohesive properties. Whereas factors such as the microstructure, surface cleanness, and roughness of a surface influence the bonding of an adhesive to a substrate, the cohesion of an adhesive results from a variety of interactions within adhesives such as chemical bonds within the polymer, cross-linking, and inter- as well as intramolecular interactions.

FIGURE 2. Chronology of adhesives use in the structural treatment of paintings, the invention of specific devices and equipment, and related literature and conferences.

In order to assess the performance of adhesives in commonly used solvents, 20 different adhesives in a total of 40 different solutions were recently tested in a research project by Mecklenburg et al. (2012). These adhesive solutions were chosen because they are the most common on the basis of a survey carried out in 2007 among the conservation community. Tensile, peel, and penetration tests were carried out to evaluate their adhesive and cohesive behavior as well as the extent of penetration expected for each of them for different substrates of known porosity. Results indicated that animal glues and gelatins develop high cohesive strengths and stiffness, far beyond all the synthetic polymers tested. Nevertheless, animal glues and gelatins are water sensitive and therefore prone to biodegradation and are strongly influenced by RH fluctuations, becoming brittle with low RH values and losing nearly all their cohesive strength with high RH. The same research showed that Gustav Berger's Original Formula 371 (BEVA [Berger ethylene vinyl acetate] 371) presents a very low cohesive strength, but it bonds well to certain supports. In other words, although the elastic modulus and the ultimate tensile strength are very low (0.6 MPa) at room conditions (~50% RH) compared to other adhesives such as animal glues and gelatins (± 68 MPa), the peel tests (or adhesion tests) showed that its adhesive bond strength to linen and polyester substrates is higher (± 6 N/cm) than the one shown by hide glue (± 4.4 N/cm) or sturgeon glues (± 5.5 N/cm; Mecklenburg et al., 2012). It is well known that BEVA products revolutionized the conservation community. However, the main concern today is not only the chemistry behind the adhesive mixture itself but also its long-term behavior and stability in use (Ploeger et al., 2014). The concern here relates to the fact that the BEVA adhesive has traditionally been used in various circumstances and for different needs without discriminating between the structural requirements in each case.

How can research into mechanical and dimensional properties of adhesives be related to hands-on conservation practice? For example, the results above indicate that although BEVA 371 could work well bonding different materials together (i.e., flaking paint), one cannot expect this adhesive to provide any stiffness to any painted system. For example, BEVA 371 could be an option to adhere flaking paint in a water-sensitive painted surface. However, when used as a lining adhesive, it requires the addition of a stiff auxiliary fabric or interleave (Andersen and Nielsen, 2012) to provide sufficient stiffness (and therefore support) to the canvas painting.

Another interesting issue to discuss is the role of solvents when using adhesives. The use of any adhesive usually requires the use of a vehicle or solvent intended to help the polymer penetrate the pores and reach the areas where strengthening is needed. Solvents used in adhesive solutions can be retained in the painted structure for long periods of time before complete evaporation. When monitoring the

change in the mechanical properties of adhesives as a function of the evaporation time, the results indicate that the thicker the adhesive film is, the longer it takes for the solvent to evaporate. Research in the context of adhesives used in paintings conservation has also revealed that different solvents have different drying times, which impacts cohesive and adhesive properties. Fast-evaporating solvents such as acetone accelerate drying but result in extremely stiff and brittle films (Mecklenburg et al., 2012).

Since treated paintings will always be a version of what the artist created, it is essential to estimate the consequences of the conservation decisions. Following the above considerations, the design of conservation strategies must be the result of a thoroughly evaluated process in which the understanding of the material's properties in a given environment must merge with the possibilities and limitations of conservation materials and methods.

The study of materials' properties helps us understand the different adhesive and cohesive strengths of adhesives, the stiffness they present, and the fact that the strength requirements for adhesives depend on what function they are to serve. As explained above, no adhesive solves all types of problems. Different causes of damage will turn into different failure mechanisms and will have different adhesive and cohesive requirements, and therefore, different adhesives in different solvents and proportions will be needed in each case. Furthermore, many structural treatments in canvas paintings go beyond the use of adhesives. The addition of fabrics, including inserts, patches, and linings, is also common practice.

STRUCTURAL IMPLICATIONS OF LINING

A lining represents a substantial change in the structure of a painting as a significant quantity of material is added and the tension of the painting may be changed through re-stretching the painting. Linings can be complicated structures with interleaves, or they can be simple additions of canvas with an adhesive. A large quantity of added material will not necessarily be reflected in a large change in properties in the overall structure since this depends on the properties of the individual materials chosen for the lining task.

The materials that may be added can be divided into the following categories: lining canvas, lining adhesive, and interleaf. Each material serves a purpose, and therefore, appropriate choices have to be made to obtain the result required. Depending on materials and approaches, the lining canvas can be thought of as a material that stiffens, reinforces, or secures the original canvas, the paint layer, or the structure as a whole. The adhesive can be thought of as a material that may impregnate, stiffen, or simply attach to the original canvas or painting. The interleaf can be seen as a material that stiffens the structure or serves as an isolation of the original structure from the lining, making it easier to reverse the treatment. All

this implies that a lining can have many purposes, depending on each individual case and the choice of the conservator.

Some lining materials shrink in high relative humidity (many types of canvas made from natural fibers) or low relative humidity (collagen-based glues in particular and paper interleaves made from natural fibers), and some are relatively flexible, whereas others are stiff when tensioned. These properties usually vary depending on the direction of testing. Most lining materials are anisotropic, as is the case for woven canvases. All these characteristics can have an effect on the structural and mechanical properties of the lined painting as a whole. A very thin layer of collagen-based glue can have a much more significant effect on the forces developing in a painting structure than a much thicker layer of a minimally hygroscopic material.

The change that a lining represents must be well defined in order to know whether the original purpose of the intervention is being met and if there are possible side effects. Thus, this knowledge constitutes a basis for future decisions about conservation and the climate around the painting.

Numerous factors govern how paintings behave at different temperature and relative humidity levels. Therefore, in order to get a first impression of the impact that linings may have on paintings two approaches are possible. One is to test lined painting mock-ups in the lab and measure their response to relative humidity. The other is to look at lined paintings in collections. However, when looking at paintings, it is difficult to know which causes originate the different degradation phenomena. The following presents a brief review of what is known from lab tests.

Each layer in a painting has a different moisture coefficient of expansion and therefore responds differently to changes in RH. The resulting force in a restrained painting was shown to be governed by the principle of superposition (Mecklenburg, 1982). This principle states that when a composite material is subjected to an external load, caused, for example, by a change in RH or tensioning, the resultant forces are equal to the sum of the forces in the separate layers, provided that all of the materials are maintained at the same degree of restraint (Hearn, 1997). When adding the measured forces in the individual layers of a painting, it is possible in theory to predict the behavior of the lined painting. The total force (F) in a painting will be equal to the sum of in-plane forces in each material in the measured direction. For any given moisture, temperature, and strain level the following therefore applies:

$$F_{(\text{painting})} = F_{(\text{canvas})} + F_{(\text{size})} + F_{(\text{ground})} + F_{(\text{paint layer})}.$$

The assumption is that the force developed in each restrained material does not affect the force on the other materials. Therefore, it should be possible to test each material separately and calculate the combined effect on the painting. This principle was used by Mecklenburg (1982) to predict the response of a restrained painting and has also proven useful

when lining materials are added (Andersen and Nielsen, 2012). For a lined painting the equation would look like

$$F_{(\text{lined painting})} = F_{(\text{painting})} + F_{(\text{adhesive})} + F_{(\text{lining canvas})}.$$

However, when the different layers interact, it becomes more difficult to predict what will happen. When a linen canvas is impregnated with an adhesive, as was often the case in older methods like glue-paste and wax-resin linings, the adhesive can interact with the swelling or shrinking canvas fibers and create an unexpected effect.

In a study of lining methods, the two traditional lining techniques, glue-paste and wax-resin, showed the biggest development in forces but in very different ways (Andersen, 2013). The wax-resin samples did not have a significant response at low relative humidity, but at levels of above 60% there was a slow but significant increase in force over 24 hours. The wax-resin mixture fills the voids between the swelling fibers in the threads of the lining canvas, and the original canvas seems to be the cause (Andersen et al., 2014). Compared to glue-paste, wax-resin is rather ductile and, contrary to what was expected, permeable to water molecules (Andersen et al., 2014). The absorption is slow, but the resulting forces in the painting structure can be remarkably high within 24 hours. This outcome indicates that understanding canvas geometry and canvas-adhesive interaction is vital to elucidate the problems with unwanted forces in lined paintings. It is evident that future research has to focus not only on moisture uptake but also on the resulting forces to obtain a fuller picture of the situation. In the results reported previously, the weft direction was much more prone to shrinkage after impregnation with wax resin than the weave direction, which indicates that the properties of the canvas still play an important role in the structure even if it is completely embedded in wax and resin (Andersen et al., 2014).

Animal glue has been the traditional glue to use in many crafts and for many purposes. In conservation it is known to be strong and stiff but also to be hygroscopic and change dimensions in both low and very high RH (>90%) with a risk of cracking (Karpowicz, 1990; Krzemień et al., 2016). It follows that traditional glue-paste lining techniques can cause the development of high forces in a painting structure (or contraction if the painting is not sufficiently tensioned; Tassinari, 1974; Young and Ackroyd, 2001; Andersen, 2013). Cracks in the corners of paintings have been regarded as an indicator of the high forces caused by contraction of, especially, animal glue, as this material imposes a risk of fracture in the paint layer as well as in the glue-paste layer itself. Cracks can also then act as expansion joints that will decrease the risk of further cracking by decreasing the forces developing in the structure. The glue-paste lining of a painting mock-up developed more force than a similar, but cracked, sample because the cracks were acting as expansion joints that released

the forces (Andersen, 2013). Aged or cracked glue-paste films in linings may therefore be of less concern when it comes to forces developing in the structure.

Modern lining methods have introduced the use of minimally hygroscopic and stiff canvases for linings (Hedley, 1981; Mehra, 1981; Hedley and Villers, 1982), and they have been able to decrease the amount of response to relative humidity in the structure (Andersen, 2013) even though some have been found to be more responsive to humidity than expected (Young and Jardine, 2012). Furthermore, because of its high stiffness polyester sailcloth has been shown to maintain a higher level of tension after stretching the lined painting than the untreated painting or the same painting lined on a linen support.

Linen or cotton canvases are, however, still used for linings as they are thought to be more in line with the original structure. Using modern adhesives such as BEVA and acrylic emulsions on such flexible canvases was found to have three risks. First, in-plane movements are not prevented when the original canvas is not restrained by a stiff structure. Shear forces between canvas and paint layers will increase, and therefore, a higher risk of cracks and delamination of paint is possible. Second, the extra linen support will typically respond to very high RH or water damage by severe contraction that can cause more flaking and buckling than if the painting had been left unlined (Andersen, 2013). Last, when the painting is retensioned after lining, extra forces will be added directly to the paint and ground layers if the support is not stiff, and subsequent contraction forces due to changing RH will further add to the risk of paint loss. This is also the case when paintings are retensioned after strip lining.

A THREE-STEP APPROACH TO STRUCTURAL CONSERVATION

Damage in the form of tears, cracks, microfissures, delamination, etc., observed in paintings is the consequence of specific failure mechanisms. They represent a great complexity in day-to-day conservation practice since they are evidence of different failure mechanisms and therefore require special consideration. In such a scenario, understanding what the objective of the conservation actions are becomes crucial and requires a multistep approach, as suggested here (Figure 3).

First, the design of conservation treatments necessarily implies defining the needs, priorities, and limitations. To do so, it is crucial to determine what caused the damage, when failure took place, and the consequences for the painting materials. Conservators have traditionally been trained to identify and define the types of alterations observed in the painted surface and to provide solutions to technical and aesthetical problems. Studies of the chemistry and mechanics of paintings in recent decades have contributed to linking

FIGURE 3. A three-step approach to developing a conservation approach.

scientific research to conservation practice. However, although chemistry has been incorporated progressively into conservation practice, understanding the exact physical mechanisms involved in degradation as well as the structural consequences of some conservation treatments needs further attention.

The second step is selecting conservation materials. The structural treatment of paintings is linked to the use of adhesives and sometimes also to the addition of new materials, such as fabrics, fillers, etc. The significant research developed in recent decades on adhesives can help conservators decide which adhesives (type of polymer, composition, molecular weight and size, glass transition temperature, adhesive/cohesive strength, etc.) to use in each case as well as which solvent and in what concentration. Nevertheless, in actual practice once the goals have been defined, many questions arise: How much strength, stiffness, and flexibility is really needed? How does the selected solvent influence such properties? What will the effects of such solvents be inside the painted layered structure in the medium to long term? How will the selected adhesive behave and age inside the painted structure, or what will the consequences of the irreversible impregnation of a porous painted structure be on mechanical and dimensional properties?

The third and last stage in the proposed multistep approach consists of determining how to actually carry out the treatment itself, that is, how to select the appropriate application method according to the needs (i.e., extent of penetration needed, quantity of adhesive needed, additional materials needed, etc.). The chosen method should preferably minimize interference with the painted structure (substrate porosity, existence of cracks or fissures to access the areas needed, side of the painting to treat, etc.) with consideration given to the possibilities and boundaries of the adhesive itself (wettability, viscosity, drying time, drying shrinkage, etc.). Although some work has been done in this direction (Maheux

and McWilliams, 1995; Buzzegoli et al., 2008), it is sometimes difficult to know if the applied adhesive(s) penetrates into the location in the structure where it is needed.

DISCUSSION AND CONCLUSION

In 1969 the American conservator Sheldon Keck wrote that many treatments were not based on an understanding of the forces involved and that some of the treatments performed aggravated the stresses that they were attempting to overcome or created new ones (Keck, 1969). In 1984 the Canadian paintings conservator Barbara Keyser argued that this was still true (Keyser, 1984). From a current perspective, conservation methods have not evolved much since then, but interventions have become fewer, with an increased focus on avoiding overtreatment of paintings and preserving the original integrity.

When looking at the degradation consequences of conservation treatments from the past, it becomes evident that there is a need for better knowledge of the composition of both artists' and conservation materials. History points out the need for critical selection of stable materials and methods that fulfill structural needs without unwanted interference and allow future retreatability. Composition and structural compatibility deserve special attention as they can help explain the extent of damage that can be induced when altering the properties of paintings, including the potential changes in response to environmental fluctuations. For example, it is well known that the use of water-sensitive adhesives will enhance paintings' response to the environment and that cradles may increase forces in the original structure of a panel painting. However, the finding that wax-resin-lined paintings may develop much higher forces with prolonged exposure to RH levels above 60% than unlined painting is less known. As research slowly progresses, more precise conservation guidelines can be suggested to improve the stability and long-term preservation of structurally treated paintings.

This chapter has discussed the effect that conservation decisions have on the long-term preservation of paintings, and possible approaches to conservation and research into structural treatments were suggested. Furthermore, if the effect of past treatments is better understood, climate conditions can be tailored to meet the needs of specific objects that have been treated by conservators. For example, we have shown that some conservation treatments such as glue-paste linings have limited the window for nondamaging climate fluctuations. Impregnations with a minimally hygroscopic substance like wax resin that penetrates deep into the canvas structure, thought to prevent moisture response, instead increased moisture response at high RH (>60%). When layers are kept more or less discrete and adhesives are not impregnating the canvas, the principle of superposition can help predict if a lining or other layers will add to the forces developing in tensioned canvas paintings.

Further evaluation of the effects of conservation treatments will allow tailoring treatments to the specific relevant climates. This requires close collaboration between conservators and scientists in future research, not only to measure deformation in materials but also to measure or calculate forces because they are the direct cause for cracks and deformation. A renewed focus on the consequences of structural treatments should help provide the much-needed assessment of relevant treatment options.

REFERENCES

- Andersen, C. K. 2013. Lined Canvas Paintings. Mechanical Properties and Structural Response to Fluctuating Relative Humidity, Exemplified by the Collection of Danish Golden Age Paintings at Statens Museum for Kunst (SMK). Ph.D. diss., Royal Danish Academy of Fine Arts, Copenhagen.
- Andersen, C. K., M. F. Mecklenburg, M. Scharff, and J. Wadum. 2014. "With the Best Intentions. Wax-Resin Lining of Danish Golden Age Paintings (Early 19th Century) on Canvas and Changed Response to RH." In *ICOM-CC, 17th Triennial Conference, Building Strong Culture through Conservation, 15–19 September 2014, Melbourne, Australia: Preprints*, ed. J. Bridgeland. Paris: International Council of Museums. <https://www.icom-cc-publications-online.org/PublicationDetail.aspx?cid=c463f919-0aed-4c24-814b-5f7232b141b2/> (accessed 05 August 2019).
- Andersen, C. K., and I. Nielsen. 2012. "Lining with Fixed Interleaf. A Case Study in the Mechanical Effects of Paper Interleaf and Binder." In *Adhesives and Consolidants in Paintings Conservation*, ed. A. Barros D'Sa, L. Bone, R. Clarricoates, and A. Gent, pp. 32–43. London: Archetype.
- Berger, G. A. 1970. A New Adhesive for the Consolidation of Paintings, Drawings and Textiles. *Bulletin of the American Group-International Institute for Conservation of Historic and Artistic Works*, 11(1):36–38.
- Buzzegoli, E., L. Landi, and D. Minotti. 2008. "The Phenomenon of Diffusion of Materials Used for Painting Consolidation in a Porous Support." In *The Care of Painted Surfaces: Materials and Methods for Consolidation, and Scientific Methods to Evaluate Their Effectiveness; Proceedings of the Conference, Milan, November 10–11, 2006*, pp. 79–87. Saonara, Italy: Il Prato.
- Callister, W. D. 2007. *Materials Science and Engineering: An Introduction*. 7th ed. New York: Wiley.
- Fieux, R. E. 1984. Silicone Polymers for Relining of Paintings. *Studies in Conservation* 29(Suppl. 1):46–49. <https://doi.org/10.1179/sic.1984.29.Supplement-1.46>.
- Fuster-López, L., and C. K. Andersen. 2014. Understanding Structural Conservation through Materials Science: Strategies and Didactics. *Revue CeROArt-Conservation et Restauration Oeuvres d'Art*, HS 2014. <https://ceroart.revues.org/4380> (accessed 05 August 2019).
- Groves, R. M., W. Osten, M. Doulgeridis, E. Kouloumpi, T. Green, S. Hackney, and V. Tornari. 2007. Shearography as Part of a Multi-functional Sensor for the Detection of Signature Features in Movable Cultural Heritage. *Proceedings of SPIE*, 6618:661810.
- Groves, R. M., W. Osten, S. Hackney, E. Kouloumpi, and V. Tornari. 2008. "Development of an Impact Assessment Procedure for Artwork Using Shearography as a Measurement Tool." In *Lasers in the Conservation of Artworks: Proceedings of the International Conference Lacona VII*, ed. M. Castillejo, P. Moreno, M. Oujja, R. Radvan, and J. Ruiz, pp. 17–21. New York: CRC Press.
- Hacke, B. 1963. En utraditionel metode til vacuum rentoilering af temperamaleri på lærred [An untraditional method for vacuum lining a tempera painting]. *Meddelelser om konservering*, 4:42–48.
- Hearn, E. J. 1997. *Mechanics of Materials: An Introduction to the Mechanics of Elastic and Plastic Deformation of Solids and Structural Materials*. 3rd ed. Volume 1. Oxford: Butterworth-Heinemann.
- Hedley, G. 1981. "The Stiffness of Lining Fabrics: Theoretical and Practical Considerations." In *ICOM Committee for Conservation, 6th Triennial Meeting, Ottawa, 21–25 September 1981: Preprints*, paper 81/2/2. Paris: International Council of Museums. [Reprinted in *Measured Opinions, Collected Papers on the Conservation of Paintings*, ed. C. Villers, pp. 76–80, London: United Kingdom Institute for Conservation, 1993.]

- Hedley, G., and C. Villers. 1982. "Polyester Sailcloth Fabric: A High-Stiffness Lining Support." In *Science and Technology in the Service of Conservation: Preprints of the Contributions to the Washington Congress*, ed. N. S. Brommelle and G. Thomson, pp. 154–158. London: International Institute for Conservation of Historic and Artistic Works.
- Hendrickx, R., G. Desmarais, M. Weder, E. S. B. Ferreira, and D. Derome. 2016a. Moisture Uptake and Permeability of Canvas Paintings and Their Components. *Journal of Cultural Heritage*, 19:445–453.
- Hendrickx, R., E. S. B. Ferreira, J. J. Boon, G. Desmarais, D. Derome, L. Angelova, D. Mannes, A. Kaestner, H. Huinink, and K. Kuijpers. 2016b. Distribution of Moisture in Reconstructed Oil Paintings on Canvas during Absorption and Drying: A Neutron Radiography and NMR Study. *Studies in Conservation*, 62(7):393–409. <https://doi.org/10.1080/00393630.2016.1181899>.
- Karpowicz, A. 1990. A Study on Development of Cracks on Paintings. *Journal of the American Institute for Conservation*, 29(2):169–180.
- Keck, S. 1969. Mechanical Alteration of the Paint Film. *Studies in Conservation*, 14(1):9–30.
- Ketnath, A. 1976. Acrylhartserv ved konservering af malerier på lærred under anvendelse af "heat seal" metoden [Acrylic resins in the conservation of canvas paintings using the heat seal method]. *Meddelelser om Konservering*, 2(7–8):223–235.
- Keyser, B. W. 1984. Restraint without Stress, History and Prospects: A Literature Review of Paintings as Structures. *Journal of the American Institute for Conservation*, 24(1):1–13.
- Klausmeyer, P., M. Cushman, I. Dobrev, M. Khaleghi, E. J. Harrington, X. Chen, and C. Furlong. 2016. "Quantifying and Mapping Induced Strain in Canvas Paintings Using Laser Shearography." In *The Noninvasive Analysis of Painted Surfaces: Scientific Impact and Conservation Practice*, ed. A. Nevin and T. Doherty, pp. 1–13. Smithsonian Contributions to Museum Conservation, No. 5. Washington, D.C.: Smithsonian Institution Scholarly Press.
- Krzemień, L., M. Łukomski, Ł. Bratasz, R. Kozłowski, and M. F. Mecklenburg. 2016. Mechanism of Craquelure Pattern Formation on Panel Paintings. *Studies in Conservation*, 61(6):1–7.
- MacIntyre, J., S. Stillwell, R. Knight, R. Wilsdon, W. Constable, and S. Cursiter. 1934. *Some Notes on Atmospheric Humidity in Relation to Works of Art*. London: Camelot Press.
- Maheux, A. F., and W. McWilliams. 1995. The Use of the Ultrasonic Mister for the Consolidation of a Flaking Gouache Painting on Paper. *Book and Paper Group Annual*, 14. <http://cool.conservation-us.org/coolaic/sg/bpg/annual/v14/bp14-03.html> (accessed 28 February 2017).
- Malowany, K., L. Tyimińska-Widmer, M. Malesa, M. Kujawińska, P. Targowski, and B. J. Rouba. 2014. Application of 3D Digital Image Correlation to Track Displacements and Strains of Canvas Paintings Exposed to Relative Humidity Changes. *Applied Optics*, 53(9):1739–1749.
- Mecklenburg, M. F. 1982. Some Aspects of the Mechanical Behavior of Fabric Supported Paintings. Washington, D.C.: Smithsonian Institution.
- Mecklenburg, M. F., L. Fuster-López, and S. Ottolini. 2012. "A Look at the Structural Requirements of Consolidation Adhesives for Easel Paintings." In *The Sticking Point: Adhesives and Consolidants in Paintings Conservation*, pp. 7–23. London: National Portrait Gallery.
- Mecklenburg, M. F., and J. E. Webster. 1977. Aluminum Honeycomb Supports: Their Fabrication and Use in Painting Conservation. *Studies in Conservation*, 22(4):177–189.
- Mehra, V. R. 1975. Nap-Bond Cold Lining on a Low Pressure Table. *Maltechnik/Restaurio*, 81(2):87–95.
- Mehra, V. R. 1981. "Minimizing Strain and Stress in Lining Canvas Paintings." In *ICOM Committee for Conservation, 6th Triennial Meeting, Ottawa, 21–25 September 1981: Preprints*, paper 81/2/14. Paris: International Council for Monuments.
- Plenderleith, H. J., and S. Cursiter. 1934. "The problem of lining adhesives for paintings - wax adhesives." Technical studies in the field of fine arts III (2), Fogg Art Museum, Harvard University: 90–113.
- Ploeger, R., C. W. McGlinchey, and E. R. de la Rie. 2014. Original and Reformulated BEVA® 371: Composition and Assessment as a Consolidant for Painted Surfaces. *Studies in Conservation*, 60(4):217–226.
- Ruhemann, H. 1953. The Impregnation and Lining of Paintings on a Hot Table. *Studies in Conservation*, 1(2): 73–76.
- Tassinari, E. 1974. Characterization of Lining Canvases. In *Lining Paintings: Papers from the Greenwich Conference on Comparative Lining Techniques*, ed. C. Villers, pp. 96–100. London: Archetype.
- Young, C., and P. Ackroyd. 2001. The Mechanical Behaviour and Environmental Response of Paintings to Three Types of Lining Treatment. *National Gallery Technical Bulletin*, 22:85–104.
- Young, C., and S. Jardine. 2012. Fabrics for the Twenty-First Century: As Artist Canvas and for the Structural Reinforcement of Easel Paintings on Canvas. *Studies in Conservation*, 57(4):237–253.

HERIe: A Decision-Supporting Tool Based on Quantitative Assessment of Damage Risk

Roman Kozłowski,^{1} Arkadiusz Kupczak,¹ Artur Działo,²
Łukasz Bratasz,^{3,4} and Michał Łukomski^{5,6}*

ABSTRACT. A web-based decision-supporting tool, HERIe is based on quantitative assessment of the climate-induced physical damage risk to heritage objects. The risk is assessed by calculating and analyzing strain versus time histories engendered in specific objects by real-world microclimates. The user is asked to provide basic characterization of the object and the 1-year (or multiyear) microclimatic data, measured or simulated for future preservation scenarios. The data are decomposed into a set of elementary sinusoidal relative humidity (RH) fluctuations using the Fourier transform. Each elementary sinusoidal RH fluctuation is then transformed, using the precalculated database, into an elementary strain fluctuation experienced by the object. The complete strain versus time history of the object is calculated by the superposition of all elementary strain fluctuations. In the final step, the user can assess the risk of damage by choosing a damage criterion from the provided list. Damage criteria are derived from mechanical properties of the objects or from collection observations. Strains at yield or at failure were proposed as damage criteria for wood or gesso. The current version of the software analyzes the influence of variations in RH and temperature on freely responding wooden panels covered with a gesso layer as a model system imitating panel paintings and on wooden elements restrained in movement as a model of wooden constructions like sides of cabinets, doors, and panel paintings restrained by rigid auxiliary support systems. The software will be expanded to include other objects and collection materials.

INTRODUCTION

In recent years, there has been growing interest in managing indoor environments in museum buildings for the protection of vulnerable art objects in a responsible manner, especially in terms of reducing energy use and carbon emissions (Padfield and Larsen, 2004; Atkinson, 2014; Staniforth, 2014). The interest has been driven by the increasing cost of energy and budget cuts, on the one hand, and the national or pan-national strategies of sustainable development, on the other. For example, improving the energy performance of existing buildings is a key measure in the European program of energy saving, set out in Directive 2010/31/EU on the energy performance of buildings (European Parliament and European Council, 2010). The directive stipulates that member states set the minimum energy performance requirements for buildings, as buildings account for 40% of total energy consumption in the European Union and the sector is expanding. Remarkably, however, the directive allows the member states not to apply such requirements for “buildings officially protected as part of a designated environment or of a special architectural or historic merit, in so far as compliance with certain minimum energy performance

¹ Jerzy Haber Institute of Catalysis and Surface Chemistry, Polish Academy of Sciences, Niezapominajek 8, PL-30239 Krakow, Poland.

² National Museum in Krakow, aleja 3 Maja 1, PL-30062 Krakow, Poland.

³ Institute for the Preservation of Cultural Heritage, Yale University, P.O. Box 27395, West Haven, Connecticut 06516, USA.

⁴ Formerly at National Museum in Krakow, Krakow, Poland.

⁵ Getty Conservation Institute, 1200 Getty Center Drive, Suite 700, Los Angeles, California 90049-1681, USA.

⁶ Formerly at Jerzy Haber Institute of Catalysis and Surface Chemistry, Polish Academy of Sciences, Krakow, Poland.

* Correspondence: nckozlow@cyf-kr.edu.pl

Manuscript received 2 June 2018; accepted 7 May 2019.

requirements would unacceptably alter their character or appearance.” To leave out historic buildings from the energy efficiency programs seems, however, a serious omission as they constitute 30% of Europe’s built substance and an important sector consuming energy. Therefore, there is a tendency to apply the sustainability targets to a growing proportion of historic buildings and, consequently, to most museums (for an example, see Hayton, 2010, for a detailed analysis of the situation in the United Kingdom).

The reason for not applying in full, as yet, the national or pan-national legislation regarding energy saving in historic buildings is insufficient research in the field; there is a lack of tools and solutions for energy efficiency in overall structures that at the same time should meet conservation requirements for the furnishings and objects they contain. The lack of adequate tools is particularly acute for museums, libraries, and archives housed in historic buildings. Institutions aim to provide strictly controlled, stable humidity and temperature conditions for their collections by inserting into leaky structures of historic buildings large, energy-intensive air-conditioning systems. These systems may require serious alterations to these structures and covering the huge costs necessary to filter, heat, cool, humidify, or dehumidify large volumes of air, depending on the outdoor conditions.

Reducing energy consumption in buildings preserving cultural heritage resources has not only economic but also ecological and ethical aspects. It would mean implementing the much-debated idea of a “green museum,” which preserves cultural heritage while respecting the limits of natural environment and resources. This attitude of the museum community was succinctly summarized in the “Joint IIC – ICOM CC Declaration on Environmental Guidelines” (International Institute for Conservation of Historic and Artistic Works, 2014): “Care of collections should be achieved in a way that does not assume air conditioning (HVAC). Passive methods, simple technology that is easy to maintain, air circulation and lower energy solutions should be considered. Risk management should be embedded in museum management processes.”

Vulnerable cultural objects—panel paintings, paintings on canvas, polychrome wooden sculptures, books, works on paper, and variable objects of decorative art made of wood, bone, leather, or textiles—are usually complex multilayer structures composed of humidity-sensitive materials. They respond to changes of RH and temperature in their environment; they shrink when they lose moisture and swell when they gain moisture. A notable effect is, however, that each material responds differently to the loss and gain of moisture. The mismatch in the response of individual materials induces tensile or compressive stresses in the structure, which can cause deformation, cracking, and delamination of the layers. Moisture-sensitive objects may also experience stress due to a restraint on their dimensional response resulting from the rigid construction restricting movement or by incorporating elements with different dimensional responses. The constraint from free movement can cause deformation and cracking.

In the 1990s, two key issues were systematically examined by Mecklenburg et al. (1998): the dimensional response of the objects to changes in temperature and RH and the critical levels of shrinkage or elongation (hereafter referred to as strain) at which materials begin to deform plastically or fail physically. The yield stress or strain of materials was proposed as a “failure criterion”; that is, allowable temperature and RH variations should not cause strains in materials exceeding their yield strains so that the response of the materials stays at all times in the elastic (reversible) region. The analysis of the mechanical response of historic objects was further refined, influencing the development of rational guidelines for the control of climate in museums and historic buildings (Bratasz, 2013).

It should be stressed, however, that existing knowledge of the mechanisms of climate-induced damage to objects serves the practice of cultural heritage protection only in a limited way. Obviously, it supports institutional, national, or international guidelines and standards containing universal recommendations that can relate to cultural heritage resources in general. An example of a document of this kind is European Standard EN 15757:2010 (European Committee for Standardization, 2010). Since its publication, the standard has been widely used as a reference for museums and various research institutions to establish climate control strategies in the field of cultural heritage protection. This usage has revealed considerable demand for supporting decision-making tools in this area. It is obvious, however, that universal standards and guidelines can be just a starting point for individual strategies for specific museum collections, as each object with its individual original structure and conservation history, acclimatized to a particular environment in which it has been displayed, needs individual levels and ranges of temperature and RH. The development of such individual strategies requires considerable engagement of scientists specialized in modeling and monitoring the response of heritage objects to microclimatic conditions. Such highly specialized research competence is not available for the majority of museum institutions, which creates a barrier to exploiting the available basic knowledge in the conservation practice.

To overcome the barriers described above, HERIE, a decision-supporting software tool (herie.mnk.pl) for quantitative assessment of the risk of physical damage for various categories of cultural objects vulnerable to real-world climates, has been developed by a collaborative effort of several institutions.

HOW DOES HERIE WORK?

The software is designed in such a way that it analyzes the impact of specific 1-year (or multiyear) temperature and RH microclimate data measured in a given gallery or historic building or simulated for various climate control scenarios. The methodology on which HERIE is based consists of four steps (Kupczak et al., 2019). They are described here for the

simplest case of a typical museum climate in which yearly average relative humidity is 50%.

STEP 1: DECOMPOSITION OF RELATIVE HUMIDITY DATA

Yearly RH variations are a combination of long-term seasonal cycles, caused, for example, by an RH decrease in winter due to heating and a return to a higher RH level in summer, and irregular medium- and short-term changes arising from weather changes outside, the opening and closing of doors and windows, the flow of visitors, and/or the intermittent operation of climate control systems. In the first step of the HERIE algorithm, the yearly or multiyear RH variations are decomposed into a set of elementary sinusoidal RH cycles of varying amplitudes and durations using the Fourier transform.

STEP 2: TRANSLATING ELEMENTARY RH CYCLES INTO ELEMENTARY STRAIN CYCLES OF THE SELECTED OBJECT

The elementary strain cycles were obtained for elementary RH cycles centered at 50% RH with systematically varied amplitudes and durations covering the whole range present in the RH versus time histories decomposed in step 1. Each elementary RH cycle was transformed into an elementary strain cycle of the specific object using finite element numerical simulation. The simulation took into account the size of the object and its composite structure as well as specific physical properties of the materials building up the object: adsorption and desorption of water vapor, moisture-related swelling and shrinkage, water vapor diffusion and surface emission coefficients, and tensile properties (elastic and shear moduli and Poisson's ratio). The matrices were obtained for four temperatures: 7°C, 15°C, 21°C, and 25°C.

The object for which the elementary strain cycles should be obtained is selected and defined by the user. Two model objects are available so far: (1) freely responding panels covered with gesso layers and (2) restrained panels.

Freely responding panels covered with gesso layers as a model system imitate panel paintings that are one of the most precious and frequently exhibited categories of cultural heritage objects. The mismatch in the response of the unrestrained wood substrate, especially in the most responsive tangential direction of the wood, and the far less responsive gesso layer has been identified as the worst-case condition for fracturing of the pictorial layer (Mecklenburg et al., 1998). The modeling of the elementary strain cycles has established the effective strain experienced by the pictorial layer induced by the elementary variations of RH for varying thicknesses of a panel and configurations of water vapor diffusion, that is, a symmetric diffusion through both the faces of a panel and an asymmetric diffusion through one of the two faces, the uncoated back face, which would simulate the extreme effect of a paint or gold layer blocking the moisture flow through the top face.

Restrained panels as a model of furniture components include doors and sides of cabinets, table tops, frames, panel

paintings reinforced with rigid wooden support systems, and other specific types of decorated wooden constructions. The modeling has provided the matrices of restrained dimensional change and engendered stresses in wood, resulting from the rigid construction restricting movement or from the assemblage of wood elements with different mutual orientations of their fiber direction.

STEP 3: SUPERPOSITION OF ELEMENTARY STRAIN CYCLES

In this step, the full strain-time history of an object, a dimensional response to the climatic variations analyzed, is obtained by summing up the elementary strain cycles corresponding to the elementary RH cycles obtained in step 1. The elementary strain cycles in the HERIE database were calculated for four temperatures. Increasing temperature leads to an increase in the water vapor diffusion coefficient and faster movement of moisture across the material and to a decrease in water vapor sorption at a given RH. Using interpolation, the elementary strain cycles can be scaled to any temperature value selected.

It has been verified that the superposition of the elementary strain cycles performed by HERIE is in agreement with the outcome of the full finite element numerical simulation for the object.

STEP 4: CALCULATING RISK INDEXES

Assessing the physical damage risk by choosing a damage criterion, the critical level of the dimensional response bringing damage, is the final step of the analysis. Currently, damage criteria are available for wood (strains at yield and at break and fatigue damage based on the acoustic emission monitoring of real objects) and for gesso (strain at failure). New damage criteria may come from other laboratory studies, monitoring of original objects, and collection observations (epidemiology studies). The damage criterion for which the risk indexes are calculated is selected and defined by the user.

ANALYZING CLIMATE DATA USING STRAIN AT FAILURE AS THE DAMAGE CRITERION FOR THE GESSO LAYER ON AN UNRESTRAINED WOOD PANEL

Gesso deforms when force is applied, and the stress-strain curves illustrate subsequent phases of the deformation by increasing stress (Figure 1). Strain is the change in length divided by the specimen's original length, and stress is calculated by dividing the force (load) applied to the test specimen by its cross-sectional area. The final recorded point of the stress-strain curve is the strain at which gesso cracks. The mechanical properties of gesso depend on the strength of the collagen glue used, the ratio of the inert solid (the pigment) to the glue, and the ambient RH, as gesso undergoes a transition from the brittle

FIGURE 1. Strain-stress curves for the gesso tested at various RH values (Rachwał et al., 2012). Strain of 0.2% close to the elongation at break for brittle gesso in the low and middle range of RH is marked with a red line. Strain below this value is assumed to be safe for the material.

to the ductile state with increasing RH. As can be seen in Figure 1, elongation at break is approximately 0.2% for stiff and brittle gesses in the low and middle range of RH, considered the worst-case conditions for gesso's vulnerability to fracture, but increases by an order of magnitude with increasing RH.

Upon a decrease in RH, wood undergoes shrinkage, inducing compressive stress and negative strain in the gesso layer, whereas upon an increase in RH, wood undergoes swelling, inducing tensile stress and positive strain in the gesso layer. The HERIe software uses 0.2% to calculate the risk index for a given strain versus time history: strain is calculated as a change in the length of the interface between the gesso layer and the wood support divided by the length of this interface at the assumed zero-strain RH level. When the absolute maximum magnitude of strain experienced by the gesso layer, in either compression or tension over its entire strain history, does not exceed 0.2%, the risk index is zero. When the absolute maximum magnitude of strain experienced by the gesso layer exceeds 0.4%, or the double strain at failure, the risk index is 1. The risk index increases linearly between 0 and 1 for maximum magnitudes of compressive or tensile strains between 0.2% and 0.4%.

Figure 2 shows variations of indoor RH in one of the rooms in the Yale University Art Gallery (YUAG) in 2015. The variations slightly exceeded the 40%–60% range

FIGURE 2. Strain versus time history (right) experienced by a 0.4 mm thick gesso layer laid on a 10 mm tangentially cut wooden panel open to a water vapor flow just through the bare wood surface opposite to the painted face, exposed to RH variations (left) in a room in the Yale University Art Gallery in 2015. It was assumed in the calculations of strain that no internal stresses (tensile or compressive) were present in the object at the 50% RH level (the zero-strain RH level). The ranges of RH and strain recommended as safe are marked with red lines.

FIGURE 3. Plots as in Figure 2 for Gallery 1 in the National Museum in Krakow in 2013. It was assumed in the calculations of strain that no internal stresses were present in the object at the long-term average RH of 45%.

recommended as safe for objects containing hygroscopic material in the “Joint IIC – ICOM CC Declaration on Environmental Guidelines” (International Institute for Conservation of Historic and Artistic Works, 2014). However, the strain experienced by a gesso layer laid on a 10 mm wooden panel exposed to the same RH variations would stay, at all times, well below the critical strain of 0.2% (Figure 2), and therefore, the gesso is deemed not to be vulnerable to fracture (risk index = 0).

Figure 3 shows RH and strain variations in one of the galleries in the National Museum in Krakow (NMK) in 2013. The yearly average RH was 45%, similar to that of YUAG, and the variations of the parameter were only somewhat bigger, with one exception. In March, a heating system operating in the gallery caused two repeated falls in indoor RH, from an average of 45% to below 25%, during a spell of cold, dry weather outdoors when the outdoor air drawn into the gallery was heated but was insufficiently humidified by the climate control system. However, the calculated strain that would be experienced by a gesso layer laid on a wooden panel exposed to such RH variations stayed just below the critical strain of 0.2% during the panel shrinkage induced by the March episode of the RH fall (Figure 2), and therefore, the variations were assumed not to involve any risk of the gesso fracturing for the type of object analyzed.

The assessment of the risk of damage to the pictorial layer based on the analysis of the strain versus time history is particularly useful in the case of unexpected large fluctuations of

RH due to, for example, failures of climate control systems. Figure 4 shows RH variations in another gallery in NMK in 2013. The yearly average RH was again 45%, and the variations were moderate, within approximately $\pm 15\%$ around the average. However, the failure of an environmental control system caused a short-lasting abrupt increase in RH from the average of 45% to above 70%. The strain experienced by a gesso layer laid on a wooden panel exposed to such RH variation would considerably exceed the critical strain of 0.2%, and the calculated risk index was 0.43.

It should be stressed at this point that the software allows users to identify the time of the year or events of greatest strain risk. Users can also calculate their own risk indexes by reading maximum strains from the strain versus time histories calculated by HERIe and using critical strains other than those proposed in the software as the most conservative, worst-case selection. For example, users can assume that gesso's elongation at break is above 0.5% at relative humidities exceeding 60% (see Figure 1), and therefore, the RH increase recorded in Gallery 2 in NMK in June 2013 involved no or little risk of gesso's fracture.

ANALYZING CLIMATE AS THE RISK FACTOR FOR FULLY RESTRAINED WOOD

Wood deforms when force is applied, and the stress-strain curves illustrate subsequent phases of the deformation

FIGURE 4. Plots as in Figure 2 for Gallery 2 in the National Museum in Krakow in 2013. It was assumed in the calculations of strain that no internal stresses were present in the object at the long-term average RH of 45%.

by increasing stress. The strain that can be recovered immediately on the release of the stress is termed the elastic response. The yield strain defines the upper limit of the elastic range at which nonrecoverable plastic deformation begins, and the final recorded point of the stress-strain curve is the strain at which wood fails via fracture. Uniform desiccation or humidification of a wooden element completely free in its movement does not induce stress in the material. However, when wood is restrained from movement and desiccated when the ambient RH decreases, it experiences an increase in tensile strain because, effectively, the material undergoes free shrinkage and is “stretched” back to its original restrained length. Similarly, if wood is restrained from movement and humidified, it experiences an increase in compressive strain because, effectively, the material undergoes free swelling and is “compressed” back to its original restrained length. The yield strain of wood and the strain at failure perpendicular to the grain are generally around 0.5% and 2%, respectively, in the midrange of RH, for example, in Bratasz (2013).

When the absolute maximum magnitude of strain experienced by the fully restrained wooden element (in compression or tension) in the entire strain-time history does not exceed 0.5%, the risk index is zero. When absolute maximum magnitude of strain experienced by the fully restrained wood exceeds 2%, the risk index is 1; for the maximum magnitudes of compressive or tensile strains between 0.5% and 2%, the risk index increases linearly between 0 and 1. Therefore, a risk index that falls between 0 and 1 would

indicate the object moving beyond elasticity and into non-recoverable plastic deformation; that is to say, the index indicates the range of plastic damage between no damage and fracture.

Figure 5 shows the strain experienced by a fully restrained wooden panel exposed to the events of greatest strain risk identified in the indoor climates shown in Figures 2–4. For the climates in YUAG and Gallery 1 of NMK, the strain stayed at all times below the critical strain of 0.5%, and therefore, the wood can be deemed not to be vulnerable to fracture. However, the abrupt increase in RH in Gallery 2 of NMK, caused by the failure of a climate control steering system in June, brought about wood swelling that slightly exceeded the critical strain of 0.5%, and the calculated risk index of 0.04 indicated potential plastic deformation.

DAMAGE CRITERIA BASED ON MONITORING OF OBJECTS

The criteria used so far in assessing the risk of damage were derived from laboratory studies of mechanical properties of wood and gesso—the materials building up the painted wood structure. Such studies are usually carried out using specimens of new materials imitating historical ones. However, the material properties obtained do not necessarily reflect those of historical objects that are aged, deformed, or fractured in the long process of adaptation to the indoor

FIGURE 5. Strain versus time history experienced by a fully restrained 10 mm tangentially cut wooden panel open to water vapor flow through the bare wood surface opposite the painted face exposed to RH variations in a room in YUAG in 2015 (left) and Galleries 1 and 2 in NMK in 2013 (middle and right, respectively). Note that the restrained shrinkage induces stretching of wood (positive strain), whereas the restrained swelling induces compression of the material (negative strain). The range of strain recommended as safe is marked with red lines.

environments in which they are preserved. Therefore, crack propagation induced by strains experienced by the object can be used as an alternative measure of risk of damage. The information on the relationship between crack propagation and strain in cracked wooden panels can be derived from earlier on-site monitoring of wooden objects displayed in museums using the acoustic emission (AE) method. The method is based on monitoring the mechanical energy released in the form of ultrasound and sound waves produced during fracturing of the material that are detected on the surface of an object using a piezoelectric transducer that converts surface vibration to an electrical signal (a microphone). Owing to the noninvasive nature, digital capture, and processing of single AE events in real time, the method is capable of continuous monitoring of crack propagation in actual objects in the real-world conditions of museums and historic buildings. Two eighteenth century pieces of furniture were monitored: a wardrobe displayed in the Gallery of Decorative Art in the National Museum in Krakow (Strojecki et al., 2014) and a French commode decorated with panels of Japanese export lacquer exhibited in the Furniture Gallery of the Victoria & Albert Museum in London (Pretzel, 2014). The AE sensors were located close to the tips of the existing cracks where further propagation was most likely (Figure 6).

The amazing sensitivity and reproducibility of the AE sensors enabled tracing extremely small sources of acoustic signals corresponding to tiny crack propagation. Figure 6 shows a plot of crack propagation in the wooden elements in the furniture monitored as a function of the amplitude of the cycles of restrained shrinkage induced by falls in the indoor RH. The plot demonstrates that no fracturing occurs for shrinkage strains below 0.2%, which can therefore be regarded as a safe critical strain, eliminating the risk of climate-induced damage in the monitored objects. The observation indicates that the objects are more vulnerable to crack propagation than new wood is to plastic deformation (safe critical strains are 0.2 and 0.5, respectively).

Further insight into the strain-crack propagation relationship was provided by a study of the dimensional response of a Dutch veneered wooden cabinet dated to around 1690–1710, displayed in Amerongen Castle in the Netherlands (Huijbregts et al., 2014). The study revealed that the wooden panels of the cabinet experienced shrinkage strain close to 0.4% when the indoor climate conditions became far drier after room heating was installed in the castle around 2011. However, a comparison of the preservation state of the cabinet in 2014 and the state recorded in archival photographs from 1974 did not indicate any damage progression in the wooden panels. If

FIGURE 6. Crack propagation as a function of shrinkage strain experienced by wooden elements in furniture (left). The data for small strains were obtained from the AE monitoring using sensors located close to the tips of the existing cracks (right).

one assumes that a 5 mm crack propagation could have been traced by the visual analysis of the state of preservation of the cabinet, an expected range of the crack propagation can be extended to 0.4% strain, as shown in Figure 6. Further AE studies of several wooden objects exposed to larger RH variations indicated that climate-induced crack propagation was minute, in the range of square millimeters (Łukomski et al., 2018). The observations collected so far can be interpreted by the acclimatization of the wooden objects monitored to presumably large RH variations in the past that caused fracturing. Further damage monitoring of the most vulnerable objects, for example, freshly treated or consolidated wood, is necessary to refine the damage criteria available in the software.

All strain versus time histories experienced by the restrained wood, exemplified by plots shown in Figure 5, are combinations of many simple swelling-shrinkage cycles of varying ranges, with the cycle strain range being defined as an algebraic difference between the largest peak and the smallest valley in the strain versus time history analyzed. The HERIE software uses a modified rain-flow counting method to obtain simple strain cycles (ASTM International, 2005). The detailed procedure is not covered here, but Figure 7 shows how the method separates shrinkage cycles of various durations embedded in the complex strain versus time history experienced by a fully restrained wooden panel exposed to RH

variations in Gallery 1 in NMK in 2013 (only the three largest shrinkage cycles exceeding 0.2% are marked).

The strain versus time history analyzed indicates the propagation of an existing crack in the wood by several millimeters due to the large shrinkage strain exceeding 0.4% caused by the March episode of a considerable fall in indoor RH. It is noteworthy that a mere reduction of this largest cycle to, for example, 0.3% would reduce the crack growth by an order of magnitude because of a dramatic decrease in the risk with a decrease in the strain range, which is evident from Figure 5.

CONCLUSIONS

In recent years, much research has focused on the environmental response of historic materials and objects so that mechanisms leading to physical damage of objects from environmental conditions of temperature and RH are better understood. The online HERIE environmental data analysis tool incorporates such research findings and aims to facilitate precise assessment of the risk of climate-induced physical damage based on the specific response of a given object to real-world microclimates, measured or simulated.

It is hoped that through its network of collaborations, HERIE will become a platform for data gathering over an

FIGURE 7. Strain experienced by a fully restrained 10 mm tangentially cut wooden panel open to water vapor flow through the bare wood surface opposite the painted face exposed to RH variations in Gallery 1 in NMK in 2013. Three wood shrinkage cycles dominating the strain versus time history, obtained by modified rain-flow analysis, are marked with red lines. Note that the restrained shrinkage induces positive strain in wood. Crack propagation related to each cycle, derived from the relationship shown in Figure 6, is indicated.

extended time period. The modeling algorithms can be refined with a growing understanding of the damage mechanisms. A particularly important task will be to collect data on aged historic materials. Taking painted wood as an example, there are limited studies of aged woods that show a small aging effect on the moisture response and mechanical properties, but there is almost nothing substantial on glues and gessoes.

The HERIE software is an open tool; with progress in research, the database of cultural heritage objects analyzed will be enlarged. Wooden cylinders of varying diameter will be added soon as a model system imitating wooden sculptures and other massive elements. The software will also be expanded to include paintings on supports other than wood. Encompassing vulnerable library materials like parchment is an urgent task in the short term. HERIE is available for testing at herie.mnk.pl. Detailed information on the methodologies used by the software is available at the above website, which also contains climate tutorials. Conservation professionals and decisions makers in museums and museum laboratories worldwide are encouraged to test the tool. The feedback gained from users is vital for refining the methodology.

ACKNOWLEDGMENTS

This study was funded in part by the statutory research fund of the Jerzy Haber Institute of Catalysis and Surface

Chemistry, Polish Academy of Sciences. This research was supported by Grant PBS2/A9/24/2013 from the Polish National Centre for Research and Development.

REFERENCES

- ASTM International. 2005. Standard Practices for Cycle Counting in Fatigue Analysis. ASTM Standard E 1049-85. West Conshohocken, Pa.: ASTM International.
- Atkinson, J. K. 2014. Environmental Conditions for the Safeguarding of Collections: A Background to the Current Debate on the Control of Relative Humidity and Temperature. *Studies in Conservation*, 59:205–212.
- Bratasz, Ł. 2013. Allowable Microclimatic Variations for Painted Wood. *Studies in Conservation*, 58:65–79.
- European Committee for Standardization. 2010. Conservation of Cultural Property – Specifications for Temperature and Relative Humidity to Limit Climate-Induced Mechanical Damage in Organic Hygroscopic Materials. European Standard EN 15757:2010. Brussels: European Committee for Standardization.
- European Parliament and European Council. 2010. Directive 2010/31/EU of the European Parliament and of the Council of 19 May 2010 on the Energy Performance of Buildings. *Official Journal of the European Union*, L153/13:13–35.
- Hayton, B. 2010. Sustainability and Public Museum Buildings, the UK Legislative Perspective. *Studies in Conservation*, 55:150–154.
- Huijbregts, Z., H. Schellen, J. van Schijndel, and B. Ankersmit. 2014. Modelling of Heat and Moisture Induced Strain to Assess the Impact of Present and Historical Indoor Climate Conditions on Mechanical Degradation of a Wooden Cabinet. *Journal of Cultural Heritage*, 16:419–427.
- International Institute for Conservation of Historic and Artistic Works. 2014. Joint IIC – ICOM CC Declaration on Environmental Guidelines. <http://www.iiconservation.org/node/5168> (accessed 14 October 2016).

- Kupczak, A., M. Jędrychowski, Ł. Bratasz, M. Łukomski, and R. Kozłowski. 2019. Processing Relative Humidity Data Using Discrete Fourier Transform to Control Strain in Art Objects. *Strain*, 55:e12311.
- Łukomski, M., W. L. Beltran, F. Boersma, J. Druzik, A. Freeman, M. Strojceki, T. Learner, and J. Taylor. 2018. Monitoring Acoustic Emission in an Epidemiological Pilot Study of a Collection of Wooden Objects. *Studies in Conservation*, 63(Suppl. 1):181–186.
- Mecklenburg, M. F., C. S. Tumosa, and D. Erhardt. 1998. “Structural Response of Painted Wood Surfaces to Changes in Ambient Relative Humidity.” In *Painted Wood: History and Conservation*, ed. V. Dorge and F. C. Howlett, pp. 464–483. Los Angeles: Getty Conservation Institute.
- Padfield, T., and P. K. Larsen. 2004. How to Design Museums with Naturally Stable Climate. *Studies in Conservation*, 49:131–137.
- Pretzel, B. 2014. “[Un]Reasonable – Broadening Acceptable Climate Parameters for Furniture on Open Display.” In *ICOM-CC, 17th Triennial Conference, Building Strong Culture through Conservation, 15–19 September 2014, Melbourne, Australia: Preprints*, ed. J. Bridgland, Article 1507. Paris: International Council of Museums.
- Rachwał, B., Ł. Bratasz, L. Krzemień, M. Łukomski, and R. Kozłowski. 2012. Fatigue Damage of the Gesso Layer in Panel Paintings Subjected to Changing Climate Conditions. *Strain*, 48:474–481.
- Staniforth, S. 2014. Environmental Conditions for the Safeguarding of Collections: Future Trends. *Studies in Conservation*, 59:213–217.
- Strojceki, M., M. Łukomski, L. Krzemień, J. Sobczyk, and Ł. Bratasz. 2014. Acoustic Emission Monitoring of an Eighteenth Century Wardrobe to Support a Strategy for Indoor Climate Management. *Studies in Conservation*, 59:225–232.

Museum Study of the Climate4Wood Research Project

Stina Ekelund,^{1,2} Paul van Duin,³ Bart Ankersmit,⁴
and André Jorissen⁵*

ABSTRACT. A very important task for conservators and other museum professionals is minimizing the risk of damage to objects in their care. Changes in the physical state of the object are to be avoided, but under which conditions these changes occur is difficult to predict; for example, fluctuations in museum climate are a high risk to objects. The focus so far has been to monitor the indoor climate instead of monitoring changes induced in the objects. This is logical because reading a climate graph is more straightforward than monitoring an object. By studying many objects in detail and collecting empirical data over a large collection of objects, our knowledge about expected damage and its relation to material and constructive parameters will increase. Understanding the mechanisms leading to damage caused by climate fluctuations will help us to predict when and where such damage might occur. The Climate4Wood research project was initiated with the aim to identify the effects of indoor climate fluctuations on the damage resistance of decorated wooden panels in museum collections. By means of a combined museum, modeling, and experimental study, climate-related changes of decorated oak wooden panels in furniture and paintings were addressed from a multidisciplinary conservation and engineering approach. The methodology and the outcome of the museum study are illustrated by examples from two studies in the Rijksmuseum collection: (1) a study of 134 doors of 49 Dutch cabinets and (2) a study of 249 Dutch seventeenth century panel paintings. The outcome of these studies is discussed, as well as how object-based information serves for the modeling and experimental studies. Examples are given of how this information can be relevant for preservation strategies and conservation practice.

INTRODUCTION

In museums and historical collections the aim is to minimize the risk of irreversible change or damage to the artifacts in our care. The main risk for wooden objects is related to the swelling and shrinkage behavior of the material. Swelling and shrinkage may cause cracks, open joints, induce delamination, cause deformation, and lead to loss of material. For hygroscopic materials the shrinkage and swelling behavior is usually considered to be related to fluctuations in the surrounding microclimate, and these conditions are therefore often strictly controlled.

The focus of scientific research since the 1990s on indoor climate-related changes to museum objects has been on materials in paintings on canvas and panel. Mechanical and dimensional properties of individual materials or combinations of materials have been investigated in a variety of climate conditions (Mecklenburg and Tumosa, 1991; Mecklenburg et al. 1998; Bratasz, 2010). However, there is a gap between the results gained from laboratory-based research and that gained from

¹ Climate4Wood Research Project, Rijksmuseum and University of Technology Eindhoven, Museumstraat 1, Postbus 74888, 1070 DN Amsterdam, Netherlands.

² Now at Building Preservation Section, Ryfylkemuseet, Nordenden 14, 4230 Sand, Norway.

³ Rijksmuseum, Museumstraat 1, Postbus 74888, 1070 DN Amsterdam, Netherlands.

⁴ Cultural Heritage Agency of the Netherlands, Smallepad 5, 3811 MG Amersfoort, Netherlands.

⁵ Department of the Built Environment, University of Technology Eindhoven, P.O. Box 513, 5600 MB Eindhoven, Netherlands.

* Correspondence: stinaekelund@hotmail.com

Manuscript received 2 June 2018; accepted 7 May 2019.

conservators' experience working with museum objects. Although scientists have discovered that many objects are less susceptible to relative humidity fluctuations than considered thus far, conservators see changes even when museum climate appears to be stable. The conservation community is asking for empirical data from larger collections of museum objects (Boersma et al., 2014; Staniforth, 2014; van Duin, 2014) to gain insight into changes to the general condition of susceptible objects. This type of information can be obtained by large-scale surveys of museum collections and can be used to supplement laboratory-based research and in situ measurements of mechanical damage to museum objects and as verification for models and simulations (Ekelund et al., 2017). This information might help to bridge the above-mentioned gap between scientists and conservators. The most interesting outcome of the museum study is that more than 90% of the observed shrinkage cracks are actually failed glue joints between boards and not cracks within the wood itself. This means that the focus of research should also be on the mechanical properties of glue and the interrelation between the mechanical behavior of wood and glue.

The objects for this research are complex, for example, a three-dimensional structure consisting of a set of boards, joined together, and decorated on one or both sides (New, 2014); in the Climate4Wood research project the term *decorated wooden panels* is used. For this research two types of decorated panels can be differentiated: paintings on wooden panels and decorated doors of cabinets. Panel paintings can be seen as a layered structure of wood with a preparatory layer of animal glue, a ground, paint layers, and varnish layers. Panels in furniture are often decorated with (plain) veneers or, as marquetry, with different wood grain directions or with molding(s) of various thicknesses. Restraint is a central aspect for understanding the changes of or damage to decorated wooden panels and has been discussed by several researchers in the literature (Michalski, 1996; Mecklenburg, 2007). The influence of restraint on the shrinkage and swelling behavior of wood has been taken into consideration by furniture and panel makers historically and is still considered today.

This paper presents empirical data obtained from examining a large group of museum objects susceptible to fluctuations in relative humidity. To carry out this museum study, a method was developed that includes collecting detailed information about the materials, construction, history, and current and historic condition of the object. From these data, the properties influencing the results (e.g., shrinkage) can be analyzed, and the most susceptible part of the panel can be identified. This paper presents part of the outcome of the museum study, and examples are given from the two groups of objects that were studied in the Rijksmuseum collection: (1) 134 doors of 49 Dutch cabinets and (2) 249 Dutch seventeenth century panel paintings.

EXPERIMENTAL METHODS

The method was developed for a large-scale object survey to be applied in the museum study of the Climate4Wood research project at the Rijksmuseum in Amsterdam. It serves to collect empirical data that will form the basis for answering questions related to the interaction between the construction, materials, history, climate fluctuations, and condition of the objects in the group. By studying many objects in detail, knowledge about what condition to expect with respect to the different parameters will increase, which can be combined with archival information. A set of selection criteria was used to limit the variations and the number of objects within the research material. For the survey of the Rijksmuseum collection all objects had to fulfill all criteria for selection: the object was made in the Netherlands, has an oak wood substrate, was made with a commonly used construction, and is decorated with paint, veneers, or moldings.

The condition of each object was recorded in two ways. First, separate parameters were detailed. Second, the overall condition of each object was then graded on a scale that takes into account the different layers of the object, the surface as well as construction.

Measurements were taken of the panel dimensions (height, width, and thickness) as well as individual members, such as parts of frames, cleats, moldings, battens for individual boards, veneer layers, and paint layer thickness, if applicable. The measurements were taken using a digital caliper with an accuracy of 0.1 mm and both a tape measure and metal ruler with an accuracy of 0.5 mm. Measurements were taken at three points of each member, for example, at the top, middle, and bottom of a board. The maximum measurement of each member was used for further analysis because it was considered more relevant than an average size measurement since the size of the object is assumed to influence the mechanical behavior and damage pattern. Out-of-plane deformation was measured by placing a straight metal ruler across the whole object on three locations perpendicular to the wood grain direction and measuring the largest distance between the object and the ruler and recording if the displacement was more than 1 mm per 200 mm panel width or height. Smaller out-of-plane deformations are not visible and therefore could not be taken into account.

The results from the museum study were statistically analyzed. A descriptive analysis was performed, taking into account frequency, mean, standard deviation, and distribution of parameters (e.g., number of boards, thickness, width, and height). Logical questions were formulated for further analysis aiming to gain a better understanding of these correlations. What is the average amount of shrinkage, and what is the standard deviation? How is this related to the thickness of the panel and to the width and the height? What is the effect of restraint within a construction? If there are shrinkage cracks, are they splits in the wood or glue joints that have broken?

RESULTS AND DISCUSSION

In this section the major outcomes and results from the museum study are illustrated with examples. All panels in this study are made of oak wood, a material that is by far the most commonly used in northern Europe and one of the selection criteria for this study. Generally, the wood used for the examined panels is high-quality, radially cut oak wood. For example, the panel paintings study shows that 96.3% are radially cut and 3.6% of panels have boards with a mixed grain direction. Not a single tangentially cut panel is recorded. Similar results were found for the cabinet door study.

The number of boards found in the panels in both doors and paintings varies from one to seven. The width of the individual boards varies from 20 to 615 mm. The distribution of 457 individual boards from 249 panel paintings follows normal law, as can be seen in Figure 1, with an average of 245 mm and a standard deviation of 97 mm.

The wood quality is described by three parameters: the density of the wood, the presence of sapwood, and the presence of knots. The density of the wood, considered to be an important parameter to describe the quality of the boards (Wadum, 1998), is measured by the number of annual rings per millimeter, and this information is obtained by dendrochronological analysis. Traditionally, narrow annual rings and a high number of annual rings per millimeter are preferred. In the case of oak wood, because each annual ring has less dense early wood, wood with narrow annual rings is less dense than wood with broader rings. Wood with narrow annual rings is therefore less affected by moisture sorption and desorption (swelling and shrinkage).

FIGURE 1. The distribution of individual board widths of 457 individual boards from 249 panel paintings.

FIGURE 2. Annual rings per millimeter versus earliest production year for different wood origins. Blue circles originate from the Baltic region, yellow diamonds originate from the Polish region, and red squares originate from the German/Netherlandish region.

In Figure 2 data for the number of annual rings per millimeter and wood origin are given over time (the earliest possible production date) for the 199 objects in the panel paintings study for which dendrochronological data have been obtained over several decades by Peter Klein. The panels range from 0.315 to 0.961 annual ring/mm. There is a significant correlation between the origin of wood and annual rings per millimeter. The highest mean is found in the group of Baltic origin, 0.7045 annual ring/mm (standard deviation [SD] = 0.17478), followed by the wood of Polish/Baltic origin, with a mean of 0.7030 annual ring/mm (SD = 0.14108). The lowest mean, 0.6365 annual ring/mm, is found in the group of German/Netherlandish origin, which also has the highest standard deviation (SD = 0.18941). If the number of annual rings per millimeter is considered a measurement of wood quality, these data support the common notion that oak wood of Baltic origin has the best quality.

For the museum study the relevant questions are the relation between wood density (annual rings per millimeter) and condition. The following condition parameters were considered: open joints, crack(s) in the wood, upraised and/or abraded paint, and paint losses and fillings. In the analysis no significant difference could be found between woods of different densities and open joints, crack(s) in the wood, and upraised and/or abraded paint. The difference between the compared means of each parameter is not significant (Student's *t* test value greater than 0.05). However, it was found that the density influences paint losses and fillings.

Can a change in wood quality over time be identified? Since a significant correlation between density and origin was identified, the origin of the wood used over time is of interest (Figure 2). There is a significant correlation between wood of a certain origin and time: wood of Baltic and Polish/Baltic origin dominates at the beginning of the investigated time period (i.e., 1600–1655), whereas wood of German/Netherlandish origin increased gradually and dominates by the end of the investigated time period (i.e., 1655–1670). This shift is pointed out by Klein (1998) and can be explained by the second Swedish-Polish War (1655–1660), stopping the trade from Baltic states and opening the market for other suppliers. Indications of an increased frequency of paint losses and fillings over time can be identified if we combine the data for annual rings per millimeter, origin, and time of production, as the frequency of panels made of wood of German/Netherlandish origin increases.

Sapwood is considered to be more susceptible to insect damage and therefore rejected by panel makers. Data regarding the presence of sapwood are available from the panel paintings study: sapwood was identified in 26.1% of the 199 panels where dendrochronological analysis was available, and the amount of sapwood varied from 1 to an unusually high number of 47 annual rings. The total number of rings per board is generally (much) greater than 100 rings. Knots were also rejected by panel makers since the wood grain direction of the knot and surrounding areas is considered to be prone to cracks and paint loss. In the panel paintings study knots were identified in 6 of the 249 investigated panels, that is, 2.4%.

For the museum study a categorization of panel constructions was made, and the panels were divided into three main categories: nonrestrained panels, panels with cross-grain members, and complex panels. The subcategories are described in Table 1. The core construction of the panel is the most determining characteristic to assess the risks of mechanical damage of decorated wooden panels. Movements in the core construction also influence the condition of overlying layers. Significant correlations were identified between restraint and several damage parameters: open joints between boards, deformation, and lifting and/or abraded decorative layers.

Free-floating panels in frame constructions are good examples of nonrestrained constructions. In this type of object the panel is set into a groove, leaving space for swelling and shrinkage. Shrinkage can be seen as narrow, dark or light areas on the panel, along the edges of the frame, where unvarnished or unpainted wood surface, previously covered by the frame, has become exposed (Figure 3). When panel paintings are still in their original frame, shrinkage may be calculated by comparing the distances between the horizontal and vertical gaps between the panel and picture frame, assuming they were more or less equal when the panel was first inserted into its frame. Shrinkage is identified on 65.2% of the non-restrained objects in the cabinet door study; the remaining panels had either been restored so that no shrinkage could be identified or had not shrunk. The shrinkage on unrestrained

cabinet door panels is, on average, 0.5% of the original width of the panel, perpendicular to the wood grain direction. Reliable shrinkage data from the study of panel paintings are not available because of treatments of the panels and the exchange of picture frames.

Panels with cross-grain members are the simplest type of historic restrained constructions. As the members of the construction cannot move freely, swelling and shrinkage over the elastic limit of the material will result in irreversible damage. Figure 4 shows an example of a panel painting where the reverse has two original battens across the grain of the panel. Panels with such cross battens usually consist of two or more boards that are glued together, and battens are attached to, or sometimes partly inserted in, the reverse of the panel. When this type of restrained panel shrinks and expands, a gap develops in the glue joint between the boards, as identified on 12 out of a total of 13 panel paintings with original cross members in this study. The 13th panel was made of a single board, and therefore, this type of damage could not develop. In exceptional cases, minor cracks starting from the end grain of the boards can also be found, usually on single-board panels.

More elaborate constructions are found in the group of complex panels such as the one shown in Figure 5, with a cleated end construction. The panel consists of multiple boards joined together with glue along the longitudinal direction. At the top and bottom the panels continue with boards of the same thickness but attached perpendicularly to the vertical boards. These cleated ends do not protrude like the previously mentioned cross battens. Both sides of the panel are flat. In this example the cross-grain cleats are butt joined, glued, and nailed to the four vertical boards. Other joints between vertical boards and cleats also exist, such as tongue and groove without nails (van Duin, 2012). When the boards of a restrained construction swell or shrink, different types of change in the core construction will occur: a gap may develop along the glue joint between the boards and on the edge of restrained constructions with members in different grain directions, and a “step” will develop. This step can be explained by the orthotropic shrinkage behavior of wood; the shrinkage in the longitudinal direction is negligible compared to that in the radial direction. As a result, the cleated ends slightly protrude on the left and right sides of the panel, as their length has remained the same but the vertical boards have been reduced in width.

Cradled panels, such as the one shown in Figure 6, also belong to the group of complex panels and correspond to the most rigid type of restraint found in the museum study. Cradles consist of a grid of wooden slats mounted to the back of a painting to act as a reinforcement that keeps the panel flat. Slats along the grain direction are permanently fixed to the reverse of the painting, whereas the secondary perpendicular slats remain loose and should be able to slide as the panel shrinks or swells. As these slats often become unmovable and restrain the panel over time, the cradle often causes severe

TABLE 1. Construction groups.

Construction category	Construction type	Abbreviation	Definition
Freely responding panels	Panel in frame construction	FC	Boards, usually two or more, joined together (with glue, dowels, and/or tongue and groove), inserted in a groove or rabbet of a frame. The corners of the frame are connected with a bridle joint, lap joint, mortise and tenon joint, miter joint, or butt joint. Nonrestrained panel but restrained construction of the frame.
Panels with cross-grain members	Simple panel construction	PC	Boards, usually two or more, joined together (with glue, dowels, and/or tongue and groove). Nonrestrained construction.
	Board and molding construction	BM	Boards, usually two or more, joined together (with glue, dowels, and/or tongue and groove). Moldings applied on at least on side, with glue, nails, and/or dowels, partly cross grain. Restrained construction.
	Cleated ends	CE	Boards, usually two or more, joined together (with glue, dowels, and/or tongue and groove). Cross-grain cleats are joined with glue, tongue and groove, and/or nails or dowels. Restrained construction.
	Panel with cross battens	PB	Boards, usually two or more, joined together (with glue, dowels, and/or tongue and groove). Cross-grain battens are attached to the back of the wood substrate, with glue, nails, and/or dowels. Restrained construction.
	Panel with local reinforcement	PL	Boards, usually two or more, joined together (with glue, dowels, and/or tongue and groove). Cross-grain reinforcements such as wood blocks or butterfly keys are attached to the back of the wood substrate, with glue, nails, and/or dowels. Locally restrained construction, at the position of the reinforcement.
Complex panels	Hollow construction	HC	Thin boards, usually two or more joined together (with glue, dowels, and/or tongue and groove), mounted on both sides of a central frame. Rails and glue blocks inside the frame are glued and/or nailed to the boards. Restrained construction.
	Kussenkast: board and molding	K	Boards, usually two or more, joined together (with glue, dowels, and/or tongue and groove). The boards are usually veneered with wood veneers in a graphic pattern (parquetry). Moldings are applied on the front face of the boards, and a thin board is attached to the moldings, creating a hollow “pillow.” The moldings are fixed with glue, nails, and/or dowels, partly cross grain. Restrained construction.
	Cradled panel	CP	Boards, usually two or more, joined together (with glue, dowels, and/or tongue and groove). A grid of slats is attached to the backside of the panel, the slats in the wood grain direction are permanently fixed, and battens in the cross-grain direction of the boards are intended to slide. In many cases cradled panels are restrained as the sliding battens are stuck.
	Frame construction, thin panels	FT	Boards, usually two or more, joined together (with glue, dowels, and/or tongue and groove), inserted in a groove of a frame. The boards are less than 7 mm thick. Thin moldings are glued onto the boards, partly cross grain. The construction is restrained by the inner moldings, and the frame is restrained.

damage to the panel. Shrinkage and swelling of cradled panel paintings commonly result in the opening of glue joints between boards and, in some cases, cracks in the actual wooden boards. These cracks are initiated from the end grain of the board and propagate along the wood grain.

The damage pattern resulting from shrinkage of restrained objects is consistent. Because of the constraint across the grain the panels cannot swell and shrink freely with fluctuations in relative humidity, leading to stress and strain and resulting in plastic deformations or cracks. In the museum study, the most common type of damage is longitudinal cracks

on restrained constructions due to shrinkage perpendicular to the grain, following the wood grain along the glue lines. Glue joint failure can be found on 90.2% of the restrained paneled doors of furniture and on 73.1% of the restrained panel paintings. The same type of damage can be found on only 19.0% of the nonrestrained panels.

Decorated panels are built up in several layers, and panels are often decorated with veneers with different grain directions. Changes to the construction layer will affect the condition of the surface layer as well. As described earlier, the most common type of change to the core construction

FIGURE 3. Shrinkage of an unrestrained panel in frame construction. The grain direction is indicated by the black arrows. The largest movements due to shrinkage and swelling occur perpendicular to the grain, indicated by red arrows. The shrinkage behavior of unrestrained panels can be observed as lines along the edge of the frame, here marked in pink. Rijksmuseum BK-15320, 1,120 × 834 × 27 mm, 1775–1800. Photo and diagram by Stina Ekelund.

is the failure of the glue joints in the longitudinal direction of the wood between the boards. The openings can be several millimeters wide and create a gap or cavity. This cavity is damaging to the decorative layers, which are attached to the surface of the assembled boards. Ground and paint layers tear apart along the joint, resulting in loose parts or loss of material. Over smaller cavities, bridging of the decorative layer is possible, but these areas are very fragile to handling or vibrations, and what is more relevant, they interrupt the image and visual impression of the artwork. Figure 7 shows a detail of the four-board panel painting with cross battens presented in Figure 4. The open joints between the boards of the substrate are visible on the front side of the panel painting as well. Along the glue joint failure of the substrate, losses of paint and ground layer can be seen. The losses are filled and retouched and, over time, discolored.

Out-of-plane deformation, warping and cupping, was found in this survey of the restrained panels to occur in 7.2% of the cabinet door panels and 5.3% of the panel paintings.

Restraining cross battens

FIGURE 4. Four-board panel with original cross battens and characteristic glue joint failure, later rejoined. Hendrik Noorderwijs, Rijksmuseum SK-C-1550, 1,177 × 1,770 × 10 mm, 1647. Top photo courtesy of Rijksmuseum; bottom photo by Stina Ekelund.

For unrestrained panels out-of-plane deformation is far less common, occurring in less than 1.0% of furniture doors panels and 2.2% of panel paintings. This can probably be explained by the high quality of the oak wood used for the substrates, mainly the exclusive use of radially cut wood as well as thin panels.

This large-scale survey, involving more than 380 naturally aged panels, provided empirical data and a number of parameters related to the construction, material, history, and condition that could then be analyzed statistically. The results from the museum study show that shrinkage cracks and failing joints are the most common types of damage registered

FIGURE 5. Shrinkage of a restrained construction. The grain direction of the panel members is indicated by black arrows. The dashed rectangles represent the nails with which the horizontal cleats are fixed to the vertical boards. The largest movements of shrinkage and swelling occur perpendicular to the grain, indicated by the red arrows. Shrinkage gaps (cracks) between the members of the panels are marked by red circles. The gaps occur in the board-to-board joint as well as between the boards and horizontal cleats. Rijksmuseum BK-1966-16, 1,170 × 830 × 30 mm, 1690–1710. Photo and diagram by Stina Ekelund.

on decorated oak wooden panels. The selection criteria for the museum study considered only oak wood, and the great majority of the panels were radial-cut boards, which explains the relatively large amount of shrinkage in the radial direction and the low frequency of out-of-plane deformation. Since the weakest points of the objects are the glue joints between the different members of the panel, the number of boards in a structure is highly significant for the current condition of the object. The correlation between restraint, that is, the restriction of a board from deforming freely, and damage is also significant. It can be concluded from the museum study that the complexity of the structure is important to understand the object's failure criteria and should therefore be considered.

FIGURE 6. Three-board panel with restraining cradle. Pieter Jansz van Asch, Rijksmuseum SK-C-88, 1,020 × 745 × 6 mm (panel without cradle), 1640–1678. Painting photo courtesy of Rijksmuseum; other photos by Stina Ekelund.

The empirical data obtained from the museum study were used for the experimental study of the Climate4Wood research project. The experimental work, involving exposure of mock-ups to well-controlled climate fluctuations, was designed on the basis of the results of this study (Luimes, 2018). The results from both these studies can be used as input parameters and validation of the thermohygro-mechanical modeling. The results from this combined approach can then be used for the development of sustainable preservation strategies and to further develop rational guidelines for sustainable indoor climate conditions.

Understanding the mechanisms that lead to visual changes of the condition will help conservators to predict when and where damage will occur and help conservators and decision makers to make well-informed decisions. The empirical data from the museum study can serve as input for the decision-making process for conservation treatments; for example, the data can serve as an input in the discussion of cradle removal.

Re-joined boards, retouched

FIGURE 7. Detail (approximately 400 × 400 mm) of Figure 4. Opening between boards as a result of glue joint failure, rejoined and retouched. Hendrik Noorderwiel, Rijksmuseum SK-C-1550, 1,177 × 1,770 × 10 mm, 1647. Photo courtesy Rijksmuseum.

The museum study also provided insight into what conditions can be expected in relation to construction, material, and historical parameters.

CONCLUSIONS

The objective of this paper was to show how construction, material, dimensional, and historical parameters can be related to patterns observed in the condition of a selected group of decorated panels in the Rijksmuseum collection. The results given were obtained using the method developed for the museum study, combining archival and visual information. In accordance with the selection criteria all panels studied were of oak wood, and the great majority of the investigated panels were made of high-quality quarter-sawn wood. The main conclusion from this study is the effect of restraint on joint failure. A restrained panel is likely to develop open joints, whereas nonrestrained panels are likely to shrink without major effects on the construction. Cracks in the actual wood and out-of-plane deformations are uncommon in restrained as well as nonrestrained panels. Damage in the decorative layers is

closely related to changes within the substrate construction, and losses of decorative layers are often located in the areas along the glue joints. The empirical data from what conservators have observed in the museum study are essential as input and part of the validation of the experimental and modeling studies of the Climate4Wood research project.

ACKNOWLEDGMENTS

This work, within the Climate4Wood research project, is financed by the research program Science4Arts of the Netherlands Organisation for Scientific Research. Climate4Wood is a collaborative research project of the Rijksmuseum, the University of Technology of Eindhoven, the Delft University of Technology, and the Cultural Heritage Agency of the Netherlands. The Climate4Wood research project started in 2012 and will be completed by 2019. The authors would like to thank Carola Klinzmann, furniture conservator of Museumslandschaft Hessen Kassel; postdoc researcher Cécilia Gauvin; dendrochronologist Peter Klein; and the Rijksmuseum paintings conservation department for their contribution to performing the museum study. Photographs of paintings are available in the open source Rijksstudio, Rijksmuseum, Amsterdam (<https://www.rijksmuseum.nl/en/photoservice>).

REFERENCES

- Boersma, F., K. Dardes, and J. Druzik J. 2014. Precaution, Proof and Pragmatism: Evolving Perspective on the Museum Environment. In "Collection Environments." *Conservation Perspective, the GCI Newsletter*, 29(2):5–9.
- Bratasz, Ł. 2010. "Acceptable and Non-acceptable Microclimate Variability: The Case of Wood." In *Basic Environmental Mechanisms Affecting Cultural Heritage: Understanding Deterioration Mechanisms for Conservation Purposes*, ed. D. Camuffo, V. Fassina, and J. Havermans, pp. 49–58. COST Action D42: Chemical Interactions between Cultural Artefacts and Indoor Environment. Florence: Nardini Editore.
- Ekelund, S., P. Van Duin, A. Jorissen, B. Ankersmit, and R. M. Groves. 2017. A Method for Studying Climate-Related Changes in the Condition of Decorated Wooden Panels. *Studies in Conservation*, 63(2):62–71.
- Klein, P. 1998. "Dendrochronological Analyses of Panel Paintings." In *The Structural Conservation of Panel Paintings: Proceedings of a Symposium at the J. Paul Getty Museum, 24–28 April 1995. Part 1: Wood Science and Technology*, ed. K. Kardes and A. Rothe, pp. 39–54. Los Angeles: Getty Conservation Institute.
- Luimes, R. A., A. S. J. Suiker, A. J. M. Jorissen, P. H. J. C. van Duin, and H. L. Schellen. 2018. Hygro-mechanical Response of Oak Wood Cabinet Door Panels under Relative Humidity Fluctuations. *Heritage Science*, 6:72.
- Mecklenburg, M. F., and C. S. Tumosa. 1991. "Mechanical Behavior of Paintings Subjected to Changes in Temperature and Relative Humidity." In *Art in Transit: Studies in the Transport of Paintings*, ed. M. F. Mecklenburg, pp. 173–216. Washington D.C.: National Gallery of Art.
- Mecklenburg, M. F., C. S. Tumosa, and D. Erhardt. 1998. "Structural Response of Painted Wood Surfaces to Changes in Ambient Relative Humidity." In *Painted Wood: History and Conservation*, ed. V. Dorge and F. C. Howlett, pp. 464–483. Los Angeles: Getty Conservation Institute.
- Mecklenburg, M. F. 2007. Determining the Acceptable Ranges of Relative Humidity and Temperature in Museums and Galleries. Part 1. Structural Response to Relative Humidity. Internal Report. Suitland Md.: Museum Conservation Institute, Smithsonian Institution. <http://www.si.edu/mci/downloads/reports/Mecklenburg-Part1-RH.pdf> (accessed February 14, 2014).

- Michalski, S. 1996. Quantified Risk Reduction in the Humidity Dilemma. *APT Bulletin: The Journal of Preservation Technology*, 27(3):25–30.
- New, B. 2014. “The Painted Support: Properties and Behaviour of Wood.” In *The Conservation of Panel Paintings and Related Objects: Research Agenda, 2014–2020*, ed. N. Kos and P. van Duin, pp. 17–72. The Hague: Netherlands Organisation for Scientific Research.
- Staniforth, S. 2014. Environmental Conditions for the Safeguarding of Collections: Future Trends. *Studies in Conservation*, 59(4):213–217.
- van Duin, P. 2012. “The Construction of Flat Decorated Doors of Dutch Seventeenth-Century Cabinets. Report of a Master Class.” In *Restoring Joints, Conserving Structures: Proceedings Tenth International Symposium on Wood and Furniture*, ed. M. Vasques Dias, pp. 121–143. Amsterdam: Stichting Ebenist.
- van Duin, P. 2014. Climate Effects on Museum Objects – The Need for Monitoring and Analysis. In “Collection Environments.” *Conservation Perspective, the GCI Newsletter*, 29(2):13–15.
- Wadum, J. 1998. “Historical Overview of Panel-Making Techniques in the Northern Countries.” In *The Structural Conservation of Panel Paintings: Proceedings of a Symposium at the J. Paul Getty Museum, 24–28 April 1995*. Part 1: *Wood Science and Technology*, ed. K. Kardes and A. Rothe, pp. 149–177. Los Angeles: Getty Conservation Institute.

Microclimate and Vibration Environment of a Custom Shipping Crate

Nobuyuki Kamba^{1,2*}

ABSTRACT. When cultural objects are transported, various hazards can occur during the different stages of the process. These include handling and packing, machine vibrations, dramatic temperature and relative humidity changes, and accidents. This study tries to clarify the conditions inside a custom shipping crate by measuring temperature, humidity, and vibration inside the packaging using electronic instruments during transportation. This paper discusses the severity of these hazards, especially temperature change and vibration.

INTRODUCTION

This study tries to clarify the conditions inside a custom shipping crate by measuring temperature, humidity, and vibration inside the packaging using electronic instruments during transportation. The equilibrium moisture content (EMC) of a hygroscopic material depends on temperature and relative humidity (RH). To maintain the same EMC in a piece of wood, the RH of the environment must decrease if the temperature decreases and vice versa. Therefore, should either temperature or RH change, strain will be induced. However, a larger strain will occur when the EMC changes. For example, for wood kept at a constant EMC and subjected to a sudden temperature change from 10°C to 40°C, the induced strain will remain less than $\pm 0.1\%$ of the strain of the wood, where such a low yield strength suggests that no fatigue will occur in the wood.

Vibration caused by transportation is random and can be expressed by the maximum acceleration (G_p), root-mean-square of varying G (G_{rms}), and power spectrum density (PSD). It becomes clear from analyzing different transportation methods that conveyance by an airport dolly has the largest G_p , G_{rms} , and PSD values. The next largest influences occur as a result of truck transportation and loading onto and unloading from a truck, an airplane, and a pallet. Movement in the museum may occasionally have influences similar to those of the handling process.

RISKS IN TRANSPORTATION OF CULTURAL OBJECTS

When cultural objects are transported, they are subjected to specific risks arising from vibrations, rapid temperature and humidity changes, sharp pressure changes, and impacts during various transportation stages and processes (manual handling, packing, transportation by equipment, unpacking). One of the specific risks is the strain that can occur in the hygroscopic material of the cultural object resulting

¹ Tokyo National Museum, 13-9 Ueno Park, Taito-ku, Tokyo 110-8712, Japan.

² Now at 3-10-5 Kozunomori, Narita-shi, Chiba 286-0048, Japan.

* Correspondence: nbd02744@nifty.com

Manuscript received 2 June 2018; accepted 7 May 2019.

from change(s) in temperature and humidity. The deformation caused by this strain, if beyond a certain value (i.e., the yield strength), can be irreversible. In addition, during unpacking, condensation may build up on the object's surface as a result of a temperature difference (Kamba and Tanaka, 1994a) between the object and the work area atmosphere. With regard to vibration, the frequency of the oscillation motion may coincide with the eigenfrequency of an object and cause resonance, generating a large amount of energy that could break the fragile joint of a connected part, whereas a strong vibration could cause bounding of an object secured in a shipping crate, thus breaking it. Furthermore, fatigue could accumulate at the joint of an object as a result of repetitive vibration. So far, we have not seen any deformation caused by the influence of temperature and humidity that has been confirmed visually, but we have seen some cases of damage to objects that could have been caused by vibration and shock, such as the impact from a drop, which could break any fragile part of an object.

Generally, packing materials have a certain level of thermal insulation. Thus, changes in temperature and humidity within the packaging are relatively moderate and occur in a delayed fashion. Consequently, it is relatively easy to identify the timing of temperature and humidity changes during transportation. On the other hand, the precise causal relationship between transportation processes and vibrations remains unclear because detailed information about these processes can only be presumed on the basis of the timetable; however, vibrations can be accurately recorded over time using an instrument. Detailed information for the entire transportation process was successfully obtained from a courier traveling with an object being transported to a special exhibition, which facilitated precise understanding of the timing of the occurrence of vibration and contributed to a breakthrough for a specific vibration analysis (Kamba and Takagi, 2008).

The magnitude of the impact of temperature and humidity changes inside a shipping crate on a cultural object, the characteristics of the vibration that occurred during transportation, and the magnitude of the impact of the vibration(s) occurring during each process on an object could be evaluated on the basis of measurements of temperature and humidity changes inside a custom shipping crate, as well as the vibration(s) induced. These factors are considered to have the most significant impacts on cultural objects during transportation. Finally, the results of tests on the deformation of wood with temperature and humidity changes are also discussed.

MICROCLIMATE INSIDE A CUSTOM SHIPPING CRATE AND INDUCED STRAINS

The characteristics of an ideal shipping crate include its relatively high airtightness and the minimal volume of air that

it contains (Kamba, 1990). When an object is made of highly hygroscopic materials such as wood, the small amount of moisture contained in the air will be absorbed into the wood when the ambient temperature decreases, which causes a corresponding decrease in the relative humidity of the air. Under the same principle, an increase in temperature will cause the wood to release moisture, with a corresponding increase in the relative humidity. The amount of water that wood can hold is far larger than the amount of water contained in the air inside the packaging. Consequently, the relative humidity is strongly influenced by the transfer of moisture into and out of the wood. When a hygroscopic object is sealed in a package with an extremely small amount of air, the interior air temperature and relative humidity of the packaging change so that the EMC of the object is maintained at a nearly constant value.

Using a diagram of the relationship between temperature and relative humidity at a constant equilibrium moisture content of wood (Kollmann, 1951), it can be understood that the temperature and humidity must change in the same direction to maintain a constant EMC value. However, the previously mentioned condition is not likely to occur if the packaging has poor airtightness and allows the flow of inbound air. Combining the temperature and relative humidity data for the interior of the shipping crate obtained during actual transportation (Figure 1), the looped changes in the temperature and relative humidity, as shown in Figures 2 to 5, follow the rule of maintaining a nearly constant EMC.

When a humidity buffering material such as a silica gel is packed with an object in a sealed crate, the EMC of the object changes with the temperature while a constant relative

FIGURE 1. The packing crate of an ancient wooden saddle coated with Japanese lacquer that was transported from the Tokyo National Museum to the Arthur M. Sackler Gallery in Washington, D.C., between 8 and 9 June 2007.

FIGURE 2. Outward trip from the Tokyo National Museum to the Arthur M. Sackler Gallery in Washington, D.C., between 8 and 9 June 2007. Combining the temperature and humidity data for the interior of the shipping crate obtained during the transportation and the data for the EMC curve of wood with changes in the temperature and humidity, following Kollmann's approach (1951), indicates that both temperature and humidity changed in a loop.

FIGURE 3. Outward trip from the Tokyo National Museum to the Montreal Museum of Archaeology and History on 3 May 2006.

humidity is maintained (Kamba and Tanaka, 1994b). In order to study the strain occurring in an object when the EMC changes, an examination was conducted using Japanese cypress wood (*Chamaecyparis obtuse*; Kamba and Nishiura, 1993). Each package had a single sample consisting of a 70g piece of cypress wood. The samples were pretreated under the same seasoning conditions, and strain gauges were attached to them in the tangential direction to measure the strain. The following four test conditions were used: (1) the test sample was sealed in a 1 L polypropylene container by itself, (2) the test sample was sealed in a 1 L polypropylene container including 20g of Art-Sorb, (3) the test sample was simply exposed to the testing environment, and (4) the above test samples were coated with

FIGURE 4. Outward trip from the Tokyo National Museum to the Museum of New Zealand Te Papa Tongarewa in Wellington between 19 and 20 February 2006.

FIGURE 5. Outward trip from the Tokyo National Museum to the National Museum of Korea on 5 October 2005.

moisture-proof silicone-modified acrylic resin to inhibit the transfer of moisture (see Table 1).

All test samples were placed in an environmental chamber in which the interior atmospheric temperature was changed from 10°C to 40°C at a constant relative humidity of 60%. The test results for conditions 1, 2, 3, and 4 were plotted in graphs with the temperature on the abscissa and the strain on the ordinate, as shown in Figures 6 to 9.

Figure 10 shows temperature and relative humidity changes within the container for condition 1 as well as the looped change. The results show that the magnitude of the strain is the smallest for condition 4, followed in ascending order by conditions 1, 2, and 3. For conditions 4 and 1, the strain in the test samples stays within approximately $\pm 0.1\%$, whereas for conditions 2 and 3, the strain values exceed $\pm 0.1\%$. Under condition 4, the test sample shows only the strain from thermal expansion and contraction caused by the temperature change, with no or minimal strain generated

TABLE 1. Test samples under the four different conditions to examine the dimensional stability of wood with the temperature-humidity change. All samples were 70 g pieces of Japanese cypress wood (*Chamaecyparis obtusa*). In the testing environment the temperature was changed from 10°C to 40°C at 60% RH.

Condition	Surface preparation	Container	Humidity buffer in container	Test sample	Testing environment
1	No coating	Sealed in 1 L polypropylene container	No buffer	70 g piece of Japanese cypress wood (<i>Chamaecyparis obtusa</i>)	temperature was changed from 10°C to 40°C, at 60 %RH.
2	No coating	Sealed in 1 L polypropylene container	With 20 g of Art-Sorb	same as above	same as above
3	No coating	Simply exposed to the testing environment without a container	No buffer	same as above	same as above
4	All samples were coated with moisture-proof silicone-modified acrylic resin	Simply exposed to the testing environment without a container	No buffer	same as above	same as above

FIGURE 6. Strain of Japanese cypress in the tangential direction under condition 1, in which the test sample was sealed in a 1 L polypropylene container. The container was placed in an environment chamber in which the interior atmospheric temperature was changed from 10°C to 40°C with a constant relative humidity.

FIGURE 7. Strain of Japanese cypress in the tangential direction under condition 2, in which the test sample was sealed in a 1 L polypropylene container along with 20 g of Art-Sorb. The container was placed in the same environment chamber as in condition 1.

by a change in the EMC. Meanwhile, under conditions 2 and 3, the test samples show strains larger than in the other conditions, generated by changes in both the temperature and EMC.

Figure 11, based on the graph from Asano et al. (1979) shows that approximately $\pm 0.1\%$ of the strain generated in the wood piece that was kept under a constant EMC condition has a far lower value than the yield stress. Studies by Mecklenburg and Tumosa (1991), Michalski (1991), and Ashley-Smith (1999) suggest that this strain will not accumulate and cause fatigue, thus minimizing the impact.

VIBRATION CHARACTERISTICS AND IMPACT MAGNITUDE FOR TRANSPORTATION PROCESSES

Cultural objects that are transported for international exhibitions undergo more complicated processes compared to those shipped domestically because international shipment involves a variety of transportation means (Kamba et al., 2008). Specifically, the processes involved include moving within a building; truck transportation; conveyance by a dolly (Figure 12); and air transportation, requiring loading

FIGURE 8. Strain of Japanese cypress in the tangential direction under condition 3, in which the test sample was simply exposed to the testing environment. The sample was placed in the same environment chamber as in condition 1.

FIGURE 9. Strain of Japanese cypress in the tangential direction under condition 4, in which the three test samples in conditions 1–3 were coated with moisture-proof acrylic resin to inhibit the transfer of moisture. The samples were placed in the same environment chamber as in condition 1.

and unloading from a truck (Figure 13). Because of the complex processes involved, GPS devices and detailed records taken by an accompanying attendant were necessary to obtain an accurate workflow.

Because the vibration that occurs during transportation is random, consisting of a combination of sinusoidal waves of various frequencies and amplitudes, the vibration characteristics can be effectively expressed using the PSD; effective G value or root-mean-square acceleration (G_{rms}); and peak, or maximum, acceleration (G_p). Further information about these points can be found elsewhere (Harris and Piersol, 2002; Vibration Research Corp, 2017). The G_p distribution had been analyzed in previous transportation studies (Saunders, 1998); therefore, consideration of the risks was somewhat focused

FIGURE 10. Temperature and relative humidity changes under condition 1, in which the test sample was sealed in a 1 L polypropylene container.

FIGURE 11. Tensile and compressive stress-strain diagram of Japanese cedar where the stress σ is on the ordinate and the strain ϵ is on the abscissa. Adapted from Asano et al., 1979.

on the unexpected events inherent in each transportation process, such as dropping and rough handling, and was not expanded to include an assessment of the potential risks that might be encountered in each process. The PSD indicates the distribution of the power density in the frequency spectrum of the time series vibration, as well as the resonance frequency. The integration of the area under the PSD curve is equal to the integration of the total energy of the entire transportation process and thus is an indicator of the severity of the transportation condition. In addition, G_{rms} expresses the mean value of the various vibration accelerations that occur during the transportation process and may be used as an indicator of the vibration severity.

The opportunities provided by various special exhibitions in 1999 allowed the use of electronic devices with built-in triaxial accelerometers to measure shock and vibration levels during the various transportation processes. Among these, the data obtained during the transportation

FIGURE 12. A dolly conveyance of pallets on an airport apron.

FIGURE 13. A packing crate loaded onto a truck by a forklift.

from Pointe-à-Callière, Montreal Archaeology and History Complex (henceforth Montreal Archaeology and History Complex), to the Tokyo National Museum are shown here as an example of a case where the details of the vibration that occurred throughout the entire transportation process could be perfectly recorded. The goal of clarifying the characteristics and impact of the vibration that occurred in each process can be reached by combining the results derived from these data and other examples. The entire transportation time from Montreal to Tokyo was 28 hours, which included 11.5 hours of temporary storage between transshipment and 16.5 hours for the actual transportation. The transportation time included 13.67 hours of air transportation, 1.67 hours of truck transportation, and 40 minutes of dolly conveyance. Furthermore, in addition to the time spent in temporary storage at the origin of the shipment and transit points, the time included 10 minutes in unloading from the aircraft, 10 minutes in unloading from the truck, 7 minutes for loading and unloading from pallets, and 3 minutes to move within the museum.

Figure 14 shows the time series acceleration of G_p recorded during the transportation process. Table 2 shows the vibrations measured during the 2006 exhibition travel, organized by handling process. Measurements were taken during

loading, unloading, and movement of objects, as well as during takeoff, flight, and landing of the aircraft. Measurements were taken during transportation from the Montreal Archaeology and History Complex to the Tokyo National Museum, with transfers at the Montreal airport, Toronto airport, and Narita airport. Movement by dolly (in bold) produced the highest G_{rms} (effective G value/root-mean-square acceleration) and the most instances of PSD (resonance frequency/power spectrum density). Vertical movement during transport also registered higher levels of G_{rms} and PSD than other directional movement.

Figures 15 to 23 show the PSD curve for each of the described processes, whereas Figure 24 corresponds to the resting state at a warehouse for comparison. On the basis of these results, it seems that the conveyance by dolly, whose G_p , G_{rms} , and PSD values are all ranked at the top level, exerts a remarkably large impact among the transportation processes (Kamba et al., 2010; Figure 25). The upper limit of the measurement device was set to 10 G; therefore, it is suspected that acceleration much larger than 10 G might have occurred. For example, a value of 14 G was measured during transportation in July 2008 at the Narita and Domodedovo airports.

Meanwhile, the shock and vibration values generated by takeoff and landing of an aircraft are small and thus will

FIGURE 14. Peak acceleration during the shipment of the return trip from Pointe-à-Callière, Montreal Archaeology and History Complex to the Tokyo National Museum between 21 and 23 October 2006.

TABLE 2. Vibrations measured during 2006 exhibition travel, organized by handling process. Measurements were taken during loading, unloading, and movement of objects and during takeoff, flight, and landing of the aircraft. Measurements were taken during transportation from the Montreal Museum of Archaeology and History Complex (MMAHC) to the Tokyo National Museum (TNM), with transfers at Montreal–Pierre Elliott Trudeau International Airport (YUL), Toronto Pearson International Airport (YYZ), and Narita (Tokyo) International Airport (NRT). Movement by dolly (in bold) produced the highest G_{rms} (effective G value/root-mean-square acceleration) and the most instances of PSD (power spectrum density/resonance frequency). Vertical movement during transport also registered higher levels of G_{rms} and PSD than other directional movement. Symbols for the direction indicate the following: → = running forward/backward, ↔ = moving left/right, ↑ = moving up/down. In the PSD column, symbols indicate the following: ● = peak PSD < 10^{-4} G²/Hz, ●● = 10^{-4} G²/Hz ≤ peak PSD < 10^{-3} G²/Hz, ●●● = 10^{-3} G²/Hz ≤ peak PSD.

Handling Process	Location	Direction	PSD	Grms
Dolly conveyance	NRT	↑	●●●	0.194
Dolly conveyance	YYZ	↑	●●●	0.191
Dolly conveyance	YYZ	↑	●●●	0.189
Dolly conveyance	YUL	↑	●●●	0.152
Dolly conveyance	YYZ	→	●●	0.104
Dolly conveyance	YYZ	→	●●	0.100
Dolly conveyance	NRT	↑	●●●	0.090
Dolly conveyance	NRT	→	●●	0.089
Dolly conveyance	YYZ	↔	●●	0.076
Dolly conveyance	YYZ	↔	●●	0.073
Dolly conveyance	YUL	↔	●●	0.064
Dolly conveyance	NRT	→	●●	0.061
Dolly conveyance	YUL	→	●●	0.054
Dolly conveyance	NRT	↔	●	0.035
Dolly conveyance	NRT	↔	●	0.026
Unloading from a truck	TNM	↑	●●	0.102
Unloading from a truck	YUL	→	●●	0.082
Unloading from a truck	YUL	↑	●●	0.078
Unloading from a truck	TNM	→	●●	0.072
Unloading from a truck	TNM	↔	●●	0.070
Unloading from a truck	YUL	↔	●●	0.040
Unloading from an aircraft	YYZ	↑	●●●	0.093
Unloading from an aircraft	NRT	↑	●●●	0.079
Unloading from an aircraft	NRT	→	●●	0.054
Unloading from an aircraft	YYZ	↔	●●	0.054
Unloading from an aircraft	YYZ	→	●●	0.052
Unloading from an aircraft	NRT	↑	●	0.040
Unloading from an aircraft	NRT	→	●	0.030
Unloading from an aircraft	NRT	↔	●	0.028
Unloading from an aircraft	NRT	↔	●	0.020
Moving by a truck	MMAHC to YUL	↑	●●●	0.081
Moving by a truck	NRT to TNM	↑	●●	0.067
Moving by a truck	MMAHC to YUL	↔	●●	0.065
Moving by a truck	NRT to TNM	↔	●●	0.043
Moving by a truck	MMAHC to YUL	→	●	0.033
Moving by a truck	NRT to TNM	→	●	0.033
Loading onto an aircraft	YUL	↑	●●	0.080
Loading onto an aircraft	YYZ	↑	●●●	0.079
Loading onto an aircraft	YYZ	→	●●	0.053
Loading onto an aircraft	YUL	↔	●●	0.052
Loading onto an aircraft	YUL	→	●●	0.046
Loading onto an aircraft	YYZ	↔	●●	0.042
Moving within the museum	MMAHC	↑	●●	0.069
Moving within the museum	MMAHC	→	●●	0.057
Moving within the museum	MMAHC	↔	●	0.043
Landing	YYZ	↑	●●	0.064
Landing	NRT	↑	●●	0.043
Landing	YYZ	→	●●	0.027
Landing	YYZ	↔	●	0.025

TABLE 2. (Continued)

Handling Process	Location	Direction	PSD	Grms
Landing	NRT	→	●	0.024
Landing	NRT	↔	●	0.016
Loading onto a truck	MMAHC	→	●●	0.060
Loading onto a truck	NRT	↔	●●	0.049
Loading onto a truck	NRT	↓	●●	0.046
Loading onto a truck	NRT	→	●●	0.038
Loading onto a truck	MMAHC	↓	●	0.037
Loading onto a truck	MMAHC	↔	●	0.033
Loading onto a pallet	YUL	↓	●	0.037
Loading onto a pallet	YUL	→	●●	0.031
Loading onto a pallet	YUL	↔	●●	0.029
Unloading from a pallet	NRT	↓	●●	0.033
Unloading from a pallet	NRT	↔	●●	0.033
Unloading from a pallet	NRT	→	●	0.025
Moving on a runway	YYZ	↓	●●	0.030
Moving on a runway	YYZ	→	●●	0.014
Moving on a runway	YYZ	↔	●●	0.014
Takeoff and flight	YUL to YYZ	↓	●●	0.027
Takeoff and flight	YUL to YYZ	↔	●	0.016
Takeoff and flight	YYZ to NRT	↓	●●	0.016
Takeoff and flight	YYZ to NRT	→	●	0.013
Takeoff and flight	YUL to YYZ	→	●	0.012
Takeoff and flight	YYZ to NRT	↔	●	0.011

FIGURE 15. Power spectral density of the dolly conveyance at the Montreal airport.

have a minimal impact on cultural objects, even though they are generally strongly felt by the human body (Figure 26). Following the conveyance by dolly, the manual handling involved in the process of loading and unloading from an aircraft, a truck, a pallet, etc., has a large impact (Figure 27). Similarly, truck transportation has a large impact (Figure 28). Attention must be given to the fact that a relatively high

FIGURE 16. Power spectral density of truck transportation from the Montreal Archaeology and History Complex to the Montreal airport.

G_{rms} was recorded for the movement that occurred within the museum. It can be determined from the data that there is a potential risk in the material handling process even though no significant G_p occurs. The PSD data also show that the level of vibration is noticeably higher in the vertical direction compared to other directions when a package is traveling, whereas no significant difference is found between the

FIGURE 17. Power spectral density of moving within the facility of the Montreal Archaeology and History Complex.

FIGURE 19. Power spectral density of the loading process onto the aircraft at the Toronto airport.

FIGURE 18. Power spectral density of takeoff and flight from the Toronto airport to the Narita airport.

FIGURE 20. Power spectral density of the unloading process from the aircraft at the Narita airport.

directions of vibration during the material handling process. The PSD had peak values in the range of 4–30 Hz in most of the processes, although for truck transportation the peak value is at approximately 2 Hz, which originates from the air suspension of the truck. As a result of the measurements and analyses, the characteristics of the vibration for every process became clear, allowing us to predict their influence at every stage of the operation. However, an evaluation of the amount of accumulated fatigue, which depends on time and vibration characteristics, still requires further study (Nakajima et al., 2007).

PSD values for conveyance by dolly and truck transportation may vary according to airport and traffic conditions. Figures 29 and 30 show the measured set of data for transportation from Narita to the Domodedovo airport, which previously had the largest G_p value, along with an extremely large G_{rms} value of 0.631 at the Domodedovo airport. The G_{rms} of truck transportation in Domodedovo was much smaller than the one in Narita.

Figure 31 shows the PSD of the conveyance by a dolly that was equipped with a suspension to prevent vibration risks, and it is clear that the PSD values decreased. However,

FIGURE 21. Power spectral density of the loading process onto the truck at the Narita airport.

FIGURE 23. Power spectral density of the loading process onto the pallet at the Montreal airport.

FIGURE 22. Power spectral density of the unloading process from the truck at the Tokyo National Museum.

FIGURE 24. Power spectral density of the resting state at the warehouse of the Tokyo National Museum.

the drawback is that these special dollies have a high cost, and therefore, a decision-making process is required to decide whether they are justified for each transportation case. Another challenge is to suppress the G_{rms} value of truck transportation, as discussed by Wada et al. (2010). A weight of 4,000 kg was placed on the carrier to suppress the vibration of an 11-ton truck equipped with an air suspension system in order to transport an extremely fragile Buddha statue. This measure reduced G_p , but the effect on the value of G_{rms} was contrary to what had been expected, as shown in Figures 32 to 35.

CONCLUSIONS

The strain to which the contents of a shipping crate are subjected as a result of temperature and relative humidity changes can be minimized by sealed packaging of the object. It was confirmed that sealed packaging suppressed the occurrence of strain, limiting the yield strength to low levels, which is understood to prevent the accumulation of fatigue. Consequently, the most effective measure to minimize the change in strain of the cultural object is the reduction of temperature changes within the crate.

FIGURE 25. Power spectral density of the dolly conveyance during the whole transportation process. Only the z component of the acceleration is shown in the diagram. The PSD values are all ranked at the top level.

FIGURE 26. Power spectral density of the air transportation. The PSD values generated by the transportation by air are remarkably small.

FIGURE 27. Power spectral density of loading and unloading from a truck during the whole transportation process. The thick red line shows the PSD curve of the dolly conveyance, and the thick purple line represents the PSD during flight.

FIGURE 28. Power spectral density of the truck transportation during the whole transportation process. The thick red line shows the PSD curve of the dolly conveyance, and the thick purple line represents the PSD during flight.

FIGURE 29. Comparison of the power spectral density of dolly conveyances during the shipment of the return trip from the Domodedovo airport to the Narita airport on 25 July 2008.

FIGURE 30. Comparison of power spectral density of truck transportation during the shipment of the return trip from the Domodedovo airport to the Narita airport in 25 July 2008.

In addition, the G_p , PSD, and G_{rms} values could be effectively used in assessing the vibration impact of each process. As a whole, higher accelerations were observed during the loading and unloading of the crate, which usually takes 10 minutes. It was also found that the vibration acceleration that occurs during conveyance by a dolly in aircraft parking apron areas is remarkably larger than that of other processes. Because this process is indispensable for air transportation and the vibration level cannot be controlled, extra attention

FIGURE 31. Power spectral density of a normal dolly conveyance during the shipment of the outward trip at the Narita airport on 14 March 2007 and a special dolly conveyance during the shipment of the return trip at the Narita airport on 20 June 2007.

FIGURE 32. Peak acceleration of truck transportation without weight on 11 November 2008.

must be given to the packaging to cope with this risk. On the other hand, the minimal vibration that occurs during air transportation has the lowest vibration risks, an important point since the amount of flight time is probably the highest in the entire transportation process. Finally, the impacts of truck transportation and the manual handling involved in loading and unloading from a truck, an aircraft, and a pallet are large, and the movement within a museum can generate the same level of impact as manual handling in some cases.

FIGURE 33. Peak acceleration of truck transportation with a 4,000 kg weight on 21 March 2009.

FIGURE 35. Root-mean-square value of acceleration of truck transportation with a 4,000 kg weight on 21 March 2009.

FIGURE 34. Root-mean-square value of acceleration of truck transportation without weight on 11 November 2008.

These findings should be taken into consideration during crate design, and the airfreight forwarder should be informed as well. Future work will address a more effective assessment of transportation quality by analyzing the accumulation of fatigue caused by vibration.

ACKNOWLEDGMENTS

I express warm and sincere thanks to Wada Hiroshi (Tokyo National Museum), Takagi Masahiro (eXsearch),

Imakita Ken (eXsearch), Tsukada Masahiko (Tokyo National University of Fine Arts), Furuya Tsuyoshi (Tokyo National Museum), Nishiura Tadateru (Kokushikan University), and Tanaka Chiaki (deceased) for their long-lasting great cooperative work, constructive comments, and warm encouragement. Suppliers: The Saver 3X90 was provided by the Lansmont Corporation (Monterey, California; <http://www.lansmont.com>). Art-Sorb was supplied by Fuji Silysia Chemical Ltd. (Nagano, Japan; <http://www.fuji-silysia.co.jp>). The silicon-modified acrylic resin Penguin Coat Top Si Clear was provided by Sunstar Engineering Inc. (Takatsuki, Japan; <http://www.sunstar-engineering.com>).

REFERENCES

- Asano, I., H. Sugiyama, M. Okuma, and T. Okano. 1979. *Mokuzai to Jutaku* [Wood and housing], chap. 2.4. Mechanical Property of Lumber, pp. 63. Tokyo: Gakkai Shuppan Center.
- Ashley-Smith J. 1999. "Physical Effect." In *Risk Assessment for Object Conservation*, pp. 218–221. Oxford: Butterworth-Heinemann.
- Harris, C. M., and A. G. Piersol. 2001. *Harris's Shock and Vibration Handbook*, pp. 11.8, 22.7. New York: McGraw-Hill.
- Kamba, N. 1990. "Variation in Relative Humidity and Temperature as Measured in a Package Case." In *ICOM Committee for Conservation, 9th Triennial Meeting, Dresden, German Democratic Republic, 26–31 August 1990: Preprints*, ed. K. Grimstad, pp. 405–409. Los Angeles: ICOM Committee for Conservation.
- Kamba, N., and T. Nishiura. 1993. "Measurement of the Dimensional Change of Wood in a Closed Case." In *ICOM Committee for Conservation, 10th Triennial Meeting, Washington, DC, USA, 22–27 August 1993: Preprints*, ed. J. Bridgland, pp. 406–409. London: ICOM Committee for Conservation.
- Kamba, N., and C. Tanaka. 1994a. Konpokesu no dannetsu to ketsuro no hassei [Relationship between thermal insulation and condensation within packing case]. *Bunkazai Hozon Shufuku Gakkaishi*, 39:8–18.
- Kamba, N., and C. Tanaka. 1994b. Yusochu no konpo kesunai ni okeru onnsitsudo kankyo to chositsuzai no kouka [The environment of packing cases during the transportation and the effect of moisture buffering materials]. *Bunkazai Hozon Shufuku Gakkaishi*, 38:28–36.

- Kamba, N., and M. Takagi. 2008. "Transportation of Cultural Properties." Paper presented at ISTA-China Packaging Symposium, Tianjin, China.
- Kamba, N., H. Wada, M. Takagi, and K. Imakita. 2010. Kukonai no dori hansokotei de hasseisuru sindo to shogekiu [Study on international air shipment of cultural properties occurrence of shock and vibration events in the dolly section at airports]. *Japan Packaging Institute Journal*, 48:204–208.
- Kamba, N., H. Wada, M. Tsukada, Y. Takagi, and K. Imakita. 2008. "Measurement and Analysis of the Global Transport Environment for Packing Cases for Artifacts." In *Conservation and Access: Contributions to the London Congress, 15–19 September 2008*, ed. D. Saunders, J. H. Townsend, and S. Woodcock, pp. 60–63. London: International Institute for Conservation of Historic and Artistic Works.
- Kollmann, F. 1951. *Technologie des Holzes und der Holzwerkstoffe* [Wood technology and wood materials]. 2nd ed. Volume 2. Berlin: Springer-Verlag.
- Mecklenburg, M. F., and C. S. Tumosa. 1991. "Mechanical Behavior of Paintings Subjected to Changes in Temperature and Relative Humidity." In *Art in Transit*, ed. M. F. Mecklenburg, pp. 173–216. Washington, D.C.: National Gallery of Art.
- Michalski, S. 1991. "Paintings – Their Response to Temperature, Relative Humidity, Shock and Vibration." In *Art in Transit*, ed. M. F. Mecklenburg, pp. 223–249. Washington, D.C.: National Gallery of Art.
- Nakajima, T., K. Tsuda, K. Kawata, and Y. Yamauchi. 2007. Hirochikuseki hyokagata shindoshikensisutemu no teian [Vibration test system using accumulated fatigue index]. *Journal of Packaging Science and Technology*, 16(1):41–51.
- Saunders, D. 1998. Monitoring Shock and Vibration during the Transportation of Paintings. *National Gallery Technical Bulletin*, 19:64–73.
- Vibration Research Corp. 2017. Random Testing. Vibration Research University. <https://vru.vibrationresearch.com/course/random-testing/> (accessed 28 May 2019).
- Wada, H., N. Kamba, H. Kaneko, and S. Maruyama. 2010. "Ashuraryuzo konpobako no bouhin koka" [Effectiveness of vibrational insulation of the packing case for a wooden sculpture such as Ashura]. In *Preprints of the 32nd Congress of the Japan Society for the Conservation of Cultural Property*, pp. 26–27. Japan Society for the Conservation of Cultural Property, Gifu, Japan.

Low-Energy Museum Storage

Poul Klenz Larsen^{1} and Morten Ryhl-Svendsen²*

ABSTRACT. The energy needed for climate control in a museum storage building can be greatly reduced by allowing a moderate annual temperature cycle. The energy saving is achieved partly by abandoning heating or cooling and partly by a less strict humidity control. Temperature moderation can be provided by the building itself. The proposed system is a highly thermally insulated building envelope with an uninsulated floor directly on the ground. The inside temperature is allowed to vary freely, buffered by the large heat store of the ground. Such a structure will completely even out the daily temperature variation and reduce the annual temperature amplitude to about half the average outside cycle. In a northern European temperate climate, the inside temperature will span less than 10°C. The relative humidity is buffered by hygroscopic materials or controlled by mechanical dehumidification. This climate control strategy relies on an almost airtight building with an air exchange rate of less than one air change per day and consumes annually as little as 1 kWh per cubic meter space. Relative humidity is easily controlled within the 40%–60% range, which is acceptable for most materials and conforms to all standards. Mechanical failure caused by this temperature variation is unlikely for most objects. However, some standards propose contradictory temperature limits. The reason might be due to recommendations that are intended for both storage and exhibition spaces, whereas temperature constancy is mainly for the benefit of human comfort and should be implemented only in permanently occupied buildings.

INTRODUCTION

This paper presents a generic model for museum and archive storage with very low energy consumption. The principle is being applied in two different locations, Ribe, Denmark, and Washington, D.C., but is suitable for any temperate climate zone. The main difference between this simple approach to climate control and conventional air conditioning is that the inside temperature is allowed to follow the outside annual cycle. The humidity control takes advantage of the weather pattern and combines humidity buffering with either winter heating or summer dehumidification. The building structure is designed to provide moderate variations in temperature and relative humidity, which calls for unusual but less expensive solutions. Orthodox air conditioning is not needed, as the described climate control system is simple to install and cheap to operate. The simplicity of the mechanical equipment affords better security against climatic failure than highly sophisticated machinery.

Unfortunately, the most influential environmental advice for museums is incompatible with the most economical climate control system. The latest version of the former British Standard 5454, now a “published document” (PD 5454), recommends 13°C–20°C for mixed archives (British Standards Institution [BSI], 2012), and the American Society of Heating, Refrigerating and Air-Conditioning Engineers (ASHRAE) guidelines for museums, galleries, archives, and libraries suggest

¹ Department of Conservation and Natural Sciences, National Museum of Denmark, Brede, 2800 Kongens Lyngby, Denmark.

² School of Conservation, Schools of Architecture, Design and Conservation, Royal Danish Academy of Fine Arts, Esplanaden 34, 1263 Copenhagen K, Denmark.

* Correspondence: poul.klenz.larsen@natmus.dk

Manuscript received 2 June 2018; accepted 7 May 2019.

15°C–25°C for class A control (ASHRAE, 2015). This temperature range was also adopted by the joint declaration by the International Institute for Conservation of Historic and Artistic Works (IIC) and International Council of Museums–Committee for Conservation on environmental guidelines (IIC, 2014). However, the lower limit, 13°C–15°C, cannot be maintained by buildings that follow the annual average temperature.

If the standards are rigidly imposed, these limits will prevent the implementation of the simplest and cheapest temperature control in museum and archive storage. However, scientific studies of the degradation of materials provide slender evidence that these temperature ranges are justified. Broader impacts can affect historic structures where upgrading may be restricted.

CONSERVATION CONSIDERATIONS

CHEMICAL DEGRADATION

A large number of reactions leading to the decay of museum objects belong in the general category called hydrolysis: the addition of water to a polymer, resulting in the breaking of the polymer chain molecule. The rate of decay increases exponentially with rising temperatures. The water required for the hydrolysis reactions is provided by the relative humidity (RH), and its potential to engage in chemical reactions—the so-called water activity—is directly proportional to the RH.

The effects of temperature and relative humidity were elegantly combined by Sebera (1994) into curves of equal degradation rate, which he called isoperms. The diagram in Figure 1 shows the curves of equal degradation rate relative to a constant climate at 20°C and 50% RH, which is set to 1. It is evident that at a moderate relative humidity level, temperature is the dominant factor. Superimposed on the diagram are the climate ranges proposed by PD 5454 (BSI, 2012) and by ASHRAE (2015) class A. The blue oval representing a dehumidified indoor climate reflects the climate range in the purpose-built, low-energy storage building in Ribe, which will be described later. This store does not comply with the recommendations, yet the chemical durability of the collection is better because of the lower winter temperature.

The Sebera diagram relates widely to organic reactions but not to ionic and crystal rearrangement reactions, such as phase transformations. These reactions are both temperature and humidity sensitive in a way that depends on the individual chemical species. Furthermore, widespread inorganic salts on the surface of objects will deliquesce at high relative humidity, providing a thin surface film of aqueous solution, which facilitates ionic corrosion reactions. The tendency of separation of components, such as plasticizers, increases at low temperature (Shashoua, 2008), but their diffusion rate also diminishes, so cooling usually favors durability. The

FIGURE 1. The Sebera isperm diagram showing curves of equal chemical reaction rate relative to the rate at 20°C and 50% RH. The relative reaction rate is marked on each curve. The curves are calculated for an activation energy of 100 kJ. The preservative effect of low temperature is evident, but low relative humidity only really gives improved durability when it is very low, at a value that would cause serious mechanical stresses to the many laminated and jointed hygroscopic objects in museum collections. The climate envelopes for PD 5454 (BSI, 2012) and ASHRAE (2015) class A and two low-energy climate-control principles are superimposed on the diagram.

history of good preservation of movie film in cold storage demonstrates this.

MECHANICAL DEGRADATION

Mechanical damage caused by too high or too low temperature is a source of worry for many conservators. A variety of materials have the capability of losing flexibility, that is, an increase in rigidity, when temperature decreases. Therefore, for objects made of very soft materials, such as wax or grease, storing at a cool temperature is critical for their conservation. This avoids deformation, which might otherwise occur on a warm summer day. Similarly, in cool conditions, dust will be less adherent to the surface of the materials, and soiling will be minimized.

For polymeric materials, the transition to the glassy state occurs at different temperatures for different materials. Below this so-called glass transition temperature (T_g), the material becomes more brittle and will crack more easily than at a higher temperature. However, cold storage is still recommended for the optimal conservation of most plastic objects, regardless of

the risk of rigidity, as the gain in chemical stability far outweighs the physical disadvantages (Shashoua, 2008).

It must be emphasized that damage following the increased stiffness at decreasing temperature is only a problem in combination with physical impacts (sudden shock, rough handling, etc.). There is no mechanical implication for objects that are simply stored at cool temperatures, even well below their glass transition temperature. Delamination issues when materials with different dimensional change upon cooling react with each other become a real problem only well below 0°C.

Paints are among the materials that are susceptible to damage at low temperature, especially when adhered to a support, such as canvas, which allows flexing by physical impact. For oil paint, T_g is below 0°C. For acrylic paints, T_g is typically between 5°C and 10°C (Michalski, 1991; Mecklenburg, 2007).

For a large, mixed collection, there will always be a few objects with special climate requirements that are not fulfilled by the conditions maintained in a general storage environment. Most often, these materials require a relative humidity diverging from normal room conditions (e.g., rusty iron, which must be kept very dry). Acrylic paint with zinc white is another such material; it becomes very stiff and delaminates easily at low temperature, as reported by Mecklenburg (2007). For such particularly fragile objects, alternative storage solutions must be found if, for example, the general storage conditions allow for a winter temperature below T_g of a component. Still, temperature has little significance with regard to mechanical damage to such objects during normal and professional handling of the general collection.

BIOLOGICAL DEGRADATION

Biological activity is mainly controlled by keeping relative humidity below about 60%. This level will prevent breeding of most insects and germination of most species of mold. An additional benefit of a cold environment is the inactivity of most insects at temperatures below about 10°C. The development of mold and fungus is also prevented by low temperatures.

TEMPERATURE CONTROL

Our starting point is typical northern European weather. There are two superimposed cycles: the annual cycle, which ranges from an average of -5°C in winter to 20°C in summer, and the daily cycle, which may span over 15°C. There are two ways to moderate the daily cycle inside a building. One is to increase the heat capacity of the wall. This does not impede heat flow, but concrete or brick absorbs heat, so it does not reach the inner space. High thermal mass is advocated in the standards and guidelines for museum storage, notably

PD 5454 (BSI, 2012). However, it is not necessary because the same damping of the daily cycle can be attained by lightweight thermal insulation. The difference is that the heat flow into the wall is much smaller, and less heat is absorbed by the structure. Dampening the annual cycle by absorbing the heat flow in the same way as for the daily cycle would require much thicker walls, of about 4 m. The necessary thickness of an insulated wall could be reduced, depending on the heat capacity of the stored collection. A cheaper solution combines thermal inertia with insulation, using the ground beneath the building as a heat store, combined with thermal insulation of the superstructure (Bøhm and Ryhl-Svendsen, 2011; Ryhl-Svendsen et al., 2011).

The museum storage building in Ribe has insulated walls and ceiling but an uninsulated floor, placed directly on the ground. Its floor dimension is 24 × 45 m, and the undivided interior space is 6.3 m high. It was described in detail by Ryhl-Svendsen et al. (2011, 2012a), and a detail from the storage hall can be seen in Figure 2. The measured temperature inside and outside the building is shown in Figure 3. The 8°C annual temperature cycle amplitude is an easily attainable moderation of the outside temperature. One could achieve a smaller amplitude, but that would make humidity control more expensive, as discussed later. The floor functions as an effective cooling surface in summer, but the temperature difference between the floor and ceiling is rarely more than 2°C, corresponding to a 6% difference in relative humidity. There is no need to insulate the area beneath the perimeter of the building. The edge effects are small, and after a few years of operation, the ground beneath the building becomes, thermally, part of the building (Figure 4).

RELATIVE HUMIDITY CONTROL

DEHUMIDIFICATION

The relative humidity arising from the diminished annual temperature cycle acting on the slowly infiltrating air will be moderate in winter because of the higher than ambient temperature. At the Ribe storage site, the temperature buffering from the ground gives a winter temperature sufficiently above ambient temperature that it holds the relative humidity above 45% (Figure 5). The water vapor concentration balance is almost even during the period from December to March. However, during the summer, dehumidification is necessary because the indoor temperature is well below the ambient one, so the relative humidity would rise to 100% with no intervention. The relative humidity could be reduced by allowing more direct solar heating of the building through the roof. But the advantage of maintaining a lower temperature is improved collection durability, and a better use of solar energy is running the dehumidifiers, rather than direct heating (Ryhl-Svendsen et al., 2013). As shown in Figure 5,

FIGURE 2. A section of the compact shelving inside the Ribe storage building. The height is about 6 m. Objects made from wood, textile, cardboard, and other hygroscopic materials are present in large quantities.

the dehumidifiers use energy almost only in summer, when solar power is abundant. If a building is airtight, the dehumidification load is very small, and sufficient power can be provided by solar voltaic panels on the roof (see Energy Considerations).

HUMIDITY BUFFERING

Hygroscopic materials absorb and release water vapor as the ambient relative humidity changes. The relative humidity can be moderated by an abundance of hygroscopic materials within a confined space. Humidity buffering has long been used in small enclosures such as showcases and transport crates. The same principle can be applied to an entire building, provided the air infiltration rate is low. It is also important that the buffer be cheap and easily accessible because of the

FIGURE 3. The temperatures measured in the Ribe storage building. The inside temperature cycle is reduced to an 8°C amplitude by temperature buffering from the floor. The graph also shows the very small variation in temperature with height inside the storage room. The filled trace shows the maximum temperature difference within the building. Even in summer, when warm air would be expected to accumulate at the ceiling, there is less than 3°C temperature difference between the floor and the ceiling 6 m above. The gray trace is the outside temperature.

FIGURE 4. The temperature distribution under the uninsulated floor at the center of the Ribe storage building after several years, compared with the temperature at various depths as well as of the surface of the nearby open field.

large quantities needed. Fortunately, many museum storage sites contain so much cellulosic material, as paper records and cardboard containers, that the collection itself may provide sufficient humidity buffering. Otherwise, clay plaster or a wall lining of unfired brick will offer the same effect.

Padfield and Jensen (2011) studied the quantification of this effect in a dynamic situation. In that study, the sorption of water vapor by a test surface was continuously measured during a regular relative humidity cycle. The vapor absorbed by 1 m² of exposed surface on the upward swing of the relative

FIGURE 5. Climate data acquired at the Ribe storage site. The relative humidity is kept close to the 50% target by only dehumidification. In winter, the relative humidity dips below this value; in summer it rises above it because of the slightly underdimensioned dehumidifier. The energy consumption for dehumidification is shown below in the diagram.

humidity was recalculated to the equivalent volume of space, which will experience the same change in relative humidity with the same injection of water vapor as that taken up by the absorbent material. This equivalent volume will depend on the time required for a relative humidity cycle because of the slow diffusion within the material. A textured clay wall plaster, for example, has a buffer value (B value) of about 100 for a four-day cycle of relative humidity. This means that 1 m² of wall has a sorptive capacity similar to 100 m³ of space. When all the absorbent surface B values are summed up this way, the building will have a virtual volume many times its actual volume. This number is then divided by the actual room volume. For museum storage, with mostly metal objects and little absorbent material, this “virtual volume ratio” may be about 10 or lower. A building such as the Ribe storage, containing a large number of hygroscopic objects and wall lining, could have a virtual volume ratio around 50. For an archive filled with paper, the ratio can be on the order of several hundred to 1,000 times the actual room volume.

A theoretical model of the course of the relative humidity at the Ribe storage site is shown in Figure 6. The model shows several scenarios with increasing humidity buffer capacity. What is important to note, however, is that no matter the amount of buffer available, the relative humidity increases with time toward the average value outside, which in Denmark is near 80%. For this reason dehumidification is necessary.

BUFFERED CONSERVATION HEATING

If a low winter temperature is not acceptable, climate control can be achieved by moderate winter heating. This periodic heating will also increase the summer temperature,

FIGURE 6. A theoretical model of the course of the relative humidity at the Ribe storage site, starting from an arbitrary 50% RH. The trace marked $B=1$ shows the RH in a space with no moisture-absorbent materials (inert room), given an air exchange rate of 0.03 per hour. It reaches 100% in summer when the outside air is warmer than inside. The other traces show the moderating effect of humidity buffer capacity illustrated by an increasing virtual room ratio (B). Note the general upward trend of RH with time, indicating the need for dehumidification.

as the ground below the building gradually equilibrates over several years to the higher average indoor temperature. However, the temperature will remain quite moderate; for example, in Denmark it will always be below ~22°C. The relative humidity will stabilize at an average value around 55% with an annual cycle, which depends on the humidity buffer value.

A virtual volume ratio over 50 is needed to avoid a disturbingly high relative humidity in summer, when the outside temperature is often higher than inside. A virtual volume ratio of 1,000 is achievable in storage areas containing paper and cardboard boxes filled to capacity. This gives a very stable relative humidity, with an annual cycle within a 5% envelope, better than can usually be achieved by air conditioning and well within all museum standards. The relative humidity need not be measured constantly and is never directly controlled. The winter heating alone defines the annual average relative humidity. Thermostats are more reliable than relative humidity sensors and the associated computer-controlled air conditioning. We call this method of climate control “buffered conservation heating” by analogy with the gentle winter heating used to keep moderate relative humidity in historic buildings that are closed in winter (see also Figure 1).

VENTILATION AND AIR QUALITY

Museum storage sites and archives are not intended for permanent occupation by people. Workshops and offices should never be located together with the collections. There

is little need for ventilation to provide for human health and comfort in a storage building. The intake of outside air should be limited as much as possible to keep away external pollutants and to minimize climatic disturbance. The Ribe storage site has an air exchange rate of 0.03 room volume per hour throughout the year. The outside air mainly enters through the door when objects are moved in and out. There is no mechanical air intake, and the building is very airtight. The outgassing of components from the collection or from the building itself may reach high concentrations due to the low ventilation rate. It is partly prevented by the proper choice of inert materials and finishes for the building and the storage shelving. Wooden construction materials should be avoided because of the emission of corrosive volatile compounds, especially acetic acid. However, the collection itself may be another source of contaminants, and these can be removed by air filtration through a recirculating system. In addition, some interior finishes, such as the clay material previously mentioned with regard to humidity buffering, also provide some control by passive sorption of pollutants (Ryhl-Svendsen and Clausen, 2009; Ryhl-Svendsen, 2011). Measurements in the Ribe storage building and other Danish low-energy museum storage sites have revealed lower than expected concentrations of indoor pollutants. We attribute this to the mostly cool temperature inside those buildings, which slows down the off-gassing from materials, yet another benefit of maintaining an unheated environment. The museum guidelines and standards are usually vague on advice about safe levels for indoor air pollutants. Especially for paper-based collections, the cost and effort of air filtration have been questioned from a cost-benefit perspective (Di Pietro et al., 2016). The issues related to air quality control in low-energy buildings still pose many unanswered questions.

A special problem exists for collections that have previously been treated with organic insecticides. They must be cleaned before they are stored at a low ventilation rate in order to minimize the potential reevaporation of insecticides into the air. In such cases, health regulations may require constant ventilation, which will make low-energy storage impossible. This is a problem that poses big challenges and deserves attention in future research and innovation.

ENERGY CONSIDERATIONS

The energy used by heating to moderate the relative humidity depends on the heat transmission through the walls and ceiling of the building. The heat loss to the ground will diminish as the years pass. The energy used by dehumidification depends entirely on the humidity of the outdoor air and the air exchange rate, which can be reduced to below one air change per day in modern buildings with simple geometry. The power consumed by the Ribe storage site dehumidification is 1.5 kWh per year for each cubic meter of storage space.

FIGURE 7. The link between the chemical reaction rate within a storage environment and the energy used for climate control. The reaction rate is normalized to that of 20°C and 50% RH, following the approach of Sebera (1994). All data points refer to places described in Ryhl-Svendsen et al. (2012a) and are comparable in the sense that they are located above ground in a Danish temperate climate but differ in the construction of the building envelope and climate control systems. The point next to the asterisk (*) is the Ribe storage site. Green data points represent unheated and dehumidified buildings. Blue points are conservation heated in winter, and red points are buildings with various degrees of air conditioning. The white point shows the reaction rate for unheated outdoor air, conditioned to 50% RH, assuming complete airtightness of a building.

Other Danish storage facilities perform even better. The energy consumption of several storage buildings in Denmark is shown in Figure 7 and compared to conservation quality in terms of chemical reaction rate (Ryhl-Svendsen et al., 2012a). There is a correlation between low energy consumption and good preservation, as predicted by the Sebera diagram. The linked reduction in cost and improvement in object durability is mainly attributable to allowing an annual variation in temperature.

The principles of low-energy climate control do not need a constant feed of energy. The buildings will cruise over temporary interruptions in supply without noticeable deterioration in their interior conditions. This makes them ideally suited to solar energy or wind power, which is naturally variable. In the case of a building the size of the Ribe storage site, having about 5% of the roof covered with solar panels will provide the necessary energy for dehumidification, which is mostly needed in summer (Ryhl-Svendsen et al., 2011, 2013). A small wind turbine will give enough power for conservation heating in winter. This gives

an opportunity to run a museum storage site or an archive entirely without external energy supply.

A STORAGE BUILDING MODEL: WASHINGTON, D.C.

The outside climate defines the inside climate of a building. This fact must be considered when the model is applied to a location with a natural climate different from that in Denmark. There are two ways to predict the inside climate and the need for supplementary climate control. One is by computer modeling of the building's hygrothermal performance, as presented in Figure 6 for the Ribe storage building. Previously, we demonstrated a similar model for a storage building in Canberra, Australia (Ryhl-Svendsen et al., 2012b). A simpler approach is by considering the monthly average of the outdoor climate. An example from Washington, D.C., is given in Figure 8 (EnergyPlus, 2016). The monthly average temperature ranges from 1°C in winter to 27°C in summer. The daily maximum and minimum temperatures can be far different from these values, but these extremes will not affect the interior conditions. The minimum and maximum temperatures inside a storage building, similar to that in the Ribe facility, are determined by reducing the amplitude of the outside average cycle by half. This will give an annual temperature span of 13°C, ranging from 9°C in winter to 22°C

in summer. The temperature is offset by 2°C from the annual average because of the heat gain from the sun and internal loads such as electric light.

The resulting average indoor relative humidity for each month is calculated with this new temperature, assuming the same moisture content of the air as for outdoors. In Figure 8, this is shown graphically by the dew point lines. Without any control, the relative humidity will be in the range of 30%–90%. With a good humidity buffer, it will be possible to keep the relative humidity between 50% and 80%. Dehumidification is needed to keep the relative humidity below 60%, but only from May to October. As for the case of the Ribe building, it can be powered entirely by photovoltaic elements on the roof of the building. Such a museum storage or archive will work with little energy consumption and is therefore quite safe and sustainable. It will also be resilient to global climate change, but the temperature and humidity levels may be slightly altered according to the ambient conditions.

CONCLUSIONS

We presented an alternative way of building museum storage to minimize energy cost and mechanical complexity without compromising the longevity of the collection, as expressed by the relative rate of organic hydrolysis reactions, risk of physical damage, or biological attack. The essential change from previous practice is to allow an annual cycle of temperature that exceeds the limits given by most recommendations. The amplitude of this cycle is limited by using a highly insulated building envelope and an uninsulated floor as a heat store. The relatively high winter temperature then gives a moderate relative humidity without mechanical aid. During the summer, dehumidification is needed in humid temperate climates such as northern Europe that have a high relative humidity throughout the year. For collections that cannot endure low temperature, buffered conservation heating can be used to moderate the relative humidity. A large humidity buffer capacity is then needed to hold down the increase in summer relative humidity. In drier locations humidity buffering by the building or the collection will keep the relative humidity moderate all year.

In northern Europe, the typical temperature cycle for an unheated but dehumidified store will be 8°C to 16°C; for a winter-heated store, it will be 14°C to 23°C. In other parts of the world with a temperate climate, for example, Washington, D.C., the temperature will be different but still acceptable for most objects. Neither of these temperature ranges conforms to PD 5454 or ASHRAE class A. At present, the limits are set at apparently arbitrary, precautionary numbers, without consideration for the energy cost and the complexity of the air conditioning. There is no doubt that the temperature variation, which we advocate, touches upon or passes through the theoretical phase changes of some materials found in mixed

FIGURE 8. The predicted climate inside a Ribe-type store when located in Washington, D.C. The statistic climate data for the monthly average of the outside temperature and humidity is shown in black (EnergyPlus, 2016). The temperature-buffered store is marked in red, and the humidity-buffered store is marked in green.

collections. However, does preventing the possibility of phase change warrant the tenfold penalty in energy costs and the considerable complexity of air conditioning?

ACKNOWLEDGMENTS

This paper has been compiled from contributions over many years by Poul Klensz Larsen, Morten Ryhl-Svendsen, Lars Aasbjerg Jensen, Tim Padfield, and Benny Bøhm. Tim Padfield prepared several of the figures. This work was financed by a Danish government scheme (UMTS funds) managed by the Danish Ministry of Culture.

REFERENCES

- American Society of Heating, Refrigerating and Air-Conditioning Engineers (ASHRAE). 2015. "Museums, Galleries, Archives, and Libraries." In *ASHRAE Handbook—HVAC Applications* pp. 23.1–23.22. Atlanta, Ga.: American Society of Heating, Refrigerating and Air-Conditioning Engineers.
- Bøhm, B., and M. Ryhl-Svendsen. 2011. Analysis of the Thermal Conditions in an Unheated Museum Store in a Temperate Climate. On the Thermal Interaction of Earth and Store. *Energy and Buildings*, 43:3337–3342.
- British Standards Institution (BSI). 2012. Guide for the Storage and Exhibition of Archival Materials. PD 5454:2012. London: British Standards Institution.
- Di Pietro, G., F. Ligterink, H. Porck, and G. de Bruin. 2016. Chemical Air Filtration in Archives and Libraries Reconsidered. *Studies in Conservation*, 61:245–254.
- EnergyPlus. 2016. Climate File: Arlington-Ronald Reagan Washington Natl AP 724050. Weather Data. U.S. Department of Energy. <https://energyplus.net/weather> (accessed 25 August 2016).
- International Institute for Conservation of Historic and Artistic Works (IIC). 2014. IIC Announces Declaration on Environmental Guidelines. <https://www.iiconservation.org/node/5168/> (accessed 25 August 2016).
- Mecklenburg, M. F. 2007. Determining the Acceptable Ranges of Relative Humidity and Temperature in Museums and Galleries: Part 2, Structural Response to Temperature. Internal Report. Suitland, Md.: Museum Conservation Institute. <https://repository.si.edu/handle/10088/7055> (accessed 1 August 2019).
- Michalski, S. 1991. "Paintings – Their Response to Temperature, Relative Humidity, Shock, and Vibration." In *Art in Transit: Studies in the Transportation of Paintings*, ed. M. F. Mecklenburg, pp. 223–248. Washington, D.C.: National Gallery of Art.
- Padfield, T., and L. A. Jensen. 2011. "Humidity Buffering of Building Interiors by Absorbent Materials." In *Proceedings of the 9th Nordic Symposium on Building Physics (NBP 2011)*, ed. J. Vinha, J. Piironen, and K. Salminen, pp. 475–482. Tampere, Finland: Tampere University Press. http://www.conservationsphysics.org/ppubs/humidity_buffering_building_interiors_nsb2011.pdf (accessed 25 August 2016).
- Ryhl-Svendsen, M. 2011. "Passive Sorption of Organic Compounds on Clay Bricks." In *Indoor Air 2011, 12th International Conference on Indoor Air Quality and Climate*, ed. R. Corsi and G. Morrison, Paper 383. Austin, Tex.: International Society of Indoor Air Quality and Climate. CD-ROM.
- Ryhl-Svendsen, M., and G. Clausen. 2009. The Effect of Ventilation, Filtration and Passive Sorption on Indoor Air Quality in Museum Storage Rooms. *Studies in Conservation*, 54:35–48.
- Ryhl-Svendsen, M., L. A. Jensen, B. Bøhm, and P. K. Larsen. 2012a. *Low-Energy Museum Storage Buildings: Climate, Energy Consumption, and Air Quality. UMTS Research Project 2007–2011: Final Data Report*. Kongens Lyngby: National Museum of Denmark.
- Ryhl-Svendsen, M., L. A. Jensen, P. K. Larsen, B. Bøhm, and T. Padfield. 2011. "Ultra-low-Energy Museum Storage." In *ICOM-CC, 16th Triennial Conference, Lisbon, Portugal, 19–23 September 2011: Preprints*, ed. J. Bridgland, pp. 1–8 Paris: ICOM-CC.
- Ryhl-Svendsen, M., L. A. Jensen, P. K. Larsen, B. Bøhm, and T. Padfield. 2013. "A Museum Building Controlled by Solar Energy." In *Climate for Collections: Standards and Uncertainties, 7–9 November 2012*, ed. J. Ashley-Smith, A. Burmester, and M. Eibl, pp. 141–148. Munich: Doerner Institute.
- Ryhl-Svendsen, M., P. K. Larsen, and L. A. Jensen. 2012b. "Ultra-low Energy Buildings for Storage in Museums and Archives." In *Healthy Buildings 2012, 10th International Conference*, ed. L. Morawska, Paper 7G.2. Brisbane, Australia: Queensland University of Technology. CD-ROM
- Sebera, D. 1994. *Isoperms: An Environmental Management Tool*. Washington, D.C.: Commission on Preservation and Access. <http://cool.conservations-us.org/byauth/sebera/isoperm/> (accessed 25 August 2016).
- Shashoua, Y. 2008. *Conservation of Plastics: Materials Science, Degradation and Preservation*. Oxford: Butterworth-Heinemann.

The Role of Micromechanics in the Epidemiology of Climate-Induced Damage

Michał Łukomski,^{1} James Druzik,¹ Vincent Beltran,¹
Ashley Freeman,¹ Foekje Boersma,² and Joel Taylor¹*

ABSTRACT. Environmental standards for cultural heritage collections have become one of heritage conservation's most discussed and controversial topics in recent years. Although not universally accepted, there has been growing agreement that museum collections can sustain greater variations in relative humidity and temperature than previously recommended.

However, broadening the variations in indoor climate has to be informed by a sound understanding of the way change affects real objects. This paper explores how epidemiology can be applied to cultural heritage to better understand the presence, or absence, of climate-induced damage, using statistical data of variable quality and credibility. The main focus of this paper is the application of micro- and nanoengineering techniques to better understand the mechanical properties of cultural materials and their interaction. Application of such techniques opens a new perspective for characterizing submillimeter samples taken from real works of art. Systematic measurements of acrylic paint samples at the micro- and nanoscales were performed to evaluate the influence of sample size, compliance of the embedding resin (edge effect), and sample polishing and cleaning procedures on the sample. Mechanical parameters such as reduced modulus and hardness were obtained for paint cross sections and compared with results obtained with nonembedded material. Those tests clearly demonstrate the feasibility for the routine application of micro- and nanoindentation techniques to characterize preexisting cross-sectional samples of historic paints, binding media, and polymer coatings and films and, consequently, improve our understanding of risk of damage caused by unstable climatic conditions for real works of art.

INTRODUCTION

Reviewing environmental standards for display or storage of cultural heritage collections has been much debated in the past decade. The foundation of this debate is well illustrated by the transcriptions of two roundtables of the International Institute for Conservation of Historic and Artistic Works (IIC): "Climate Change and Museum Collections" (IIC, 2008) and "The Plus/Minus Dilemma: The Way Forward in Environmental Guidelines" (IIC, 2010). Both generally conclude that managing indoor environments in a responsible manner, especially in terms of reducing energy consumption and carbon emissions, is a necessity in a world facing climate and energy threats. The fact that broadening the acceptable range of climate fluctuations can help reduce energy consumption and make museums more sustainable was thoroughly discussed and practically demonstrated (Artigas, 2007; Łukomski et al., 2013). Also, the growing debate that museum collections can sustain greater variations in relative humidity (RH) and temperature (T) than previously recommended was reflected in the Bizot Green Protocol (Bizot

¹ Getty Conservation Institute, 1200 Getty Center Drive, Suite 700, Los Angeles, California 90049-1681, USA.

² KB, National Library of the Netherlands, Prins Willem-Alexanderhof 5, 2595 BE, The Hague, Netherlands

* Correspondence: mlukomski@getty.edu

Manuscript received 2 June 2018; accepted 7 May 2019.

Group, 2015) and the joint IIC and International Council of Museums–Committee for Conservation (ICOM-CC) declaration (IIC and ICOM-CC, 2014). Both documents underline, however, the difficulties in developing strategies for optimum protection of museum collections, resulting from insufficient knowledge of how environmental conditions influence real objects. Elucidating damage mechanisms and determining environmental conditions that cause damage are therefore essential for defining long-term strategies for the preservation of collections.

Because of the great importance of the issue for the whole museum community, the problem has been addressed by numerous national and international research projects (e.g., Friendly Heating, Noah's Ark, and Climate4Wood). This work has resulted in a range of publications and reports describing the presence, or absence, of climate-induced damage for particular objects, groups of objects, or whole collections. The amount of existing information is extensive, but to help develop general recommendations for collections, these observations need to be interpreted using sound methodologies capable of dealing with statistical data of variable quality and credibility.

In this paper, we present how the extent and variability of existing information make it possible to use an epidemiological approach to develop rational guidelines for collection environments. However, unknown or limited information about the quality of evidence and the lack of sound information about the mechanical properties of historic materials are the critical gaps, which can limit the effective application of an epidemiological methodology. Both can be addressed by laboratory studies. The possibility of routine mechanical characterization of historic materials using the nanoindentation technique will be discussed in detail.

EPIDEMIOLOGY

Epidemiology is a branch of medical science that deals with the incidence, distribution, and control of disease in a population. It has proven to be a very effective, and broadly accepted, tool for population-based health management, enabling societies to assess the health states and needs of a target population and implement and evaluate medical interventions. The effectiveness of epidemiology is based on rigorous methodology capable of providing sound results for a group of very diverse members subjected to poorly defined or unknown stresses.

Applied to cultural heritage, epidemiology can identify how a physical condition or environmentally derived adverse effect is distributed in museum collections (diverse objects with often unknown history). Thus, it may be used to develop rational guidelines for collection environments by identifying safe indoor recommendations with respect to *T* and RH fluctuations.

In epidemiology, the quality of evidence is very important: how strong is an association, and does it rise to the level of convincing causation? The standard model for ranking the quality of evidence within epidemiology has favored some version of the pyramidal structure shown in Figure 1. It builds from general background information up through basic study designs into critically appraised articles; validated predictive models, including web-based tools; and finally, systematic reviews, including metastudies. These all build upon the evidence to demonstrate and, ultimately, prove causality. If the conservation field were to apply this epidemiological approach, more systematic studies with a known quality of evidence would be needed. This concept has been addressed in previous papers (Koestler et al., 1994; Suenson-Taylor et al., 1999).

There have been several epidemiological studies in the cultural heritage field. In an excellent example of a retrospective cohort study, a group of 34 deteriorated books from the New York Public Library was compared with duplicates supplied by other libraries from around the United States to show the effects of urban air pollution on paper (Kimberly and Emley, 1933). Similar, although less convincing, was an approach applied to analyzing the relationship between heating energy and cumulative damage to painted wood in historic churches (Melin and Legner, 2014) and, recently, to a wooden furniture collection (Ekelund et al., 2014). Suzanne Keene's assessment treatment study for archaeological iron (1983–2003) follows an explicit epidemiological design employing survival probability and life tables (Keene, 1994).

The biggest challenge present in the above-mentioned studies is related to the quality of recorded evidence with respect to sample statistics and accuracy of observations. Sampling quantities in epidemiology require some reasonable

FIGURE 1. Pyramidal structure ranking the quality of evidence within an epidemiological study in cultural heritage research. Adapted from Hugel (2013).

estimate of the results for what is to be measured in advance. Estimation of a sample size for studies based on the comparison of groups of objects exposed to different conditions requires one to predefine five conditions (Gordis, 2014). The first condition ensures that one must be able to estimate the difference in the response rates of the groups that are being measured, whereas the second condition ensures that an estimate of one of the groups is possible. After those two conditions are fulfilled, then one should be able to specify the appropriate level of statistical significance. In the third condition, the α or p value is set to 0.05, meaning that there is only a 1 in 20 chance that the two comparison groups do not statistically represent the populations from which they are drawn. This condition also reduces the probability for making a type I error, that is, missing a statistically valid result predicted by the hypothesis being tested. The fourth condition, $1 - \beta$, sets the mark high for avoiding a type II error, that is, deriving a false-positive result or thinking that a benefit exists when it really does not. The fifth condition tests equally for both positive and negative effects, that is, whether a one-sided or two-sided test is going to be performed.

With the use of standard commercial and publicly available computational techniques, it is possible to evaluate the appropriate sample size, as represented in Figure 2 using OpenEpi software (Dean et al., 2013). It is assumed that

one cohort group of wooden objects will serve as the control ($50\% \pm 5\%$ RH) and the other is allowed to vary through the largest possible ranges of observable change, plotted as a percentage of the group. This might correspond to a similar range of RH variation. It is also assumed that there is adequate time for full response by all hygroscopic objects. The statistical value for α , or the more commonly known p value, was set to 0.05. The power, $1 - \beta$, was set to 0.80, and we tested for two-sidedness. Results presented in Figure 2 show that, keeping the control group unchanged, if only 1% of the collection were to show a measurable adverse effect, the number of samples in each group would have to be in the thousands, which is practically impossible to analyze. But as the response difference between the two groups grew larger (as the noncontrol group was exposed to a more extreme condition), the number of required samples per group (to meet our statistical criteria) grew smaller. Our calculations were based upon the percentage of expected collection response and not the percent RH fluctuation, but they share a similarity in their numerical values. The primary x axis in Figure 2 is the percentage of exposed collection with a measurable change, but a secondary axis was added at the top representing the difference in RH fluctuation extremes between the collections to make the important point that sample numbers drop quickly as the percentage of the collection with measurable adverse effects increased.

FIGURE 2. Number of samples necessary to perform rigorous epidemiological analysis calculated with OpenEpi: $1 - \alpha = 0.95$, $1 - \beta = 0.80$, two-sided. DIC = Digital Image Correlation.

There are ways to reduce sample size. One can make the exposure fluctuations more extreme or decide to populate cohorts with a skewed distribution of those objects thought to represent the most sensitive categories. However, if these two ways are not feasible, then the sensitivity of the assessment technology must be increased to reduce the sample size. Some measuring techniques are listed in Figure 2. Visual observation and ranking are the least sensitive. Simple handheld measurements are a little more precise, followed by conventional photography, computational imaging, and then the most powerful tools of acoustic emission, thermography, and laser speckle interferometry. Combining techniques can increase detection limits to the degree that they each provide unique information. This leads to the conclusion that to be effective, an epidemiological study for a collection of cultural heritage objects requires recording physical features at a high level of accuracy and the precision to reproducibly detect small-scale changes. Within the frame of the Managing Collection Environments Initiative, a research and education program of the Getty Conservation Institute, a pilot study is being conducted to determine the optimum level of precision, from an epidemiological point of view, in documenting the preservation state of objects (Getty Conservation Institute, 2014).

This study combines the application of acoustic emission (AE) monitoring with physical measurements and photographic documentation of various historic, nonmuseum wooden objects subjected to well-controlled environmental stresses. AE has already proven to be an effective nondestructive method of tracing fracture intensity in wooden cultural objects, where stress has been induced by variations in *T* and RH. A proper, quantitative calibration of sensors and an anticorrelation measuring scheme to reduce environmental noise allow AE systems to trace microdamage development in historic objects (Strojecki et al., 2014). Complementary to AE monitoring, measurements of dimensions and crack width and photographic documentation of cracks and paint flaws are carried out. The goal of our pilot study is to establish the reliability and reproducibility of these different methods (with different precisions and accuracies) in recording climate-induced condition changes. This study will contribute to developing protocols that could be applied by institutions in monitoring the preservation state of their collections at the level required by epidemiological methodology.

Although epidemiology is often viewed as a set of statistical tools used to elucidate the associations of exposures to outcomes, a deeper understanding of this methodology is that of discovering causal relationships. Correlation is a necessary but not sufficient criterion for inference of causation. Therefore, when using epidemiological methodology to establish conditions leading to physical damage, it is crucial to understand the mechanical properties of materials and their interactions. This task, easy in many design and engineering applications, poses challenges that are very difficult to

overcome in the cultural heritage field and requires undertaking extraordinary measures.

MECHANICAL CHARACTERIZATION OF ARTISTIC MATERIALS

Conventional methods for measuring the mechanical properties of a material require the destruction of large samples. A typical tensile test specimen for paint and coating research has a width of 1 cm and a length of 10 cm and must be uniform in thickness, whereas samples on the order of several millimeters in length, again with uniform thickness, are suitable for various thermomechanical instrumentations. However, obtaining such samples of historic material in a quantity sufficient for characterizing a range of paint types and the distribution of the aging factor across time is practically impossible. As a result, samples mimicking historic materials (mock-ups of similar composition and manufacture technology) and subjected to accelerated aging at elevated temperature and humidity are generally used to approximate the physical properties of naturally aged artists' materials. Nonetheless, recommendations for exhibition and storage conditions based on the analysis of mock-up samples are often questioned in relation to artificial aging (which does not reflect the complexity of physical and chemical processes) and prepared mock-ups (which do not always mimic the precise composition of the artist's materials).

The use of small-scale engineering techniques, such as micro- and nanoindentation, provide an alternative means of mechanical properties characterization that is suitable for the direct examination of historic samples at the submillimeter scale. Developed in the mid-1970s, nanoindentation has become a well-established technique used for the mechanical characterization of materials (Hay and Pharr, 2000; Van Landingham, 2003). It is particularly well suited in industrial applications where the physical size of samples is predominately small. Standard tests use a probe with a well-defined geometry and are performed by applying, pausing, and then removing a predefined load to the sample. The resulting force-displacement curve serves as the "mechanical fingerprint" of the material, from which quantitative mechanical properties are determined, including the elastic modulus, the elastic-plastic energy ratio, creep, and storage and loss modulus (when measurements are performed in dynamic mode). Furthermore, microscopic observation of the probe imprints allows one to determine the hardness and fracture toughness of the sample. Although most successful for homogeneous, nonviscous media, this technique can also provide useful information about a diverse range of materials. Recently, nanoindentation has been successfully applied in the characterization of historic painting materials, demonstrating its capability of consistent measurements on submillimeter cross-sectional paint samples (Salvant et al.,

2011; Wright et al., 2014). These results signal the potential of nanoindentation to mechanically characterize a wider set of historic materials, which is essential for supporting and furthering conservation practice and the development of predictive models.

In preventive conservation research, micro- and nanoindentation can address two significant gaps in knowledge: the probabilistic distribution of mechanical properties across a typical collection of a certain age, and the aging factor, which alters the mechanical properties of different artists' materials. However, preceding a systematic study of a collection of historic materials, it is first necessary to evaluate how the preparation of cross-sectional samples may influence the measured mechanical properties of the embedded material. In this study, the mechanical properties of the same paint are compared when nanoindentation is applied to two sample preparations: a submillimeter cross section and a free film.

MATERIAL

The material selected for this study was titanium white (TiO_2) acrylic-based paint. Acrylic paints, which consist of a latex binder and a variety of fillers, are a common medium for modern artists. Latex-based paints can be either elastic or viscous, depending on pigment volume concentrations and environmental conditions. The frequent appearance of acrylic paints in collections makes it important to characterize its mechanical properties as a function of temperature and humidity. Thus, this class of material represents a challenging case study for mechanical properties characterization.

Test samples were prepared using TiO_2 acrylic-based paint from Golden Artist Colors with a pigment volume concentration of 0.38 and a particle diameter of 300 nm (Hagan et al., 2009). The free paint film was cast on Mylar in wells defined by multiple layers of 3M Scotch tape. The wells were filled with wet paint and brought level with the tape using a glass slide, resulting in a wet film thickness of 0.46 mm; care was taken to prevent bubbles from appearing in the material. All castings were then dried uncovered in ambient laboratory conditions for at least 30 days. The thickness of dry paint was equal to 0.15 mm. The cross-sectional paint samples were prepared by embedding submillimeter samples of the free film in Technovit 2000 LC resin, which was then cured with UV radiation for ~40 min. Afterward, samples were polished using Micro-Mesh cloths (Scientific Instrument Services) with particle sizes ranging from 30 to 2 μm .

APPARATUS

Nanoscale characterization of paint samples was conducted using an ultra nanoindentation tester from Anton Paar.

This apparatus is capable of performing indentation with a force up to 100 mN and a penetration depth up to 100 μm with a nanoscale resolution and is fixed to a high stiffness frame alongside a micro combi module (microindentation and microscratch testing), an atomic force microscope (Nanosurf Nanite B), and an optical microscope. A sample stage with an XYZ stepping motor allows for automated positioning between the ultra nanoindentation tester and micro combi modules and the imaging units with accuracy sufficient to locate individual indents. The frame and stage are also attached to a vibration-isolating table to lessen the influence from vibration and noise. The overall system (frame with modules, stage, and table) is installed within a climatic chamber that enables analysis in a range of temperature and relative humidity conditions and reduces thermal drift during extended experiments. All presented results were obtained using a diamond Berkovich tip for which reference measurements were performed on a silica standard at 50% RH and 22°C.

The analysis of load-displacement data for each individual indentation process establishes a set of mechanical parameters for the material. Three distinguishing parameters of the loading-unloading curve are the maximum load, the maximum displacement, and the elastic unloading stiffness, which allows one to define the hardness and elastic modulus of the sample. The hardness (H) is defined by the ratio of the maximum load (P_{max}) to the projected contact area (A) made in the test material by the indenter:

$$H = \frac{P_{\text{max}}}{A},$$

where the projected area is directly related to the maximum depth of indentation (Fischer-Cripps, 2009). The reduced elastic modulus (E_r) can be calculated on the basis of the unloading curve using the Oliver-Pharr method (Oliver and Pharr, 1992). The obtained E_r value is related to Young's modulus (E) and Poisson's ratio (ν) of the tested material and the indenter itself (indicated by the subscript i) as follows:

$$\frac{1}{E_r} = \frac{1 - \nu^2}{E} + \frac{1 - \nu_i^2}{E_i}.$$

Since Young's modulus of the indenter (frame and diamond tip) is several orders of magnitude higher than that of the tested material, it is possible to omit the last term in the above equation, simplifying the equation to the following:

$$E_r = E/(1 - \nu^2).$$

Poisson's ratio for the TiO_2 acrylic-based paint was not measured in this study. Other authors report values between 0.35 and 0.5 (Hagan et al., 2011), but to avoid choosing an arbitrary value from this range, the reduced modulus rather than Young's modulus (dependent on Poisson's ratio) was reported when discussing the experimental results. Analysis of the indentation loading-unloading curve also allows assessing the

relative change in the indentation depth when under constant load (C_{IT}). This measure provides information about the creep properties of the test material.

EXPERIMENTAL PROCEDURE

An important step in the study design was the selection and optimization of the measurement protocol. The indentation schema allows for the control of load, displacement, delay time, and cycling. When characterizing material properties, the load control measurement schema is the most common. This schema, however, does not allow for precise control of the maximum indentation depth and, in the case of very shallow indents, may lead to systematic error due to the size effect (Han et al., 2016). An alternative approach is to control displacement, but the pronounced stress relaxation exhibited by both Technovit 2000 LC resin and TiO₂ acrylic-based paint when deformed may lead to imprecise results. The problem is that relaxation at a constant penetration depth leads to a significant reduction of force exerted by the indenter on the material surface and, as a consequence, only a very short retraction curve is available for stiffness calculation.

Specification of the experimental parameters was based on a series of tests performed on embedded paint and free-film paint samples. Since the experiments sought to compare the mechanical properties of different material types, rather than establishing absolute values, the main criterion of the indentation scheme was that the results obtained would be only weakly dependent on the initial parameter values. It is critical to carefully choose the suite of parameters that results in an

FIGURE 3. Schematic representation of the indentation-controlled procedure. A detailed description is provided in the text.

appropriate maximum indentation depth (h_{max}), although this is made difficult by conflicting requirements. Shallow indentations allow for efficient use of the available sample surface and, as a consequence, more statistically accurate results. On the other hand, deeper indentations may be necessary to avoid errors caused by the roughness of the sample surface and surface size effects. To mitigate these issues, a combined load and strain control method was employed (see Figure 3).

The key parameters of the test are rate of displacement (phase 1), depth h_0 (phase 1), length of the pause (phase 2), and probe retraction speed (phase 3). The first part of the curve represents the displacement-controlled indentation with a constant rate of displacement ($\frac{dh}{dt}$) up to a pre-defined indentation depth, h_0 . During the second phase of the experiment, a constant force (equal to that recorded at h_0) is applied to the sample, resulting in h_{max} . Loading in the second phase should be longer than the time constant of creep, allowing for an accurate evaluation of C_{IT} . The third phase is again displacement controlled, with unloading of the sample at a constant speed. This segment of the load-displacement curve is used to calculate the stiffness of the test material. It should be noted that movement of the probe during unloading is slower than during the loading phase to allow for more precise calculations of the slope of the load-displacement curve. A measurement rate of 45 Hz was selected for all phases of this indentation scheme. Measurements of E_r at different h_{max} values are presented for resin and free paint film in Figure 4.

As the E_r of free paint film becomes only weakly dependent on h_{max} values higher than 3 μm , this value was selected

FIGURE 4. Reduced modulus measured for different h_{max} for resin and free paint film. Fitted exponents show trends for both resin and free paint film.

as the optimum maximum indentation depth (Figure 4). When applying this indentation procedure to resin, the resulting $h_{\max}$ of 1.6 μm is almost two times shallower. Although this depth of indentation on resin is too small to measure E_r independent of the indentation depth, the procedure was adopted because the focus of this experiment was a comparison between embedded and nonembedded paint. Tests presented in the next section were performed at 22°C and 50% RH using a Berkovich indenter with the following parameters: a loading strain rate of 0.4 s^{-1} , pause duration of 120 s, and an unloading speed of 1.8 $\mu\text{m}/\text{min}$. The distance between indents within each series of measurements was not smaller than 50 μm .

COMPARISON OF CROSS-SECTIONAL AND FREE-FILM SAMPLES

The aim of the experiment was to explore how nanoindentation can be used to characterize mechanical properties of historic materials in submillimeter samples. It was achieved by comparing the mechanical properties of cross-sectional and free-film TiO_2 acrylic-based paint samples. The free film of paint was self-adhered onto a glass slide and polished using the same procedure used to prepare the surface of the cross-sectional sample. The free-film sample offers a

virtually boundless surface for nanoindentation measurements. Conversely, measurements performed on the submillimeter paint sample embedded in resin may be affected by the proximity to the resin-paint interface. To investigate this phenomenon, a series of measurements at varying distances from the resin-paint edge was performed on the embedded paint sample (Figure 5). Measurements were also performed with two different predefined indentation depths ($h_0 = 1.2$ and 0.7 μm).

Results are summarized in Figures 6 and 7. The first observation was that values of H and E_r recorded in the middle of the cross-sectional sample agreed within statistical uncertainty with those obtained for the free paint film. This agreement remained consistent for both deep ($h_{\max} = 3 \mu\text{m}$ for paint and 1.6 μm for resin) and shallow ($h_{\max} = 1.9 \mu\text{m}$ for paint and 0.9 μm for resin) indentations. Results obtained with the smaller indentation depths have a larger statistical error resulting from similar scales of the indentation depth and surface roughness. It should be also noted that values of H and E_r are different for the two sets of measurements because of the size effect illustrated in Figure 4.

In Figures 6 and 7, a pronounced dependency of the measured properties on the distance from the resin-paint interface is observed. This dependence may result from the significant difference in stiffness between the paint and resin and/or the possible diffusion of the resin into the paint structure during

FIGURE 5. Cross-sectional sample of TiO_2 acrylic-based paint. The red rectangle shows the area where nanoindentation measurements were performed. On the right side a geometrical representation of the indentation matrix is presented.

FIGURE 6. Measured reduced modulus of the paint as a function of the distance from the sample edge for two different h_0 . The paint-resin interfaces are located at 0 and 270 μm . Red and blue dotted lines represent E_r obtained for the free-film sample and resin, respectively.

FIGURE 7. Measured hardness of the embedded paint as a function of the distance from the sample edge for two different h_0 . The paint-resin interfaces are located at 0 and 270 μm . Red and blue dotted lines represent H obtained for the free-film sample and resin, respectively.

the embedding process. These two effects can be distinguished by performing indentation measurements with different depths. If the interface effect is geometrical, the influence from the resin-paint interface should be evident in deep indentations and, to a lesser extent, in shallow indentations.

Conversely, if the diffusion of the resin into the paint fundamentally changes the material properties, measurements should not depend on the depth of indentation. Two series of measurements of H and E_r performed with different indentation depths show similar results (Figures 6 and 7), indicating that the diffusion of resin into the paint structure should be taken into consideration when examining a cross-sectional TiO_2 acrylic-based paint sample at distances smaller than 70 μm from the resin-paint interface. Further details can be found in (Freeman et al., 2019)

CONCLUSIONS

The combined application of an array of documentation tools and analytical procedures has the potential to address the development of climate control strategies for specific collections. The field of epidemiology provides a reliable and well-elaborated methodology that has proven effective for the study of health and disease in human populations. Epidemiological principles can be directly applied to the cultural heritage field if one can tackle the issues of quality of evidence and causality.

The presented research demonstrated the use of existing methods to address these issues where they are most needed. The development of microdamage in objects can be monitored using acoustic emission, which provides sufficient accuracy to reduce the statistical uncertainty to a level manageable from the point of view of an epidemiological methodology. By using different documentation protocols when monitoring object response, one can examine the quality of evidence of existing studies. Furthermore, by promoting these protocols, the conservation community can improve the quality of evidence in studies they perform, which in turn would feed into evidence synthesis and meta-analysis (Figure 1).

The inference of causation can be addressed by better understanding the mechanical properties of historic materials. Nanoindentation has been shown to be particularly well suited for this task. The experiments conducted on free-film and cross-sectional samples of TiO_2 acrylic-based paint show that reliable measurements on embedded cross sections are possible, but a proper protocol must be elaborated, and the geometrical effects of the sample must be taken into consideration. Restrictions for mechanical characterization using nanoindentation result from the properties of existing samples (e.g., material type, embedding method, surface polishing) rather than limitations of the measuring technique itself.

Subsequent research seeks to extend the measurement program to investigate correlations between the nano-, micro-, and macroproperties for specific classes of artistic materials. Establishing such a relationship would make accessible the use of nanoindentation data within existing predictive models of material behavior and predictive tools built specifically for the conservation field.

ACKNOWLEDGMENTS

The research was supported by the Getty Conservation Institute's Managing Collections Environments Initiative. We would like to thank Stefan Michalski for insightful discussions on epidemiology and nanomechanics.

REFERENCES

- Artigas, D. J. 2007. A Comparison of the Efficacy and Costs of Different Approaches to Climate Management in Historic Buildings and Museums. Ph.D. diss., University of Pennsylvania, Philadelphia.
- Bizot Group. 2015. Bizot Green Protocol. National Museum Directors' Council. <http://www.nationalmuseums.org.uk/what-we-do/contributing-sector/environmental-conditions> (accessed 13 October 2016).
- Dean, A. G., K. M. Sullivan, and M. M. Soe. 2013. OpenEpi: Open Source Epidemiologic Statistics for Public Health. Version 3.01. <http://www.openepi.com> (accessed 15 October 2016).
- Ekelund, S., P. Van Duin, A. Jorissen, B. Ankersmit, R. M. Groves, H. Schellen, and A. Suiker. 2014. "Climate4Wood Museum Study: The Systematic Analysis of Climate-Related Damage on Decorated Wooden Panels in the Rijksmuseum." In *ICOM-CC, 17th Triennial Conference, Building Strong Culture through Conservation, 15–19 September 2014, Melbourne, Australia: Preprints*. Paris: International Council of Museums. <https://www.icom-cc-publications-online.org/PublicationDetail.aspx?cid=bf01cc83-6c50-4a86-b7c4-ae3e9f2c04e4/> (accessed 14 October 2016).
- Fischer-Cripps, A. C. 2009. *The IBIS Handbook of Nanoindentation*. Sydney, Australia: Fischer-Cripps Laboratories.
- Freeman, A., M. Łukowski, and V. Beltran. 2019. Mechanical Characterization of a Cross-Sectional TiO₂ Acrylic-Based Paint by Nano-Indentation. *Journal of the American Institute for Conservation* 58(3):1–13.
- Getty Conservation Institute. 2014. Managing Collection Environments Initiative. http://www.getty.edu/conservation/our_projects/education/managing/overview.html (accessed 13 October 2016).
- Gordis, L. 2014. *Epidemiology*. Philadelphia: Elsevier Saunders.
- Hagan, E. W. S., M. Charalambides, C. R. T. Young, and T. Learner. 2009. Tensile Properties of Latex Paint Films with TiO₂ Pigment. *Mechanics of Time-Dependent Materials*, 13:149–161. <https://doi.org/10.1007/s11043-009-9076-y>.
- Hagan, E. W. S., M. Charalambides, C. R. T. Young, T. Learner, and S. Hackney. 2011. Influence of the Inorganic Phase Concentration and Geometry on the Viscoelastic Properties of Latex Coatings through the Glass-Transition. *Polymer*, 52:1662–1673.
- Han, C.-S., S. H. R. Sanei, and F. Alisafaei. 2016. On the Origin of Indentation Size Effects and Depth Dependent Mechanical Properties of Elastic Polymers. *Journal of Polymer Engineering*, 36(1):103–111.
- Hay, J. L., and G. M. Pharr. 2000. "Instrumented Indentation Testing." In *Mechanical Testing and Evaluation*, ed. H. Kuhn and D. Medlin, pp. 232–243. ASM Handbook, No. 8. Materials Park, Ohio: ASM International.
- Hugel, K. 2013. The Journey of Research - Levels of Evidence. Canadian Association of Pharmacy in Oncology. <http://www.capho.org/blog/journey-research-levels-evidence> (accessed 16 October 2016).
- International Institute for Conservation of Historic and Artistic Works (IIC). 2008. Climate Change and Museum Collections. <https://www.iiconservation.org/sites/default/files/dialogues/climate-change-en.pdf> (accessed 15 October 2016).
- International Institute for Conservation of Historic and Artistic Works (IIC). 2010. The Plus/Minus Dilemma: The Way Forward in Environmental Guidelines. Transcript of a discussion held on 13 May 2010, Milwaukee, Wis., in collaboration with the American Institute for Conservation and its annual meeting. Dialogues for the New Century. <https://www.iiconservation.org/sites/default/files/dialogues/plus-minus-en.pdf> (accessed 15 October 2016).
- International Institute for Conservation of Historic and Artistic Works and International Council of Museums—Committee for Conservation (IIC and ICOM-CC). 2014. Environmental Guidelines – IIC and ICOM-CC Declaration. https://www.iiconservation.org/sites/default/files/news/attachments/5681-2014_declaration_on_environmental_guidelines.pdf (accessed 17 October 2016).
- Keene, S. 1994. Real-Time Survival Rates for Treatments of Archaeological Iron. In *Ancient and Historic Metals: Conservation and Scientific Research; Proceedings of a Symposium Organized by the J. Paul Getty Museum and the Getty Conservation Institute, November 1991*, ed. by D. A. Scott, J. Podany, and B. B. Considine, pp. 249–264. Los Angeles: Getty Conservation Institute.
- Kimberly, A. E., and A. L. Emley. 1933. *A Study of the Deterioration of Book Papers in Libraries*. Bureau of Standards Miscellaneous Publications, No. 140. Washington, D.C.: National Bureau of Standards.
- Koestler, R. J., P. Brimblecombe, D. Camuffo, W. S. Ginell, T. E. Graedel, P. Leavengood, J. Petushkova, M. Steiger, C. Urzi, V. Verges-Belmin, and T. Warscheid. 1994. "Group Report: How Do External Environmental Factors Accelerate Change?" In *Durability and Change: The Science, Responsibility, and Cost of Sustaining Cultural Heritage*, ed. W. E. Krumbeyn, P. Brimblecombe, D. E. Cosgrove, and S. Staniforth, pp. 149–163. New York: John Wiley.
- Łukowski, M., J. Czop, M. Strojceki, and Ł. Bratasz. 2013. "Acoustic Emission Monitoring: On the Path to Rational Strategies for Collection Care." In *Climate for Collections: Standards and Uncertainties*, ed. J. Ashley-Smith, A. Burmester, and M. Eibl, pp. 69–79. Chippenham, U.K.: CPI Antony Rowe.
- Melin, C. B., and M. Legner. 2014. The Relationship between Heating Energy and Cumulative Damage to Painted Wood in Historic Churches. *Journal of the Institute of Conservation*, 37(2):94–109. <https://doi.org/10.1080/19455224.2014.939096>.
- Oliver, W. C., and G. M. Pharr. 1992. An Improved Technique for Determining Hardness and Elastic Modulus Using Load and Displacement Sensing Indentation Experiments. *Journal of Materials Research*, 7(6):1564.
- Salvant, J., E. Barthel, and M. Menu. 2011. Nanoindentation and the Micromechanics of Van Gogh Oil Paints. *Applied Physics A: Materials Science and Processing*, 104(2):509–515.
- Strojceki, M., M. Łukowski, L. Krzemien, J. Sobczyk, and Ł. Bratasz. 2014. Acoustic Emission Monitoring of an Eighteenth-Century Wardrobe to Support a Strategy for Indoor Climate Management. *Studies in Conservation*, 59(4):225–232.
- Suenson-Taylor, K., D. Sully, and C. Orton. 1999. Data in Conservation: The Missing Link in the Process. *Studies in Conservation*, 44(3):184–194.
- Van Landingham, M. R. 2003. Review of Instrumented Indentation. *Journal of Research of the National Institute of Standards and Technology*, 108:249–265.
- Wright, M., M. Hudson, M. Kokkori, K. Muir, F. Casadio, K. Faber, and K. R. Shull. 2014. "Quantifying the Mechanical Properties of Artists' Paints with Nanoindentation." In *Proceedings of the 2014 Annual Meeting of the Adhesion Society*, pp. 285–287. Red Hook, N.Y.: Curran Associates.

The Mechanical Behavior of Library and Archive Materials

A. Carver-Kubik and James Reilly*

ABSTRACT. The mechanical behavior of fine-art objects has been the subject of major conservation research for several decades. However, works of art are only one element of the world's cultural heritage. Printed materials dating from the fifteenth century to the present represent the bulk of our cultural heritage. Printed materials, such as books, embody a great deal of knowledge and culture, and many of them have significant artifactual value. Emphasis has been placed on the preservation of the paper or parchment on which the intellectual content is printed. Changing attitudes in bibliographic research and conservation practices have resulted in an interest in the preservation of the entire bound volume. Studying the mechanical behavior of books is particularly challenging as they are three-dimensional, complex, composite objects made of a variety of materials and constructed in a variety of ways. Digital image correlation (DIC) is a relatively new imaging technology that allows us to study three-dimensional objects. The Image Permanence Institute has been studying the chemical and mechanical stability of collection materials for 30 years. Our research has led us to understand that it may take weeks or even months for an entire bound volume to equilibrate to a change in environment. However, through experiential evidence it appears the outside, or "skin," of the book reacts to changes in environment more quickly. Using DIC, we are now exploring the mechanical behavior of bound volumes in order to determine safe temperature and relative humidity limits. The results of this research will better inform our models for sustainable environmental parameters.

INTRODUCTION

The mechanical behavior of fine-art objects, particularly paintings on panel and canvas, has been the subject of conservation research for several decades. However, works of fine art are only one element of the world's cultural heritage. Printed materials dating from the fifteenth century to the present embody a great deal of knowledge and culture, and many of them have significant artifactual value. Libraries and archives are the repositories for most of these materials. Although significant research has gone into the role of environment on the chemical stability of book materials, namely, cellulosic and collagen-based materials, the effects of temperature and humidity on the mechanical behavior of bound volumes have not been as extensively studied. Recently, the Image Permanence Institute (IPI) has taken on the challenge of better understanding the mechanical behavior of library and archive materials. Following the methodological approach to materials research established by conservation scientists at the Smithsonian Institution, new tools are being used to approach age-old problems in hopes of establishing practical guidelines for the limits of temperature and relative humidity (RH) control.

One main reason for the lack of research on the mechanical behavior of library and archive materials has been earlier attitudes toward the preservation of printed materials and bound volumes. Until very recently, library and archive practices

Image Permanence Institute, Rochester Institute of Technology, Gannett Building 7B, Room 2000, 70 Lomb Memorial Drive, Rochester, New York 14623, USA.

* Correspondence: ackpph@rit.edu

Manuscript received 2 June 2018; accepted 7 May 2019.

mainly emphasized preservation of the intellectual content held within the bound volume. Research regarding bindings was limited to their functional durability or else to an art historical approach to fine bindings with an eye to preserving decoration and embellishments. Simple or plain bindings were not only ignored but considered more or less disposable. General attitudes were that a book's binding was merely functional. It served to protect the text block from damage and to keep the text block together in order to prolong the life and usefulness of the book (Pearson et al., 2010). As a result, with the exception of very fine bindings, rebinding a physically damaged book was and continues to be common practice (see Figure 1).

Harold Tribolet and Kenneth Sonderland (1969) presented a history of bookbinding as it relates to book preservation in a 1969 issue of *Library Quarterly*. The article relates the decline in chemical and structural stability of books to a decline in the quality of craftsmanship and materials as demand for books increased after the eighteenth century. This article, intended for library and archive professionals, advocated the practice of rebinding damaged books, albeit with a thoughtful and measured approach saying, "prolonging the life of the book is the logical objective in most instances.

However, the manner which this is done requires intelligent judgement" (Tribolet and Sonderland, 1969:130). The authors go on to describe making assessments on the rarity of a book to determine if it requires repair by a skilled binder or if it deserves a simple rebinding or something in between. They not only advocate for the rebinding of books but extoll the excellence of "perfect" bindings in which the text block is glued to the cover with a synthetic adhesive. This type of binding has proven to be problematic as the adhesive often fails, resulting in the text block becoming detached from the cover. In more recent years, bibliophiles follow the adage "perfect binding, isn't."

PHYSICAL VERSUS CHEMICAL INSTABILITY

Because of the emphasis on preservation of information, past research focused on the chemical degradation of the paper and parchment on which the content of the book was written or printed. The poor stability of paper produced in the latter half of the nineteenth century and into the first half of the twentieth century raised an alarm regarding the

FIGURE 1. These three books from the Rochester Institute of Technology's Cary Graphic Arts Collection were printed in the sixteenth century by Robert Estienne. The book on the left was rebound with a simple twentieth century binding. The book on the right was rebound with a much more elaborate twentieth century binding. The center book is in its original, simple vellum wrapper. Image by A. Carver-Kubik.

potential for a major loss of our intellectual heritage due to cellulose degradation. As Edwin Williams (1970:3) so aptly stated in *Library Quarterly*, “Everything in library collections is deteriorating today, was deteriorating yesterday, and will continue to deteriorate tomorrow although we ought to retard the process.” William J. Barrow of the Barrow Research Laboratory answered this call to action and took on the issue of paper degradation and loss of cultural heritage. After decades of research the laboratory published the series *Permanence/Durability of the Book*. Part 7 (Barrow, 1974), addresses the physical and chemical properties of book papers. Like the work of Tribolet and Sonderland, this publication describes a correlation between changes in papermaking practices and the decline in chemical and physical stability of paper from 1507 to 1949. In this study, the physical attributes of paper were considered only in relation to chemical degradation; paper becomes weak and brittle as the cellulose chain breaks down. Subsequent important studies by a variety of scientists address the role of environment on the degradation of cellulose and collagen materials, particularly the effects of high RH, which leads to hydrolysis in cellulose and gelatinization in collagen materials. Until recently, studies in the dimensional properties of paper were mainly produced for the printing industry. Understanding dimensional changes of paper and how they relate to changes in environment are essential to four-color printing as a change in paper dimensions can easily result in a print with poor color registration.

In recent years, there has been a major shift in bibliographic scholarship. Although a book’s binding still performs a utilitarian function, there is significantly more consideration for the binding itself. Scholars now regard the entire book as a cohesive object rather than just a convenient carrier of information. The British Library Preservation Advisory Centre’s pamphlet *Bookbindings* epitomizes this shift in scholarship, emphasizing the need to preserve all bindings, even the simplest binding (Pearson et al., 2010). Every detail, including the materials that were used, the style of binding, and the way the text block is sewn, has research value. The pamphlet states, “each and every one of these bindings is potentially of interest and worth caring for, not only for its function of holding the text in place but also for its artefactual value, its contribution to the individual history of the book it covers,” and also “bookbindings are worth preserving not only for their aesthetic qualities but for their value as an intrinsic part of our documentary cultural heritage (Pearson et al., 2010:1–2).”

Conservation practices have followed this trend not only in conservation research but also in treatment approaches. Conservators are turning their attention to a better understanding of specific binding styles and techniques ranging from elaborate bindings to simple paper and modern mass-produced bindings. Treatments tend to be more thoughtful and conservative, with emphasis on preserving the integrity of the original design while maintaining an acceptable level

of function. The British Library warns that “regardless of the quality of the conservation work, something of the original is lost during treatment. This can lead to a less useful or less valuable item” (Henderson, 2013:1). In addition, treating individual volumes takes considerable time, and books that are being treated are not available for use. Therefore, libraries and archives are beginning to take a broader, preventive approach to conservation that relies on environmental management. Understanding moisture sorption of organic materials and its relationship to a material’s physical behavior is the key to providing environmental parameters of proper temperature and RH for preventive conservation.

HYGROEXPANSIVITY OF PAPER AND PARCHMENT

In 1986 Paul Banks discussed the problem of moisture sorption and physical behavior in the *Book and Paper Group Annual*, stating that books and bound manuscripts are complex, composite objects made from a wide range of materials with different hygroexpansivities; that is, they expand and contract because of variations in moisture content as the RH in the surrounding air changes. The materials are at some points restrained by one another and at others are free to expand and contract. It is necessary to understand not only the expansivity of each unrestrained material but also that of restrained materials. Smithsonian scientists recognized this problem as well and published several papers on the role of temperature and RH on mechanical behavior of cellulosic material aimed toward preservation of collections. In a 2001 paper exploring chemical and physical changes of both naturally and accelerated aged cellulose, Smithsonian scientists concluded that paper itself is relatively dimensionally unresponsive compared to other materials used in the construction of books and that paper will likely not exceed its elastic limits unless completely restrained to a more environmentally responsive substrate (Erhardt et al., 2001). It is the other, more responsive materials, such as wood or collagen-based materials, that determine the environmental parameters for bound volumes (Erhardt et al., 2001).

Although the hygroexpansivities of cellulosic materials, such as wood and cotton paper, are well known, less is known about hygroexpansivities of collagen materials like vellum or parchment and leather, as well as other materials used in the construction of books, including cloth, book board (pasteboard, pulpboard, millboard), and adhesives (collagen glues, synthetic adhesives). Several studies have been done on the response of collagen-based materials to moisture changes (Mecklenburg, 1988; Dernovskova et al., 1995; Bowden and Brimblecombe, 2002); however, it is still unclear what the elastic limits are. As a result, the mechanical behavior of books and recommended RH limits are based on theoretical calculations derived from what is known about

cellulosic materials, such as the sorption isotherm for pure cellulose, and experimental data on the hygroexpansivity of some cotton papers (Tumosa et al., 1995; Erhardt et al., 1997). There is little information published on the basis of actual experimental evidence of the mechanical behavior of common book materials or of actual books, especially compared to what is available for painting materials. As a result, there is a lack of consensus in recommended temperature and RH limits for libraries and archives. Some agencies recommend tight RH control allowing a 40%–50% range (LYRASIS, 2013), whereas others suggest a broader range of 35% to 60% (Henderson, 2013). It is still unclear how much of the physical damage seen in books is attributed to handling versus environmental extremes, much less exactly what can be considered an environmental extreme.

Understanding the relationship between moisture and organic materials is key to gaining an understanding of the mechanical behavior of library and archive materials. For cellulosic and collagen-based materials, the extent of physical expansivity is proportional to the extent of moisture sorption. Materials will absorb and desorb water and expand and contract as the ambient relative humidity changes, creating strain within the materials. Tumosa et al. (1996) determined that the point at which many organic materials experience plastic, or permanent, deformation occurs at a strain of at least 0.004, or 0.4% elongation. In a Smithsonian Conservation Analytical Laboratory report titled “Guidelines for the Museum Climate,” Erhardt et al. (1995) state that unrestrained cellulosic material will not likely experience plastic deformation. It is only when the materials are restrained that dimensional change can cause enough strain for damage to occur. They state that materials will not experience damage if the change in RH does not last long enough for full mechanical response to occur (full moisture equilibration). Therefore, rapid RH fluctuations within the allowable RH range will not produce stresses and strains that exceed the elastic limit. LYRASIS and others contradict this assessment, stating that rapid fluctuation in temperature and RH cause the most damage to collections (LYRASIS, 2013).

EXPERIMENTAL GOALS

The IPI is seeking to answer these questions and establish environmental parameters for library and archive material. Of particular interest is to determine how low RH affects bound volumes as many collections experience winter dryness. We have done several studies on moisture equilibration of library and archive materials. The unpublished research of Jean-Louis Bigourdan, a senior research scientist at IPI, on understanding temperature and moisture equilibration found that although temperature equilibration is fast, taking only a few hours, it will take several weeks for a book to reach full moisture equilibration at 20°C. The

reason is likely because water vapor has to diffuse through the entire object, which takes considerable time. Studies by Mecklenburg agree that it will take months for a large object to come to near equilibration (Mecklenburg and Tumosa, 1999). British Standards Institute publication PAS 198 concurs, noting that it will take weeks for a tight stack of papers to equilibrate fully and large wooden objects take weeks or months to equilibrate fully (British Standards Institute, 2012). However, experientially, it has been observed that the outside, or “skin,” of bound volumes reacts quickly to changes in RH. Mecklenburg also states that small, thin objects like a single sheet of paper or parchment will take only hours to fully equilibrate (Mecklenburg and Tumosa, 1999). Moisture equilibration and therefore mechanical response of the skin of the book may be more akin to the response of a single sheet of paper or parchment, taking hours to fully respond, rather than the center of the book, which takes several weeks to fully respond.

DIGITAL IMAGE CORRELATION

Through a grant from the National Endowment for the Humanities (NEH), IPI is using a 3-D digital image correlation (DIC) system to investigate the mechanical response of the skin of bound volumes. Digital image correlation is a photogrammetry system for measuring mechanical deformation of an object’s surface. The advantage of DIC over other testing methods is that it is possible to test completely unrestrained materials and to measure actual strain in three-dimensional structures such as books. The system requires the test samples to have a high-contrast, random pattern of speckled dots on its surface, either naturally occurring or applied. Two digital cameras are positioned in front of the test sample, and images are captured in stereo at regular intervals during the test period. The images are uploaded to specially designed software that tracks the movement of the applied speckles in three dimensions. Algorithms calculate in-plane and out-of-plane displacement as well as the strain for the material tested. Data are produced as numerical data that can be graphed as well as visual 2-D and 3-D maps that can be animated (see Figures 2 and 3).

Originally applied to materials testing for industrial and building applications, DIC has been adopted for cultural heritage materials. Earlier studies using DIC to determine strain in paintings on canvas (Kujawinska et al., 2011; Lasyk et al., 2011; Malesa et al., 2011) and for tapestries (Lennard and Dulieu-Barton, 2014) provided proof of concept that this system is effective in acquiring dimensional displacement and strain data for organic materials. This system will allow us to gain an understanding not only of the expansivities of unrestrained materials but also that of restrained materials in order to better understand the elastic limits of bound volumes.

FIGURE 2. The DIC software produces 3-D maps that can be exported as video files. This parchment sample is from an 1823 indenture. Average principle strain is shown after the RH was changed from 50% to 30%.

The first phase of IPI's NEH-funded project is to gather data on the unrestrained mechanical behavior and elastic limits of materials from which archive and library objects are made, such as various types of modern and historic paper, parchment, leather, book board, and book cloth. We will then begin to gather data on three-dimensional bound volumes.

To initiate the first phase of the project, several preliminary tests were conducted. The digital image correlation technique involves imprinting the sample materials with a particular type of dot pattern that the image-processing software uses to measure displacement. Researchers using DIC to monitor strain in tapestries were able to utilize the natural weave pattern of the tapestry as the basis for image correlation (Lennard and Dulieu-Barton, 2014). With a few exceptions, book materials are fairly homogenous with no

naturally occurring pattern. Therefore, a speckle pattern had to be applied to our test samples. The software requires a high-contrast dot pattern that evenly covers about 50% of the sample and works best when the dots are about 5 pixels across in the final processed images. Therefore, the camera setup (focal length, distance from samples, stereo geometry), size of the dots imprinted on the samples, and method of applying the dots had to be determined.

REFINING DIC APPARATUS AND EXPERIMENTAL SETUP

Applying the dots to the samples posed a challenge. The dot application system supplied to us when the system was

FIGURE 3. The DIC software also produces a 2-D map. The highlighted parchment sample is from an 1823 indenture. Average principle strain is shown after the RH was changed from 50% to 30%.

purchased consisted of aqueous ink and relief dot templates (rubber stamps). However, the ink produced dots with too little contrast for the software to analyze effectively. Applying the dot pattern by hand using the rubber stamps led to problems achieving the correct dot density and variation. We decided to use traditional letterpress and printer's ink to print the dot pattern on our samples. Most books and documents were printed with letterpress from the invention of the press in 1450 until about 1960. The Rochester Institute of Technology is fortunate to house the Cary Graphic Arts Collection, which includes an impressive collection of working letterpress presses. The curators at the Cary were enthusiastic about the project and agreed to help us print our test samples.

In order to print the samples, a printing matrix needed to be made. Preliminary tests were done to determine the optimal camera setup as well as dot size and pattern for the matrix. Two 5.0-megapixel digital cameras with 8mm Schneider

compact lenses were mounted to a tripod apparatus with an aluminum arm and cross bar. The cameras were positioned at a 35° angle directly above the sample materials (see Figure 4). This angle was determined by the DIC apparatus manufacturer as the optimal stereo angle for the 8mm lenses. The tripod height was adjusted to allow the maximum field of view in order to accommodate the maximum number of samples to be tested at one time. Several dot sizes and patterns were tested in order to determine the appropriate diameter of dot (5 pixels in the final image) and the optimal dot density and amount of variation for the software. A dot pattern with dots 0.06 inch (1.524 mm) in diameter, 60% dot density, and 70% dot variation was selected. Preliminary tests were also done to determine the best sample size. The DIC system has a high level of accuracy. We found that large samples measuring 10 × 10 inches (25.4 × 25.4 cm) and smaller samples measuring 4 × 4 inches (10.16 × 10.16 cm) of the same materials

FIGURE 4. The DIC setup in IPI's walk-in chamber. Image by A. Carver-Kubik.

yielded the same displacement and strain results. We determined the smaller, 4×4 inch (10.16×10.16 cm), sample size would allow us to maximize the number of samples tested at one time. We decided to print 8×8 inch (20.32×20.32 cm) samples and then cut the samples down to 4×4 inches (10.16×10.16 cm) in order minimize printing time and effort. The final dot pattern was produced from a digital file on a polymer letterpress printing matrix made by Boxcar Press. The samples were printed by the Cary's assistant curator, Amelia Hugill-Fontanel, using a Vandercook cylinder press (see Figure 5).

The IPI testing chamber is a programmable walk-in temperature- and humidity-controlled chamber capable of consistent RH control from 10% to 80% RH and temperatures between 10°C and 30°C . Our preliminary tests showed that the test chamber required modifying and tuning. The distribution of temperature and humidity conditions was even throughout the room; however, the velocity of the air flow caused the unrestrained samples to move out of position. Even minimal restraint of the samples to hold them in place imposed strain, skewing the test results. The solution was to place a filter in front of the air circulation fans, minimizing the velocity of air flow but still maintaining even distribution of temperature and humidity. Another issue observed in the preliminary tests was that the RH rapidly oscillated around the set point, giving 3%–4% RH swings. Some test samples, particularly parchment, respond quickly to changes in RH, resulting in rapid expansion and contraction of the samples.

FIGURE 5. (left) Amelia Hugill-Fontanel, assistant curator of the Cary Collection, printing samples using a Vandercook press. (above) The speckle pattern printed onto each sample has dots 0.06 inch in diameter, 60% dot density, and 70% dot variation. Image by Stephanie Hofner.

The DIC software was not able to track the movement, producing bad data and, in some cases, no data. The chamber uses a proportional-integral-derivative (PID) controller, a control loop feedback mechanism used in many control systems. The PID controller had to be tuned so that the chamber maintained a steady RH at each desired set point and was able to transition smoothly between programmed set points without significant overshoot or being sluggish.

MOISTURE EQUILIBRATION EXPERIMENT

The final preliminary step was to determine the testing profile. Because mechanical behavior is linked to moisture sorption, it was important to know the rate of full moisture equilibration in order to avoid false results. If the soak time (duration at a single RH set point) was too short and materials were not allowed to fully equilibrate, it may have appeared as if they had permanently deformed when, in reality, they may not have had sufficient time to fully expand or contract. Although some studies suggest it takes only hours for small, thin objects like a single sheet of paper or parchment to fully equilibrate (Mecklenburg and Tumosa, 1999), we needed to know exactly how many hours it took for our samples to reach full moisture equilibration. Also, there is little information on the moisture equilibration of leather and book board. To determine this, a representative selection of 4 × 4 inch single sheets of test materials was equilibrated at 10% RH for 60 hours. The samples were weighed and then sealed in aluminum foil bags. The RH in the chamber was raised to 80%. Each sample was removed from its bag and placed on a digital balance. The weight gain of each sample was recorded with a digital single-lens reflex camera set to the time-lapse function. An image was recorded every 5 minutes for 24 hours. Each sample was set aside in the chamber and then weighed a final time after having been in the chamber for at least 1 week or longer before being resealed in an aluminum foil bag. The chamber RH was dropped to 10%, and the experiment was repeated.

RESULTS

When the absorption data were plotted, it appeared as if the paper and parchment samples had reached full moisture equilibrium between 40 minutes and 3 hours, the book cloth equilibration ranged from 2 to 7 hours, and the leather and book board did not reach equilibrium within the 24-hour test period. However, when the samples were weighed again after having been in the test chamber for 1 week or longer, each sample had gained significantly more weight. For example, the Arches 100% cotton paper gained an additional 2.46% of water weight, about a third of its total percent weight gain. Each sample gained at least a quarter to a third percent more water weight after the initial 24-hour test period

(see Figures 6 and 7). From these data we calculated that it may take between 1 and 4 days for most paper, cloth, and parchment samples to fully equilibrate at 80% RH, and it may take leather more than 5 days to fully equilibrate. We also found that desorption happened far more quickly than absorption. All samples reached full moisture equilibration at 10% RH, well within the 24-hour test period. The Arches paper was tested again within a more moderate RH range. The sample was equilibrated at 50% RH, the chamber set point was increased to 70% RH, and the sample was left to equilibrate for 5 days. Within this more moderate range, the sample reached full moisture equilibrium in a few hours. The Arches is the only sample tested thus far within this more moderate RH range.

We have not identified any studies on cellulosic material that suggest this kind of sorption behavior; however, published studies on the hygroscopic behavior of parchment corroborate our findings. In general, parchment absorbs and desorbs a significant amount of water with changes in RH conditions (Mecklenburg, 1988; Hansen et al., 1992). It has been found that absorption time is generally slower than desorption time and that historical parchment has a higher and quicker sorption curve than modern parchment (Dernovskova et al., 1995). The amount of water it absorbs and the sorption rate are, in part, determined by the thickness of the material and the amount of gelatin in the material (Dernovskova et al., 1995). Under conditions of high heat and humidity the collagen structure in parchment and leather breaks down in a process called gelatinization, resulting in a material that has a mixture of gelatin and collagen. Historical parchment, such as IPI's samples, likely has some gelatin content.

Moisture equilibration rates for cellulosic and collagen-based materials need to be studied further. This phenomenon of surprisingly long equilibration time in high-RH conditions is likely due to the molecular interactions between water and cellulose or collagen chains. Although it is known that high-RH conditions are dangerous for collection materials because of the risk of chemical and biological decay as well as a decrease in mechanical stability, it is unknown if or how this extra gain in water weight impacts the dimensional displacement of the materials leading to mechanical damage.

After more than a year of preliminary tests and planning, we have just begun our initial experiments using DIC on library and archive materials. These first experiments, looking at the dimensional response of unrestrained materials, are within the more moderate RH range of 30% to 70% RH. This is indicative of the range we see in real-world collections storage spaces and mirrors the test parameters used for our previous studies in moisture equilibration of library and archive materials. We will also look at the upper and lower extremes between 10% and 80% RH. In our preliminary tests and our initial experiments, we are seeing a strong correlation between the rate of RH change, water weight gain in grams, and the initial slope of the strain curve. In both instances the initial response is quite rapid and nearly in sync

FIGURE 6. (top) Most cellulosic samples reach equilibrium within 3 hours. This graph shows percent weight change over time in hours. (bottom) All samples gained a significant amount of water weight after the initial 24-hour test period at 80% RH. The yellow bars show percent weight change after 24 hours, and the blue bars represent percent weight change after 1 week or longer. The sample code is as follows: C for cloth and P for paper.

FIGURE 7. (top) Most parchment samples reach equilibrium within 5 hours, and leather samples nearly reach equilibrium within 20 hours. This graph shows percent weight change over time in hours. (bottom) All samples gained a significant amount of water weight after the initial 24-hour test period at 80% RH. The yellow bars show percent weight change after 24 hours, and the blue bars represent percent weight change after 1 week or longer. The sample code is as follows: L for leather and V for parchment or vellum.

FIGURE 8. Mean principle strain of sample V1 (1823 parchment indenture) versus percent RH. The initial response of the sample is immediate as the RH drops. The response then becomes gradual.

with the increase or decrease in RH; the materials quickly absorb or desorb water and expand or contract, respectively. The response then slows, and changes happen much more slowly before reaching equilibrium (see Figure 8).

We have also observed that the amount of water absorbed and dimensional response vary. These differences are likely dependent on a variety of variables. For paper and cloth, they may be dependent on the fiber composition, type of sizing used, age, and thickness of the sample. For leather and parchment, they may be dependent on the type, age, and diet of the animal as well as the thickness and age of the material and variations in how the material was produced. Other variables to consider for bound volumes are not only the materials used but also the construction and structure of the book. It is unclear how the style of binding and sewing impacts a book's dimensional response.

Another variable that needs further research is the impact of the rate of RH change on mechanical response. Researchers in the field have not reached a consensus on whether damage is potentially greater with slow changes in RH or rapid changes. PAS 198 states that change in RH will cause less stress if it occurs over several months rather than a few days

(British Standards Institution, 2012). However, the notion put forth in PAS 198 that slow change in RH is better because it allows the material to slowly adapt is rejected by Padfield (2005:10–11). He says this is only a “quarter truth,” indicating the issue is more complicated. He states, “Slow change does not diminish the strain caused by material properties such as the differential shrinkage of wood in its three directions.” It has yet to be determined if this effect extends to the differential response of various restrained book materials.

CONCLUSION

The IPI's research on the use of digital image correlation methods to study the mechanical behavior of single sheets of paper, parchment, book cloth, and cardboard as well as bound volumes is promising. The results of experiments done to better estimate moisture equilibration times for a single sheet of such materials so far show conformity with expected behaviors in a moderate 50%–70% RH range. However, samples continue to absorb moisture when exposed to 80% RH for long periods of time. When materials are exposed to

very low RH, moisture desorption is more rapid than moisture absorption. The end goal of this research is to refine our understanding of the mechanical response of bound volumes and establish proper environmental parameters for library and archive materials based on experimental evidence. This will help to ensure that original bindings will remain intact and be available for future generations to research and enjoy.

ACKNOWLEDGMENTS

The authors thank their colleagues for their guidance and assistance with this project. Amelia Hugill-Fontanel, associate curator in the Cary Collection, and Steven Galbraith, curator in the Cary Collection, shared their expertise in book materials, printing, and binding. Amelia Hugill-Fontanel printed the test samples. IPI staff Douglas Nishimura, Jean-Louis Bigourdan, Patricia Ford, and Daniel Burge also offered their expertise and guidance on this project.

REFERENCES

- Banks, P. N. 1986. Formal Environmental Standards for Storage of Books and Manuscripts: A Status Report. *Book and Paper Group Annual*, 5:124–128.
- Barrow, W. J. 1974. *Permanence/Durability of the Book. Part 7: Physical and Chemical Properties of Book Papers, 1507–1949*. Richmond, Va.: W. J. Barrow Research Laboratory.
- Bowden, D., and P. Brimblecombe. 2002. “The Thermal Response of Parchment and Leather to Relative Humidity Changes.” In *Microanalysis of Parchment*, ed. R. Larsen, pp. 63–72. London: Archetype.
- British Standards Institution. 2012. Specification for Managing Environmental Conditions for Cultural Collections. PAS 198:2012. London: British Standards Institution.
- Dernovskova, J., H. Jirasova, and J. Zelinger. 1995. An Investigation of the Hygroscopicity of Parchment Subjected to Different Treatments. *Restaurator*, 16:31–44.
- Erhardt, W. D., M. F. Mecklenburg, C. S. Tumosa, and M. H. McCormick-Goodhart. 1995. Guidelines for the Museum Climate: Report to the Task Force on Indoor Air Quality in Museums. Herndon, Va.: International Society of Indoor Air Quality and Climate.
- Erhardt, D., M. F. Mecklenburg, C. S. Tumosa, and M. McCormick-Goodhart. 1997. “The Determination of Appropriate Museum Environments.” In *The Interface between Science and Conservation*, ed. S. Bradley, pp. 153–163. British Museum Occasional Paper, No. 116. London: British Museum.
- Erhardt, D., C. S. Tumosa, and M. F. Mecklenburg. 2001. “Chemical and Physical Changes in Naturally and Accelerated Aged Cellulose.” In *Historic Textiles, Papers, and Polymers in Museums*, ed. J. M. Cardamone, pp. 23–37. Washington, D.C.: American Chemical Society.
- Hansen, E. F., N. L. Steve, and H. Sobel. 1992. The Effects of Relative Humidity on Some Physical Properties of Modern Vellum: Implications for the Optimum Relative Humidity for the Display and Storage of Parchment. *Journal of the American Institute for Conservation*, 31:325–342.
- Henderson, J. 2013. *Environment*. London: British Library Preservation Advisory Centre.
- Kujawinska, M., M. Malesa, K. Malowany, A. Piekarczyk, L. Tyminska-Widmer, and P. Targowski. 2011. Digital Image Correlation Method: A Versatile Tool for Engineering and Art Structures Investigations. *Proceedings of SPIE*, 8011:80119R. <https://doi.org/10.1117/12.915566>.
- Lasyk, Ł., M. Łumoski, and Ł. Bratasz. 2011. Simple Digital Speckle Pattern Interferometer (DSPI) for Investigation of Art Objects. *Optical Applicata*, 41:687–700.
- Lennard, F., and J. M. Dulieu-Barton. 2014. Quantifying and Visualizing Change: Strain Monitoring of Tapestries with Digital Image Correlation. *Studies in Conservation*, 59, <https://doi.org/10.1179/2047058413Y.0000000097>.
- LYRASIS. 2013. Environmental Specification for the Storage of Library and Archival Material. Preservation Services Leaflet. Atlanta, Ga.: LYRASIS.
- Malesa, M., K. Malowany, L. Tyminska-Widmer, E. A. Kwiatkowska, M. Kujawinska, B. J. Rouba, and P. Targowski. 2011. Application of Digital Image Correlation (DIC) for Tracking Deformations of Paintings on Canvas. *Proceedings of SPIE*, 8084:80840L. <https://doi.org/10.1117/12.889452>.
- Mecklenburg, M. F. 1988. “The Effects of Atmospheric Moisture on the Mechanical Properties of Collagen Under Equilibrium Conditions.” In *Preprints of 16th Annual Meeting of the American Institute for Conservation of Historic and Artistic Works*, ed. S. Z. Rosenberg, pp. 231–244. Washington, D.C.: American Institute for Conservation of Historic and Artistic Works.
- Mecklenburg, M. F., and C. S. Tumosa. 1999. Temperature and Relative Humidity Effects on the Mechanical and Chemical Stability of Collections. *ASHRAE Journal*, 41:69–74.
- Padfield, T. 2005. How to Keep for a While What You Want to Keep Forever. http://www.padfield.org/tim/cfys/phdk/phdk_tp.pdf (accessed 29 July 2016).
- Pearson, D., J. Mumford, and A. Walker. 2010. *Bookbindings*. London: Preservation Advisory Centre.
- Tribolet, H. W., and K. W. Sonderland. 1969. Binding Practice as Related to the Preservation of Books. *Library Quarterly: Information, Community, Policy*, 40:128–137.
- Tumosa, C. S., D. Erhardt, M. F. Mecklenburg, and M. McCormick-Goodhart. 1995. The Effects of Relative Humidity and Temperature on Exhibited Objects. *Cahiers d'étude Comité de Conservation (ICOM-CC)*, 1:9.
- Tumosa, C. S., M. F. Mecklenburg, D. Erhardt, and M. McCormick-Goodhart. 1996. A Discussion of Research on the Effects of Temperature and Relative Humidity on Museum Objects. *Western Association for Art Conservation*, 18:19–20.
- Williams, E. E. 1970. Deterioration of Library Collections Today. *Library Quarterly*, 40:3–17.

Future Trends in Studies of the Mechanics of Artists' Paints

*Kenneth R. Shull**

ABSTRACT. In this brief paper I present what amounts to an opinion piece regarding future investigations of the mechanics of artists' paints. The field is ripe for the incorporation of new experimental and computational methods. Many of these methods are being developed outside the context of cultural heritage science. The cultural heritage field is well poised to take advantage of these developments for several reasons, including the intrinsic educational and cultural value of these investigations. Two examples are described here: nanoindentation and quartz crystal rheometry. An advantage of nanoindentation is that it requires a very small sample size and can be used to study actual historic samples. Quartz crystal rheometry is a new technique developed largely in my laboratory at Northwestern. It requires the use of model paint formulations but provides quantitative information about the time-dependent properties of the paint coating and the response of these properties to environmental conditions.

INTRODUCTION

Investigations of the long-term aging of artists' paints present a variety of practical challenges to the materials science research community. The most obvious technical challenge is the inability to directly perform experiments over relevant timescales, which can range from decades to centuries. Artificial aging by changing the temperature or other environmental conditions is not a promising strategy because the degradation mechanisms can be affected by these changes. For example, increasing the temperature to speed up different chemical processes that occur in an aging paint will not enhance all processes at the same rate since these processes will be characterized by a variety of activation energies. As a result, the properties of an artificially aged sample will not necessarily be representative of a material that has been aged under ambient conditions over a very long period of time. Mecklenburg and his coworkers recognized this and performed a very careful set of investigations of the mechanical properties of paint films naturally aged for a period of years or even decades (Erlebacher et al., 1992; Erhardt et al., 2000; Mecklenburg and Tumosa, 2001; Mecklenburg et al., 2005; Tumosa et al., 2005). This work has led to a remarkable database of material behavior that continues to serve as a valuable resource to the cultural heritage science community. Mecklenburg's vision at the time he initiated this work was quite extraordinary and forward thinking. What does the corresponding vision for fundamental investigations of the mechanics of artists' paints look like in 2019? I don't claim to have a comprehensive answer to this question, but I do have some specific thoughts that I believe will be helpful to the subset of the cultural heritage science community that is interested in issues related to the mechanical properties of artists' paints. The first point is a philosophical one related

Department of Materials Science and Engineering, Northwestern University, 2220 Campus Drive, Evanston, Illinois 60208-3108, USA.

* Correspondence: k-shull@northwestern.edu

Manuscript received 2 June 2018; accepted 7 May 2019.

to strategies for addressing important questions in this field in the absence of some of the financial driving forces relevant in many related fields of science. After a very brief discussion of this topic, I give two examples of relatively recent experimental capabilities in materials science that are likely to have an important impact on our understanding of artists' paints and on the evolution of the mechanical properties of these materials over long periods of time. Finally, I discuss my view of the computational chemistry approaches that are beginning to play an important role in this field.

SYNERGIES WITH OTHER FIELDS

Progress in understanding the behavior of artists' paints is limited by a very practical question that all of us involved in fundamental research are compelled to answer: who is going to pay for the research to be performed? My central assumption is that an increasingly important part of the path forward is to find research problems that are of simultaneous benefit to the cultural heritage science, industrial research, and educational communities. The argument can most readily be made at the educational level. It is often much easier to motivate a student to think about what has happened to the visual appearance of a Rembrandt painting over the past several hundred years than to get them to think about the curing kinetics of a commercial automotive paint or other industrial coating, for example. However, the need to enhance coating performance and to fund work in this area is recognized by a broader constituency that is able to pay for this work. Fortunately, the industrial coatings and cultural heritage science communities use similar tools and can benefit from each other, provided that these communities interact with one another in a helpful way. Examples where I have pursued this approach in my own research include the development of *in situ* rheometric techniques that can be used to monitor curing and aging of paint and the use of nanoindentation to characterize a range of different paint coatings. These examples are described in more detail below.

NEW EXPERIMENTAL METHODS

NANOINDENTATION

Nanoindentation is a technique that involves pressing a hard indenter of known shape into a material while monitoring the load and displacement in order to measure the hardness and elastic modulus of the material. The technique requires that a small sample, with dimensions in the range of ~100 μm or more, be embedded in a suitably chosen resin and polished to obtain a smooth surface. A schematic of the sample geometry, illustrating the tip-sample contact, is shown in Figure 1a, and a representative indentation curve is shown

FIGURE 1. (a) Schematic representation of a nanoindentation experiment. (b) A typical load-displacement relationship for the indentation of the polyester resin used to embed the paint samples, labeled to illustrate the values of three experimental quantities ($P_{\max}$, $\delta_{\max}$, and S) that are used to extract paint properties from the indentation curve.

in Figure 1b. The hardness, H , of a material is given by the ratio of the maximum compressive load, $P_{\max}$, to the projected contact area of the nonrecoverable impression made in the material by the indenter, A :

$$H = \frac{P_{\max}}{A},$$

The projected area can be obtained from the displacement, δ , by a variety of approaches that have been described in the literature, with the method of Oliver and Pharr (1992) being the most common method of analysis. Since the material is viscoelastic, a well-defined hold period is typically introduced before the unloading portion of the experiment. The elastic modulus is determined from S , the initial slope of the unloading curve at the end of this hold period.

Despite this inherent difficulty, I am still hopeful that nanoindentation will play an important role in elucidating the state of the paint within a composite paint film. The primary reason for optimism is that much more information exists in a single nanoindentation experiment than the two single values (modulus and hardness) that are obtained for the standard analysis. This analysis is based solely on the use of three individual numbers from the nanoindentation curve, $P_{\max}$, $\delta_{\max}$, and S . More complete methods of analysis are needed that make use additional information contained within the indentation curve. One example involves the details of the load relaxation that is observed as the displacement is held fixed at the maximum value, $\delta_{\max}$. In the "displacement-controlled" experiments preferred within my research group, this load relaxation corresponds to the drop in the compressive load from point A to point B in Figure 1b. The hardness value from the loads measured at these two points will obviously be different, in some cases dramatically so. This difference depends on the length of time that the displacement is held fixed at $\delta_{\max}$ (typically 1 or 2 minutes in my own experiments) and is an additional property of the material than can be utilized.

Additional useful information can be obtained by performing indentation experiments under carefully controlled environmental conditions. Temperature and humidity are obvious conditions to investigate. For example, an oil-based paint in which the ester bonds have been hydrolyzed to a large extent would be expected to have a very different response at very high and very low values of relative humidity. Similar approaches involving measurements while the sample is being exposed to an equilibrium vapor pressure of other liquids, apart from water, can be similarly useful.

Many of these experiments involve the use of new experimental protocols requiring a certain degree of technique development. To some extent these techniques are already being developed within the broader materials science community. Some of the research questions and required methods are quite specific to conservation science, however, and the required protocols are not likely to be developed elsewhere. Some of this development work is quite tedious but also necessary. Examples include studies of the best embedding media to use for sample preparation so that the results are not affected by the method of sample preparation. Also, instrumental artifacts that impact details of the load-displacement relationship can lead to erroneous interpretations if not properly understood. These instrumental issues become quite important when understanding the load relaxation experiments, for example, since a small displacement drift in the device will be incorrectly interpreted as stress relaxation within the material itself. Careful calibration experiments with rigid materials need to accompany published data sets in order to assess these instrumental limitations.

QUARTZ CRYSTAL RHEOMETRY

Although some specific experimental protocols are needed for nanoindentation to have a larger impact on cultural heritage science, the general method is well established and can be performed with commercially available instruments. In this section I describe a much more specialized technique called quartz crystal rheometry that has been developed in my own research laboratory at Northwestern University. The technique is an adaptation of the quartz crystal microbalance and provides the mass per area, the modulus-density product at a fixed frequency (in this case, 15 MHz), and the viscoelastic phase angle at this same frequency for a film coated on the electrode surface of a vibrating quartz crystal, as shown schematically in Figure 2. I use it here as an example of a new experimental technique that can be applied to examine the aging properties of a variety of polymer coatings, including artists' paints. The technique is based on the fact that the electrical impedance across a quartz crystal vibrating at its resonance condition is closely coupled to the mechanical load impedance of a thin film that is placed on a crystal surface. For films in the appropriate thickness regime (typically, several micrometers for the films of interest to us) the load impedance depends on both the mass of the film and

FIGURE 2. Schematic representation of a quartz crystal microbalance, applied in this case as both a mass balance and a high-frequency rheometer.

its viscoelastic properties. The method has a long history, but its use as a technique for quantifying the time dependence of polymer curing is relatively new. A description of the application of the technique to quantitatively determine the properties of a thin polymer film was given previously (DeNolf et al., 2011, 2014), as was its application to investigate the cure kinetics of an alkyd paint system (Sturdy et al., 2014, 2016).

Examples illustrating the capabilities of quartz crystal rheometry are shown in Figure 3. In Figure 3a I show the time dependence of the film mass over 5 orders of magnitude in time, from several minutes out to ~3 years (Sturdy et al., 2016). These data correspond to a commercial alkyd film, and the mass response can be separated into three regimes. In regime I, corresponding to the first several minutes after deposition of the film, the mass decreases as excess solvent in the paint medium evaporates. Regime II corresponds to a mass increase due to oxygen incorporation into the film during the initial stages of the oxidative crosslinking process and is complete after ~1 day. Regime III corresponds to the late stages of curing, where the mass decreases as volatile compounds evolved during the late stages of the cure process are released. The identity and quantity of these volatile compounds can be used to provide information regarding the mechanisms by which

FIGURE 3. (a) Mass of an alkyd paint film as a function of cure time. (b) Time dependence of the modulus-density product for alkyd films with different loadings of zinc oxide, normalized to account for the effects of filler loading on the modulus.

curing occurs. Significantly, these processes are still ongoing, giving measurable changes in the film mass and mechanical response for a period of at least several years.

The quartz crystal rheometric technique also provides mechanical property information at the quartz vibrational frequency of 15 MHz. The inverse of this frequency gives the timescale of the material response probed by the quartz crystal rheometric experiment, which in this case is ~ 60 ns. The shear modulus that I measure at this frequency is a dynamic shear modulus with real and imaginary components corresponding to the storage and loss moduli at 15 MHz. Equivalently, I can express the complex modulus in terms of its magnitude, $|G^*|$, and phase angle, ϕ , which is the convention used in my lab. Quartz crystal rheometry measures the product of $|G^*|$ and the density, ρ . Figure 3b plots $|G^*|\rho$ at 15 MHz for the same commercial alkyd sample used in Figure 3a, but with different volume fractions, ϕ_{ZnO} , of zinc oxide, representative of zinc white pigment used in a variety of artist paint samples. The zinc oxide increases $|G^*|\rho$ by a factor that depends on ϕ_{ZnO} . I have normalized by this factor in Figure 3b to illustrate the effects that the zinc oxide filler has on the properties of the alkyd itself. Effects are observed only at cure times exceeding 10 days, where the ZnO-filled samples have a measurably lower value of the modulus than the samples without the ZnO. I have tentatively attributed this to ZnO catalyzed hydrolysis of the alkyd backbone.

The quartz crystal rheometry experiments have some important similarities to the Mecklenburg work in that the aim is to monitor the properties of freshly cast films over a long time period. The quartz crystal experiments require the use of films within a narrow thickness range close to 5 μm . An important advantage arising from the use of films in this range is that significant composition and property gradients throughout the thickness of the material do not exist. The diffusion of oxygen and other small-molecule constituents is fast enough so that the composition can be assumed to be uniform throughout the full thickness, an assumption that cannot be made for the much thicker films commonly used for traditional mechanical experiments. There are, of course disadvantages arising from the quartz crystal rheometric measurement as well, in that it is a fixed-frequency measurement that is sensitive only to linear viscoelastic (low strain) properties of the material. When coupled with appropriate model systems and an overall framework for interpreting results, important mechanistic information can be obtained from these experiments in order to generate a predictive capability. This predictive capability originates from computational approaches that are described in a general sense in the following section.

THE ROLE OF COMPUTATION AND CONCLUSIONS

A conception of the role that computational science plays in this field is illustrated in Figure 4, within the specific

FIGURE 4. The role of computational microkinetic modeling in conservation science.

context of artists' paints. The artist begins with a set of starting materials and production methods (which are often not known to researchers in detail) and produces an object that continues to evolve and age over time. Through a variety of investigations, the conservation science community develops an understanding of the aged paint in as much detail as possible. I refer to this understanding as a "virtual paint," in that it is an incomplete picture of the actual paint, generated from the information that is available. This understanding evolves in a way that brings the virtual paint into closer conformity with the actual paint. Many of the tools utilized in this process are experimental tools able to assess either historical art objects or closely related physical models and include indentation and quartz crystal rheometry as described above. Examples of experimental techniques that have been applied to the analysis of network formation in oil-based paints include Fourier transform infrared spectroscopy (Lazzari and Chiantore, 1999; Oyman et al., 2005a), Raman spectroscopy (Ellis et al., 1990; Oyman et al., 2005a, 2005b), nuclear magnetic resonance (Muizebelt et al., 1994; Muizebelt and Nielen, 1996; Oyman et al., 2005a), size exclusion chromatography (Lazzari and Chiantore, 1999; Oyman et al., 2005b; Bouwman and Gorkum, 2007), and mass spectrometry (Muizebelt et al., 1994; Muizebelt and Nielen, 1996), among others.

Computational methods play an important role in the development of the virtual paint because existing experimental techniques are not able to probe many of the relevant structural features of an actual paint sample at a molecular level. One overall aim of computational approaches in the area of film structure involves the development of a detailed microkinetic model that will enable the community to build a much higher level of structural and chemical detail into the virtual paint than is currently available. The computational model accounts for the rich species diversity of the starting materials and relevant aging protocols involving very long times that are not experimentally accessible and is based on

experimentally validated reaction pathways and kinetic parameters. Computational models become very important for highly aged samples for which direct experimental investigations are simply not feasible. Development of the computational microkinetic model and the associated virtual paint will enable a range of questions to be answered, including the following:

- What is the fraction of soluble products that might be susceptible to extraction by a given cleaning treatment?
- How will different storage conditions affect the chemical and mechanical response of the paint, including its tendency toward embrittlement?
- How reliable are analytical parameters that conservation scientists use to describe drying oils with respect to modifications such as heat pretreatments or other interventions beyond curing in ambient conditions?

The overall effort as it pertains to the behavior of artists' paints is a large one that extends well beyond the efforts of a single research group. My purpose here is not to outline the complete scope of these activities, which are ongoing in a variety of research groups throughout the world. My main point here is that these computational approaches need to be at the center of our efforts of understanding changes in paint structure at the molecular level over long periods of time. Once validated computational models of structure are in hand, these models can be used to understand the corresponding mechanical response of the material.

ACKNOWLEDGMENTS

The thoughts expressed in this paper are my own impressions regarding the future of paint mechanics as it relates to conservation science. The conservation science field is relatively new to me, and I am indebted to the large number of people who have taught me much about this field. They include many of the participants at the symposium held at the Smithsonian where an oral version of this paper was presented. I continue to learn much from my current and past colleagues at Northwestern University and the Art Institute of Chicago, including Francesca Casadio, Marc Walton, and Kathy Faber. Many of the opinions expressed here are not at all unique to me and have been formed through a variety of conversations. This is particularly true of the computational work, which is all performed by my Northwestern collaborators, Linda Broadbelt and Lindsay Oakley. I have also benefited from conversations with Johanna Salvant, Etienne Barthel, and Michał Łukomski regarding some of the details of nanoindentation. Etienne Barthel, for example, has expressed to me the same conclusion I mention regarding the dominance of the inorganic filler content in determining the elastic properties of the actual paint sample. I have also benefited from funding from the National Science Foundation, where the educational and scientific value of research in cultural heritage science has been appreciated and supported. Lauren Sturdy played a key

role in developing the quartz crystal rheometric technique, as have several additional Ph.D. students within my research group, including Garret DeNolf and Josh Yeh. National Science Foundation funding has been supplied through the Division of Materials Research (DMR-1241667) and through the Graduate Research Fellowship program (DGE-1324585). Finally, I am grateful to the Northwestern University/Art Institute of Chicago Center for Scientific Studies in the Arts (NU-ACCESS, supported by the Mellon foundation), which supplied seed funding to develop the quartz crystal microbalance rheometric technique as applied to artists' paints and also provided support to develop some of our collaborative efforts involving computational chemistry.

REFERENCES

- Bouwman, E., and R. Gorkum. 2007. A Study of New Manganese Complexes as Potential Driers for Alkyd Paints. *Journal of Coatings Technology and Research*, 4(4):491–503. <https://doi.org/10.1007/s11998-007-9041-0>.
- DeNolf, G. C., L. Haack, J. Holubka, A. Straccia, K. Blohowiak, C. Broadbent, and K. R. Shull. 2011. High Frequency Rheometry of Viscoelastic Coatings with the Quartz Crystal Microbalance. *Langmuir*, 27(16):9873–9879. <https://doi.org/10.1021/la200646h>.
- DeNolf, G. C., L. F. Sturdy, and K. R. Shull. 2014. High-Frequency Rheological Characterization of Homogeneous Polymer Films with the Quartz Crystal Microbalance. *Langmuir*, 30(32):9731–9740. <https://doi.org/10.1021/la502090a>.
- Ellis, G., M. Claybourn, and S. E. Richards. 1990. The Application of Fourier Transform Raman Spectroscopy to the Study of Paint Systems. *Spectrochimica Acta, Part A: Molecular Spectroscopy*, 46(2):227–241. [https://doi.org/10.1016/0584-8539\(90\)80092-D](https://doi.org/10.1016/0584-8539(90)80092-D).
- Erhardt, D., C. S. Tumosa, and M. F. Mecklenburg. 2000. Natural and Accelerated Thermal Aging of Oil Paint Films. *Studies in Conservation*, 45(Suppl. 1):65–69. <https://doi.org/10.1179/sic.2000.45.Supplement-1.65>.
- Erlebacher, J. D., E. Brown, M. F. Mecklenburg, and C. S. Tumosa. 1992. "The Effects of Temperature and Relative Humidity on the Mechanical Properties of Modern Painting Materials." In *Materials Issues in Art and Archaeology III*, ed. P. Vandiver, J. R. Druzik, G. S. Wheeler, and I. Freestone, pp. 359–370. MRS Symposium Proceedings, No. 267. Pittsburgh: Materials Research Society. <https://doi.org/10.1557/PROC-267-359>.
- Lazzari, M., and O. Chiantore. 1999. Drying and Oxidative Degradation of Linseed Oil. *Polymer Degradation and Stability*, 65(2):303–313. [https://doi.org/10.1016/S0141-3910\(99\)00020-8](https://doi.org/10.1016/S0141-3910(99)00020-8).
- Mecklenburg, M. F., and C. S. Tumosa. 2001. Traditional Oil Paints: The Effects of Long-Term Chemical and Mechanical Properties on Restoration Efforts. *MRS Bulletin*, 26(1):51–54. <https://doi.org/10.1557/mrs2001.19>.
- Mecklenburg, M. F., C. S. Tumosa, and D. Erhardt. 2005. "The Changing Mechanical Properties of Aging Oil Paints." In *Materials Issues in Art and Archaeology VII*, ed. P. B. Vandiver, J. L. Mass, and A. Murray, pp. 13–24. MRS Symposium Proceedings, No. 852. Warrendale, Pa.: Materials Research Society. <https://doi.org/10.1557/PROC-852-003.1>.
- Muizebelt, W. J., J. C. Hubert, and R. A. M. Venderbosch. 1994. Mechanistic Study of Drying of Alkyd Resins Using Ethyl Linoleate as a Model Substance. *Progress in Organic Coatings*, 24(1–4):263–279.
- Muizebelt, W. J., and M. W. F. Nielen. 1996. Oxidative Crosslinking of Unsaturated Fatty Acids Studied with Mass Spectrometry. *Journal of Mass Spectrometry*, 31(5):545–554. [https://doi.org/10.1002/\(SICI\)1096-9888\(199605\)31:5<545::AID-JMS329>3.0.CO;2-1](https://doi.org/10.1002/(SICI)1096-9888(199605)31:5<545::AID-JMS329>3.0.CO;2-1).
- Oliver, W. C., and G. M. Pharr. 1992. An Improved Technique for Determining Hardness and Elastic Modulus Using Load and Displacement Sensing Indentation Experiments. *Journal of Materials Research*, 7(6):1564–1583. <https://doi.org/10.1557/JMR.1992.1564>.
- Oyman, Z. O., W. Ming, and R. van der Linde. 2005a. Oxidation of Drying Oils Containing Non-conjugated and Conjugated Double Bonds Catalyzed by a Cobalt Catalyst. *Progress in Organic Coatings*, 54(3):198–204. <https://doi.org/10.1016/j.porgcoat.2005.06.004>.

- Oyman, Z. O., W. Ming, R. van der Linde, R. van Gorkum, and E. Bouwman. 2005b. Effect of $[\text{Mn}(\text{acac})_3]$ and Its Combination with 2,2'-Bipyridine on the Autoxidation and Oligomerisation of Ethyl Linoleate. *Polymer*, 46(6):1731–1738. <https://doi.org/10.1016/j.polymer.2004.12.045>.
- Salvant, J., E. Barthel, and M. Menu. 2011. “Nanoindentation and the Micromechanics of Van Gogh Oil Paints.” *Applied Physics A*, 104:509–515. <https://doi.org/10.1007/s00339-011-6486-x>.
- Sturdy, L., F. Casadio, M. Kokkori, K. Muir, and K. R. Shull. 2014. Quartz Crystal Rheometry: A Quantitative Technique for Studying Curing and Aging in Artists' Paints. *Polymer Degradation and Stability*, 107:348–355. <https://doi.org/10.1016/j.polymdegradstab.2014.02.009>.
- Sturdy, L. F., A. Yee, F. Casadio, and K. R. Shull. 2016. Quantitative Characterization of Alkyd Cure Kinetics with the Quartz Crystal Microbalance. *Polymer*, 103:387–396. <https://doi.org/10.1016/j.polymer.2016.09.063>.
- Tumosa, C. S., D. Erhardt, M. F. Mecklenburg, and X. Su. 2005. “Linseed Oil Paint as Ionomer: Synthesis and Characterization.” In *Materials Issues in Art and Archaeology VII*, ed. P. B. Vandiver, J. L. Mass, and A. Murray, pp. 25–31. MRS Symposium Proceedings, No. 852. Warrendale, Pa.: Materials Research Society. <https://doi.org/10.1557/PROC-852-OO3.2>.

Future Trends in Mechanical Research Applied to Heritage Science

*Łukasz Bratasz,¹ Liu Liu,² Cynthia Schwarz,³
and Anne Gunnison³*

ABSTRACT. Despite unquestionable developments in the understanding of the mechanical behavior of heritage objects in response to their environment, several significant gaps in this knowledge still exist. This paper aims to identify some of these gaps and suggest future applications of mechanical research to heritage science. One area in need of further study is the interface between the chemical degradation of modern materials and their mechanical properties, especially material shrinkage. The pressing need for further research in this area is illustrated in the case study of two identical cellulose acetate objects made by Marcel Duchamp. After being housed in two different environments the objects arrived at dramatically different states of preservation. Unexpected material shrinkage not related to plasticizer loss was also confirmed by the artificial aging of samples prepared in the laboratory. This paper also focuses on gaps in knowledge that create barriers in the development of meaningful models for risk assessment and management of heritage collections. There is a lack of adequate models to assess the risk of mechanical damage caused by extreme but rare climate variations and to estimate the rate of mechanical damage caused by a large number of moderate ones. The absence of these models has impeded progress toward a consensus on museum standards with wider RH variations. It also creates a barrier in communication with decision makers when designing strategies for climate control in new museum buildings or when retrofitting existing ones. This barrier limits the implementation of more energy efficient strategies of collection care in museums, libraries, and archives.

INTRODUCTION

The notion that the deterioration of objects is related to the environment, more precisely, to indoor climate, existed long before the first museums were created. Historically, we see this concept reflected in good practice and housekeeping rules (Staniforth, 2013), which over centuries evolved into the climate specifications we know today. This evolution was driven by two factors: first, a better, albeit incomplete, understanding of the cause-effect relationship between climate parameters, namely, temperature and relative humidity (RH), and deterioration processes and, second, the development in the first half of the twentieth century of mechanical systems to control indoor climate.¹

Without going into detail and acknowledging the existence of a complex mix of various deterioration mechanisms, in specific instances (i.e., glass deterioration), one can say that the general structure of the degradation processes related to climate is well understood. Within this structure we can distinguish several key processes:

¹ The Cultural Heritage Research Group, Jerzy Haber Institute of Catalysis and Surface Chemistry, Polish Academy of Sciences, ulica Niezapominajek 8, 30-239 Krakow, Poland.

² Institute of Culture and Heritage, Northwestern Polytechnical University, Xi'an 710000, China.

³ Yale University Art Gallery, Yale University, P.O. Box 208271, New Haven, Connecticut 06520, USA.

* Correspondence: ncbratas@cyf-kr.edu.pl

Manuscript received 2 June 2018; accepted 7 May 2019.

- biological degradation, including fungal growth and insect infestation
- chemical degradation, in particular degradation of chemically unstable materials, corrosion, and pyrite degradation
- phase changes of hydrates and dissolution of hygroscopic salts
- mechanical damage caused by material dimensional response to climate variations

The biological damage caused by fungal or pest infestation and chemical degradation are both cumulative processes that are dependent on temperature and RH. The chemical degradation of heritage materials can be caused by interaction with several environmental agents, among the most important being temperature, RH, pollutants, and visible and UV light. In recent years, the chemical degradation of plastics has become more and more relevant as the number of objects in museums' collections made of synthetic polymers has systematically increased. The most common are polymethyl acrylate, polyesters, polyurethanes, polyolefins, polyvinyl chloride, cellulose nitrate, and cellulose acetate.²

Humidity variations can lead to various types of erosion of mineral materials contaminated with soluble salts, especially archaeological objects, pottery, ceramics, masonry sculptures, etc. This deterioration is because the physical structure of some hydrates can change in response to changes in relative humidity and temperature. Additionally, some minerals can deliquesce above a certain RH and recrystallize when RH drops below this value.³

The dimensional response of materials to temperature or relative humidity changes can cause cracking or delamination of brittle materials. However, the risk generated by temperature variations is practically negligible, with the exception of extreme temperature changes typically larger than $\pm 40^{\circ}\text{C}$ (Mecklenburg et al., 1992; Richard et al., 1998). Such changes commonly occur during object freezing for pest control or during transportation. The risk is also practically limited to laminated objects composed of materials having very different temperature expansion coefficients such as ceramics or glass and metal in enamels and mirrors and oil paint and wood in its longitudinal direction in furniture or musical instruments. At this point, it is worth mentioning that past temperature specifications as well as recent ones recommending temperature between 15°C and 25°C (American Society of Heating, Refrigerating and Air-Conditioning Engineers [ASHRAE], 2015; International Institute for Conservation of Historic and Artistic Works, 2014) were adopted not to diminish the risk of mechanical damage induced by temperature changes but to ensure the thermal comfort of visitors and museum staff. In fact, except for certain materials like acrylic paints, which become brittle at low temperatures, cool storage is optimal for library, archive, and mixed museum collection objects endangered by the chemical degradation of

polymers (see Sebera, 1994; Strang and Grattan, 2009; Strlič et al., 2015) or biological infestation.

In contrast to temperature, RH specifications were proposed to safeguard vulnerable collections from mechanical damage. With the exception of specifications for historic buildings with limited potential for climate control, for example, class 2 of Thomson's (1978) influential guidelines, most past RH specifications were not designed according to actual objects needs, but rather according to the best available technology. This resulted in the dissemination of a very stringent band of allowable RH fluctuation as energy costs were low, and asking difficult questions was avoided. Partially, the reason for such situations was a poor understanding of the mechanism of mechanical damage development caused by climate variations. This situation continued until Marion Mecklenburg and his group at the Smithsonian undertook research that laid a foundation for our understanding of the structural response of objects to changes in ambient RH (Mecklenburg and Tumosa, 1991). Sensitive materials—wood, animal glue, gesso, paints, paper, ivory, textiles, and leather—respond dimensionally to humidity changes. These materials shrink when they lose moisture and swell when they gain moisture. Responsive materials may also experience stress due to a restraint on their dimensional response resulting from an external construction restricting movement or by assembling materials that respond differently to RH changes, which is the case with panel and canvas paintings. Materials can also experience internal restraint as moisture diffusion is not instantaneous and uneven moisture change induces uneven dimensional response. The stress resulting from restrained movement can cause deformation as stress exceeds the yield point and can continue to cracking of the material when the stress exceeds its strength. Mecklenburg (2007) systematically examined the dimensional response to climatic changes and the critical levels of strain and stress at which materials begin to deform plastically or fail physically for wide classes of materials.

The model developed by Mecklenburg provided the field's first maps of allowable RH variations. These maps, as well as maps obtained by other researchers, take into account the amplitude, duration, and starting RH levels (Mecklenburg et al., 1998; Jakiela et al., 2008; Bratasz et al., 2015) and propose environmental specifications for collections of historic objects (Erhard and Mecklenburg, 1994; ASHRAE, 2015).

Scientific research into the damaging impact of RH variations on some materials was further refined by taking into account their vulnerability to fatigue fracture (Michalski, 1991; Rachwał et al., 2012; Bratasz et al., 2015), a consequence of the cumulative strain effects caused by cyclically repeated RH fluctuations, which may range from slow seasonal changes (i.e., an RH decrease in winter due to heating and a return to a higher RH level in summer) to brief RH fluctuations, even under an hour in duration, for example, during object transportation.

The most general conclusion from a critical review of existing data and recent publications is that moderate variations within the approximate RH range 30%–60% are safe for almost all collection objects. This range was derived using the extremes of conservative criteria of the materials' yield and fatigue fracture and assumptions of maximal possible material response. The quoted allowable RH variations correspond approximately to class of control B of the ASHRAE specifications. This class of control is often the only possible moderate-cost strategy in historic buildings also in use as museums, with limited potential for precise climate control.

Further broadening the allowable fluctuations can result from observations that objects survived remarkably well in conditions that were even broader than 30%–60%. Therefore, climate specifications based on the acclimatization concept remain a useful tool, especially when electronic monitoring systems can provide long-term past climate records in remarkable detail.

FUTURE RESEARCH

Despite unquestionable developments in the understanding of the mechanical behavior of heritage objects in response to their environments, several significant gaps in knowledge still exist. The purpose of this paper is to share our opinion on what those gaps are and what future trends in mechanical research in the field of heritage science will be.

COUPLING OF CHEMICAL DEGRADATION WITH MECHANICAL DAMAGE

Although objects made of modern materials began to appear in museum collections in the 1940s, conservation strategies for these objects were not well investigated until the 1980s. The reason, in part, is that severe structural degradation of modern materials develops over a relatively long dormant period during which the properties of these materials remain almost unchanged. However, recently, the anxiety of conservators and curators related to storage, exposition, and transport has been reflected in the growing number of conference presentations, scientific publications, and research projects focused on problems specific to the degradation of museum objects made of plastic (Preservation of Plastic Artefacts in Museum Collections [POPART], 2016). A review of existing information shows significant progress in the ability of the conservation community to precisely characterize materials and degradation products. This progress is especially visible in our understanding of chemical reactions leading to plastics degradation. However, the cause and effect relationship between chemical degradation and the resulting changes in mechanical properties

is much less researched and understood. Especially missing is information about material dimensional changes, which are usually the first manifestation of undergoing chemical changes.

The case study presented below of Marcel Duchamp's *Little Large Glass* is, in our opinion, a convincing illustration of the need for new research, as existing explanations of the mechanisms of material deformation are not complete.⁴ In the mid-twentieth century, the Yale University Art Gallery received several objects created by Marcel Duchamp as part of the Société Anonyme Collection. The gift included two of Duchamp's "deluxe" versions of the *Boîte-en-valise*. The piece is a leather valise containing 69 miniature replicas and color reproductions of Duchamp's most famous works. Within each of the *boîtes* is a small replica of Duchamp's *The Bride Stripped Bare by Her Bachelors, Even*, called the *Large Glass*. This miniature version of his famous work is referred to as the *Little Large Glass*. The replica is a 0.6 mm thick transparent cellulose acetate (CA) sheet on which imagery has been etched, printed, and stenciled. Among the other pieces donated with the Société Anonyme Collection was a stand-alone *Little Large Glass*, not associated with a *boîte* but identical to those within each *Boîte-en-valise* (Figure 1).

Within the last 5 years, the stand-alone *Little Large Glass* was encapsulated in Mylar as part of a rehousing effort. In early 2015, liquid had accumulated in the encapsulation (Figure 2). The Mylar was opened, and the liquid immediately formed crystals—later characterized with Fourier transform infrared spectroscopy as primarily the plasticizer triphenyl phosphate (TPP)—across both sides of the object, as shown in Figure 4. When first removed from the Mylar, the CA substrate was relatively flat, but over the course of the week it undulated, and over the next few weeks, it cupped.

An acetic acid odor indicates that the CA is partially hydrolyzed. When compared to the *Large Glass* reproductions in the two *boîtes* of the YUAG collection, the difference is striking, with the two in situ still relatively planar and the plastic clear.

The analysis of the behavior of the *Little Large Glass* indicates that processes of plasticizer diffusion and evaporation, which are frequently used to explain shrinkage of plastics over a time (Preservation of Plastic Artefacts in Museum Collections [POPART], 2016), cannot explain the above observations. First, encapsulating the object between Mylar sheets would have limited rather than accelerated plasticizer diffusion and evaporation, indicating that another transport mechanism was involved. Second, separation of the plasticizer from the material, both when visible as droplets in Figure 2 and as crystallization of the plasticizer shown in Figure 3A, did not cause any readily visible dimensional change. Therefore, the main and open question is, What is the primary cause for the observed CA shrinkage? The answer to this question is fundamental for the development of

FIGURE 1. *Boîte-en-valise* containing *Little Large Glass* (left; Marcel Duchamp, *Boîte-en-valise*, 1948, Yale University Art Gallery, 1948.102) and its replica (right; Marcel Duchamp, *Little Large Glass*, circa 1942, Yale University Art Gallery, 1953.6).

an effective preservation strategy and treatment options not only for this piece but also for collections containing millions of objects made with CA film, as in the case of the Disney Animation Research Library (Hoeyng et al., 2016).

Tests performed at the Yale Institute for the Preservation of Cultural Heritage were able to shed some light on the degradation and related shrinkage of cellulose acetate. For our testing, both samples prepared in the lab and commercially purchased CA films were used. In total, almost 200 CA samples were prepared by casting acetone-solubilized CA into 0.04 mm films using a drawdown bar. The film was then cut into 120 × 8 mm flat samples. The samples have plasticizer contents of 0%, 10%, 20%, and 40%. A 1:1 mixture of TPP and diethyl phthalate (DEP) was used as a plasticizer. Additionally, commercial CA film with a thickness of 0.035 mm was purchased from Electron Microscopy Sciences.

Samples were artificially aged in a climate chamber at 70°C ± 2°C and 75% ± 3% RH in three desiccators. The aging conditions were chosen to be close to conditions of tests carried out at the Getty Conservation Institute on commercial CA (Richardson et al., 2014) for comparison. One desiccator contained only NaCl saturated solution to additionally stabilize the RH. The second one contained NaCl solution and a container with acetic acid (AA), and the third one contained

NaCl solution, AA, and TPP and DEP. Acetic acid was added to create an environment mimicking the worst-case environment typical for tightly enclosed small volumes resulting from the accumulation of AA released during CA hydrolysis. The plasticizers were added to the third desiccator to block plasticizer diffusion and evaporation from the material in order to see the role of these processes in CA degradation.

The experiment was planned to run for many days, similar to the test performed by Richardson et al. (2014). Surprisingly, all samples that were exposed to AA underwent sudden and severe deformation after 13–15 hours. Interestingly, shrinkage occurred in all samples independent of plasticizer content, indicating that observed mechanical damage is related to some changes in the CA matrix. The only observed difference between the behaviors of samples with different plasticizer contents was the development of a noticeable efflorescence of plasticizer crystals on the sample surface containing 40% of the plasticizer, similar to the efflorescence observed on Duchamp's *Little Large Glass*. All samples aged in the AA-free environment survived the test without any observable change.

Both the empirical observations of Duchamp's *Little Large Glass* and the preliminary test described above indicate that the mechanism of material shrinkage leading to deformation

FIGURE 2. *Little Large Glass* encapsulated between Mylar sheets. Liquid droplets are visible on the surface.

FIGURE 3. Three stages of *Little Large Glass* after the object was removed from the Mylar: (A) immediately, (B) 1 week, and (C) 2 years after object removal.

in cellulose acetate objects still needs to be understood for better preservation and treatment of modern materials.

FURTHER REFINEMENT OF ALLOWABLE RANGE OF CLIMATE VARIATIONS

The past 30 years of scientific research underscore the relationship between biological, chemical, and mechanical degradation processes and climate parameters and allow the heritage preservation field to better define the optimal climate for mixed museum collection while keeping cost reasonable. If access to the collection is not a priority, the conservation community knows how to build economic but at the same time almost zero energy storage for collections and significantly reduce the rate of chemical degradation of organic materials and the risk of mechanical damage, as shown by Larsen and Ryhl-Svendsen (this volume). The conservation community still debates environmental standards for heritage collections on display or in storage, where demand for human comfort cannot be neglected. The “no change” position has been best articulated by the National Gallery in London on their web page on “Paintings and Their Environment” (National Gallery, 2017). The position is supported

by painting conservators in Germany, Austria, and Switzerland, as expressed by the Doerner Institute (2013.) and by the paper of Burmester and Eibl (2014). As a consequence, many institutions still follow stringent climate specifications. Therefore, energy consumption remains high and could be significantly reduced as shown by the Museum Conservation Institute (2015) and Łukowski et al. (2013).

Despite the lack of consensus on new environmental standards, the main conclusion from the ongoing discussion is that many existing ones intended to help museums, libraries, and archives to meet their responsibility to preserve cultural collections have the following characteristics:

- They are too tight and therefore impossible to implement in most buildings, especially historic buildings.
- They require significant financial, organizational, and environmental costs.
- They do not address actual priorities, even those related to climate parameters, of most institutions identified by practical risk assessment.

Subsequent sections aim to identify the main barriers preventing museum communities from reaching a common consensus toward broadening the acceptable RH variations in a museum climate.

ANALYSIS OF MECHANICAL BEHAVIOR OF MATERIALS IN RESPONSE TO CLIMATE VARIATIONS

As mentioned above, today, the conservation community has enough information to reliably assess the risk of mechanical damage to many categories of museum objects. This information comprises both conceptual models of materials' responses to climate changes and key material parameters. These parameters include moisture diffusion and surface emission coefficients, sorption isotherms, hygric and temperature expansion coefficients, Young's moduli, Poisson's ratios, yield points, and strength. Additionally, the secant modulus and failure strain master curves and fatigue parameters are known for some art materials. The increasing availability of specialized software for numerical simulation and the development of powerful computers now also allow us to analyze the structural response of objects composed of several materials and of complex geometry to long-term real world climate variations.

One of the main barriers to the acceptance of the results based on the analysis of mechanical behavior showing that a far wider RH range is safer than previously assumed is that the supporting arguments have been obtained via new or artificially aged samples. Therefore, there is a need to determine more mechanical parameters using original historic samples. The project started at the Getty Conservation Institute (Łukomski et al., this volume) aims at the mechanical microcharacterization of statistically relevant groups of historic artistic materials and will be a fundamental step forward to address this gap. As large sets of historic materials are available only as submillimeter samples, new nanoindentation techniques seem especially promising. One of the open questions is, however, how to use nanoindentation to determine yield strain and strain at failure—key failure criteria used in all models assessing risk of damage—in historic microsamples.

Another vital element of mechanical models that requires more attention is the level of residual stress in artifacts. The usual practice is to assume zero stress for average climate parameters. There is a tacit assumption behind this practice that the relaxation time of materials is much shorter than the period during which a material was exposed to that particular environment and that stress relaxation leads to zero stress. This assumption might hold for some materials but definitely does not apply to all. Hence, there is a need to study the long-term time-dependent behavior of materials, especially those that exhibit limited potential for stress relaxation, like wood and certain decorative layers. The new data would give the conservation community a better understanding of the safe range of climatic conditions for objects in climates that differ significantly from "optimal" museum conditions.

Most of the mechanical research aimed at determining the safe range of climate variation has been focused on vulnerable museum objects like paintings, furniture, textiles, etc. However, minor sound mechanical analysis has been

performed for library and archival collections. The conceptual model of mechanical damage developed by Mecklenburg needs to be refined to address these objects, especially illuminated parchments, manuscripts, and books. In such objects, mechanical damage is related not only to cracks, tears, wear, and delamination but also to three-dimensional deformation.

The gap in sound data in this area is well illustrated by the fact that the new standard ISO 11799:2015 (International Standard Organization [ISO], 2015) does not specify stringent climate specification like the previous edition (ISO, 2003) did, yet it also does not suggest any safe range of RH fluctuation, leaving it deliberately vague. The new ISO technical recommendation (ISO, 2018) upholds the opinion that the optimum range of RH variations for all archival or library collections cannot be specified but suggests that, generally, the optimum falls in the range of 30%–60% RH.

It is clear that research focusing on library and archival materials' responses to RH variations, for example, the research presented by A. Carver-Kubik and James Reilly (this volume), can enable the development of better-informed and more environmentally friendly strategies of climate control in libraries and archives. The potential impact on improving energy efficiency and reduction of CO₂ emission in the heritage sector is large as a rough estimation shows that there are two times more archives than museums globally.

ACCLIMATIZATION CONCEPT

The acclimatization of heritage objects to a particular indoor environment within which they have been preserved has been a well-established concept in the conservation field, and it has been widely used to establish the criteria for climate control. Michalski (2009, 2014a) coined the term *proofed fluctuation*, defined as the pattern of the largest RH or temperature fluctuations to which a collection had been exposed in the past. It was assumed that the risk of continued physical damage from fluctuations that do not go beyond the proofed pattern is extremely low. The proofed fluctuation concept is a very convenient tool for collection managers as it eliminates the need for elaborate mechanical response analysis and offers a risk assessment for an entire collection based solely on past climate records. Michalski (2014b) provided a practical method for extrapolating to multiple future cycles from a maximum historic fluctuation of $\pm X\%$ RH; for example, at $\pm 0.9X\%$ up to 30 future fluctuations are tolerable, at $\pm 0.65X\%$ up to 1,000 future fluctuations are tolerable, etc.

Mechanical tests performed by Michalski (1991) showed that the cracking of the glue ground layer on linen starts after 10^6 cycles of 0.1% strain amplitude and continues for an increasing number of such cycles. Kozłowski et al. (2011) also showed that after crack initiation in the glue ground layer applied on wood, cracking continues for thousands of repeated

cycles before the density of cracks saturates. Strojceki et al. (2014), using the acoustic emission method, showed that the cracking process was still active in a wooden wardrobe dated to 1785 with an estimated rate of crack propagation of 0.6 mm/year. In the gallery, where the wardrobe was exhibited, the amplitude of yearly RH variations was 35%. Assuming an equal rate of crack propagation during the 27 years since a climate control system was introduced, one can estimate that the crack length increased by 16 mm in that time. Before 1989, for almost 200 years, the wardrobe was stored in interiors without humidity control. For such interiors in the Polish climate, a 55% amplitude of RH variations is typically recorded. Using the approach proposed by Michalski, one can calculate that for a RH cycle with an amplitude of 55%, the rate of crack propagation is 600 mm/year (1,000 times larger than for the 35% amplitude). The obtained propagation rates enable calculation of the damage development from the moment the wardrobe was constructed to the present. The obtained value, 122 m, is unrealistically large. This result suggests that the rate of crack propagation caused by fluctuations is less than the “proofed” one and decreases slower than in the Michalski model.

The above observations indicate that more experimental and theoretical work is required to understand fatigue damage in historic objects and to estimate the contribution of large numbers of climate cycles to damage development. Using the obtained results, a new model should be developed not on the basis of the plot of the amplitude of an alternating stress versus the number of cycles to failure, so called *S-N* curve (as in Michalski's approach), but rather on an analysis of the damage propagation rate in a material in which damage already exists. The application of nondestructive methods for direct damage tracing in historic objects can be particularly suitable for providing data supporting development of such a model.

PRACTICAL TOOLS

The development of damage functions for biological and chemical processes leading to the loss of collections value proved successful in optimizing collections care in many museums, libraries, and archives. However, only the development of simple and easy-to-use tools and risk indicators opened the doors for wider application of scientific research to collections management. Such tools, for example, the time-weighted preservation index (TWPI) proposed by the Image Permanence Institute and WuFi Bio software designed by the Fraunhofer Institute, have been increasingly used in recent years. In particular, TWPI proved to be a powerful tool when defining preservation targets and designing preservation strategy in museums, libraries, and archives, according to the excellent British standard PAS 198:2012 (British Standards Institution, 2012). Unfortunately, there are no adequate and easy-to-use

tools similar to TWPI for the quantitative assessment of the risk of mechanical damage to various object categories caused by climate variations. Proposed tools, such as eClimateNotebook (Image Permanence Institute, 2016) and the method proposed by Martens (2012), do not reflect the physical reality of heritage objects with sufficient detail. A lack of adequate tools creates a barrier in communication with decision makers when designing a new sustainable preservation strategy for a collection, which requires a balance of collection care with associated financial and environmental costs. Finding that balance requires that decision makers know the relationship between expected mechanical damage, for example, the increase of crack length and percentage of the collection affected, and various climate control strategies. When this information is combined with information about cost and CO₂ emission, an adequate cost-benefit analysis can be successfully performed.

An attempt to fill the existing gap and develop such a tool, named HERIE by its authors, has been undertaken by a consortium of research institutions as presented by Kozłowski et al. (this volume). Using a web-based platform, the user is asked to provide a basic characterization of the object and the 1-year (or multiyear) microclimatic data, measured or simulated for future preservation scenarios. The risk is assessed by calculating and analyzing strain versus time histories in specific objects in real-world microclimates. All calculations are performed using a predefined database, so using the HERIE tool does not require any experience in mechanical analysis. HERIE is freely available for testing at <http://herie.mnk.pl>.

CONCLUSIONS

Ideally, future trends in mechanical research applied to the heritage field will address the interface between the chemical degradation of synthetic materials and the resulting mechanical changes, as well as some aspects of mechanical damage development caused by climate variations. This opinion grew out of the identification of the gaps in our knowledge that make collection management less effective in terms of both collection care and the associated environmental costs. However, this topic is one of a long list of other interesting and important research ideas that have not been adequately addressed. Despite this, we hope that this work will help young and talented researchers to identify their own interests at the crossroads where the humanities and engineering disciplines meet.

NOTES

1. An interesting overview of the history of climate control and climate specifications in museums can be found in Bratasz (2013), Luciani (2013), Bickert (2014), and Michalski (2014b).
2. A thorough review of plastic degradation can be found in Shashoua (2008).

3. Comprehensive information on mineral interaction with climate can be found in Waller (1992).
4. See, for example, the POPART Damage Atlas (POPART, 2016).

REFERENCES

- American Society of Heating, Refrigerating and Air-Conditioning Engineers (ASHRAE). 2015. "Museums, Galleries, Archives and Libraries." In *ASHRAE Handbook—HVAC Applications*, pp. 21.1–21.26. Atlanta, Ga.: American Society of Heating, Refrigerating and Air-Conditioning Engineers.
- Bickersteth, J. 2014. Environmental Conditions for Safeguarding Collections: What Should Our Set Points Be? *Studies in Conservation*, 59(4):218–224.
- Bratasz, Ł. 2013. Allowable Microclimatic Variations for Painted Wood. *Studies in Conservation*, 58(2):65–79.
- Bratasz, Ł., M. Łukowski, A. Klisińska-Kopacz, W. Zawadzki, K. Dzierżęga, M. Bartosik, J. Sobczyk, F. J. Lennard, and R. Kozłowski. 2015. Risk of Climate-Induced Damage in Historic Textiles. *Strain*, 51:78–88.
- British Standards Institution. 2012. Specification for Managing Environmental Conditions for Cultural Collections. PAS 198:2012. London: British Standards Institution.
- Burmester, A., and M. Eibl. 2014. Stable Is Safe. The Munich Position on Climate and Cultural Heritage. http://www.doernerinstitut.de/downloads/Statement_Doerner_Bizot_en.pdf (accessed 16 September 2016).
- Doerner Institute. 2013. Projects: Stable Is Safe. http://www.doernerinstitut.de/en/projekte/Bizot/bizot_1.html (accessed 16 September 2016).
- Erhardt, D., and M. Mecklenburg. 1994. "Relative Humidity Re-examined." In *Preventive Conservation Practice, Theory and Research*, ed. A. Roy and P. Smith, pp. 32–38. London: International Institute of Conservation.
- Hoeyng, K., S. Etyemez, K. McCormick, M. Schilling, and A. Phenix. 2016. "Curling, Ripples, Dimples: Observations from a Condition Survey of Animation Cels." In *Saving the Now: Crossing Boundaries to Conserve Contemporary Works: Contributions to the Los Angeles Congress, 12–16 September 2016*, ed. A. Nevin, J. Townsend, J. Atkinson, D. Saunders, and A. Brokerhof, pp. 294–296. London: International Institute for Conservation of Historic and Artistic Works.
- Image Permanence Institute. 2016. eClimateootebook. <https://www.eclimatenotebook.com> (accessed 16 September 2016).
- International Institute for Conservation of Historic and Artistic Works. 2014. Environmental Guidelines—IIC and ICOM-CC Declaration. <https://www.iiiconservation.org/node/5168/> (accessed 16 September 2016).
- International Standard Organization (ISO). 2003. Information and Documentation - Document Storage Requirements for Archive and Library Materials. ISO 11799:2003. Geneva: International Standard Organization.
- International Standard Organization (ISO). 2015. Information and Documentation - Document Storage Requirements for Archive and Library Materials. ISO 11799:2015. Geneva: International Standard Organization.
- International Standard Organization (ISO). 2018. Technical Report Information and Documentation — Management of the Environmental Conditions for Archive and Library Collections. ISO/TR 19815:2018. Geneva: International Standard Organization.
- Jakiela, S., Ł. Bratasz, and R. Kozłowski. 2008. Numerical Modelling of Moisture Movement and Related Stress Field in Lime Wood Subjected to Changing Climate Conditions. *Wood Science and Technology*, 42:21–37.
- Kozłowski, R., Ł. Bratasz, Ł. Lasyk, and M. Łukowski. 2011. "Allowable Microclimatic Variations for Painted Wood: Direct Tracing of Damage Development." In *Facing the Challenges of Panel Paintings Conservation: Trends, Treatments and Training*, ed. A. Phenix and A. S. Chui, pp. 158–164. Los Angeles: Getty Conservation Institute.
- Luciani, A. 2013. Historical Climates and Conservation Environments. Historical Perspectives on Climate Control Strategies within Museums and Heritage Buildings. Ph.D. diss., Politecnico di Milano, Milan.
- Łukowski, M., J. Czop, M. Strojceki, and Ł. Bratasz. 2013. "Acoustic Emission Monitoring: On the Path to Rational Strategies for Collection Care." In *Climate for Collections: Standards and Uncertainties*, ed. J. Ashley-Smith, A. Burmester, and M. Eibl, pp. 69–80. London: Archetype.
- Martens, M. 2012. Climate Risk Assessment in Museums: Degradation Risks Determined from Temperature and Relative Humidity Data. Ph.D. thesis, Technische Universiteit Eindhoven, Eindhoven, Netherlands.
- Mecklenburg, M. F. 2007. Determining the Acceptable Ranges of Relative Humidity and Temperature in Museums and Galleries: Part 1, Structural Response to Relative Humidity. Internal Report. Suitland, Md.: Museum Conservation Institute. <http://www.si.edu/mci/downloads/reports/mecklenburg-part1-rh.pdf> (accessed 31 August 2016).
- Mecklenburg, M. F., and C. S. Tumosa. 1991. "Mechanical Behavior of Paintings Subjected to Changes in Temperature and Relative Humidity." In *Art in Transit: Studies in the Transport of Paintings*, ed. M. F. Mecklenburg, pp. 173–217. Washington, D.C.: National Gallery of Art.
- Mecklenburg, M. F., C. S. Tumosa, and D. Erhardt. 1998. "Structural Response of Painted Wood Surfaces to Changes in Ambient Relative Humidity." In *Painted Wood: History and Conservation*, ed. V. Dorge and F. C. Howlett, pp. 464–483. Los Angeles: Getty Conservation Institute.
- Mecklenburg, M., C. S. Tumosa, and M. H. McCormick-Goodhart. 1992. "A General Method for Determining the Mechanical Properties Needed for the Computer Analysis of Polymeric Structures Subjected to Changes." In *Materials Issues in Art and Archaeology III*, ed. P. B. Vandiver, J. R. Druzik, G. S. Wheeler, and I. C. Freestone, pp. 337–292. MRS Symposium Proceedings, No. 267. Pittsburgh: Materials Research Society.
- Michalski, S. 1991. "Paintings, Their Response to Temperature, Relative Humidity, Shock and Vibration." In *Art in Transit: Studies in the Transport of Paintings*, ed. M. F. Mecklenburg, pp. 223–248. Washington, D.C.: National Gallery of Art.
- Michalski, S. 2009. "The Ideal Climate, Risk Management, the ASHRAE Chapter, Proofed Fluctuations, and Towards a Full Risk Analysis Model." In *Proceedings of Experts' Roundtable on Sustainable Climate Management Strategies, Tenerife, 2007*, ed. F. Boersma, pp. 1–19. Los Angeles: Getty Conservation Institute.
- Michalski, S. 2014a. "The Power of History in the Analysis of Collection Risks from Climate Fluctuations and Light." In *ICOM-CC, 17th Triennial Conference, Building Strong Culture through Conservation, 15–19 September 2014, Melbourne, Australia: Preprints*, ed. J. Bridgland, pp. 1–8. Paris: International Council of Museums.
- Michalski, S. 2014b. "Climate Guidelines for Heritage Collections: Where We Are in 2014 and How We Got Here." In *Proceedings of the Smithsonian Institution Summit on the Museum Preservation Environment*, ed. S. Stauderman and W. G. Tompkins, pp. 7–22. Washington, D.C.: Smithsonian Institution Scholarly Press.
- Museum Conservation Institute. 2015. Culmination of 20 Years of Green, Energy Savings Research. Museum Conservation Institute, Smithsonian Institution. <http://www.si.edu/mci/english/research/consulting/MuseumEnvironment.html> (accessed 31 August 2016).
- National Gallery. 2017. Paintings and Their Environment. <http://www.nationalgallery.org.uk/paintings/caring-for-the-paintings/paintings-and-their-environment?viewPage=4> (accessed 16 September 2016).
- Preservation of Plastic Artefacts in Museum Collections (POPART). 2016. Damage Atlas. <http://popart-highlights.mnhn.fr/collection-survey/damage-atlas/index.html> (accessed 16 September 2016).
- Rachwał, B., Ł. Bratasz, L. Krzemień, M. Łukowski, and R. Kozłowski. 2012. Fatigue Damage of the Gesso Layer in Panel Paintings Subjected to Changing Climate Conditions. *Strain*, 48(6):474–481.
- Richard, M., M. F. Mecklenburg, and C. S. Tumosa. 1998. "Technical Considerations for the Transport of Panel Paintings." In *The Structural Conservation of Panel Paintings*, ed. K. Dardes and A. Rothe, pp. 525–556. Los Angeles: Getty Conservation Institute.
- Richardson, E., M. Giachet, M. Schilling, and T. Learner. 2014. Assessing the Physical Stability of Archival Cellulose Acetate Films by Monitoring Plasticizer Loss. *Polymer Degradation and Stability*, 107:231–236.
- Sebera, D. K. 1994. *Isoperms: An Environmental Management Tool*. Washington, D.C.: Commission on Preservation and Access.
- Shashoua, I. 2008. *Conservation of Plastics: Materials Science, Degradation and Preservation*. Oxford: Butterworth-Heinemann.
- Staniforth, S. 2013. *Historical Perspectives on Preventive Conservation*. Los Angeles: Getty Conservation Institute.
- Strang, T., and D. Grattan. 2009. Temperature and Humidity Considerations for the Preservation of Collections – The Isoperm Revisited. *e-Preservation Science*, 6:122–128.
- Strlič, M., C. M. Grossi, C. Dillon, N. Bell, K. Fouseki, P. Brimblecombe, E. Menart, K. Ntanos, W. Lindsay, D. Thickett, F. France, and G. De Bruin. 2015. Damage Function for Historic Paper. Part III: Isochrones and Demography of Collections. *Heritage Science*, 3:40.

Strojecki, M., M. Łukomski, L. Krzemień, J. Sobczyk, and Ł. Bratasz. 2014. Acoustic Emission Monitoring of an Eighteenth-Century Wardrobe to Support a Strategy for Indoor Climate Management. *Studies in Conservation*, 59(4):225–232.

Thomson, G. 1978. *The Museum Environment*. London: Butterworths.

Waller, R. 1992. “Temperature and Humidity-Sensitive Mineralogical and Petrological Specimens.” In *The Care and Conservation of Geological Material: Minerals, Rocks, Meteorites, and Lunar Finds*, ed. F. Howie, pp. 25–50. London: Butterworth-Heinemann.

Appendix 1: Thoughts on “Some Aspects of the Mechanical Behavior of Fabric Supported Paintings”

*Marion F. Mecklenburg**

I was asked to write a brief introduction discussing the background that led me to develop the ideas expressed in the article “Some Aspects of the Mechanical Behavior of Fabric Supported Paintings,” which was released in 1982. In all honesty it was really a matter of circumstances, the support of many wonderful people, and considerable luck. My interest in fine arts conservation really started when I was a child growing up in Norfolk, Virginia, in the 1950s. I was taking art lessons at what was then called the Norfolk Museum (now named the Chrysler Museum of Art) when I met Robert Scott Wiles, who was a painting conservator there. As young art students we were given tours of the conservation studio, and my parents developed a friendship with Bob Wiles, so the family kept in touch. The family then moved to Washington, D.C., and we found that Bob had opened a conservation studio in Washington. In 1966 I asked Bob Wiles if I could apprentice with him and was fortunate to get a job under his supervision. Now a critical point here is that although I did have some college education, I had as yet not completed a degree at that time. This was to have important consequences on my future educational directions.

The first painting I worked on was a full-length portrait of Thomas Jefferson by George Catlin after the painting by Thomas Sully that belongs to the State Capitol in Richmond, Virginia. It was covered with an extensive crackle pattern over the entire painting, and I was asked to inpaint the cracks. Bob’s philosophy was, and rightfully so, if one couldn’t properly reconstruct a damaged painting, then one had no business opening up old repairs. Well, I managed to overcome this hurdle, and frankly, the earlier art lessons were a great help. At the time it was standard practice to reline paintings with linen and a mixture of natural waxes and resins. Shortly thereafter we switched to microcrystalline waxes and terpene resins. This time with Bob Wiles was invaluable since it was necessary to learn the “craft of conservation” before answers to the questions that were beginning to form in my mind could be found. For example, I was concerned about the use of what I thought was considerable heat in the lining process. I had seen impasto flattened and moiré patterns caused by the close contact of the original and lining textiles. The latter was more prevalent with the introduction of hot tables, which we did not have at the time. Lining with handheld hot irons and cupping with a shot glass were the standard practice at the Wiles studio. I also wondered what caused the extensive crackle pattern on the Sully portrait of Jefferson. Naturally, I started reading everything I could get my hands on as Bob

Museum Conservation Institute, Smithsonian Institution, 4210 Silver Hill Road, Suitland, Maryland 20746, USA.

* Correspondence: mecklenburgm224@gmail.com

Manuscript received 2 June 2018; accepted 7 May 2019.

Wiles had a very good library of conservation- and artist's materials-related books and journals. Additionally, I started investigating my further education related to this field.

In 1960 Caroline and Sheldon Keck started the graduate program in conservation at New York University (NYU). Basically, the program was teaching many of the things I was learning with Bob Wiles, but there was considerably more, such as providing a very brief background in chemistry and art history. There was also one critical aspect that I was not getting as a new student in the field, which was knowledge about the fundamental materials and construction of paintings. That I had to get from artists' handbooks and other source materials, and frankly, they were useful, but there seemed to me that there was a lot conflicting and often confusing information. In 1970 the Kecks started the conservation training program at Cooperstown, New York, and in the same year Oberlin college started their conservation training program in Ohio. It was even later, in 1974, that the Winterthur/University of Delaware Art Conservation Program was started. All three were master's degree programs. As it turned out for me in 1967, the educational possibilities in conservation were quite limited. I needed a bachelor's degree to even apply to NYU, and the other three programs were yet to open. During my reading on conservation-related matters, one issue that consistently appeared about art and preservation was the effects of adverse environments. The effects of the environment are both chemical and structural issues. Yet there was almost no systematic research related to the structure of art anywhere. In fact, much of the work carried out in any art conservation was structural in nature, yet there was little discussion about the rationale for choosing such treatments. The first edition of Garry Thomson's book *The Museum Environment* did not come out until 1978. And even then he admitted that his environmental recommendations were based largely on creature comfort as little actual research had been conducted on the structural effects of the environment.

It now was decision time about furthering my education. What I decided was to see if I could go back to a university and major in structural engineering. In 1967 I attended night school at the University of Maryland University College for one semester, after which I was accepted into the University of Maryland Civil Engineering Department of the College of Engineering as a full-time student majoring in structures. This did present problems as Bob Wiles needed a full-time employee, and I was full time in school. Fortunately, this was resolved as I was offered a part-time position with Russell Quandt, who was the conservator for the Corcoran Gallery of Art and the Abby Aldrich Rockefeller Folk Art Collection in Williamsburg, Virginia. Russell, who I believe studied under the Kecks, was a most interesting man to work with. He had as many questions about my studies in engineering as those related to art conservation. One day in our discussions I asked him if he knew why environmental changes were harmful to canvas-supported paintings. His response was that the canvases on

the paintings were dimensionally responding to the moisture changes, hence causing the paint to crack. I responded by then asking him, if that were so, why did we continue to use linen canvas as a lining material as this would seem to make matters worse. His response was "tradition," and we both had to laugh after that. But these were not unreasonable questions, and they merited further study. In June of 1970 two major things occurred: I received my B.S. degree in engineering, and unfortunately, Russell passed away. This was a crushing blow for both his family and me as he was fun to be with and had a great inquisitive mind. I still think about him and miss him. It must be said here that where many thought my educational direction was foolish, Russell had encouraged it.

In my last semester as an undergraduate I accepted a fellowship offer to work on a master's degree in engineering. In all candor my decision to go for the master's program at the University of Maryland was not solely based on the fellowship but constant rumblings about dissension in the ranks at NYU and the Kecks leaving to start a new and yet untested training program at Cooperstown. So although I was returning to the university in the fall, I was no longer employed as a conservator. As it turns out, fate intervened, and I was approached by Judith Webster, who was both a conservator and, along with her husband, Donald, a dealer in fine arts. They needed someone to do structural work in paintings such as linings, etc., and Judy would finish with the cleaning and inpainting. Judy had been trained in the fine arts and was an accomplished painter. This relationship turned out to be the best of all possible worlds and is truly what made the research in the structural aspects possible for me.

In May of 1971, Judy Webster and I jointly opened a small conservation studio in Washington, D.C. The plan going in was that I was to help Judy with her work, but I was able to take on private work as I could get it. Over the next 5 years many things happened. First, the business grew rapidly, and I obtained my master's degree in 1972. As it turned out, the Washington area needed a private conservation treatment resource, and although I wasn't aware of the need, I think Judy had this in mind all along. She seemed to always be thinking ahead. The second part of this period was that it gave me time to think about the questions forming about the structure of art. For example, although we initially continued to use canvas as a lining material, we were also gradually switching to multiple layers of fiberglass as a lining substitute. It was also during this time that we constructed our first hot table. Experimentation showed us that we could use minimum pressure successfully. It was also during this time that I started experimenting with wax adhesives. I found that the addition of terpene resins actually had little effect on the strength of the mixture but did have a kind of eutectic effect in that it could lower the melting temperature of the wax-resin mixture. At the same time, I found that it was possible to purchase microcrystalline waxes with lower melting points, eliminating the need for resins altogether. The development and use of aluminum

honeycomb panels as painting supports also occurred at this time, largely prompted by the need to support some very irregularly shaped canvas painting. Judy and I wrote an article on the use of honeycomb panels that was published later in 1977 in *Studies in Conservation* (22(4):177–189). I think this was my first formally published article. One of the positive aspects of this time period was the opportunity to have open discussions with other museum conservators working in the Washington area. At the same time, I came to be aware of one of the really ugly truths about trying to be innovative. It opens one up to rather serious criticism for breaking with tradition. This criticism was to be an unfortunate theme for much of my research career. It made me aware that it wasn't enough to try to improve our understanding of the structure of art, it would be necessary to go on a massive campaign of education. That required a very strong and systematic research program that justified any changes in conservation treatment that might be considered. This program was to be a massive undertaking, and I was unsure at the time as to how to accomplish it or even if it was possible.

Around 1975, we found that the conservation business was growing so fast that we had to consider moving to much larger spaces. At the same time the D.C. government decided to retroactively apply a service tax on conservation income. We tried to fight this off through legal channels but were unsuccessful and finally agreed to a settlement payment. But it also hastened our decision to not only move to a much larger space but to get out of D.C. In 1976 we moved to Kensington, Maryland, gaining over six times the space we had in Washington.

By this time we had had requests from different schools to see if we would accept both short-term and long-term interns, and we did both. So at least we felt that we were having some positive impact. Further, the Kensington facility became the proving ground for some of our research ideas. Also at this time, we had clients that included major institutions in the Washington area and states, private collectors, and art dealers. The business was now financially stable with resources to consider a modest research program. So it now became an issue to determine how to proceed.

I think that everyone will agree that as structures cultural artifacts are complex in that they contain multiple and diverse materials in many different combinations. Further, if any analytical approach is to be successful, it has to be capable of handling these complex shapes and materials. There are different analytical techniques to be considered, and one is computer modeling. But to be successful in modeling, a database of the mechanical properties of cultural materials had to be created. Such a database did not exist. This was clearly the first step in any such research endeavor. My educational background now included many courses in mathematics; various structural analytical techniques, including computer modeling; and techniques in testing the mechanical properties of materials. So at least I had the background to

develop and begin a test program. Further, it was necessary to design and construct the test equipment needed to analyze the mechanical properties of cultural materials. Since nearly all of the cultural material of interest to us was influenced by the environment, the equipment needed to be capable of measuring low-level forces and deformations on multiple small specimens in contained spaces so that the temperature and relative humidity (RH) could be tightly controlled.

In 1978, I started casting different commercial artists' oil paints on polyester sheets so thin films of these paints could be removed and tested as free films. I really had no idea as to how long it would take for these paints to naturally dry and become usable test specimens. I just had to wait it out and see what happened. In the meantime, the test equipment was designed, constructed, and calibrated. I could at least test other materials such as linen canvas, cast samples of hide glue, and other materials. The information I was trying to develop was the mechanical properties of the materials at different levels of RH. They included the complete stress-strain plot, the strength of the material, and the stiffness or flexibility, also known as the elastic modulus. All of this information was to become useful later. Further information needed was the dimensional response of the materials to changes in RH.

The reason that changes in RH can cause damage to a material is the expansion and contraction it undergoes with those changes. If, however, a material is restrained and desiccated, it is unable to contract and develops internal forces or stresses. If those stresses exceed the strength of the material, it will fail. So one basic test would be to restrain a material and monitor the stresses developed as the RH was lowered, although acquiring these data through this process can be slow. First, it takes a fairly long time for cultural materials, even small samples, to equilibrate to changes in the environment. Even a very thin sample of hide glue takes about 12 to 24 hours to come to equilibrium to a change in RH. Second, all cultural materials have time-dependent properties. This means that a sample of material that has been subjected to a force will either stress relax or deform over time depending on whether it is restrained or not. All this information had to be sorted out before it could be used. The solution to this was to apply a load to a restrained sample of a material and measure the length of time it took for the sample to come to equilibrium. After observing the time it takes for a sample to equilibrate to a new environment and fully stress relax after loading, it became clear that building a materials database was going to take a very long time unless one had a very vast array of test facilities where large numbers of materials could be tested simultaneously.

This level of testing was beyond the means of our lab; however, by carefully selecting and testing materials at least a proof of concept program could be completed. This approach was the one that would ultimately lead to the report "Some Aspects of the Mechanical Behavior of Fabric Supported Paintings," which was submitted to Smithsonian

Institution in 1982. I had successfully applied to the National Museum Act at the Smithsonian Institution for modest funds to expand the test program at the lab in Kensington but also established a research collaboration with my master's degree advisor, Dr. James Colville at the University of Maryland. Through this collaboration, I was able to have access to the computers at the university to do the preliminary modeling that was developed for "Some Aspects." It was also possible to develop additional materials testing and analytical methodologies that could be useful in the future. This work led to a Ph.D. degree for Jim Colville's nephew, William Kilpatrick, and some of his dissertation was presented at the Washington conference of the International Institute for Conservation of Historic and Artistic Works in 1982.

If I was to establish a broader research program, I needed to get a job at a major institution, and for this I needed to complete a Ph.D. program of my own. This I did in 1984 and ultimately ended up at the Smithsonian Institution thanks to Tim Padfield. Tim's interest in the work I was doing was instrumental in recommending me to the Smithsonian Institution. On looking back over the years it became clear that the North American philosophy on conservation training emphasized the "craft of conservation" without a strong, fundamental training in the "science of conservation." I also think that this is still the norm as the programs are 2-year training programs, compared to many European programs leading to B.A., M.A., and Ph.D. degrees. Maybe this will change in the not too distant future.

Some Aspects of the Mechanical Behavior of Fabric Supported Paintings

Marion F. Mecklenburg

I. INTRODUCTION

The deterioration of “fabric supported” oil paintings has generated perhaps as much debate during the last four hundred years as have the paintings themselves. In many cases the causes of damage are obvious; accidental tears, biological attack and saturation with water usually are easily identifiable. Not as apparent, however, are the causes of persistent cracking and flaking even after relatively recent conservation treatment. An historically long list of painters have commented on the effects of using excessive animal skin glue,¹ while recent writers have stressed the hygroscopic nature of the fabric support.² Some have discussed the effects of stretchers, while others have further compounded the problem by introducing the concept of paint film behavior with the associated idea that paint films become brittle with “age,”³ or more precisely, with oxidation and polymerization of the oil films. If artists used oil paint directly, perhaps fewer forms of deterioration and destruction would occur, since the addition of dryers and resins alters the mechanical properties of the design layer. Clearly the number of variables is large enough that a systematic analysis of all mechanisms of deterioration of fabric supported oil paintings will take considerable time and resources.

Over the years the general consensus has been reached that environmental moisture plays a significant role in the mechanical deterioration of paintings, based on the assumption that artists’ materials expand and contract due to gain and loss of water associated with changes in environmental moisture. Expansion and contraction have become designated as the primary sources for the cracking and flaking of paint from the fabric support. As a result, attempts are made to stabilize the moisture content of the air in most museums.

The magnitude of environmental moisture content (water vapor present in the air) is usually indicated by the term “percent relative humidity” (%RH), and although an increase in relative humidity might suggest an increase in the water vapor present, this is not always so. A decrease in ambient temperature can cause an increase in RH while the actual amount of water vapor present remains the same.⁴ Relative humidity provides a good way to relate the moisture content of a material specimen to the condition of the surrounding air at a given temperature.

An example of a material influenced by environmental moisture is wood, which swells with an increase in RH and shrinks when RH decreases.⁵ This motion has long been considered the source of destruction of paint on a panel painting. When the panel contracts in excess of the paint’s ability to do so, the paint cleaves under

Though not formally published, this paper first appeared in 1982. The research was supported in part by a grant from the National Museum Act.

compression. Does the wood also expand so much during high RH that the paint film is "stretched" and found to crack under tension? Although the precise mechanisms of the behavior of panel paintings due to RH are yet to be fully determined, a basic principle apparently is at work. A material swells or contracts in an attempt to relieve *stress* generated within that material. Expansion and contraction are *stress release* mechanisms. If a material cracks (due to tension) or crushes and cleaves (due to compression), then it has been unable to completely relieve stress by expanding or contracting and by definition has failed due to excessive stress. In a material such as wood, stress can result from the development of internal force, such as swelling due to water vapor absorption when the wood is restrained, or of external force, such as bending or pulling, or from a combination of both. Similarly, the paint on a fabric supported oil painting cracks because of excessive unrelieved stress, whether the source of the stress is internal or external to the paint. The key questions for the conservator are: what are the sources of the stress, and how does it relate to environmental moisture?

The study of stress development within a material falls under a broad area of investigation called *mechanics*, which can be further broken down into

- 1) the study of the mechanical properties of the materials themselves, and
- 2) the stress analysis of the structures formed by the materials.

All materials found in the traditional oil painting (wood, fabric, glue and oil paint) gain and lose moisture with changes in environmental moisture. To the degree that they do this, they change both dimensionally and in their mechanical properties. The amount of moisture uptake is normally plotted in equilibrium moisture isotherms (EMI). The putrified bast fibers of flax, used to weave linen, are approximately 95% cellulose, while cotton fibers are about 97–99% pure cellulose.⁶ Because of their similar compositions, and since the EMI for cotton is well established (considerably more research has been done on cotton), it is presented here (Figure 1) as a general indication of the EMI for flax, and gives a good description of water content (moisture regain) versus RH. The moisture content is described in terms of moisture regain—the percent weight of water versus weight measured when the fibers are bone dry.

The principal constituent of hide glue is collagen, the fibrous connective tissue found in mammals and fish.⁷ Dry collagen absorbs water from the atmosphere, and the amount of water it can absorb is related to RH (Figure 2).

In both cellulose and collagen the amount of water absorbed can be large, affecting their mechanical behavior. In addition to their ability to absorb, their rate of moisture uptake significantly increases from about 75% RH to 100% RH. This will have some important implications later in the discussion.

FIGURE 1. Sorption isotherm for cotton at 20° C. From J.W.S. Hearle, R.H. Peters, *Moisture in Textiles* (New York: Textile Book Publishers, Inc., Division of Interscience Publishers, Inc. Manchester and London, The Textile Institute, Butterworth Scientific Publications), 1960, p. 18, Figure 8.

Much has been written about the moisture permeability of oil paints, while little research has been done on their actual moisture content. Preliminary research suggests, however, the variability and importance of moisture content. For example, a 42-month old specimen of flake white oil paint (lead carbonate) weighing 0.2520 grams at 5% RH gains 0.0040 grams of water at 98% RH. This is an increase of only 1.6% water by weight, but different pigments and drying times probably affect the amount of water gained. In this particular specimen the change in moisture content was small, yet its effect on the paint was dramatic; this effect will be described below.

Since so much has been written on wood behavior and moisture content, I refer the reader to various texts listed in the endnotes.

As these artists' materials gain and lose moisture they tend to change dimensionally, to expand and contract, which will be described in detail below. A frequently encountered misconception is that this movement is the sole source of

FIGURE 2. Absorption of water vapor by collagen. From F. Haurowitz, *Chemistry and Biology of Proteins* (New York: Academic Press), 1950, p. 91, Figure 24.

stress development and hence of cracking of the material, but this movement is not sufficient, for stress is only developed if the material is either partially or fully restrained during changes in moisture content. For fabric supported oil paintings, this restraint can come either from the various layers of the painting or from the stretcher.

II. DIMENSIONAL CHANGES (EXPANSION AND CONTRACTION)

Straightforward observation of the dimensional behavior of the artists' materials as a function of moisture content reveals useful data. Figures 3a through 3d show the changes in length of four different paint samples versus RH. Each sample had been aged 36 months in an environmentally uncontrolled interior room. All samples were taken from tubes as commercially available from various manufacturers and represent a much larger group of specimens. All paint and glue samples were isolated and free of any substrate. Tests were run over a period of several weeks, with samples cycled from low to high humidity and back again (or vice versa) several times. Some full cycles required nearly a week because the samples were allowed to equilibrate at a particular RH for about twelve hours before the corresponding measurement was taken. Shown here are plots of the fifth cycle. By this time the cycles had become regular, contrasting early cycles during which many specimens sagged considerably at high humidity.

The white lead, titanium dioxide and vermilion changed only slightly in total length, while the burnt umber changed

dramatically with the variation in RH. These differing dimensional changes among types of paint probably effect the overall structure of the painting, but the present discussion is confined to differences among classes of materials, for example, between paint and glue. The behavior of the "vermillion," an artificial azo pigment,⁸ seemed typical of this kind of pigment. When gaining moisture all specimens increased in rate of expansion at about 75-80% RH.

Figure 4 demonstrates the rather massive dimensional changes of rabbit skin glue. This specimen was representative of many cast from granular rabbit skin glue mixed according to the manufacturer's directions. Of all the artists' materials glue demonstrates the greatest change in length, and it can be cited as the prime source of stress development in paintings.

The dimensional changes in fabric are more difficult to observe in a cyclic fashion, for once the free-hanging fabric enters a period of high RH the yarn configuration is altered so that the specimen shrinks (Figure 5a,b). This shrinkage alters the behavior of the free-hanging specimen. Therefore, for a free-hanging specimen, the first pass from low to high RH, before the change in yarn configuration happens, is the only one that reflects the behavior of a stretched fabric. A general picture of force developing behavior in the stretched fabric is more accurately observed from figure 11a (showing tangent modulus vs. RH) and from tests of restrained linen (figure 12).

III. CHANGE IN MODULUS

To understand the behavior and deterioration of fabric supported paintings we must determine why paint and glue develop forces at all and why a thin layer of glue develops so much more force than does a paint layer ten times as thick. Actually, two materials with identical dimensional responses to moisture, upon being restrained, can develop very different forces. From a mechanical point of view, this is because the materials have different "mechanical properties". The modulus of one material is greater than the modulus of the other. The modulus of a material expresses the relationship between stress and strain, where stress is the distribution of force within the material and strain is the material deformation with respect to the undeformed dimensions. (For further definitions, see Glossary.)

The concept of the modulus is fundamental to the interpretation of material behavior; it is the quantity that allows us to determine the magnitude of stress a material will develop if it is strained (expanded or contracted). Mathematically the modulus is defined as the ratio of stress to strain,

$$E = \sigma / \epsilon \quad \text{in which} \quad \begin{array}{l} E = \text{modulus} \\ \sigma = \text{force/area} = \text{stress} \\ \epsilon = \text{deformation/unrestrained} \\ \quad \text{length} = \text{strain} \end{array}$$

FIGURE 3 A, B. Unrestrained dimensional change in oil paint vs. relative humidity at 70° F.

FIGURE 3 C, D. Unrestrained dimensional change in oil paint vs. relative humidity at 70° F.

One way of looking at the force developed by shrinkage is to imagine that a specimen of material which would normally be restrained from shrinkage is allowed to contract. The amount of contraction is its deformation, δ , that is, the contracted length subtracted from the restrained length, $\delta = L_r - L_c$. The strain of the specimen then becomes the deformation divided by the contracted length, $E = \delta / L_c$. The stress of the restrained specimen is σ_r and is equal to the strain times the modulus, that is,

$$\sigma = \epsilon \times E = (\delta / L_c) \times E = (L_r - L_c / L_c) \times E$$

The total force (F) measured is then equal to the stress of the restrained specimen times its cross-sectional area ($F = \sigma \times A$, where A is equal to its width times its thickness).

These relationships show that as the thicknesses of the glue and paint increase so does the total force. A higher modulus also increases the total force.

If a history of the stress-strain behavior of the materials discussed in this paper (glue, paint and fabric) were recorded, it would show that the properties of these materials are influenced by moisture content as well. While glue and paint show very low values of E (modulus) at high humidity, they have very high values of E at low humidities.

Figures 6 through 11 illustrate the general stress-strain behaviors of oil paint, glue size and fabric. While the absolute magnitudes of the various properties may vary somewhat, the overall performance is the same within each group of material.

For the paint, interpretation of the stress-strain curves (Figures 6a,b,c,d) explains important aspects of its behavior.

FIGURE 4. Unrestrained dimensional change in rabbit skin glue vs. relative humidity at 70° F.

At very high humidity the paint is quite *flexible* and exhibits very *plastic* behavior. It *creeps* to the point where it will completely release any applied stress within a short period of time, usually within a few hours. In addition, the *breaking stresses* of the paint are extremely low, while the *breaking strains* are high. Since the paint exhibits such plastic behavior, tensile failure is extremely unlikely at very high humidity except under extraordinary circumstances. However, as the RH decreases the paints exhibit more elastic behavior and demonstrate less creep. At very low humidity the paint also becomes quite *brittle* and while the breaking stress is the highest, the breaking strain is the lowest. The paint's ability

FIGURE 5 A, B. Unrestrained dimensional change in linen fabric vs. relative humidity at 70° F.

to accommodate dimensional changes is significantly altered by desiccation. The transition point from a generally plastic to a generally elastic behavior seems to occur at about 60% RH, 71° F, though this can vary slightly from pigment to pigment and with the age of the paint. Note that for the burnt umber (Figure 6d) breaking stress does not show on the graph because the breaking strain, even at extremely low RH, was very large.

With increased oxidation and polymerization of the paint a general increase in the modulus will occur at all levels of RH and a general decrease in breaking stress follows. When the paint is most brittle and cannot appreciably creep at low RH it has the highest potential for developing stress and thus for becoming itself part of the support of the painting.

Figure 7 shows the *tangent moduli* of the paint samples. The tangent modulus conveniently displays the change in modulus of the four paint samples as RH changes.

FIGURE 6A. Effect of relative humidity on stress-strain properties of flake white in linseed oil, 36 months old, at 70° F.

FIGURE 6B. Effect of relative humidity on stress-strain properties of titanium dioxide in linseed oil, 36 months old, at 70° F.

FIGURE 6C. Effect of relative humidity on stress-strain properties of artificial vermilion (azo) in safflower oil, 36 months old, at 70° F.

FIGURE 6D. Effect of relative humidity on stress-strain properties of burnt umber in linseed oil, 36 months old, at 70° F.

FIGURE 7. Effect of relative humidity on the tangent modulus of four paint samples: 1) burnt umber in linseed oil, 2) flake white in linseed oil, 3) titanium dioxide in linseed oil, 4) artificial vermilion in safflower oil.

The hide glue, in this case rabbit skin glue, demonstrates the greatest changes in mechanical properties with varied moisture content of all the materials (Figure 8). At about 95% RH the material is quite flexible and has a modulus of 4000 psi; at 10% RH the modulus is nearly 400,000 psi. Of all the materials found in a painting, glue has the highest modulus, and it has a breaking strength approaching 10,000 psi. At about 75% RH its material properties change tremendously, corresponding to the most significant change in its moisture content. Figure 9 shows this change while relating the modulus to RH.

Fabric exhibits more complex behavior because it is not a homogeneous material; it is a structure fabricated by weaving yarns of spun flax fibers. Nevertheless some general observations can be made. With respect to the stress-strain curve (Figure 10a,b), at low strain much of the behavior simply results from straightening crimped yarns (crimp removal zone at strains below 0.025). After crimp removal the actual yarn behavior takes over. Although increased moisture influences the modulus by making the crimp more difficult to remove,

FIGURE 8. Effect of relative humidity on stress-strain properties of rabbit skin glue.

moisture affects the actual yarn behavior to a lesser degree, and thus the yarn behavior contributes less to the modulus of the fabric. Very high moisture content appears to lubricate the fibers so that slippage occurs, and a lower yarn modulus results as the strain increases. i.e., more elongation results from less stress.

In general, when testing isolated fabric specimens the warp and weft directions show obvious differences (Figure 11a,b). Stretched fabrics found on paintings seem to behave similarly in both directions and similarly to the warp of an isolated test fabric. These similarities are due to stretching the fabric before painting. Raw fabric weft yarns have very little crimp, but upon stretching, the warp yarns induce more crimp into the weft yarns (crimp transfer), making the stretched fabric more *orthotropic*. Visual examination of actual painting fabrics and of Figures 16 and 17 bear this out.

Equally important is that although a fabric, upon being stretched, appears to lose some of the yarn crimp (is strained

FIGURE 9. Effect of relative humidity on the tangent modulus of rabbit skin glue.

beyond the crimp removal zone), the first time the fabric is subjected to high humidity the yarn fibers slip and the fabric relaxes and returns to the crimp behavior zone. In fact, to maintain a high strain on a fabric and subject it to high humidity without losing much of the fabric tension seems impossible.

Having now discussed the dimensional changes and the modulus changes of the materials, their comparison becomes of interest. In the paint specimens characteristic behavior exists: paints that develop the high modulus undergo small dimensional changes; paints with generally low modulus behavior undergo fairly large dimensional changes. If restrained, the paints with high modulus are the ones that will develop high stress (e.g., titanium dioxide and artificial vermilion). Very low modulus paints maintain such plastic behavior that little or no stress develops (e.g., burnt umber). As an oil film

oxidizes and polymerizes, the modulus increases, so higher stress development should be expected in older, restrained films. Unfortunately, strength of the film is not necessarily maintained as time passes.

The glue film exhibits both high modulus development and large dimensional changes, and if restrained, should show very high stress development. This phenomenon will be discussed later.

The fabric develops both high modulus and dimensional change at humidities above 80%, and as expected, most force development appears in this range.

IV. RESTRAINED TESTING

The foregoing discussion alludes to the development of a tensile stress within a material when that material, which would otherwise contract with a loss of moisture content, is restrained from contraction. If the dimensions of the specimen of material are known, then that stress is measurable. If these dimensions are not easily obtained, as in a sample of fabric, then the total force developed at one end of the specimen is measurable.

Tests were run on strips of linen (comparable to that found in a given painting), having dimensions 7×0.5 inches with a 32×32 thread per inch count; on cast strips of rabbit skin glue with the same length and cross-sectional area of 0.000483 square inch; and on cast strips of paint 7 inches long with a cross-sectional area of 0.00243 square inch. The individual specimens were restrained to a near constant length and the force developed by each specimen while changing the RH at a constant temperature was measured, to observe the relative behavior of each material.

Taking the warp direction sample of the linen first, a record was made of force versus RH (Figure 12). In this case two distinct sections of the graph are apparent: from zero to 85% RH; and from 85% to 100% RH. The graph is relatively flat with a slight increase in total force as the specimen is desiccated, but at 85% RH and above, a rapid and marked increase in total force is observable. This behavior was measured during a cycle of four days duration and was repeated during several following cycles. Above 95% RH the total force becomes even higher, reaching the point where some fiber slippage occurs and resulting in a net decrease in force on the specimen.

Next a cast strip of rabbit skin glue was tested. It was actually somewhat thicker than the layer normally found in a painting, so the recorded forces were mathematically corrected to those for a film 0.00048 inch thick and 0.5 inch wide. The plot of the total force versus RH is shown in Figure 13. The complete cycle lasted three days. This plot clearly shows the remarkably high force development in rabbit skin glue. From 96% RH to about 80% RH relatively little total force is developed, while from 80% RH to 5% RH massive

FIGURE 10A. Effect of relative humidity on stress-strain properties of linen in warp direction, medium weight, 32 yarns per inch (#8800 Ulster), at 71° F.

FIGURE 10B. Effect of relative humidity on stress-strain properties of linen in Weft (Fill) Direction, medium weight, 30 yarns per inch (#8800 Ulster), at 71° F.

FIGURE 11A. Effect of relative humidity on stress strain properties of linen in warp direction, medium weight, 32 yarns per inch (#8800 Ulster), at 71° F.

force is developed. (Note that going from low RH to high RH a different path is followed.)

Finally a strip of paint was tested. It was 42 months old and chosen for its degree of drying.⁹ The pigment was an azo pigment, vermillion, in safflower oil and showed nearly twice the modulus of white lead and titanium dioxide paints after comparable drying time. As with the rabbit skin glue, the dimensions were corrected, this time to 0.0048 inch thick and 0.5 inch long.

Figure 14 shows that above 75% RH no force developed in the specimen, but from 75% RH to 5% RH force developed and at a faster rate than that of the fabric tested. At humidities of 75% and above, the paint creeps, losing all ability to maintain a force.

Opinions have been expressed that a painting, composed of layered materials, is too complex for analysis and that research on its separate layers does not offer meaningful information for the total painting. Actually, the opposite is true, because the material behaviors of the individual materials can be summarized mathematically to project the performance of a total structure, in this case a painting. Therefore, if the

FIGURE 11B. Effect of relative humidity on stress strain properties of linen in Weft (Fill) Direction, medium weight, 30 yarns per inch (#8800 Ulster), at 71° F (preliminary results).

forces developed by the separate materials are added together at each point of RH, a composite results. Figure 15 shows the composite of the individual materials tested and indicates that the general character of each material is retained. This graph, then, predicts the behavior of an actual painting of similar construction.

To compare this theoretical analysis with the actual behavior of a painting, samples from a 1912 painting by the American artist Duncan Smith were tested. Test strips were cut in both the warp and weft directions, each 7 inches long and 0.5 inch wide. They were tested in the same manner as the specimens of individual materials, that is, they were held at a constant length during the full humidity cycle. The paint film was essentially uncracked having only microscopic fissures at the top of the weave pattern. The painting consists of a medium weight linen with layers of rabbit skin glue, white lead oil ground and a thin wash of ivory black paint totalling 0.017 inch in thickness.

FIGURE 12. Restrained specimen force development vs. relative humidity at 71°F for linen in warp direction (#8800 Ulster). Length 7 inches. Width 0.5 inches (16 yarns).

FIGURE 13. Restrained specimen force development vs. relative humidity at 71°F for rabbit skin glue. Length 7 inches. Thickness adjusted to 0.0048 inch. Resultant cross-sectional area 0.00024 square inch.

FIGURE 14. Restrained specimen force development vs. relative humidity at 71°F for artificial vermilion in safflower oil. Length 7 inches. Width 0.5 inch. Thickness 0.0048 inch. Cross-sectional area 0.0024 square inch.

FIGURE 15. Restrained specimen force development vs. relative humidity at 71° F. Composite of forces in Figures 12 through 14.

The painting samples yielded similarly shaped curves (Figures 16 and 17) even though one curve illustrates the behavior of the warp direction and the other describes that of the weft (fill). Both curves compare to the mathematically projected composite plot of Figure 15. Even the magnitudes of the forces are remarkably alike in all these, indicating that the theoretical composite plot reflects the general behavior of both the warp and weft directions of specimens from an actual painting.

Most important is that the force can now be identified as originating in specific layers as a function of RH. From zero to 80% RH the single most important source of force is the glue layer; the paint layer is the next, and lastly, the fabric. Since these forces are directly proportional to the thicknesses of the respective layers, thicker paint and glue layers would develop even higher forces. Even more significant is that the fabric is responsible for a decreasing proportion of the total force in a painting as the RH decreases. In fact, at 50% RH the fabric of the hypothetical composite is supporting only 13% of the total force and at 10% RH the fabric is supporting only 10% of the force. In other words, the glue is really the support of the painting having a glue size layer and the paint film is the second contributing support. The only time a painting in the humidity range below 80% is fully supported by the fabric is after a crack through the paint, ground and glue layers has formed. After crack formation, the fabric simply acts as a

“safety net” holding the pieces of the painting together. Under very high RH conditions, from about 85% to 100% RH for the restrained painting, the fabric is responsible for nearly all of the force in the given examples and only under these circumstances it is actually “supporting” the painting.

V. AXIAL BEHAVIOR

The difficulty in describing the structural behavior of a painting is that intuition about materials can betray understanding. Obviously a “stretched” material is in “tension,” i.e., positive strain, positive stress. But layers of a painting can literally contract in negative strain and still be in tension (positive stress). The positive and negative values must be correctly interpreted. Force (stress) and displacement (strain) are different properties which vary in magnitude, not only from layer to layer, but also from one area of a painting to another.

Taking the simplest examples first, we can begin to systematically examine the behavior of a painting. The simplest behavior might be called the “axial behavior”, or the structural behavior in a single planar direction as a function of the layers present.

A one-inch wide strip isolated from an uncracked painting, extending from one stretcher bar to the parallel bar, could

FIGURE 16. Restrained specimen force development vs. relative humidity at 71°F for warp direction sample from painting by Duncan Smith, dated 1912.

FIGURE 17. Restrained specimen force development vs. relative humidity at 71°F for weft (fill) direction sample from painting by Duncan Smith, dated 1912.

be illustrated as in Figure 18a. Upon expanding the stretcher, the strip of painting also would expand as shown in Figure 18b. That *all layers* of the painting expand (fabric, glue size, ground and paint) is important, and structurally speaking, all layers are strained. But strain can originate in any of the layers, so we must identify the sources of strain other than that from stretcher expansion.

Interlayer interactions become significant when strain in the painting occurs differentially, that is to say, non-uniformly. Suppose that after expanding the stretcher as in Figure 18b moisture were applied to the right half of the painting. In this case (Figure 19b), point A moves to the right to point A', and if the motion were severe enough the contraction of the fabric on the wetted side would compress and cleave the paint off the painting (Figure 19c). This could happen since water softened the glue size, deteriorating the bond of the ground to the fabric. Evidence of this mechanism often appears where water has condensed and collected behind the lower stretcher bar of a hanging painting. The fabric beneath the cleaved paint, is directly responsible for the local damage. If the shrinkage of the fabric were severe enough, tensile cracking of the paint on the left side would occur due to expansion, and again all layers of the painting would be strained. Note that the overall dimensions of the painting were not changed; the moisture content of the painting was uneven and an in-plane displacement occurred. This behavior illustrates the point that while a stretcher

can maintain the outside dimensions of a painting, it can do nothing to stop in-plane displacement. The stretcher would restrain massive contraction if the painting were uniformly wetted or if it were subjected to very high humidity. This restraint would correspond to the considerable increase in fabric tension due to very high humidity shown earlier in this discussion. Of concern is the question, does an environment of high humidity, or of any particular humidity, guarantee uniform moisture content of a painting? The answer is "no."

Fabric "shrinkage" at very high humidity causing cleavage in one part of a painting and simultaneous cracking in another part is a frequently observed phenomenon. What is not so obvious is that the glue size can cause similar paint compression and cleavage at the other end of the humidity spectrum, at severe desiccation.

Now consider a sequence of possible steps that could occur in a painting at low humidity. Start with the fixed strip of painting at 50% RH. If the length of this specimen is held constant and the specimen is desiccated evenly, then the stress in the paint, the glue and the fabric increases, but each to a different magnitude. If the paint film were old enough and the painting were given an initial "tension" at 50% RH, then the increase in stress in the paint film due to desiccation (Figure 18b) could be sufficient to crack the painting. The paint film could be described as having been "prestressed" at 50% RH so that lowering the RH was sufficient to crack the paint. In

FIGURE 18 A, B. Expansion of a painting due to either stretching or stretcher expansion. All layers are therefore strained.

FIGURE 19 A, B, C. In-plane displacement due to uneven moisture content: a) Initial condition prior to displacement, b) Displacement upon wetting right section, c) Damage resulting from displacement.

this case neither the glue nor the fabric contributed actively to the paint film failure. Again, while the stretcher could fix the outside dimensions of the painting, it could not stop this internal stress development.

Crack formation modifies the geometry of the painting as a structure. Prior to cracking the total force acting on the painting is the algebraic sum of the forces acting on each layer. The force in each layer is simply the stress in the layer times its cross-sectional area. Once a crack forms in the paint film and ground, partial stress release occurs in the cracked layers and the total force in the painting decreases slightly (cracking is a stress release mechanism). More important though is the relocation of the forces in the painting and its consequences. At the crack, the *geometric center of total force* of the painting is located just below the middle of the glue layer. But between the cracks, the center of force still lies above the middle of the glue layer and a

series of offset force lines appears (Figure 20b). In order to regain full axial alignment of the geometric center of force, displacement occurs and the painting “cups” (Figure 20c). Remember that the outside dimensions of the painting have not changed since the original “pre-tension” at 50% RH; only the change to low RH is required for this cracking, displacement and cupping. If the painting had been stretched even more tightly at 50% RH, the cracks could have formed at that time with the same resultant cupping. The important point here is that stretching a painting “conditions” it for humidity related failure. The tighter it is stretched, the more prone the painting is to damage due to desiccation; the less initial tension, the less prone it is to cracking at low RH. Lowering the initial stress in a paint film contributes to longevity of the painting.

The concept of axial displacement of forces has other interesting implications. An obvious one is of course the change

FIGURE 20 A, B, C, D. Locations of geometric center of force in a painting: a) Prior to cracking of ground and paint film; b) Force relocation immediately after cracking of ground and paint film; c) Force realignment displacing all layers out of picture plane, “Cupping”; d) Force locations in unrestrained painting in low RH: glue in tension, ground and paint layers in compression.

caused by a patch on the reverse of a painting. Eventually the patch shows up as a distortion on the front of the painting. The patch lowers the center of force of the painting in that area, and the “lifting” of the patch is simply the realignment of forces throughout the painting. Another example is a painting which has a very thick but very uneven design layer. Originally the painting is basically flat, yet ultimately a mirror image of the painting appears on the reverse (Figure 21a, b). This demonstrates the active structural participation of a thick paint layer. It is definitely supporting a great deal of the painting.

Suppose now that a painting has cracked for one of the reasons above and is no longer restrained. This could happen if the painting were left in low humidity long enough to permit the stretcher to contract or if a tacking edge fails. The painting seemingly relaxes. However, now observable is that while the paint film is relieved of all tensile stress, the glue size is not. The paint film alone restrains the full stress-relieving contraction of the glue layer, and the paint is now forced into compression and a form of “ridging” can occur (Figure 20d). Usually no general cleavage occurs since the bond of the fabric to the ground is at its strongest, unlike cleavage at high RH discussed earlier; but, interlayer cleavage is most likely to happen at this time when the paint film is in compression and the glue size is in tension. This interlayer cleavage happens simply because the dimensional contraction of the glue is so much greater than that of the paint layer. The fabric does not inhibit this behavior since it is incapable of developing compression stress.

This behavior suggests that at some point all layers are initialized or are at minimum stress. This point actually lies at about 85% RH (Figures 16, 17). Above 85% RH any residual stress and strain from the period of low RH in the

ground, paint and glue layers are reduced to zero due to swelling of these layers. Every time a painting is allowed to enter this high humidity zone the fabric begins to increase its role in supporting the painting, and all glue and paint layers “initialize” to a near zero stress level so that any previously stress-induced deformations of the design layer are “set”. From approximately this point, 85% RH, dimensional changes in the various layers can be measured. For example, unrestrained paint (white lead) at 85% RH will shrink about 0.3% if subjected to 10% RH; glue, however, will shrink 2.4% with a change from 85% RH to 10% RH. This is a substantial difference.

Clearly, the balance of forces in a painting is delicate. If a painting is stretched too tightly, tensile cracking of the design layer is risked, and the painting is conditioned for further low humidity stress development. On the other hand, if it is too loose, compression cleavage of the paint at high humidity or compression ridging at low humidity are strong possibilities. Finding the exact balance is not a simple task.

VI. BIAXIAL BEHAVIOR

In this discussion the assumption has been made that with some exceptions the outside dimensions of a painting remain fixed. However, when wood stretchers are used the dimensions remain fixed only if the painting is held at constant humidity and temperature. Such maintenance is not always found. The general behavior of the stretcher can be simply stated by saying that stretcher contraction at low humidity lowers the stress development in a painting and stretcher expansion at high humidity increases the stress. The influence of the stretcher can be imagined as counter-clockwise rotation

FIGURE 21. Locations of geometric center of force in a painting with heavy but uneven design layer: a) Immediately after application of force. b) Distortion resulting after sustained force realignment.

of the graphs in Figures 16 and 17, lowering the left sides and raising the right sides. Though not readily apparent but of utmost importance is that this effect can only be assumed at certain points on the painting because the stretcher does not release stress uniformly under low RH conditions. This is because: 1) changes in the wood are greater across the grain than along the grain direction; 2) the painting is tacked to the stretcher bar and is unable to release stress in the direction parallel to and near each stretcher bar.

To stretch a painting “evenly” and to increase stress uniformly in all directions, the edges must follow paths by which a “rectangle” drawn on the surface of the “painting” will enlarge without a net change in shape or proportion. When attempting to carefully stretch a linen so that the yarns are not distorted but remain parallel to the edges of the stretcher, the diagonal path required for each point along the edge becomes apparent. When a stretcher is “keyed out,” however, the points along the edges follow the horizontal and vertical paths of the stretcher bars (Figure 22). Expanding the

stretcher thus enlarges the rectangle and simultaneously distorts it to a diamond shape, as seen in Figure 23 where the solid lines represent the expanded but distorted grid, and the dotted lines represent the initial, pre-stretched position. As a result of the distortion of the painting, a principal stress orientation occurs and cracks will form at the corners about 45° from the stretcher bars and usually they will be parallel to one another. Figure 23 is the graphic display from a finite element analysis computer program which shows the principle stress orientation. The expansion of a stretcher due to high humidity is nearly identical to keying out the stretcher with the minor exception that the stretcher bar does expand slightly along the grain direction in high humidity. Why and when the cracking occurs is important to understand. Cracking occurs because expansion of the stretcher strains all layers of the painting and therefore stresses all layers, including the paint. At low humidity the paint film is most brittle, cannot withstand expansion and is most likely to crack. At high humidity, on the other hand, the glue, ground and paint

FIGURE 22. Movement of edges during stretcher expansion: a) Broken vectors – Path required for uniform expansion and uniform stress development in a painting. b) Solid Vectors – Path taken during stretcher expansion.

FIGURE 23. In-plane distortion, stress development and crack formation due to expansion of stretcher (computer output). From J. Colville, M.F. Mecklenburg, *Report on the Deterioration of Fabric Supported Paintings* (Submitted to National Museum Act, Smithsonian Institution, Washington, D.C. 1978).

layers are much more flexible and are more likely to withstand expansion. Why does the need to expand paintings seem to arise at low humidity? Simply because this is when the stretcher shrinks and corner “draws” and “drapes” appear in the painting. An expanding stretcher increases tensile stress in the direction indicated in Figure 23. The contracting stretcher relieves that stress and if contraction is great enough the painting literally goes into compression and buckles at the corners, after which the painting is keyed out.

Another, even more serious problem can develop at low humidity. At low RH stress in the paint and glue layers can increase so tremendously (Figures 16 and 17) that the stretcher contraction cannot release this stress completely or uniformly and another stress pattern develops. This is illustrated in Figure 24, a graphic display of computer output. A series of crack “waves” develops, radiating from the corner of the painting. This is the result both of stress increase in all layers of the painting at low humidity and of stretcher contraction. The less the stretcher contracts, the less pronounced the wave crack curvature. Corner drape occurs simultaneously with wave cracks. If the stretcher did not contract during this low humidity period then no drape would result; nor would partial stress release in the various layers occur, and cracking would be random and more extensive.

In addition to these results of low humidity failure mechanisms, wave cracks and drapes, the center of the painting usually is cracked perpendicularly to its long direction (Figure 25). Although this effect has been associated with differences

FIGURE 24. Residual stress distribution and crack formation at the corner of a painting resulting from desiccation of glue size, ground and paint layers accompanied by stretcher shrinkage.

FIGURE 25. Residual stress distribution and crack formation resulting from desiccation of the entire painting. Vectors show directions and relative magnitudes of residual stress in central zone of painting.

between the weave directions of the fabric, another explanation now appears more valid because, first, the general fabric behavior does not appear to differ much from warp to weft at any humidity; and second, the fabric is responsible for very little of the total force in a painting at low RH.

To understand the formation of these central area cracks, assume that a painting is subjected to low humidity resulting in high stress development in the paint, ground and glue layers. If the stretcher did not contract the stress could be assumed uniform, and if cracks were to form they would be random throughout the painting.

Now assume that the period of time to achieve desiccation is long and that the stretcher does contract. Stretcher bars are normally of the same stock on all sides so that the amount of contraction is the same in both directions. If the amount of contraction of the stretcher bar is δ (deformation), then the release of stress in the central section of the painting can be computed in both the vertical (short) and horizontal (long) directions. Since stress is related to strain, a strain release means a stress release. To compute the strain release in the horizontal or long direction, use

$$\epsilon_{LR} = \delta/L_L;$$

in the vertical or short direction use

$$\epsilon_{SR} = \delta/L_S.$$

Because L_L is much greater than L_S the strain release in the short direction is much greater than the strain release in the long direction; and a much greater stress is released in the short direction than in the long direction. Therefore, the residual or

unrelieved stress in the long direction is sufficient to crack the painting while residual stress in the short direction is not.

VII. CONCLUSION

This discussion of some highlights of the mechanical behavior of the fabric supported painting certainly must be considered only as an introduction to a field requiring much broader investigation. For example, among aspects yet to be discussed are the thermal properties of the materials.

But some conclusions can be drawn even at this stage of the study. Previously the structural role of the linen fabric support has been completely over-estimated at humidities under 85%. The structural participation of the paint itself, on the other hand, was almost entirely neglected in traditional discussions of painting behavior. The structural role of the glue size had been most definitely under-estimated.

A concept of great importance to understand is that if a painting is stretched, then all layers are stressed and "pre-tensioned" for further stress development resulting from desiccation. While a painting can be restrained at the edges, this does nothing to stop in-plane displacement or damage due to humidity extremes. Although a wood stretcher does contract and relieve some stress at low humidity, it does so unevenly, causing general stress patterns to appear. The situation would be worse if a stretcher were not to contract at all, for then no stress would be released.

This study surely demonstrates the potential devastation resulting from exposure to the extreme ends of the humidity scale. Holding an environment at a constant temperature and RH certainly appears to reduce damage to fabric supported paintings, but the assumption should not be made that humidity oscillation is the cause for damage because a constant environment also obviates extreme desiccation and extremely high humidity. There is some evidence that the most extreme oscillations in humidity, from below 20% RH to above 85% RH, cause continually increasing desiccated stress development in the rabbit skin glue. This must be explored in detail.

Other evidence shows that a narrow band of oscillation in RH might be quite acceptable if these oscillations occur within relatively short periods of time, probably less than eight hours. The reason for this is the very slow rate of moisture loss from paint. A film of paint only 0.01 inch thick might take at least 24 hours to lose 90% of its moisture if desiccated from 85% RH. And this rather long period of time was required in a controlled situation where the air was constantly agitated by high velocity air fans to facilitate moisture loss from all exposed surfaces of the paint specimen.

The rate of moisture loss from the glue size and cellulose is much faster, but is considerably buffered by the paint film in an actual painting. A completely closed backing board of a hygroscopic material will act to buffer the painting further. More study of the rate of moisture loss would be exceedingly

valuable. If such studies were to reveal that the stringent control of museum environments for fabric supported paintings might be relaxed a bit, then substantial savings in energy costs soon would be realized. Comparison between rates of moisture loss and the lengths of time works of art spend in different environments while traveling would provide valuable packing and shipping guidelines.

Along with controlled environments certain measures in conservation should be reassessed. An obvious concept is that if a painting can be supported stress-free then the probability of further cracking, cupping, and hence flaking, is over. But this is unrealistic because to let a painting expand and contract in order to relieve the humidity related stress development, the layers would have to change dimensions at different rates; since they are bonded together this is impossible. On the other hand, stretching a painting can pre-condition it to increased stress development. Clearly a compromise must be reached. A long-held assumption has been that lining a painting to linen would support the painting further. Now recognizable is that if a painting is linen-lined with a hide glue adhesive, then the glue adhesive does far more to support the painting than the linen. In the northeastern United States and most of Canada, the use of hide glue as a lining adhesive is ill-advised, for interior spaces during the winter season routinely reach relative humidities below 15%. At low RH, the in-plane contraction of such an adhesive is unacceptable, particularly since it is usually applied more thickly as a lining adhesive than when used as the size layer, and the linen lining fabric, like the original support fabric, does little to restrain in-plane displacement.

In summary, to support a painting, the material chosen must: 1) be capable of developing and maintaining a large percentage of the total force of a stretched painting; 2) be able to restrain in-plane displacement as developed by dessicated glue and paint films; 3) restrain out-of-plane distortion such as cupping and buckling. Other factors to be considered when choosing the support include: 1) the modulus of the lining material when a high modulus is preferable; 2) the total thickness of the lining material, since thickness gives more structural stiffness and can be achieved with multiple layers of the material; 3) the total dimensions of the painting, as well as the thickness of the paint.

At one extreme of supports is the inert, solid panel which carries nearly 100% of the forces in a painting. Several people have offered other promising alternatives.¹⁰ Further study of the structural behavior of paintings will more clearly define the mechanical requirements for a lining support as well as for the lining adhesive. If the proper support is chosen, then the options available in choosing the adhesive might be broadened considerably.

While the research has come a certain distance, it has much further to go for utmost precision and refinement in understanding. Methods are now available for analyzing both the materials of paintings and the structure itself without

experimenting on the objects themselves. Two significant points already clear are that the stress development within a painting will never be completely eliminated and that avoiding the extremes of relative humidity cannot be over-emphasized.

NOTES

1. W. Percival-Prescott, *The Lining Cycle, Fundamental Causes of Deterioration in Paintings on Canvas: Materials and Methods of Impregnating and Lining from the 17th Century to the Present Day*, Conference on Comparative Lining Techniques, (Great Britain: Greenwich, 1974).
2. K. Wehlte, *The Materials and Techniques of Painting with a Supplement on Color Theory*, trans. Ursus Dix, (New York: Van Nostrand Reinhold Company, 1975), 342-350.
G. Thompson, *The Museum Environment*, (London and Boston: Buttersworth, 1978), 82.
F. duPont Cornelius, "Movement of Wood and Canvas for Paintings in Response to High and Low Humidity," *Studies in Conservation*, 12 (1967), 76-79.
3. S. Keck, "Mechanical Alteration of the Paint Film," *Studies in Conservation*, 14 (1969), 9-30.
A. Elm, "Some Mechanical Properties of Paint Films," *Official Digest*, 25 (1953), 750-774.
M.G. Shikher, "Deformation Properties of Linseed Oil Films", trans. R.E. Smith and W. Borowski, *Journal of Applied Chemistry*, 12 (1932), 1884-1891, (Moscow and Leningrad, USSR Academy of Science Publishing House).
A. V. Damfilov and Ye o G. Ivancheva, "Mechanical Properties of Pigmented Oil Films", trans. R.E. Smith and W. Borowski, *Journal of Applied Chemistry* 20 (1947), 676-683, (Moscow and Leningrad, USSR Academy of Science Publishing House)
4. J.P. Lee and F.W. Sears, *Thermodynamics*, (Reading, Massachusetts: Addison-Wesley Publishing Company Inc., 1955), 318-322.
F.P. Durham, *Thermodynamics*, (Englewood Cliffs, New Jersey: Prentice-Hall Inc., 1959), 241.
5. A.J. Panshin and Carl deZeeuw, *Textbook of Wood Technology*, (New York: McGraw-Hill Book Company, 1949), 201-207.
6. Ernest R. Kaswell, *Wellington Sears, Handbook of Industrial Textiles*, (New York: Wellington Sears Company, Inc., 1963), 17-19.
7. K. H. Gustavson, *The Chemistry and Reactivity of Collagen*, (New York: Academic Press Inc., 1956), 30.
8. On azo pigments, synthetic organic pigments of the aniline type, see K. Wehlte, 54.
9. To determine the "degree of drying" of the paints, the magnitudes of modulus development were the criteria.
10. G. Hedley, *The Stiffness of Lining Fabrics: Theoretical and Practical Considerations*, ICOM Committee for Conservation, 6th Triennial Meeting, Ottawa, 1 (1981).
G.A. Berger, "Unconventional Treatments for Unconventional Paintings," *Studies in Conservation*, 21 (1976), 115-128.
R.E. Fieux, "Teflon Coated Fiberglass as a Support for Relining Paintings," *Bulletin of the American Institute for Conservation of Historic and Artistic Works*, 14 (1973), 73-74.
A.G. Boissonnas, "Relining with Glass Fiber Fabric," *Studies in Conservation*, 6 (1961), 26-30.

GLOSSARY

- Brittle—A material is said to be brittle if it breaks without yielding.
Creep—Continuing deformation without an increase in applied force.
Elastic—A material is said to be elastic if it returns to its original dimensions after having been deformed by an applied force and the force has been removed.
Mechanics—The study of the effects of force on bodies. In this paper it is limited to static systems.
Modulus—The ratio of stress to strain; this ratio is the slope of the stress-strain curve.

Orthotropic—Exhibits similar material behaviors at 90° directions, in this paper, the direction of the weave (warp and weft).

Plastic—A material is said to be plastic if after having been deformed by an applied force it does not return to its original dimensions.

Strain—Change in length per unit length, i.e., inches per inch.

Breaking Strain—Strain magnitude at which a material fails either in tension or compression.

Stress—Force per unit area, i.e., pounds per square inch.

Breaking Stress—Stress magnitude at which a material fails either in tension or compression.

Tangent Modulus—Slope of the stress-strain curve tangent to the curve at the origin of the coordinates.

Yielding—A material is said to yield when its behavior changes from elastic to plastic.

Appendix 3: Bibliography of Publications by Marion F. Mecklenburg, Chronological Listing from 1977 to 2017

- Mecklenburg, M. F., and J. E. Webster. 1977. Aluminum Honeycomb Supports: Their Fabrication and Use in Painting Conservation. *Studies in Conservation*, 22(4):177–189.
- Colville, J., and M. F. Mecklenburg. 1978. Report on the Deterioration of Fabric Supported Paint Films: Phase I - Research Report. Washington, D.C.: Smithsonian Institution.
- Colville, J., W. Kilpatrick, and M. F. Mecklenburg. 1982. "A Finite Element Analysis of Multi-layered Orthotropic Membranes with Application to Oil Paintings on Fabric." In *Science and Technology in the Service of Conservation: Preprints of the Contributions to the Washington Congress*, pp. 146–150. London: International Institute for Conservation of Historic and Artistic Works.
- Mecklenburg, M. F. 1982. Some Aspects of the Mechanical Behavior of Fabric Supported Paintings. Washington, D.C.: Smithsonian Institution.
- Mecklenburg, M. F. 1984. The Role of Water on the Strength of Polymers and Adhesives. Ph.D. diss., University of Maryland, College Park.
- Mecklenburg, M. F., and P. Albrecht. 1985. Effect of Humidity on Behavior of Polymeric Materials. *Polymer Preprints*, 26(2):247–248.
- McNamara, D. K., C. O. Arah, H. M. Hand, and M. F. Mecklenburg. 1988. "Fracture Toughness Testing of High-Performance Adhesives." In *Proceedings of the 1988 ASME Winter Annual Meeting*, pp.111–116. Chicago: ASME.
- Mecklenburg, M. F. 1988. "The Effects of Atmospheric Moisture on Mechanical Properties of Collagen under Equilibrium Conditions." In *Preprints of 16th Annual Meeting of the American Institute for Conservation of Historic and Artistic Works*, ed. S. Z. Rosenberg, pp. 231–244. Washington, D.C.: American Institute for Conservation of Historic and Artistic Works.
- van der Reyden, D. L., M. F. Mecklenburg, M. T. Baker, and M. Hamill. 1988. Update on Current Research into Aqueous Light Bleaching at the Conservation Analytical Laboratory. *Book and Paper Group Annual*, 7:73–106. <http://cool.conservation-us.org/coolaic/sg/bpg/annual/v07/bp07-11.html> (accessed 18 April 2018).
- Arah, C. O., H. M. Hand, D. K. McNamara, and M. F. Mecklenburg. 1989. Techniques for Screening Adhesives for Structural Applications. *Journal of Adhesion Science and Technology*, 3(4):261–275.
- Arah, C. O., D. K. McNamara, H. M. Hand, and M. F. Mecklenburg. 1989. The Correlation between Adhesive Stress Relaxation and Joint Performance. *Science of Advanced Materials and Process Engineering Journal*, 25(4):11–14.
- Arah, C. O., D. K. McNamara, H. M. Hand, and M. F. Mecklenburg. 1989. "The Effect of Adhered Stiffness on Adhesive Behavior." In *Abstracts from Proceedings of the 12th Annual Adhesion Society Meeting*, pp. 25a–25c. Kansas City, Mo.: Adhesion Society.
- Erhardt, D., and M. F. Mecklenburg. 1989. Relative Humidity and the Care of Museum Collections. *Preprints of Papers, presented at the National Meeting - American Chemical Society, Division of Environmental Chemistry*, 29(2):238–239.
- Mecklenburg, M. F., J. A. Joyce, and P. Albrecht. 1989. "Separation of Energies in Elastic-Plastic Fracture." In *Nonlinear Fracture Mechanics. Volume 2: Elastic-Plastic Fracture*, ed. J. D. Landes, A. Saxena, and J. G. Merkle, pp. 594–612. ASTM Special Technical Publication, No. 995. Philadelphia: American Society for Testing and Materials.
- Organ, R. M., and M. F. Mecklenburg. 1989. Notes on the Test-Jig Made and Used by Marion F. Mecklenburg. Internal Report. Washington, D.C.: Conservation Analytical Laboratory, Smithsonian Institution.
- Collins, S., M. W. Ballard, and M. F. Mecklenburg. 1990. "Fabric Selection and Its Relationship to Dimensional Changes in Support Systems for Constrained Fabric Mounting Devices." In *Textiles and Costumes on Parade: Exhibition Successes and Disasters*, pp. 10–20. Harpers Ferry, W.Va.: Harpers Ferry Regional Textile Group.
- Mecklenburg, M. F., C. O. Arah, D. McNamara, H. Hand, and J. A. Joyce. 1990. "Adhesive Fracture Testing." In *Fracture Mechanics: Twenty-First Symposium*, ed. J. P. Gudas, J. A. Joyce, and E. M. Hackett, pp. 307–321. ASTM Special Technical Publication, No. 1074. Philadelphia: American Society for Testing and Materials.

Note: Digital versions of all papers listed in the bibliography can be accessed through Smithsonian Research Online (<https://research.si.edu/>) using "mecklenburg, m" as the search term.

- Arah, C. O., D. K. McNamara, H. M. Hand, M. F. Mecklenburg, A. Dasgupta, and B. K. Hornbeck. 1991. "Structural Analysis of Adhesively Bonded Joints of Tubular Geometry." In *Preprints from the 36th International SAMPE Symposium*, pp. 372–382. Covina, Calif.: Society for the Advancement of Material and Process Engineering.
- Hand, H. M., C. O. Arah, D. K. McNamara, and M. F. Mecklenburg. 1991. Effects of Environmental Exposure on Adhesively Bonded Joints. *International Journal of Adhesion and Adhesives*, 11(1):15–23.
- Mecklenburg, M. F. 1991. "Applied Mechanics of Materials in Conservation Research." In *Materials Issues in Art and Archaeology II*, ed. P. B. Vandiver, J. R. Druzik, and G. S. Wheeler, pp. 105–122. MRS Symposium Proceedings, No. 185. Pittsburgh: Materials Research Society.
- Mecklenburg, M. F., ed. 1991. *Art in Transit: Studies in the Transport of Paintings*. Washington, D.C.: National Gallery of Art. <https://repository.si.edu/handle/10088/8128> (accessed 18 April 2018).
- Mecklenburg, M. F. 1991. "Some Mechanical and Physical Properties of Gilding Gesso." In *Gilded Wood Conservation and History*, ed. D. Bigelow, E. Cornu, G. J. Landrey, and C. Van Horne, pp. 163–170. Madison, Conn.: Sound View Press.
- Mecklenburg, M. F., and C. S. Tumosa. 1991. "An Introduction into the Mechanical Behavior of Paintings under Rapid Loading Conditions." In *Art in Transit: Studies in the Transport of Paintings*, ed. M. F. Mecklenburg, pp. 137–171. Washington, D.C.: National Gallery of Art.
- Mecklenburg, M. F., and C. S. Tumosa. 1991. "Mechanical Behavior of Paintings Subjected to Changes in Temperature and Relative Humidity." In *Art in Transit: Studies in the Transport of Paintings*, ed. M. F. Mecklenburg, pp. 173–216. Washington, D.C.: National Gallery of Art.
- Murray, A., R. E. Green, M. F. Mecklenburg, and C. M. Fortunko. 1991. "NDE Applied to the Conservation of Wooden Panel Painting." In *Nondestructive Characterization of Materials IV*, ed. C. O. Ruud, pp. 73–80. New York: Plenum Press.
- Murray, A., R. E. Green, M. F. Mecklenburg, and C. M. Fortunko. 1991. "Non-destructive Evaluation of Works of Art." In *Art in Transit: Studies in the Transport of Paintings*, ed. M. F. Mecklenburg, pp. 249–260. Washington D.C.: National Gallery of Art.
- Richard, M., M. F. Mecklenburg, and R. M. Merrill, eds. 1991. *Art in Transit: Handbook for Packing and Transporting Paintings*. Washington, D.C.: National Gallery of Art.
- Erlebacher, J. D., E. Brown, M. F. Mecklenburg, and C. S. Tumosa. 1992. "The Effects of Temperature and Relative Humidity on the Mechanical Properties of Modern Painting Materials." In *Materials Issues in Art and Archaeology III*, ed. P. B. Vandiver, J. R. Druzik, G. S. Wheeler, and I. C. Freestone, pp. 359–370. MRS Symposium Proceedings, No. 267. Pittsburgh: Materials Research Society.
- Erlebacher, J. D., M. F. Mecklenburg, and C. S. Tumosa. 1992. The Mechanical Behavior of Artists' Acrylic Paints with Changing Temperature and Relative Humidity. *Polymer Preprints*, 33(2):646–647.
- Erlebacher, J. D., M. F. Mecklenburg, and C. S. Tumosa. 1992. "The Mechanical Behavior of Artists' Acrylic Paints with Changing Temperature and Relative Humidity." In *AIC Paintings Specialty Group Postprints: Papers Presented at the Twentieth Annual Meeting*, pp. 35–40. Washington, D.C.: American Institute for Conservation of Historic and Artistic Works.
- Hand, H. M., C. O. Arah, D. K. McNamara, and M. F. Mecklenburg. 1992. Effects of Environmental Exposure on Adhesively Bonded Joints. *Construction and Building Materials*, 6(4):227–234.
- Mecklenburg, M. F., C. S. Tumosa, and M. H. McCormick-Goodhart. 1992. "A General Method for Determining the Mechanical Properties Needed for the Computer Analysis of Polymeric Structures Subjected to Changes in Temperature and Relative Humidity." In *Materials Issues in Art and Archaeology III*, ed. P. B. Vandiver, J. R. Druzik, G. S. Wheeler, and I. C. Freestone, pp. 337–358. MRS Symposium Proceedings, No. 267. Pittsburgh: Materials Research Society.
- Murray, A., E. Boltz, C. M. Fortunko, M. F. Mecklenburg, and R. E. Green. 1992. "Air-Coupled Ultrasonic System for Nondestructive Evaluation of Wooden Panel Paintings." In *3rd International Conference on Nondestructive Testing, Microanalytical Methods and Environment Evaluation for Study and Conservation of Works of Art*, ed. M. Marabelli and P. Santopadre, pp. 441–450. Brescia, Italy: Italian Society for Nondestructive Testing.
- Murray, A., C. M. Fortunko, M. F. Mecklenburg, and R. E. Green. 1992. "Detection of Delaminations in Art Objects Using Air-Coupled Ultrasound." In *Materials Issues in Art and Archaeology III*, ed. P. B. Vandiver, J. R. Druzik, G. S. Wheeler, and I. C. Freestone, pp. 371–377. MRS Symposium Proceedings, No. 267. Pittsburgh: Materials Research Society.
- van der Reyden, D. L., C. Hofmann, M. T. Baker, and M. F. Mecklenburg. 1992. "Modern Transparent Papers: Materials, Degradation, and the Effects of Some Conservation Treatments." In *Materials Issues in Art and Archaeology III*, ed. P. B. Vandiver, J. R. Druzik, G. S. Wheeler, and I. C. Freestone, pp. 379–395. MRS Symposium Proceedings, No. 267. Pittsburgh: Materials Research Society.
- McCormick-Goodhart, M. H., and M. F. Mecklenburg. 1993. "Cold Storage Environments for Photographic Materials." In *Final Program and Advance Printing of Paper Summaries, IS&T's 46th Annual Conference*, pp. 277–280. Springfield, Va.: Society for Imaging Science and Technology.
- Mecklenburg, M. F., and C. S. Tumosa. 1993. Computer Modeling of the Effects of Temperature and Relative Humidity on Stresses in the Layers of Cultural Materials. *Polymeric Materials, Science and Engineering: Proceedings of the ACS Division of Polymeric Materials Science and Engineering*, 68:226–228.
- Erhardt, W. D., and M. F. Mecklenburg. 1994. "Relative Humidity Re-examined." In *Preventive Conservation: Practice, Theory and Research; Preprints of the Contributions to the Ottawa Congress*, ed. A. Roy and P. Smith, pp. 32–38. London: International Institute for Conservation.
- Mecklenburg, M. F., M. H. McCormick-Goodhart, and C. S. Tumosa. 1994. Investigation into the Deterioration of Paintings and Photographs Using Computerized Modeling of Stress Development. *Journal of the American Institute for Conservation*, 33(2):153–170.
- Mecklenburg, M. F., and C. S. Tumosa. 1994. Mechanics Research of NASM Materials and Environmental Effects on Their Properties. Interim Report, No. 1. Washington, D.C.: Conservation Analytical Laboratory, Smithsonian Institution.
- Mecklenburg, M. F., C. S. Tumosa, and J. D. Erlebacher. 1994. Mechanical Behavior of Artist's Acrylic Paints Under Equilibrium Conditions. *Polymer Preprints*, 35(2):297–298.
- Murray, A., E. S. Boltz, M. C. Renken, C. M. Fortunko, M. F. Mecklenburg, and R. E. Green. 1994. "Air-Coupled Ultrasonic System for Detecting Delaminations and Cracks in Paintings on Wooden Panels." In *Nondestructive Characterization of Materials VI*, ed. R. E. Green, C. O. Rudd, and K. J. Kozaczek, pp. 103–110. New York: Plenum Press.
- Smithsonian Institution, Office of Public Affairs. 1994. Work of Smithsonian Scientists Revises Guidelines for Climate Control in Museums and Archives. Smithsonian Institution News, 21 August. [Reprinted in *Abbey Newsletter*, 18:4–5, 1994.]
- Erhardt, W. D., and M. F. Mecklenburg. 1995. "Accelerated vs Natural Aging: Effects of Aging Conditions on the Aging Process of Cellulose." In *Materials Issues in Art and Archaeology IV*, ed. P. B. Vandiver, J. R. Druzik, J. L. G. Madrid, I. C. Freestone, and G. S. Wheeler, pp. 247–270. MRS Symposium Proceedings, No. 352. Pittsburgh: Materials Research Society.
- Erhardt, W. D., M. F. Mecklenburg, C. S. Tumosa, and M. H. McCormick-Goodhart. 1995. Determinación de las fluctuaciones permisibles de humedad relativa [The determination of allowable relative humidity fluctuations]. *Apoyo*, 6(1):6–8.
- Erhardt, W. D., M. F. Mecklenburg, C. S. Tumosa, and M. H. McCormick-Goodhart. 1995. The Determination of Allowable RH Fluctuations. *WAAC Newsletter*, 17(1):19–23.
- Erhardt, W. D., M. F. Mecklenburg, C. S. Tumosa, and M. H. McCormick-Goodhart. 1995. Guidelines for the Museum Climate: Report to the Task Force on Indoor Air Quality in Museums. Herndon, Va.: International Society of Indoor Air Quality and Climate.
- Mecklenburg, M. F., C. S. Tumosa, and M. H. McCormick-Goodhart. 1995. "A General Model Relating Externally Applied Forces to Environmentally Induced Stresses in Materials." In *Materials Issues in Art and Archaeology IV*, ed. P. B. Vandiver, J. R. Druzik, J. L. G. Madrid, I. C. Freestone, and G. S. Wheeler, pp. 285–292. MRS Symposium Proceedings, No. 352. Pittsburgh: Materials Research Society.
- Mecklenburg, M. F., C. S. Tumosa, and N. Wyplosz. 1995. "The Effects of Relative Humidity on the Structural Response of Selected Wood Samples in the Cross Grain Direction." In *Materials Issues in Art and Archaeology IV*, ed. P. B. Vandiver, J. R. Druzik, J. L. G. Madrid, I. C. Freestone, and G. S. Wheeler, pp. 305–324. MRS Symposium Proceedings, No. 352. Pittsburgh: Materials Research Society.
- Tumosa, C. S., W. D. Erhardt, M. F. Mecklenburg, and M. H. McCormick-Goodhart. 1995. The Effects of Relative Humidity and Temperature on Exhibited Objects. *Cahiers d'étude Comité de Conservation (ICOM-CC)*, 1:9.

- http://archives.icom.museum/study_series_pdf/1_ICOM-CC.pdf (accessed 18 April 2018).
- Albrecht, P., and M. F. Mecklenburg. 1996. "Predicting Cohesive Strength of a Bonded Joint from Properties of Bulk Adhesive." In *Fiber Composites in Infrastructure: Proceedings of the First International Conference on Composites in Infrastructure*, ed. H. Saadatmanesh and M. R. Ehsani, pp. 152–165. Tucson: Department of Civil Engineering, University of Arizona.
- Erhardt, W. D., M. F. Mecklenburg, C. S. Tumosa, and T. M. Olstad. 1996. "New vs Old Wood: Differences and Similarities in Physical, Mechanical, and Chemical Properties." In *ICOM Committee for Conservation, 11th Triennial Meeting, Edinburgh, Scotland, 1–6 September 1996: Preprints*, Volume 2, ed. J. Bridgland, pp. 903–910. London: James and James.
- Mecklenburg, M. F., and C. S. Tumosa. 1996. A Report on Artists' Materials. *American Artist*, 60(645):12–16.
- Mecklenburg, M. F., and C. S. Tumosa. 1996. "The Relationship of Externally Applied Stresses to Environmentally Induced Stresses." In *Fiber Composites in Infrastructure: Proceedings of the First International Conference on Composites in Infrastructure*, ed. H. Saadatmanesh and M. R. Ehsani, pp. 956–971. Tucson: Department of Civil Engineering, University of Arizona.
- Mecklenburg, M. F., C. S. Tumosa, M. H. McCormick-Goodhart, and W. D. Erhardt. 1996. Keep It Wet. *New Scientist*, no. 2011:44.
- Murray, A., M. F. Mecklenburg, C. M. Fortunko, and R. E. Green. 1996. Air-Coupled Ultrasonic System: A New Technology for Detecting Subsurface Flaws in Painting on Wooden Panels. *Journal of the American Institute for Conservation*, 35(2):145–162.
- Tumosa, C. S., M. F. Mecklenburg, D. Erhardt, and M. H. McCormick-Goodhart. 1996. A Discussion of Research on the Effects of Temperature and Relative Humidity on Museum Objects. *WAAC Newsletter*, 18(3):19–20.
- Erhardt, D., M. F. Mecklenburg, C. S. Tumosa, and M. H. McCormick-Goodhart. 1997. "The Determination of Appropriate Museum Environments." In *The Interface between Science and Conservation*, ed. S. Bradley, pp. 153–163. British Museum Occasional Papers, No. 116. London: British Museum.
- McCormick-Goodhart, M. H., C. S. Tumosa, and M. F. Mecklenburg. 1997. Predicting the Environmental Response of Gelatin Containing Composite Structures. *Imaging Science Journal*, 45(3/4):244–245.
- Tumosa, C. S., and M. F. Mecklenburg. 1997. Some Mechanical Properties of Skin. *Mid-Atlantic Association of Forensic Scientists (MAAFS) Newsletter*, 25(1):18–22.
- Collins, S., M. F. Mecklenburg, and M. W. Ballard. 1998. "Fabric Selection and Its Relationship to Dimensional Changes in Support Systems for Constrained Fabric Mounting Devices." In *International Perspectives on Textile Conservation: Papers from the ICOM-CC Textiles Working Groups Meetings, Amsterdam 13–14 October 1994 and Budapest 11–15 September 1995*, ed. Á. Tímár-Balázsy and D. Eastop, pp. 162–169. London: Archetype.
- Mecklenburg, M. F., C. S. Tumosa, and W. D. Erhardt. 1998. "Structural Response of Painted Wood Surfaces to Changes in Ambient Relative Humidity." In *Painted Wood: History and Conservation*, ed. V. Dorge and F. C. Howlett, pp. 464–483. Los Angeles: Getty Conservation Institute.
- Richard, M., M. F. Mecklenburg, and C. S. Tumosa. 1998. "Technical Considerations for the Transport of Panel Paintings." In *The Structural Conservation of Panel Paintings: Proceedings of a Symposium at the J. Paul Getty Museum*, ed. K. Dardes and A. Rothe, pp. 525–556. Los Angeles: Getty Conservation Institute.
- Tumosa, C. S., M. H. McCormick-Goodhart, and M. F. Mecklenburg. 1998. The Physical Properties of Photographic Film Polymers Subjected to Cold Storage Environments. *Polymer Preprints*, 39(2):1245–1246.
- Erhardt, D., C. S. Tumosa, and M. F. Mecklenburg. 1999. "Material Consequences of the Aging of Paper." In *ICOM Committee for Conservation, 12th Triennial Meeting, Lyon, 29 August–3 September 1999: Preprints*, Volume 2, ed. J. Bridgland and J. Brown, pp. 501–506. London: James and James.
- Grissom, C. A., A. E. Charola, A. Boulton, and M. F. Mecklenburg. 1999. Evaluation over Time of an Ethyl Silicate Consolidant Applied to Ancient Lime Plaster. *Studies in Conservation*, 44(2):113–120.
- Mecklenburg, M. F., and C. S. Tumosa. 1999. Temperature and Relative Humidity Effects on the Mechanical and Chemical Stability of Collections. *ASHRAE Journal*, 41(4):69–74.
- Tumosa, C. S., and M. F. Mecklenburg. 1999. "Materials Characterization and the Computer Modeling of Works of Art." In *Abstracts Pittcon 99*, Abstract 858. Pittsburgh: Pittsburgh Conference and Exposition.
- Tumosa, C. S., J. Millard, D. Erhardt, and M. F. Mecklenburg. 1999. "Effects of Solvents on the Physical Properties of Paint Films." In *ICOM Committee for Conservation, 12th Triennial Meeting, Lyon, 29 August–3 September 1999: Preprints*, Volume 1, ed. J. Bridgland and J. Brown, pp. 347–352. London: James and James.
- Erhardt, D., C. S. Tumosa, and M. F. Mecklenburg. 2000. Can Artists' Oil Paints Be Accelerated Aged? *Polymer Preprints*, 41(2):1790–1791.
- Erhardt, D., C. S. Tumosa, and M. F. Mecklenburg. 2000. "Natural and Accelerated Thermal Aging of Oil Paint Films." In *Tradition and Innovation: Advances in Conservation, Contributions to the IIC Melbourne Congress*, ed. A. Roy and P. Smith, pp. 65–69. London: International Institute for Conservation of Historic and Artistic Works.
- Erhardt, D., C. S. Tumosa, and M. F. Mecklenburg. 2001. "Chemical and Physical Changes in Naturally and Accelerated Aged Cellulose." In *Historic Textiles, Papers and Polymers in Museums*, ed. J. M. Cardamone and M. Baker, pp. 23–37. ACS Symposium Series, No. 779. Washington, D.C.: American Chemical Society.
- Mecklenburg, M. F., and C. S. Tumosa. 2001. Traditional Oil Paints: The Effects of Long-Term Chemical and Mechanical Properties on Restoration Efforts. *MRS Bulletin*, 26(1):51–55.
- Tumosa, C. S., M. F. Mecklenburg, and M. H. McCormick-Goodhart. 2001. "The Physical Properties of Photographic Film Polymers Subjected to Cold Storage Environments." In *Historic Textiles, Papers and Polymers in Museums*, ed. J. M. Cardamone and M. Baker, pp. 136–144. ACS Symposium Series, No. 779. Washington, D.C.: American Chemical Society.
- Von Endt, D. W., W. D. Erhardt, A.-S. M. El-Easly, W. R. Hopwood, M. F. Mecklenburg, and C. S. Tumosa. 2002. Recent Examination of Some Irradiated Mail. *SPNHC Newsletter*, 16(1):13, 16.
- Tumosa, C. S., and M. F. Mecklenburg. 2003. Weight Changes in Acrylic Emulsion Paints and the Implications for Accelerated Ageing. *WAAC Newsletter*, 25(3):12–14.
- Tumosa, C. S., and M. F. Mecklenburg. 2003. Weight Changes on Oxidation of Drying and Semi-drying Oils. *Collection Forum*, 18(1–2):116–123.
- Mecklenburg, M. F., C. S. Tumosa, and D. Erhardt. 2004. New Environmental Guidelines at the Smithsonian Institution. *Papyrus*, 5(3):16–17.
- Mecklenburg, M. F., C. S. Tumosa, and A. Pride. 2004. Preserving Legacy Buildings. In "HVAC Retrofit." Supplement, *ASHRAE Journal*, 46(6):S18–S23.
- Mecklenburg, M., C. Tumosa, and A. Pride. 2004. Preserving Legacy Buildings. *ABOK Journal*, 7:72–77.
- Tumosa, C. S., and M. F. Mecklenburg. 2004. Moisture Isotherms of Acrylic Emulsion Paints. *WAAC Newsletter*, 26(3):12–14.
- Tumosa, C. S., M. F. Mecklenburg, and D. Erhardt. 2004. Letters to the Editors. *Studies in Conservation*, 49(1):70–72.
- Erhardt, D., C. S. Tumosa, and M. F. Mecklenburg. 2005. Long-Term Chemical and Physical Processes in Oil Paint Films. *Studies in Conservation*, 50(2):143–150.
- Hagan, E., E. Quasney, and M. F. Mecklenburg. 2005. "A Parametric Analysis of Relative Humidity Effects on Traditional Panel Paintings." In *Materials Issues in Art and Archaeology VII*, ed. P. B. Vandiver, J. L. Mass, and A. Murray, pp. 3–11. MRS Symposium Proceedings, No. 852. Warrendale, Pa.: Materials Research Society.
- Mecklenburg, M. F. 2005. "The Structure of Canvas Supported Paintings." In *Canvases: Behaviour, Deterioration and Treatment, Interim Meeting: International Conference on Painting Conservation*, ed. M. Castell Agusti, pp. 119–155. Valencia, Spain: Universidad Politécnica de Valencia.
- Mecklenburg, M. F., C. S. Tumosa, and D. Erhardt. 2005. "The Changing Mechanical Properties of Aging Oil Paints." In *Materials Issues in Art and Archaeology VII*, ed. P. B. Vandiver, J. L. Mass, and A. Murray, pp. 13–24. MRS Symposium Proceedings, No. 852. Warrendale, Pa.: Materials Research Society.
- Tumosa, C. S., and M. F. Mecklenburg. 2005. The Influence of Lead Ions on the Drying of Oils. *Reviews in Conservation*, 6:39–47.
- Tumosa, C. S., D. Erhardt, M. F. Mecklenburg, and X. Su. 2005. "Linseed Oil Paint as Ionomer: Synthesis and Characterization." In *Materials Issues in Art and Archaeology VII*, ed. P. B. Vandiver, J. L. Mass, and A. Murray, pp. 25–31. MRS Symposium Proceedings, No. 852. Warrendale, Pa.: Materials Research Society.
- Fuster-López, L., M. F. Mecklenburg, M. Castell, and V. Guerola. 2006. "Idoneidad estructural de las masillas de relleno empleadas en pintura sobre lienzo. ¿Qué estamos buscando?" [Suitability of structural putties used in paintings on canvas paintings. What are we looking for?]. In *Actas del XVI Congreso de Conservación y Restauración de Bienes Culturales*, ed. P. Roig Picazo, pp. 1299–1314. Valencia, Spain: Universidad Politécnica de Valencia.

- Fuster-López, L., M. F. Mecklenburg, M. Castell, and V. Guerola. 2006. "Idoneità Meccanica degli stucchi usati nel riempimento di mancanze di dipinti su tela" [Suitability of stuccoes used for filling voids in canvas paintings]. In *Atti del IV Congresso Nazionale IGIC Lo Stato dell'Arte IV*, pp. 599–608. Florence, Italy: Nardini Editore.
- Mecklenburg, M. F., M. Rossi, and L. Fuster-López. 2006. "Failure Mechanisms in Canvas Supported Paintings: Approaches for Developing Consolidation Protocols." In *The Care of Painted Surfaces: Materials and Methods for Consolidation, and Scientific Methods to Evaluate Their Effectiveness; Proceedings of the Conference, Milan, November 10–11, 2006*, pp. 49–58. Saonara, Italy: Il Prato.
- Erhardt, D., C. S. Tumosa, and M. F. Mecklenburg. 2007. "Applying Science to the Question of Museum Climate." In *Museum Microclimates: Contributions to the Copenhagen Conference*, ed. T. Padfield and K. Borchersen, pp. 11–18. Copenhagen: National Museum of Denmark. <http://www.conservationsphysics.org/mm/musmic/musmic150.pdf> (accessed 18 April 2018).
- Fuster-López, L., M. F. Mecklenburg, D. J. Y. Marco, S. V., Palomino, and A. F. B. Dos Santos. 2007. Effects of Mordants on the Mechanical Behaviour of Dyed Silk Fabrics: Preliminary Tests on Cochineal Dyestuffs. *Arché: Publicación del Instituto Universitario de Restauración del Patrimonio de la UPV*, no. 2:115–120.
- Mecklenburg, M. F. 2007. Determining the Acceptable Ranges of Relative Humidity and Temperature in Museums and Galleries: Part 1, Structural Response to Relative Humidity. Internal Report. Suitland, Md.: Museum Conservation Institute, Smithsonian Institution.
- Mecklenburg, M. F. 2007. Determining the Acceptable Ranges of Relative Humidity and Temperature in Museums and Galleries: Part 2, Structural Response to Temperature. Internal Report. Suitland, Md.: Museum Conservation Institute, Smithsonian Institution.
- Mecklenburg, M. F. 2007. "Micro Climates and Moisture Induced Damage to Paintings." In *Museum Microclimates: Contributions to the Copenhagen Conference*, ed. T. Padfield and K. Borchersen, pp. 19–25. Copenhagen: National Museum of Denmark. <http://www.conservationsphysics.org/mm/musmic/musmic150.pdf> (accessed 18 April 2018).
- Fuster-López, L., M. F. Mecklenburg, M. Castell, and V. Guerola. 2008. "Filling Materials for Easel Paintings: When the Ground Reintegration Becomes a Structural Concern." In *Preparation for Painting: The Artist's Choice and Its Consequences*, ed. J. H. Townsend, T. Doherty, G. Heydenreich, and J. Ridge, pp. 180–186. London: Archetype Books.
- Finozzi, A., R. Bestetti, F. Rizzi, R. Giorio, M. Romano, T. Maifreni, C. Sbrulino, M. F. Mecklenburg, and C. Lodi. 2009. "Studio comparato nel comportamento di modelli-finiti sottoposti a diversi trattamenti di impregnazione in condizione di variazioni ambientali" [Comparative study of the final-model behavior undergone by various impregnation treatments under changing ambient conditions]. In *L'attenzione alle superfici pittoriche: Materiali e metodi per il consolidamento e metodi scientifici per valutarne l'efficacia*, 2: *Atti del 4 Congresso Internazionale, Colore e Conservazione, Materiali e Metodi, Milano, 2008*, ed. D. Kunzelman, pp. 61–86. Padua, Italy: Il Prato.
- Rogala, D., S. Lake, C. Maines, and M. Mecklenburg. 2009. A Closer Look: Condition Issues in Abstract Expressionist Ground Layers. *Postprints of the American Institute for Conservation of Historic and Artistic Works Paintings Specialty Group*, 22:41–46.
- Silva, M. F., M. T. Doménech-Carbó, L. Fuster-López, S. Martin-Rey, and M. F. Mecklenburg. 2009. Determination of the Plasticizer Content in Poly(vinyl Acetate) Paint Medium by Pyrolysis-Silylation-Gas Chromatography-Mass Spectrometry. *Journal of Analytical and Applied Pyrolysis*, 85:487–491.
- Del Hoyo-Meléndez, J. M., and M. F. Mecklenburg. 2010. A Survey on the Light-Fastness Properties of Organic-Based Alaska Native Artifacts. *Journal of Cultural Heritage*, 11(4):493–499.
- Rogala, D., S. Lake, C. Maines, and M. Mecklenburg. 2010. Condition Problems Related to Zinc Oxide Underlayers: Examination of Selected Abstract Expressionist Paintings from the Collection of the Hirshhorn Museum and Sculpture Garden, Smithsonian Institution. *Journal of the American Institute for Conservation*, 49(2):96–113.
- Silva, M. F., M. T. Doménech-Carbó, L. Fuster-López, M. F. Mecklenburg, and S. Martin-Rey. 2010. Identification of Additives in Poly(vinylacetate) Artist's Paints Using PY-GC-MS. *Analytical and Bioanalytical Chemistry*, 397(1):357–367.
- Antoine, B., M. F. Mecklenburg, R. J. Speakman, and M. J. Wachowiak. 2011. The Conservation of Letterpress Copying Books: A Study of the Baird Collection. *Book and Paper Group Annual*, 30:9–27.
- Del Hoyo-Meléndez, J. M., and M. F. Mecklenburg. 2011. An Investigation of Reciprocity Principle of Light Exposures Using Microfading Spectrometry. *Spectroscopy Letters: An International Journal for Rapid Communication*, 44(1):52–62.
- Del Hoyo-Meléndez, J. M., and M. F. Mecklenburg. 2011. The Use of Micro-fading Spectrometry to Evaluate the Light Fastness of Materials in Oxygen-Free Environments. *Spectroscopy Letters: An International Journal for Rapid Communication*, 44(2):113–121.
- Del Hoyo-Meléndez, J. M., M. F. Mecklenburg, and M. T. Doménech-Carbó. 2011. An Evaluation of Daylight Distribution as an Initial Preventive Conservation Measure at Two Smithsonian Institution Museums, Washington, D.C., USA. *Journal of Cultural Heritage*, 12(1):54–64.
- Del Hoyo-Meléndez, J. M., M. F. Mecklenburg, and M. T. Doménech-Carbó. 2011. Determination of the Annual Light Exposure Received by Two-Dimensional Museum Objects Displayed on Vertical Surfaces using Photometric Measurements. *Studies in Conservation*, 56(1):31–40.
- Doménech-Carbó, M. T., M. F. Silva, E. Aura-Castro, L. Fuster-López, S. Kröner, M. L. Martínez-Bazán, X. Más-Barberá, M. Mecklenburg, L. Osete-Cortina, A. Doménech, J. V. Gimeno-Adelantado, and D. J. Yusa-Marco. 2011. Study of Behaviour on Simulated Daylight Ageing of Artists' Acrylic and Poly(vinyl Acetate) Paint Films. *Analytical and Bioanalytical Chemistry*, 399(9):2921–2937.
- Fuster-López, L., A. Murray, M. F. Mecklenburg, D. Yusa-Marco, G. Mirdrikvand, and M. Doutré. 2011. "Filling Materials for Easel Paintings: Current Formulations, Traditional Concerns." In *ICOM-CC, 16th Triennial Conference, Lisbon, Portugal, 19–23 September 2011: Preprints*, ed. J. Bridgland and C. Antomarchi. Paris: ICOM-CC. <http://icom-cc-publications-online.org/PublicationDetail.aspx?cid=9e310b8c-92e9-4769-8a67-e061bde4647d> (accessed 18 April 2018).
- Maines, C. A., D. Rogala, S. Lake, and M. F. Mecklenburg. 2011. "Deterioration in Abstract Expressionist Paintings: Analysis of Zinc Oxide Paint Layers in Works from the Collection of the Hirshhorn Museum and Sculpture Garden, Smithsonian Institution." In *Materials Issues in Art and Archaeology IX*, ed. P. B. Vandiver, C. L. Reedy, W. Li, and J. L. R. Sil, pp. 275–286. MRS Symposium Proceedings, No. 1319. Pittsburgh: Materials Research Society.
- Canon, D., M. T. Doménech-Carbó, L. Fuster-López, and M. F. Mecklenburg. 2012. "La Pintura tratada con agentes biocidas" [Paintings treated with biocides]. In *Aproximación al Estudio de los Procesos de Limpieza en Obra Pictórica Contemporánea*, ed. M. T. Doménech-Carbó, L. Fuster-López, and L. Osete-Cortina, pp. 111–125. Valencia, Spain: Universidad Politécnica de Valencia.
- Fuster-López, L., M. F. Silva, and M. F. Mecklenburg. 2012. "Ensayos de resistencia mecánica" [Mechanical resistance tests]. In *Aproximación al Estudio de los Procesos de Limpieza en Obra Pictórica Contemporánea*, ed. M. T. Doménech-Carbó, L. Fuster-López, and L. Osete-Cortina, pp. 91–109. Valencia, Spain: Universidad Politécnica de Valencia.
- Mecklenburg, M. F. 2012. "Technical Assessment of Cultural Objects in the Planning of Transport." In *Moving Collections: Processes and Consequences*, ed. I. A. T. Bronken, S. Braovac, T. M. Olstad, and A. A. Ørnhoi, pp. 1–8. London: Archetype Books.
- Mecklenburg, M. F., and J. M. Del Hoyo-Meléndez. 2012. Development and Application of a Mathematical Model to Explain Fading Rate Inconsistencies Observed in Light-Sensitive Materials. *Coloration Technology*, 128(2):139–146.
- Mecklenburg, M. F., L. Fuster-López, and S. Ottoloni. 2012. "A Look at the Structural Requirements of Consolidation Adhesives for Easel Paintings." In *Adhesives and Consolidants in Painting Conservation*, ed. A. Barros D'Sa, L. Bone, A. Gent, and R. Ciarricoates, pp. 7–23. London: Archetype.
- Ortiz Miranda, A. S., M. T. Doménech-Carbó, L. Fuster-López, and M. F. Mecklenburg. 2012. "La limpieza de pintura tratada con agentes biocidas" [The cleaning of paintings treated with biocides]. In *Aproximación al Estudio de los Procesos de Limpieza en Obra Pictórica Contemporánea*, ed. M. T. Doménech-Carbó, L. Fuster-López, and L. Osete-Cortina, pp. 127–148. Valencia, Spain: Universidad Politécnica de Valencia.
- Doménech-Carbó, M. T., M. F. Silva, E. Aura-Castro, A. Doménech-Carbó, L. Fuster-López, J. V. Gimeno-Adelantado, S. U. Kröner, M. L. Martínez-Bazán, X. Más-Barberá, M. F. Mecklenburg, L. Osete-Cortina, and D. J. Yusa-Marco. 2013. "Multitechnique Approach to Evaluate Cleaning Treatments for Acrylic and Polyvinyl Acetate Paints." In *New Insights into the Cleaning of Paintings: Proceedings from the Cleaning 2010 International Conference, Universidad Politécnica de Valencia and Museum Conservation Institute*, ed. M. F. Mecklenburg, A. E. Charola, and R. J. Koestler,

- pp. 125–134. Smithsonian Contributions to Museum Conservation, No. 3. Washington, D.C.: Smithsonian Institution Scholarly Press.
- Mecklenburg, M. F., A. E. Charola, and R. J. Koestler, eds. 2013. *New Insights into the Cleaning of Paintings: Proceedings from the Cleaning 2010 International Conference, Universidad Politécnica de Valencia and Museum Conservation Institute*. Smithsonian Contributions to Museum Conservation, No. 3. Washington, D.C.: Smithsonian Institution Scholarly Press. <http://opensi.si.edu/index.php/smithsonian/catalog/book/28> (accessed 18 April 2018).
- Mecklenburg, M. F., C. S. Tumosa, and E. P. Vicenzi. 2013. “The Influence of Pigments and Ion Migration on the Durability of Drying Oil and Alkyd Paints.” In *New Insights into the Cleaning of Paintings: Proceedings from the Cleaning 2010 International Conference, Universidad Politécnica de Valencia and Museum Conservation Institute*, ed. M. F. Mecklenburg, A. E. Charola, and R. J. Koestler, pp. 59–67. Smithsonian Contributions to Museum Conservation, No. 3. Washington, D.C.: Smithsonian Institution Scholarly Press.
- Szczepanowska, H., F. W. Shockley, D. G. Furth, P. Gentili, D. Bell, P. T. DePriest, M. Mecklenburg, and C. Hawks. 2013. Effectiveness of Entomological Collection Storage Cabinets in Maintaining Stable Relative Humidity and Temperature in a Historic Museum Building. *Collection Forum*, 27(1–2):43–53.
- Tumosa, C. S., and M. F. Mecklenburg. 2013. “Oil Paints: The Chemistry of Drying Oils and the Potential for Solvent Disruption.” In *New Insights into the Cleaning of Paintings: Proceedings from the Cleaning 2010 International Conference, Universidad Politécnica de Valencia and Museum Conservation Institute*, ed. M. F. Mecklenburg, A. E. Charola, and R. J. Koestler, pp. 51–58. Smithsonian Contributions to Museum Conservation, No. 3. Washington, D.C.: Smithsonian Institution Scholarly Press.
- Krzemiński, L., M. Łukowski, Ł. Bratasz, R. Kozłowski, and M. F. Mecklenburg. 2016. Mechanism of Craquelure Pattern Formation on Panel Paintings. *Studies in Conservation*, 61(6): 324–330.
- Fuster-López, L., and M. F. Mecklenburg. 2017. “A Look into Some Factors Influencing the Film Forming Properties of Oil Paint Films in Copper Paintings and the Effects of Environment in Their Structural Behaviour.” In *Paintings on Copper and Other Metal Plates: Production, Degradation and Conservation Issues*, ed. L. Fuster-López, I. Chulia Blanco, M. F. Sarrió Martín, M. L. Vázquez de Ágredos Pascual, L. Carlyle, and I. Wadum, pp. 95–102. Valencia, Spain: Universidad Politécnica de Valencia.

SUMMARY OF REQUIREMENTS FOR SMITHSONIAN CONTRIBUTIONS SERIES

For comprehensive guidelines and specifications, visit <https://scholarlypress.si.edu>.

ABSTRACTS must not exceed 300 words.

TEXT must be prepared in a recent version of Microsoft Word; use a Times font in 12 point for regular text; be double-spaced; and have 1" margins.

REQUIRED ELEMENTS are title page, abstract, table of contents, main text, and references.

FIGURES must be numbered sequentially (1, 2, 3, etc.) in the order called out; have components lettered consistently (in size, font, and style) and described in captions; include a scale bar or scale description, if appropriate; include any legends in or on figures rather than in captions. Figures must be original and must be submitted as individual TIF or EPS files.

FIGURE FILES must meet all required specifications in the Digital Art Preparation Guide. Color images should be requested only if required.

TAXONOMIC KEYS in natural history manuscripts should use the aligned-couplet form for zoology. If cross referencing is required between key and text, do not include page references within the key, but number the keyed-out taxa, using the same numbers with their corresponding heads in the text.

SYNONYMY IN ZOOLOGY must use the short form (taxon, author, year:page), with full reference at the end of the manuscript under "References."

REFERENCES should be in alphabetical order, and in chronological order for same-author entries. Each reference should be cited at least once in main text. Complete bibliographic information must be included in all citations. Examples of the most common types of citations can be found at SISIP's website under Resources/Guidelines & Forms.